

SPECIFICATIONS OF MATERIALS INDEX

Particulars

Page No.

General Technical Specifications-General
Standard Technical Specifications

3

M.	1.		Water	5
M.	2.		Lime	5
M.	3.		Cement	5
M.	4.		White Cement	5
M.	5.		Coloured Cement	5
M.	6.		Sand	6
M.	7.		Stone Dust	6
M.	8.		Stone Grit	6
M.	9.		Cinder	7
M.	10.		Lime Mortar	7
M.	11.		Cement Mortar	8
M.	12.		Stone coarse aggregates For Nominal Mix Concrete	8
M.	13.		Black trap or equivalent Hard Stone Coarse aggregate For design Mix concrete	9
M.	14.		Brick bats aggregates	9
M.	15.		Brick	9
M.	16.		Stone	9
M.	17.		Laterite stone	10
M.	18.		Mild Steel Bars	10
M.	19.		High yield strength steel deformed bars	10
M.	20.		High tensile steel wires	10
M.	21.		Mild Steel binding Wires	11
M.	22.		Structural Steels	11
M.	23.		Galvanised iron sheets	11
M.	23.	A	G.I. Valleys gutters ridges	11
M.	24.		Asbestos cement sheets	11
M.	25.		Mangalore pattern roof tiles	11
M.	26.		Shuttering	11
M.	27.		Expansion Joints, premodulded Filler	12
M.	28.		Expansion Joints, copper strips & hold Fast	12
M.	29.		Teak wood	13
M.	29.	A	Non Teak wood	13
M.	30.		Wooden Flush door shutters (Solid Core)	13
M.	31.		Aluminium Doors, Windows, Ventilators	14
M.	32.		Rolling steel gate	14
M.	33.		Collapsible steel gate	15
M.	34.		Welded steel Wire Fabric	15
M.	35.		Expanded metal sheets	15
M.	36.		Mild Steel Wires (Wire gauze Jali)	15

M.	37.		Plywood	16
M.	38.		Glass	16
M.	39.		Acrylic sheets	17
M.	40.		Particle board	17
M.	41.		Expanded polystyrene or Framed sty roper slabs	17
M.	42.		Resign boded Fiber glass	17
M.	43.		Fixtures and Fastening	18
M.	44.		Paints	19
M.	45.		French Polish	19
M.	46.		Marble pipes For marble mosaic terrazzo	19
M.	47.		Flooring tiles	20
M.	48.		Rough Kota stone	21
M.	49.		Polished Kota stone	22
M.	50.		Dholpur Stone slab	22
M.	51.		Marble slab	22
M.	52.		Granite stone slab	22
M.	53.		P.V.C. Flooring	23
M.	54.		Facing tiles	23
M.	55.		White glazed tiles	24
M.	56.		Galvanized iron pipes and fitting	24
M.	57.		Bib cooks and stop cock	24
M.	58.		Gun metal Wheel valve	24
M.	59.		while glazed porcelain wash basin	24
M.	60.		European type water closed	24
M.	61.		Orrissa type water closet	25
M.	62.		Indian type water closet	25
M.	62.	A	Foot Rests	25
M.	63.		Glazed earthenware sink	25
M.	64.		Glazed earthenware lipped type flat back urinal/Corner type urinal	25
M.	65.		Low level enamel Hushing tank	25
M.	66.		Cast Iron flushing cistern	25
M.	67.		Flush cock	26
M.	68.		Cash iron pipes and fitting	26
M.	69.		Nahni Trap	26
M.	70.		Gulley Trap	26
M.	71.		Glazed stoneware pipes and filling	27
M.	72.		Wall peg rail	27
M.	73.		G. 1. Water spout	27
M.	74.		Asbestos cement pipe (A.C. pipe)	27
M.	75.		Crydon ball valve	27
M.	76.		Bitumen fell for water proofing and damp proofing	27
M.	77.		Selected Earth	27
M.	78.		barbed-Wire	28

GENERAL TECHNICAL SPECIFICATIONS FOR BUILDING WORKS

GENERAL:

1. In the specifications "as directed" / "approved" shall be taken to mean "as directed" / "approved by the Engineer-in-Charge".
2. Wherever a reference to any Indian Standard appears in the specifications, it shall be taken to mean as a reference to the latest edition of the same in force on the date of agreement.
3. In "Mode of Measurement" in the specifications wherever a dispute arises in the absence of specific mention of a particular point of aspect the provisions on these particular points, or aspects in the relevant Indian Standards shall be referred to
4. All measurements and computations, unless otherwise specified, shall be carried out nearest to the following limits:
 - (i) Length, width and depth (height) 0.01 meter
 - (ii) Areas 0.01 Sq.Mt.
 - (iii) Cubic Contents 0.01 Cu.Mt.

In recording dimensions of work the sequence of length, width and height (depth) or thickness shall be followed.
5. The distance which constitutes lead shall be determined along the shortest practical route and note necessarily the route actually taken The decision of the Engineer-in-charge in this regard shall be taken as final.
6. Where no lead is specific, it shall mean "all leads"
7. Lift shall be measured from plinth level.
8. Up to "floor two level" means actual height of floor (Maxi 4 M) up to 3 Mt. above plinth level.
9. Definite particulars covered in the items of work, though not mentioned or elucidated in it specifications shall be deemed to be included therein.
10. Reference to specifications of materials as made in the detailed specification of the items of works is in the form of a designation containing them number of the specification of the material and prefix 'M' e.g. 'M-5',
11. Approval to the samples of various materials given by the Engineer-in-charge shall not absolve the contractor from the responsibility of replacing defective material brought on site or materials used in the work found defective at a later date. The contractor shall have no claim to any payment or compensation whatsoever on account of any such materials being rejected by the Engineer-in-charge.
12. The contract rate of the item of work shall be for the work completed in all aspects.
13. No collection of materials shall be made before it is got approved from the Engineer-in-charge.
14. Collection of approved materials shall be done at site of work in a systematic manner. Materials shall be stored in such a manner as to prevent damage, deterioration or

- intrusion of foreign matter and to ensure the preservation of their quality and fitness for the work.
15. Materials, if and when rejected by the Engineer-in-charge, shall be immediately removed from the site of work.
 16. No materials shall be stored prior to, during and after execution of a structure in such a way as to cause or lead to damage or overloading of the various components of the structure.
 17. All works shall be carried out in a workmanlike manner as per the best techniques for the particular item.
 18. All tools, templates, machinery and equipment for correct execution of the work as well as for checking lines, levels, alignment of the works during execution shall kept in sufficient numbers and in good working condition on the site of the work.
 19. The mode, procedure and manner of execution shall be such that it does not cause damage or over-loading of the various components of the structure during execution or after completion of the structure.
 20. Special modes of construction not adopted in general Engineering practice if proposed to be adopted by the Contractor, shall be considered only if the contractor provides satisfactory evidence that such special mode of construction is safe, sound and helps in speedy construction and Completion of work to the required strength and quality. Acceptance of the same by the Engineer-in-Charge shall not, however absolve the contractor of the responsibility of any adverse effects and consequences of adopting the same in the course of execution of completion of the work.
 21. All installations pertaining to water supply and fixtures there of as well as drainage lines and sanitary fittings shall be deemed to be completed only after giving satisfactory tests by the contractor.
 22. The contractor shall be responsible for observing the rules and regulations imposed under the "Minor Minerals Act", and such of the laws and rules prescribed by Government from time to time.
 23. All necessary safety measures and precautions {including those laid down in the various relevant Indian Standards) shall be taken to ensure the safety of men. Materials and machinery on the works as also of the work itself.
 24. The testing charges of all materials shall be borne by the Contractor.
 25. Approval to any of the executed items for the work does not in any relieve the contractor of his responsibility for the correctness, soundness and strength of the structure as per the drawings and specifications.

SPECIFICATIONS OF MATERIALS

M-1 Water

- 1.1. Water shall not be salty brackish and shall be clean, reasonably clear and free objectionable quantities of silt and traces of oil and injurious alkalis, salts, organic matter and other deleterious material which will either weaken the mortar of concrete or cause efflorescence or attack the steel in R.C.C. Container for transport, storage and handling of water shall be clean. Water shall conform to the standard specified in I.S. 456-1978.
- 1.2. If required by the Engineer-in-Charge it shall be tested by comparison with distilled water. Comparison shall be made by means of standard cement tests for soundness, time of setting and mortar strength as specified in I.S. 269-1976. Any indication of unsoundness, change in time of setting by 30 minutes or more or decrease of more than 10 per cent in strength, of mortar prepared with water sample when compared with the results obtained with mortar prepared with distilled water shall be sufficient cause for rejection of water under test.
- 1.3. Water for curing mortar, concrete or masonry should not be too acidic or too alkaline. It shall be free of elements which significantly affect the hydration reaction or otherwise interfere with the hardening of mortar or concrete during curing or those which produce objectionable stains or other unsightly deposits on concrete or mortar surfaces.
- 1.4. Hard and bitter water shall not be used for curing.
- 1.5. Potable water will generally be found suitable for curing mortar or concrete.

M-2. Lime

- 2.1. Lime shall be hydraulic lime as per I.S. 712-1973. Necessary tests shall be carried out as per I.S. 6932 (Parts I to X) 1973.
- 2.2. The following field tests for limes are to be carried out:
 - (1) A very rough idea can be formed about the type of lime by its visual examination i.e. fat lime bears pure white colour, lime in form of porous lumps of dirty white colour indicates quick lime, and solid lumps are the unburnt lime stone.
 - (2) Acid tests for determining the carbonate content in lime. Excessive amount of impurities and rough determination of class of lime.
- 2.3. Storage shall comply with I.S. 712-1973. The slaked lime, if stored, shall be kept in a weather proof and damp-proof shed with impervious floor and sides to protect it against rain, moisture, weather and extraneous materials mixing with it. All lime that has been damaged in any way shall be rejected and all rejected materials shall be removed from site of work.
- 2.4. Field testing shall be done according to I.S. 1624-1974 to show the acceptability of materials.

M-3. Cement

- 3.1. Cement shall be ordinary Portland slag cement as per I.S. 269-1976 or Portland slag cement as per I.S. 455-1976.

M-4. White Cement

- 4.1. The white cement shall conform to I. S. 8042-E-1978.

M-5. Coloured Cement

- 5.1. Coloured cement shall be with white or grey Portland cement as specified in the item of the work.

- 5.2.** The pigments used for coloured cement shall be of approved quality and shall not exceed 10% of cement used in the mix. The mixture of pigment add cement shall be properly ground to have a uniform colour and shade. The pigments shall have such properties to provide for durability under exposure to sunlight and weather.
- 5.3.** The pigment shall have the property such that it is neither affected by the cement nor detrimental to it

M-6 Sand

- 6.1.** Sand shall be natural sand, clean, well graded hard strong, durable and gritty particles free from injurious amounts of dust, clay kankar nodules, soft or flaky particles shale, alkali salts organic matter, loam, mica or other deleterious substances and shall be got approved from the Engineer-in-Charge. The sand shall not contain more than 8 percent of silt as determined by field test, if necessary the sand shall be washed to make it clean.
- 6.2. Coarse Sand :** The fineness modulus of coarse sand shall not be less than 2.5 and shall not exceed 3.0. The sieve analysis of coarse shall be as under :

I.S. Sieve Designation	Percentage by Weight Passing sieve	I.S. Sieve Designation	Percentage by Weight Passing Sieve
4.75 mm	100	600 Micron	30 - 100
2.36 mm	90 to 100	300 Micron	5 - 70
1.18 mm	70 - 100	150 Micron	0 - 50

- 6.3. Fine Sand :** The fineness modulus shall not exceed 1.0. The sieve analysis of fine sand shall be as under :

I.S. Sieve Designation	Percentage by Weight Passing through	I.S. Sieve Designation	Percentage by Weight Passing through
4.75 mm	100	600 Micron	40 - 85
2.36 mm	100	300 Micron	5 - 50
1.18 mm	70 - 100	150 Micron	0 - 10

M-7 Stone Dust :

- 7.1.** This shall be obtained from crushing hard black trap or equivalent. It shall not contain more than 8% of silt as determined by field test will measuring cylinder. The method of determining silt contents by fields test is given as under :
- 7.2.** A sample of stone dust to be tested shall be placed without drying in 200 mm. measuring cylinder. The quantity of the sample shall be such that it fills the cylinder up to 100 mm. mark. The clean water shall be added up to 150 mm. mark. The mixture shall be stirred vigorously and the content allowed to settle for 3 hours.
- 7.3.** The height of silt, visible as settled layer above the stone dust shall be expressed as percentage of the height of the stone dust below. The stone dust containing more than 8% silt shall be washed so as to bring the content within the allowable limit.
- 7.4.** The fineness modules of stone dust shall not be less than 1.80.

M-8. Stone Grit

- 8.1.** Grit shall consist of crushed or broken stone and be hard, strong, dense, durable, clean of proper gradation and free from skin or coating likely to prevent proper adhesion of mortar Grit shall generally be cubical in shape and as far as possible flakey elongated pieces shall be avoided. It shall generally

comply with the provisions of I.S. 383-1970. Unless special stone of particular quarries is mentioned grit shall be obtained from the best black trap or equivalent hard stone as approved by the Engineer-in-charge. The grit shall have no deleterious with cement.

8.2. The Grit shall conform to the following gradation as per sieve analysis :

I.S. Sieve Designation	Percentage Passing through sieve	I.S. Sieve Designation	Percentage by Weight Passing through Sieve
4.75 mm	100	600 Micron	40 - 85
2.36 mm	100	300 Micron	5 - 50
1.18 mm	70 - 100	150 Micron	0 - 10

8.3 The crushing strength of grit will be such as to allow the concrete in which it is used to built up the specified strength of concrete.

8.4. The necessary tests for grit shall be carried out as per the requirements of I.S.2386 (Parts I to VIII) 1963 as per instructions of the Engineer-in-charge. The necessity of test will be decided by the Engineer-in-charge.

M-9. Cinder

9.1. Cinder is will burnt furnace residue which has been fused or sintered into lumps of varying sizes.

9.2. Cinder aggregates shall be well burnt furnace residue obtained from furnace using coal fuel only it shall be sound clean and tree from clay dirt, ash or other deleterious matter.

9.3 The average grading for under aggregates shall be as mentioned below :

I.S. Sieve Designation	Percentage Passing	I.S. Sieve Designation	Percentage Passing
20 mm	100	4.75 mm	70
10 mm	86	2.36 mm	32

M-10 Lime Mortar

10.1 Lime shall conform to specification M-2. Water shall conform to specification M-1.

Sand shall conform to specification M-6.

10.2. Proportion of Mix:

10.2.1. mortar shall consist of such proportions of slaked lime and sand as may be specified in item The slaked lime and sand shall be measured by volume

10.3. Preparation of mortar:

10.3.1. Lime mortar shall be prepared by wet process as per I S 1625-1971 .Power driven mill shall be used for preparation of lime mortar. The slaked lime shall be placed in the mill in an even layer and ground for 180 revolutions with a sufficient water. Water shall be added as required during grinding (care being taken not to add more water) that will bring the mixed material to a consistency of stiff paste. Thoroughly wetted sand shall then be added evenly and the mixture ground for another 180 revolutions.

10.4. Storage:

10.4.1. Mortar shall always be kept damp, protected from sun and ram till used up, covering it by tarpaulin or open sheds.

10.5. Use:

10.5.1. All mortar shall be used as soon as possible after grinding. It should be used on the day on which it prepared, But in no case mortar made earlier than 36 hours shall be permitted for use.

M-11. Cement Mortar

11.1. Water shall conform to specification M-1. Cement shall conform to specifications M-3 and Sand shall conform to M-6

11.2. Proportion of Mix

11.2.1. Cement and sand shall be mixed to specified proportion, sand being measured by measuring boxes, the proportion of cement will be by volume on the basis of 50 Kg/Bag of cement being equal to 0.0342 cu.m. The mortar may be hand mixed or machine mixed as directed.

11.3. Preparation of Mortar :

11.3.1. In hand mixed mortar, cement and sand in the specified proportions shall be thoroughly mixed dry on a clean impervious platform by turning over at least 3 times or more till a homogeneous mixture of uniform colour is obtained. Mixing platform shall be so arranged that no deleterious extraneous material shall get mixed with mortar or mortar shall flow out. While mixing, the water shall be gradually added and thoroughly mixed to form a stiff plastic mass of uniform colour so that each particle of sand shall be completely covered with a film of wet cement. The water cement ratio shall be adopted as directed

11.3.2. The mortar so prepared shall be used within 30 minutes of adding water. Only such quantity of mortar shall be prepared as can be used within 30 minutes.

M-12. Stone Coarse Aggregate for Nominal Mix Concrete

12.1. Coarse aggregate shall be of machine crushed stone of black trap or equivalent and be hard strong, dense, durable, clean and free from skin and coating likely to prevent proper adhesion of mortar.

12.2. The aggregate shall generally be cubical in shape unless special stones of particular quarries are mentioned aggregates shall be machine crushed from the best black trap or equivalent hard stone as approved aggregate shall have no deleterious reaction with cement. The size of the coarse aggregate for plain cement and ordinary reinforced cement concrete shall generally be as per the table given below.

However in case of reinforced cement concrete the maximum limit may be restricted to 6 mm. less than the minimum lateral clear distance between bars or 6- mm. less than the cover whichever is smaller.

TABLE

I.S. Sieve Designation	Percentage passing for single sized aggregates of Nominal size			I.S. Sieve Designation	Percentage passing for single sized aggregates of Nominal size		
	40 mm	20 mm	16 mm		40 mm	20 mm	16 mm
80 mm	-	-	-	12.5 mm	-	-	-
63 mm	100	-	-	10 mm	0.5	0.02	0.30
40 mm	85-100	100	-	4.75 mm	-	0.5	0.5
20 mm	0-20	85-100	100	2.35 mm	-	-	-
16 mm	-	-	85-100				

Note : This percentage may be varied somewhat by the Engineer-in-charge when considered necessary for obtaining better density and strength of concrete.

12.3. The grading test shall be taken in the beginning and at the change of source of materials. The necessary tests, indicated in I.S. 383-1970 and 456-197f shall have to be carried out to ensure the acceptability. The aggregates shall be stored separately and handled in such a manner as to prevent the intermixing of different aggregates. If the aggregates are covered with dust, they shall be washed with water to make them clean. .

M-13. Black Trap or Equivalent Hard Stone Coarse

- 13.1. Aggregate For Design Mix Concrete :** Coarse aggregate shall be of machine crushed stone of black trap or equivalent hard stone and be hard, strong, dense, durable, clean and free from skin and coating likely to prevent proper adhesion of mortar.
- 13.2.** The aggregates shall generally be cubical in shape. Unless special stones of particular quarries are mentioned, aggregates shall be machine crushed, from the best, black trap or equivalent hard stones as approved, Aggregate shall have no deleterious with cement
- 13.3.** The necessary tests indicated in I S. 383-1970 and I.S.456-1978 shall have to be carried out to ensure the acceptability of the material.
- 13.4.** If aggregate is covered with dust it shall be washed with water to make it clean.

M-14. Brick Bats Aggregate

- 14.1.** Brick bat aggregate shall be broken from well burnt or slightly over burnt and dense bricks. It shall be homogeneous in texture, roughly cubical in shape, clean and free from dirt of any other foreign material. The brick bats shall be of 40 mm - 50 mm. size unless otherwise specified in the item. The under burnt or over burnt brick bats shall not be allowed.
- 14.2** The brick bats shall be measured by suitable boxes or as directed.

M-15. Bricks

- 15.1.** The bricks shall be hand or machine molded and made from suitable soils and kiln burnt. They shall be free from cracks and flaws and nodules of free lime they shall have smooth rectangular faces with sharp corners and shall be of uniform colour.
The bricks shall be moulded with a frog of 100 mm. x 40 mm. and 10 mm. to 20 mm. deep on one of its flat sides. The bricks shall not break when thrown on the ground from a height of 600 mm.
- 15.2.** The size of modular bricks shall be 190 mm.x 90 mm.x 90 mm.
- 15.3.** The size of the conventional bricks shall be as under :
(9" x 4.3/8" x 2,3/4") 225 x 110 x 75 mm.
- 15.4.** Only bricks of one standard size shall be used on one work. The following tolerances shall be permitted in the conventional size adopted in a particular work.
Length + 1/8" (3.0 mm.) Width \pm 1/16" (1.50 mm.) Height + 1/16" (1.50 mm.)
- 15.5.** The crushing strength of the bricks shall not be less than 35 Kg/Sq. Cm. The average water absorption shall not be more the 20 percent by weight Necessary tests for crushing strength and water absorption etc. shall be carried out as per I.S. 3495 (Part-I to IV) - 1976

M-16. Stone

- 16.1.** The stone shall be of the specified variety such as Granite/Trap Stone/ Quartzite or any other type of good hard stones. The stones shall be only from the approved quarry and shall be hard sound, durable and free from defects like cavities, cracks, sand holes, flaws injurious veins, patches of loose or soft materials etc. and weathered portions and other structural defects Or imperfections tending to affect their soundness and strength. The stone with round surface shall not be used. The percentage of water absorption shall not be more than 5% of dry weight. When tested in accordance with I.S. 1124-1974. The minimum crushing strength of stone shall be 200 Kg/.Sq. Cm. unless otherwise specified.
- 16.2.** The samples of the stone to be used shall be got approved before the work is started
- 16.3.** The Khanki facing stone shall be dressed by chisel as specified in the item for khanki facing in required shape and size. The face of the stone shall be-so dressed that the bushing on the

exposed face shall not project by more than 40 mm. from the general wall surface and on face to be plastered it shall not project by more than 19 mm. nor shall it have depressions more than 10 mm. from the average wall surface.

M-17. Laterite Stone

- 17.1. Laterite stone shall be obtained from the approved quarry it shall be compacted in texture sound, durable and free from soft patch. It shall have minimum crushing strength of 100 Kg/Sq. Cm. in its dry condition. It shall not absorb water more than 20% of its own weight, when immersed for 24 hours in water. After quarrying, the stone shall be allowed to weather for some time before using in work.
- 17.2. The stone shall be dressed into regular rectangular blocks so that all faces are free from waviness and unevenness, and the edges true and square
- 17.3. Those types of stone in which white clay occurs should not be used
- 17.4. Special corner stones shall be provided where so directed.

M-18. Mild Steel Bars

- 18.1. Mild steel bars reinforcement for R.C C. work shall conform to I.S. 432 (Part -II) 1966 and shall be of tested quality. It shall also comply with relevant part of I.S. 456-1978.
- 18.2. All the reinforcement shall be clean and free from dirt, paint, grease, mill scale or loose or thick rust at the time of placing
- 18.3. For the purpose of payment, the bar shall be measured correct up to 10 mm. length and weight payable worked out at the rate specified below :

1.	6 mm	0.22 Kg./Rmt.	8.	20 mm.	2.47 Kg/Rmt.
2.	8 mm	0.39 Kg./Rmt.	9.	22 mm.	2.98 Kg/Rmt.
3.	10 mm	0.62 Kg./Rmt.	10.	25 mm.	3.85 Kg/Rmt.
4.	12 mm	0.89 Kg./Rmt.	11.	28 mm.	4.83 Kg/Rmt.
5.	14 mm	1.21 Kg./Rmt.	12.	32 mm.	6.31 Kg/Rmt.
6.	16 mm	1.58 Kg./Rmt.	13.	36 mm.	7.99 Kg/Rmt.
7.	18 mm	2.00 Kg./Rmt.	14.	40 mm.	9.86 Kg/Rmt.

M-19. High Yield Strength Steel Deformed Bars

- 19.1. High yield strength steel deformed bars shall be either cold twisted other rolled and shall conform to I.S. 1786-1966 and I.S. 1139-1966 respectively.
- 19.2. Other provisions and requirements shall conform to specification No. M-18 for Mild Steel Bars.

M-20. High Tensile Steel Wires

- 20.1. The high tensile wires for use in pre stressed concrete work shall conform to I.S,2090-1962.
- 20.2. The tensile strength of the high tensile steel bars shall be as specified in the item. In absence of the given strength the minimum strength shall be taken as per Para 6-1 of the I.S. 1785-1962. Testing shall be done as per I.S. requirements.
- 20.3. The high tensile steel shall be free from loose mill scale, rust, oil, grease, or any other harmful matter. Cleaning of steel bars may be carried out by immersion in solvent solution, wire brushing or passing through a pressure box containing Carborudum.
- 20.4. The high tensile wire shall be obtained from manufacturers. in coils having diameter not less then 350 times the diameter of wire itself so that wire springs back straight on being uncoiled .

M-21. Mild Steel Binding Wire

- 21.1.** The mild steel wire shall be of 1.63 mm. or 1.22 mm. (16 to 18 gauge) diameter and shall conform to I.S. 280-1972.
- 21.2.** The use of black wire will be permitted for binding reinforcement bars. It shall be free from rust oil paint, grease loose mill scale or any other undesirable coating which may prevent adhesion of cement mortar.

M-22. Structural Steel

- 22.1.** All structural Steel shall conform to I S. 226-1985: The steel shall be free from the defects mentioned in I.S 226-1975 and shall have a smooth finish. The material shall be free from loose mill scale, rust pits or other defects affecting the strength and durability. River bars shall conform to I.S. 1148-1973.
- 22.2.** When the steel is supplied by the Contractor test certificate of the manufacturers shall be obtained according to I.S. 226-1975 and other relevant Indian Standards.

M-23. Galvanised Iron Sheets

- 23.1.** The galvanised iron sheets shall be plain or corrugated sheets of gauges as specified in item The G.I. Sheets shall conform to I.S.277-1977. The sheets shall be undamaged in carnage and handling either by rubbing off of zinc coating or otherwise. They shall have clean and bright surface and shall be free from dents, bends, holes, rust or white powdery deposit.
- 23.2.** The length and width of G.I. sheets shall be as directed as per site condition.

M-23.A : G.I. Valleys gutter, ridges

- 23.A.1.** The G.I. ridges and hips shall be of plain galvanised sheets Class - 3 of the thickness as specified in item. These shall be 600 mm. in width and properly bent up to shape without damage to the sheets in process of bending.
- 23.A.2.** Valleys gutters and flashings shall also be of galvanised sheet of thickness as specified in item Valleys Shall be 900 mm. wide overall and flashing shall be 380 mm. wide overall They shall be bent to the required shape without damage to the sheet in the process of bending.

M-24. Asbestos Cement Sheets

- 24.1.** Asbestos cement sheets plain, corrugated of semi-corrugated shall conform to I.S.459-1970 The thickness of the sheets shall be as specified in the item. The sheets shall be free from all defects such as cracks, holes, deformities chipped edges or otherwise damaged.
- 24.2. Ridges & Hips :**
- 24.2.1.** Ridges and hips shall be of same thickness as that of A.C. sheets. The types, of ridges shall be suitable for the type of sheets and location.
- 24.2.2.** Other accessories to be used in roof such as flashing pieces eaves filler pieces, valley gutters, north light, and ventilator curves, barge boards etc, shall be of standard manufacture and shall be suitable for the type of sheets and location.

M-25. Manglore Pattern Roof Tiles

- 25.1.** The mangalore pattern tiles shall conform to I S 654-1972 for Class AA or Class A type as specified in item. Samples of the tiles to be provided shall be got approved from the Engineer-in-charge. Necessary tests shall be carried out as directed.

M-26. Shuttering

- 26.1.** The shuttering shall be either of wooden planking of 30 mm. minimum thickness with or without steel lining or of steel plates stiffened by steel angles The shuttering shall be supported on battens and beams and props of vertical bullies properly cross braced together so as to make the

centering rigid. In places of bullies props, brick pillar of adequate section built in mud mortar may be used.

- 26.2. The form work shall be sufficiently strong and shall have camber so that it assumes correct shape after deposition of the concrete and shall be able to resist forces caused by vibration of live load of men working over it and other incidental loads associated with it. The shuttering shall have smooth and even surface and its joints shall permit leakage of cement grout.
- 26.3. If at any stage of work during or after placing concrete in the structure, the form work sags or bulges out beyond the required shape of the structure, the concrete shall be removed and work redone with fresh concrete and adequately rigid form work. The complete form work shall be got inspected by and got approved from the Engineer-in charge, before the reinforcement bars are placed in position.
- 26.4. The props shall consist of bullies having 100 mm minimum diameter measured at mid length and 80 mm. at thin end shall be placed as per design requirement. These shall rest squarely on wooden sole plates 40 mm. thick and minimum bearing area of 0-10 sq.m laid on sufficiently hard base.
- 26.5. Double wedges shall further be provided between the sole plate and the wooden props so as to facilitate tightening and easing of shuttering without jerking the concrete
- 26.6. The timber used in shuttering shall not be so dry as to absorb water from concrete and swell or bulge nor so green or wet as to shrink after erection. The timber shall be properly sawn and planed on the sides and the surface coming in contact with concrete wooden form work with metal sheet lining or steel plates stiffened by steel angles shall be permitted
- 26.7. As far as practicable, clamps shall be used to hold the forms together and use of nails and spikes avoided.
- 26.8. The surface of timber shuttering that would come in contact with concrete shall be well wetted and coated with soap solution before the concreting is done. Alternatively coat of raw linseed oil or oil of approved manufacture may be applied in place of soap solution. In case of steel shuttering either soap solution or raw linseed oil shall be applied after thoroughly cleaning the surface. Under no circumstances black or burnt oil shall be permitted.
- 26.9. The shuttering for beams and slabs shall have camber of 4 mm per meter (1 in 250) or as directed by the Engineer-in-charge so as to offset the subsequent deflection. For cantilevers, the camber at free end shall be 1/50 of the projected length or as directed by the Engineer-in-charge.

M- 27. Expansion Joints - Premoulded filler

- 27.1. The item provides for expansion joints in R.C C. frame structures for internal joints, as well as exposed joints, with the use of premoulded bituminous joint filler.
- 27.2. Premoulded bituminous joints filler i.e. performed strip of expansion joints filler shall not get deformed, or broken by twisting bending or other handling when exposed to atmospheric condition. Pieces of joints filler that have been damaged shall be rejected
- 27.3. Thickness of the per-moulded joints filler shall be 25 mm. unless otherwise specified.
- 27.4. Premoulded bituminous joints filler shall conform to I S 1838-1961

M-28. Expansion joints-Copper strips & hold .fasts

- 28.1. The item provide for expansion joints in R.C.C. frame structure for internal joints, as well as exposed joints, with the use of premoulded bituminous joints filler.
- 28.2. Copper sheet shall be of 1.25 mm. width and or 1 25 mm. width and the " U " shape in the middle. Copper strip shall have holdfast of 3 mm diameter copper rod fixed to the plate soldered on strip at

intervals of about 30 cm or as shown in the drawing or as directed. The width of each flange (horizontal side) of the copper plate Jo be embedded in the concrete work shall be 25 mm depth of "U" to be provided in the expansion joint, in the copper plate shall be of 25 mm.

M-29. Teak wood

29.1. The teak wood shall be of good quality as required for the item to be executed. When the kind of wood is not specifically mentioned, good Indian teak wood as approved shall be used.

29.2. Teak wood shall generally be free from large, loose dead or cluster knots, flaws, shakes, warps, twists, bends or any other defects. It shall generally be uniform in substance and of straight fibers as far as possible. It shall be free from rot decay, harmful fungi and other defects of harmful nature which will affect the strength, durability or its usefulness for the purpose for which it is required. The colour shall be uniform as far as possible. Any effort like painting using any adhesive materials made to hide the defects shall render the pieces liable to rejection by the Engineer-in-charge.

29.3. All scantlings, planks etc. shall be sawn in straight lines and planes in the direction of grains and of uniform thickness.

29.4. The tolerances in the dimensions shall be allowed at the rate of 1.5 mm per face to be planed.

29.5. First class teak wood

29.5.1. First class teak wood shall have no individual hard and-sound knots, more than 6 sq. cm. in size and the aggregate area of such knots shall not be more than 1% of area of piece, The timber shall be closed grained.

29.6. Second Class Teak Wood:

29.6.1. No individual hard and sound knots shall be more than 15 sq. cms. in size and aggregates area of such knots shall be not exceed 2% of the area of piece.

M-29. A Non-teak wood:

The non-teak wood shall be chemically treated, seasoned as per I.S. Specifications and of good quality. The type of wood shall be got approved before collecting the same on site Fabrication of wooden members shall be started only after approval. For this purpose wood of Bio, Kalai, Sires. Saded, Behda, Jamun, Sisoo will be used for door where as only Kalai. Sires, Halda. Kalam etc. will be permitted for shutters after proper seasoning and chemical treatment.

The non-teak wood shall be free from large loose dead of cluster knots, flows, shakes, warps, bends or any other defects, It shall be uniform in substance and of straight fibers as far as possible It shall be free fro rots, decay, harmful fungi and other defects of nature which will effect the strength, durability or its usefulness for the purpose for which it is required. The colour of wood shall be uniform as far as possible. The scantlings planks etc. shall be saw in straight lines and planes in the direction of grain and of uniform thickness. The department will use the Agency to produce certificate from Forest Department in event of dispute and the decision of the Department shall be final and binding to the contractor. The tolerance in the dimension shall be allowed at 1.5 mm. per face to be planed.

M-30. Wooden flush door shutters (solid core)

30.1. The solid core type flush door shutters shall be of decorative or non-decorative type as specified in the drawing. The size and thickness of the shutter shall be as specified in drawings or as directed. The timber species for core shall be used as per I.S.2202 (part -I) 1980. The timber shall be free from decay and insect attack Knots and knot holes less than half the width of cross-section of the members in which they occur may be permitted. Pitch pockets, pitch streaks and harmless pin

holes shall be permissible except in the exposed edges of the core members. The commercial plywood, cross-bands shall conform to I.S. 303-1275.

- 30.2.** The face panel of the shutters shall be formed by gluing by the hot press process on both faces of the core with either plywood or cross-bands and face veneers. The1 hopping, rebating opening of glazing, venation etc. shall be provided if specified in the drawing.
- 30.3.** All edges of the door shutters shall be square. The shutters shall be free from twist or warp in its plane. Both faces of the shutters shall be sand papered to smooth even texture.
- 30.4.** The shutters shall be tested for-
- (1) End immersion test:** The test shall be carried out as per I.S.2202 (part-1) 1980 There shall be no delamination at the end of the test.
- (2) Knife Test :** The face panel when tested in accordance with I.S 1659-1979 shall pass the test.
- (3) Glue adhesion test :** The flush door shall be tested for glue adhesive test in accordance with I S 2202 (part -I) 1980. The shutters shall be considered to have passed the test, if no delamination occurs in the glue lines in the plywood and if no single determination more than 80 mm in length and more than 3 mm in depth has occurred in the assembly glue lines between the plywood face and the style and rail. Delamination at the corner shall be measured continuously around the corner Delamination at the knots, knot hole and other permissible wood defects shall not be considered in assessing the sample.
- 30.5.** The tolerance in size of scud core type flush door shall be as under :
- In Nominal thickness ± 1.2 mm. In Nominal height ± 3 m
- 30.6.** The thickness of the shutter shall be uniform throughout with a permissible variation of not more than 0.8 mm. when measured at any points.

M-31. Aluminum doors, windows, ventilators

- 31.1.** Aluminum alloy used in the manufacture of extruded window sections shall conform to I.S. designation HEAWP of I.S. 733-1975 and also to I S. Designation WVG-WP of I.S 1285-1975 The section shall be as specified in the drawing and design. The fabrication shall be done as directed
- 31.2.** The hinges shall be cast or extruded aluminum hinges of same type as in window but of larger size.
- 31.3.** The hinges shall normally be of 50 mm. projecting type. Non-projecting type of hinges may also be used if directed. The handles of door shall be of specified design. A suitable lock for the door Operable either from outside or inside shall be provided. In double shutter door, the first closing shutter shall have concealed aluminum alloy bolt at top and bottom.

M-32. Rolling Shutters

- 32.1.** The rolling shutters shall conform to I.S.6248-1979 Rolling shutters shall be supplied of specified type with accessories. The size of the rolling shutters shall be specified in the drawings. The shutters shall be specified in the drawings. The shutters shall be constructed with interlocking lath sections formed from cold rolled steel strips not less than 0.9 mm. thick and 80 mm. wide for shutters up to 3.5 m .width not less than 1.25 mm. thick and 80 mm wide for shutters 3.5 m. in width and above unless otherwise specified.
- 32.2.** Guide channels shall be of mild steel deep channel section and of rolled pressed or built up (fabricated) joint less construction The thickness of sheet used shall not be less than 3.15 mm.
- 32.3.** Hood covers shall be made of M S. Sheets not less than 0.90 mm. thick. For shutters having width 3.5 Meter and above, the thickness of M.S. sheet for the hood cover shall be not less than 1 25 mm.

- 32.4.** The spring shall be of best quality and shall be manufactured from tested high tensile spring steel wire of strip of adequate strength to balance the shutters in all position. The spring pipe shaft etc. shall be supported on strong M S of malleable C I. brackets. The brackets shall be fixed on or under the lintel as specified with raw plugs and screws bolts etc.
- 32.5.** The rolling shutters shall be of self rolling up to 8 Sq. m. clear area without ball bearing and up to 12 Sq.m. clear area with ball bearing. If the rolling shutters are of larger, then gear operated type shutters shall be used.
- 32.6.** The locking arrangement shall be provided at the bottom of shutter at both ends The shutters shall be opened from outside.
- 32.7.** The Shutters shall be completed with door suspension shafts, looking arrangements, pulling hooks, handles and other accessories.

M-33. Collapsible Steel Gate

- 33.1.** The collapsible steel gate shall be in one or two leaves and size as per approved drawings or as specified. The gate shall be fabricated from best quality mild steel channels, flats etc. Either steel pulleys or ball-bearings shall be provided in every double channel Unless otherwise specified the particulars of collapsible gate shall be as under.
- (a) Pickets : These shall be of 20 mm. M.S. channels of heavy sections unless otherwise shown on drawings. The distance centre to centre of pickets shall be 12 cms .with an opening or 10 Cms
- (b) Pivoted M.S. flats shall be 20 mm x6 mm
- (c) Top and bottom guides shall be from tee of flat iron of approved size.
- (d) The fittings like stoppers fixing, locking cleats, brass handles and cast iron rollers shall be of approved design and size

M-34. Welded Steel Wire Fabric

- 34.1** Welded steel wire fabric for general purpose shall be manufactured form cold drawn steel wire "as drawn" or galvenised steel conforming to I.S. 226-1975 with longitudinal and transverse wire securely connected at every intersection by a process of electrical resistance welding and conforming to I.S.4948-1974. it shall be fabricated and finished in workmanlike manner and shall be free from injurious defects and shall be rust proof The type of mesh shall be oblong or square as directed The mesh sizes and sizes if wire for square 3b well as oblong welded steel wire fabric shall be as directed The steel wire fabric in panels shall be in one whole piece in each panel as far as stock sizes permit.

M-35 Expanded Metal Sheets

- 35.1.** The expanded metal sheets shall he free from flaws joints broken strands laminations and other harmful surface defects. Expanded metal steel sheet shall confirm to IS-412-1975. except that blank sheets need not be with guaranteed mechanical properties The size of the diamond mesh of expanded metal and dimensions of strands (width and thickness) shall be as specified. The tolerance on nominal weight of expanded metal sheets shall be of + 10 percent.
- 35.2.** Expanded metal in panels shall be in one whole piece in each panel as far as stock sizes permit. The expanded metal sheets shall be coated with suitable protective coating to prevent corrosion.

M-36. Mild Steel Wire (Wire Gauze Jali)

- 36.1.** Mild steel wire may be galvanized as indicated. All finished steel wire shall be well cleanly drawn to the dimensions and size of wire as specified in item. The wire shall be sound free from splits surface flaws, rough jagged and imperfect edges and other harmful surface defects and shall conform to I.S. 280-1978.

M-37. Plywood

37.1. The plywood for general purpose shall conform I.S. 303-17-1975.

Plywood is made by cementing together than boards or starts of wood into panels. There are always an odd number of layers, 3,5,7,9, ply etc. The piles are placed so that grain of each layer is at right angles to the grain in the adjacent level.

37.2. The chief advantages of plywood a single board of the same thickness is the more uniform strength of the plywood, along the length and width of the plywood and greater resistance to cracking and splitting with charge in moisture content.

37.3. Usually synthetic resins are used to gluing, phenolic resins are usually cured in a hot press which compresses and simultaneously heats the plies between hot plates which maintain a temperature of 90 degree C to 140 degree C and a pressure of 11 to 14 Kg/ Sq. Cm on the wood. The time of heating may be anything from 2 to 60 minutes depending upon thickness

37.4. When water glue are used the wood absorbs so much water that the finished plywood must be dried carefully. When synthetic resigns are used as adhesive the finished plywood must be exposed to an atmosphere of controlled humidity until the proper amount of moisture has been absorbed.

37.5. According to I.S. 303-1975 the plywood for general purpose shall be of the grades namely BWR, WWR and CWR depending up to the adhesives used for bonding the veneers and it will be further classified into six types namely AA, AB, AC, BB, BC and CC based on the quality of the two faces each face being of three kinds namely A, Band C After pressing, the finished plywood should be reconditioned to a moisture content not less than 8 percent and not more than 16 percent.

37.6. Thickness of plywood Boards

Board	Thickness	Board	Thickness	Board	Thickness	Board	Thickness
3 Ply	3 mm	5 Ply	5 mm	7 Ply	9 mm	9 Ply	16 mm
	4 mm		6 mm		13 mm		19 mm
	5 mm		8 mm		16 mm	11 Ply	19 mm
	6 mm		9 mm	9 Ply	13 mm		25 mm

M-38. Glass

38.1. All glass shall be of the brief quality, free from specks, bubbles, smokes veins, air holes blisters and other defects. The kind of glass to be used shall be as mentioned in the item or specification or in the special provision or as shown in detailed drawings. Thickness of glass panes shall be uniform. The specifications for different kinds of glass shall be as under.

38.2. Sheet Glass

38.2.1. In absence of any specified thickness or weight in the item or detailed specifications of the item of work, sheet glass shall be weighing 7.5 Kg/Sq. m for panes up to 600 mm x 600 mm.

38.2.2. For panes larger than 600 mm x 600 mm and up to 800 mm x 800 mm the glass weighing not less than 8.75 Kg/Sq m shall be used for bigger panes up to 900 mm x 900 mm. glass weighing not less than 8.75 Kg/Sq. m shall be used. For bigger panes up to 900 mm x 900 mm. glass weighting not less than 11.25 Kg/Sq. m. shall be used

38.2.3. Sheet glass shall be patent flattened glass of best quality and for glazing and framing purposes shall conform to I.S. 1761-1960. Sheet glass of the specified colours shall be used, if so shown, on detailed drawings or so specified For important buildings and for panes with any dimension over 900 mm plate glass of specified thickness shall be used

38.3. Plate Glass:

38.3.1. When plate glass is specified it shall be "polished patent plate glass" of best quality It shall have both the surface ground flat and parallel and polished to obtain clear undisturbed vision and reflection The plate glass shall be of the thickness mentioned in the item or as shown in the detailed drawing or as specified. In absence of any specified thickness, the thickness of plate glass to be supplied shall be 6 mm and a tolerance of 0.20 mm shall be admissible

38.4. Obscured Glass:

38.4.1. This type of glass transmits light so that vision is partially or almost completely obscured. Glass shall be plain rolled, figured, ribbed or fluted, or frosted glass as may be specified as required. The thickness and type of glass shall be as per details on drawings or as specified or as directed

38.5. Wired Glass:

38.5.1. Glass shall be with wire netting embedded in a sheet of planet glass. Electrically welded 13 mm Georgian square mesh shall be used Thickness of glass shall not be less than 6 mm Wired glass shall be of type and thickness as specified

M-39. Acrylic Sheets

39.1. Acrylic sheets shall be of thickness as specified in the item and of an specified shape and size as the case may be panels may be flat or curved It should be light in weight it shall be colourless or coloured or opaque as specified in the item. Colourless sheet shall be as transparent as the finest optical glass. Its light transmission rate shall be about 95% Transparency shall not be affected for the sheets of larger thickens, it shall be extremely resistant to sunlight weather and low temperatures. It shall not sow any significant yellowing or change in physical properties or loss of light transmission over a longer period of use. The sheet shall be impact resistant also Sheets should be of such quality that they can be cut, bent jointed as desired Solution for the joints shall be used as per the requirement of manufacturer.

M-40. Particle board

40.1. The particle boards used for face panels shall of best quality free from any defects. "I he particle boards shall be made with phenolmaldehyde adhesive The particle boards shall conform I S 3087-1905 "Specification for wood particle board for general purpose" The size and the thickness shall be as indicated.

M-41. Expanded polystyrene or framed styroper slabs

41.1. The expanded polystyrene ceiling boards and tiles shall be of approved make and shall be of sizes, thickness, finish and colour as indicated. It shall be of high density and suitable for use as insulating material. The insulating material shall be like slabs of Thermocole etc.

M-42. Resign bonded fiber glass.

42.1. The resign bonded fiber glass tiles or roils shall be of approved make and shall be of sizes. thickness and finish as indicated.

42.2. For test of Mineral wool thermal insulation [Blanket I S 3144-1965 shall be followed

42.3. Insulation wool blanks shall be with the following coverings on one or both sides as indicated

- (1) Bituminous Hessian Kraft paper suitable for use in position where moisture has to be excluded.
- (2) Hessian cloth or Kraft paper for keeping out dust
- (3) G.I wire netting, suitable for surfaces to be plaster over

M-43. Fixtures and fastenings

43.1. General:

- 43.1.1. The fixtures and fastenings, that is butt hinges tee and strap hinges sliding door bolts, tower bolts, door latch, bath-room latch, handles door stoppers, casement window fasteners, casement stays and ventilators catch shall be made of the metal as specified in the item or its specification.
- 43.1.2. They shall be of iron, brass, aluminum chromium plated iron, chromium plated brass, copper oxidised iron, copper oxidised brass or anodised aluminum as specified
- 43.1.3. The fixtures shall be heavy medium or light type. The fixtures and fastenings shall be smooth finished and shall be such as will ensue ease of operations.
- 43.1.4. The samples of fixtures and fastenings shall be got approved as regards, quality and shape before providing them in position.
- 43.1.5. Brass and anodised aluminium fixtures and fastenings shall be bright finished

43.2. Holdfasts:

- 43.2.1. Holdfasts shall be made from mild steel flat 30 cm length and one of the holdfasts shall be bent at right angle and two nos of 6 mm. diameter holes shall be made in it for fixing it to the frame with screws. At the other end, the holdfast shall be forked and bent at right angles in opposite directions.

43.3. Butt hinges:

- 43.3.1. Railway standard heavy type butt hinges shall be used when so specified
- 43.3.2. Tee and strap hinges shall be manufactured from M S Sheet

43.4. Siding door bolts (Aldrops):

- 43.4.1. The aldrops as specified in the item shall be used and shall be got approved.

43.5. Tower bolts (Barrel Type):

- 43.5.1. Tower bolts as specified in the item shall be used and shall be got approved

43.6. Door Latch:

- 43.6.1. The size of door latch shall be taken as the length of latch.

43.7. Bathroom Latch:

- 43.7.1. Bathroom latch shall be similar to tower bolt.

43.8. Handle:

The size of the handles shall be determined by the inside grip length of the handles. Handles shall have a base plate of length 50 mm. more than the size" of the handle.

43.9. Door Catch:

- 43.9.1. Door stoppers shall be either floor door stopper type or door catch type Floor stopper shall be of overall size as specified and-shall have a rubber cushion.

43.10. Door Stoppers:

- 43.10.1. Door catch shall be fixed at a height to about 900 mm from the floor level such that one part of the catch is fitted on the inside of the shutter and the other part is fixed in the wall with necessary wooden plug arrangements for appropriate fixity The catch shall be fixed 20 mm inside the face of the door for easy operation of catch.

43.11. Wooden Door Stop with hinges:

- 43.11.1. Wooden door stop of size 100 mm x 40 mm x 40 mm shall be fixed on the door frame with a hinges of 75 mm. size and at a height of 900 mm. from the floor level The wooden door stop shall be provided with 3 coats of approved oil paint

43.12. Casement Window Fastener:

43.12.1. Casement window fastener for single leaf window shutter shall be left or right handed as directed.

43.13. Casement stays (Straight Red Stay):

43.13.1. The stays shall be made from a channel section having three holes at appropriate position so that the window can be opened either fully or partially as directed. Size of the stay shall be 250 mm to 300 mm. as directed.

43.14. Ventilator Catch:

43.14.1. The pattern and shape of the catch shall be as approved

43.15. Pivot:

43.15.1. The base and socket plate shall be made from minimum 3 mm. thick plate: and projected pivot shall not be less than 12 mm 'diameter and 12 mm. length and shall be firmly riveted to the base plate in case of iron pivot and in single piece plate in the case of brass pivot.

M-44. Paints:

44.1. (A) Oil paints :

44.1.1. Oil paints shall be of the specified colour and as approved. The ready mixed paints shall only be used. However, if ready mixed paint of specified shade or tint is not available white ready mixed paint with approved stainer will be allowed In such a case the contractor shall ensure that the shade of the paint so allowed shall be uniform.

44.1.2. All the paints shall meet with the following general requirements.

(i) Paint shall not show excessive setting in a freshly opened full can and shall easily be ready spread with a paddle to a smooth homogeneous state. The paint shall show no curdling, levering caking or colour separation and shall be free from lumps and skins.

(ii) The paint as received shall brush easily, possess good leveling properties and show no running or sagging tendencies.

(iii) The paint shall not skin within 48 hours in a three quarters filled closed container.

(iv) The paint shall dry to a smooth uniform finish free from roughness, grit unevenness and other imperfections.

44.1.3. Ready mixed paint shall be used exactly as received from the manufacturers and generally according to their instructions and without any admixtures whatsoever

44.2. (B) Enamel paints:

44.2.1. The enamel paint shall satisfy in general requirements in specification of oil paints, Enamel paint shall conform to I.S. 2933-1975.

M-45. French Polish

45.1. The French polish of required tint and shade shall be prepared with the below mentioned ingredients and other necessary materials:

(i) Denatured spirit of approved quality (ii) Chandras (iii) Pigment.

45.2. The French polish so prepared shall conform to I S : 348-1 9C8.

M-46. Marble chips for marble mosaic terrazzo

46.1. The marble chips shall be of approved quality and shades. It shall be hard, sound, dense and homogeneous in texture with crystalline and coarse grains It shall be uniform in colour and free from stains cracks, .decay and weathering.

46.2. The size of various colours of marble chips ranging from the smallest up to 20 mm shall be used where the thickness of top wearing layer is 6 mm size The marble chips of approved quality and

colours only as per grading as decided by the Engineer-in-charge shall be used for marble mosaic tiles or works.

- 46.3.** The marble chips shall be machine crushed. They shall be free from foreign matter, dust etc. Except as above, the chips shall conform to I S 2114-1962

M-47. Flooring Tiles

47.1. (A) Plain Cement tiles;

- 47.1.1.** The plain cement tiles shall be of general purpose type. These are the tiles in the manufacture of which no pigments are used. Cement used in the manufacture of tiles shall be as per Indian Standards.

- 47.1.2.** The tiles shall be manufactured from a mixture of cement and natural aggregates by pressure process. During manufacture the tiles shall be subjected to pressure of not less than 140 Kg/Sq. Cm. The proportion of cement to aggregate in the backing of the tiles shall be not less than 1 .3 by weight The wearing face, through the tiles are of plain cement, shall be provided with stone chips of 1 to 2 mm. size. The proportions of cement to aggregate in the wearing layer of the tiles shall be three parts of cement to one parts chips by weight. The minimum thickness of wearing layer shall be 3 mm. The colour and texture of wearing layer shall be uniform throughout its face and thickness. On removal from mould, the tiles shall be kept in moist condition continuously at least for seven days and subsequently, if necessary, for such long period as would ensure their conformity to requirements of I.S.1237-1980 regarding strength resistance to wear and water absorption.

- 47.1.3** The wearing face of the tiles shall be plane, free from projections, depressions and cracks and shall be reasonably parallel to the back face of the tile. All angles shall be right angle and all edges shall be sharp and true.

- 47.1.4.** The size of tiles generally be square shapes 24.85 Cm x24.85 Cm. or 25 Cm x 25 Cm The thickness of tiles shall be 20 mm.

- 47.1.5.** Tolerance of length and breadth shall be plus or minus one millimeter Tolerance on thickness shall be plus 5mm.

- 47.1.6.** The tiles shall satisfy the tests as regards transverse strength, resistance to wear and water absorption as per I.S 1237-1980.

47.2. (B) Plain Coloured Tiles:

- 47.2.1.** The tiles shall have the same specification as for plain cement tiles as per (A) above except that they shall have a plain wearing surface wherein pigments are used. They shall conform it I.S. 1237-1980.

- 47.2.2.** The pigments used for colouring cement shall not exceed 10 percent by weight of cement used in the mix. The pigments, synthetic or otherwise, used for colouring tiles shall have permanent colour and shall not contain materials detrimental to concrete

- 47.2.3** The colour of the tiles shall be specified in the item or as directed

47.3. (C) Marble mosaic tiles:

- 47.3.1.** These tiles have same specification as per plain cement tiles except the requirements as stated below.

- 47.3.2.** The marble mosaic tiles shall conform to I.S 1237-1980. The wearing face of the tiles shall be mechanically ground and filled. The wearing face of tiles shall be free from projections depressions and cracks and shall be reasonably parallel to the back face of the tiles. All angles shall be right angles and all edges shall be sharp and true.

- 47.3.3.** Chips used in the tiles be from smallest up to 20 mm. size. The minimum thickness of wearing layer of tiles shall be 6 mm. For pattern of chips to be had on the wearing face; a few samples with or without their full size photographs as directed shall be approved by the Engineer-in-charge, for approval.
- 47.3.4.** Any particular samples if found suitable shall be approved by the Engineer-in-charge, or he may ask for a few more samples to be presented. The samples shall have to be made by the contractor till a suitable sample is finally approved for use in the work. The Contractor shall ensure that the tiles supplied for the work shall be in conformity with the approved sample only, in terms of its dimensions, thickness of backing layer and wearing surface, materials, ingredients, colour, shade, chips, distribution etc. required.
- 47.3.5.** The tiles shall be prepared from cement conforming to Indian Standards or coloured port land cement generally depending upon the colour of tiles to be used or as directed.
- 47.4. (D) Chequered Tiles :**
- 47.4.1.** Chequered tiles shall be plain cement tiles or marble mosaic tiles. The former shall have the same specification as per (A) above and the latter as per marble mosaic tiles as per (C) except as mentioned below
- 47.4.2.** The tiles shall be of nominal size of 250 mm. x 250 mm. or as specified. The centre to centre distance of chequer shall not be less than 25 mm. and not more than 50 mm. The overall thickness of the tile shall be 22 mm
- 47.4.3.** The grooves in the chequers shall be uniform and straight. The depth of the grooves shall not be less than 3 mm. The chequered tiles shall be plain coloured or mosaic as specified. The thickness of the upper layer measured from the top of the chequers shall not be less than 6 mm. The tiles shall be given the first grinding with machine before delivery to site.
- 47.4.4.** Tiles shall conform to relevant I.S 1237-1980.

47.5. (E) Chequered Tiles For Stair Cases :

- 47.5.1.** The requirements of these tiles shall be the same as chequered tiles as per (D) above except in following respects :
- (1) The length of a tile including nosing shall be 300 mm (2) The minimum thickness shall be 28 mm (3) The nosing shall have also the same wearing layer as at the top. (4) The nosing edge shall be rounded (5) The front portion of the tile for a minimum length of 75 mm. from and including the nosing shall have grooves running parallel to nosing and at centers not exceeding 25 mm. Beyond that the tiles shall have normal chequer pattern.

M-48. Rough Kotah Stone

- 48.1.** The Kotah stones shall be hard even, sound, and regular in shape and generally uniform in colour. The colour of the stone shall generally be green Brown coloured shall not be allowed for use. They shall be without any soft veins, cracks or flaws.
- 48.2.** The size of the stones to be used for flooring shall be of size 600 mm x 600 mm and/or size 600 mm. x 450 mm as directed. However smaller sizes will be allowed to be used to the extent of maintaining required pattern. Thickness shall be as specified
- 48.3.** The edges of stones shall be dressed to a minimum of 30 mm on accounts of chisel dressing of edges shall be permitted for length as well as breadth. Tolerance in thickness shall be ± 3 mm
- 48.4.** The edges of stones shall be truly chiseled and table rubbed with coarse sand before paving. All angles and edges of the stones shall be true, square and free from chipping and surface shall be true and plain.

- 48.5.** When machine cut edges are specified, the exposed and the edges at joints shall be machine cut
The thickness of the exposed machine cut edges shall be uniform

M-49. Polished Kotah Stoics

- 49.1.** Polished kotah stone shall have the same specification as per rough kotah stone except as mentioned below :
- 49.2.** The stones shall have machine polished surface. When brought on site, the stones-shall be single polished or double polished depending upon its use. The stones for paving shall generally be single polished The stones to be used for dedo, skirting, sink, veneering, sills steps etc. where machine polishing after the stones are fixed in situ is not possible shall be double polished

M-50. Dholpur Stone Slab

- 50.1.** Dholpur stone slab shall be of best quality as approve by the Engineer-m-charge. The stone slab shall be without my veins, cracks, and flaws The stone slab shall be even sound and durable regular in snaps and of uniform colour
- 50.2.** The size of the stone shall be as specified in the item or detailed drawing or as approved by the Engineer-in-charge. The thickness of the stone shall be as specified in the item of work with the permissible tolerance of plus or minus 2 mm. The provision in respect of polishing as for polished kotah stone shall apply to polished Dholpur stone also. All angles and edges of the face of the stone slab shall be fine chiseled or polished as specified in the item of work and all the four edges shall be machine cut All angles and edges of the stone slab shall be true and plane.
- 50.3.** The sample of stone shall be got approved by the Engineer-in-charge for a particular work It shall be ensured that the stones to be used in a particular work shall not differ much in shade or tint from the approved sample.

M-51. Marble Slab

- 51.1.** Marble slab shall be white or of other and of best quality as approved by the Engineer-in-charge
- 51.2.** Slabs shall be hard, close, uniform and homogeneous in texture. They shall have even crystalline gram and free from defects and cracks. The surface shall be machine polished to an even and perfect plane surface and edges machine cut true and square. The rear f ice shall be rough to provide key for the mortar.
- 51.3.** Marble slabs with natural veins, if selected shall have to be laid as per the pattern given by the Engineer-in-charge.
Size of the slab shall be minimum 460 mm x 450 mm and preferably 600 mm x 600 mm. However, smaller sizes will be allowed to be used of the extent of maintaining required pattern.
- 51.4.** The slab shall not be thinner than the specified thickness at its thinnest part. A few specimen of finished slab to be used shall be deposited by the Contractor in the office for reference
- 51.5.** Except as above the marble slabs shall conform to I.S. 1130-1969

M-52. Granite Stone slab

- 52.1.** Granite shad be of approved colour and quality. The stone shall be hard, even sound and regular in shape and generally uniform in colour. It shall be without any soft veins, cracks of flaws.
- 52.2.** The thickness of the stone shall be specified in items
- 52.3.** All exposed faces shall be double polished to tender truly smooth and even reflecting surface. The exposed edges and corners shall be rounded off as directed. The exposed edges shall be machine cut and shall have uniform thickness.

M-53. P.V.C. Flooring

53.1. P.V.C. sheets for P.V.C., floor covering shall be of homogenous flexible type conforming to I S 3462-1966. The P.V.C. covering shall neither develop any toxic effect while put to use nor shall give off any disagreeable odour.

53.2. Thickness of flexible type covering tiles shall be as specified in the description of the item

53.3. The flexible type shall be backed with Hessian or other woven fabric The following tolerances shall be applicable on the nominal dimensions of the rolls or tiles :

(a) Thickness + 015 mm.

(b) Length or Width

(1) 300 mm. Square tiles ± 0.20 mm. (3) 900 mm Square tiles ± 0.60 mm.

(2) 600 mm. Square tiles ± 0.40 mm. (4) Sheets and roll ±0.10 percent.

53.4. Adhesive:

53.4.1. The adhesive for PVC flooring shall be of the type and make recommended by the manufactures of PVC sheets/tiles.

M-54. Facing Tiles

54.1. The facing tiles (burnt clay facing bricks) shall be free from cracks, and nodules of free lime. They shall be thoroughly burnt and shall have plane rectangular faces with parallel sides and sharp straight right angled faces. The texture of the finished surface that will be exposed when in place shall conform to an approved sample consisting not less than for stretcher bricks each representing the texture desired. The facing tiles shall have a pleasing appearance, sufficient resistance to penetration by ram and greater durability than common bricks. The tiles shall conform to I.S. 2691-1972.

54.2. The standard size of facing brick tiles shall be 19 x 9 x 4 cms. The facing brick tiles shall be provided with frog which shall conform to I.S. 11077-1976.

54.3. The permissible tolerance in dimensions specified above shall be as follows:

Size	Tolerance for	
	1st Class Brick	2nd Class Brick
19 cm.	± 6 mm	± 10 mm
9 cm.	± 3 mm	± 7 mm
4 cm.	± 1.5 mm	± 3 mm

54.4. The tolerance for distortion or warpage of face or edges of individual brick from a plane surface and from a straight line respectively shall be as follows:

Facing dimensions	Permissible tolerance
Max. below 19 cms.	Max. 2.5 mm
- do - above 19 cm.	Max. 3.0 mm

54.5. The average compressive strength obtained as a sample of five tiles when tested in accordance with the procedure laid as per I S 1077-1976 shall be not less than 175 Kg/Sq Cm. The average compressive strength of any individual bricks shall be not less than 160 Kg / Sq.Cm.

54.6. The average water absorption for five bricks tiles shall not exceed 12 percent of average weight of brick before testing. The absorption for each individual bricks shall not exceed 25 percent.

54.7. The brick tiles when tested in accordance with I.S. 1077-1976, the rate of efflorescence shall not be more than "Slightly effloresced"

M-55. White glazed tiles

- 55.1.** The tiles shall be of best quality as approved by the Engineer-in-charge. They shall be flat and true to shape. They shall be free from cracks, crazing spots chipper) edges and corners. The glazing shall be of uniform shade.
- 55.2.** The tiles shall be nominal size of 150 mm x 150 mm unless otherwise, specified. The maximum variation the stated sizes other than the thickness of tile shall be plus or minus 1.5 mm. The thickness of tile shall be 6 mm. Except as above the tiles shall conform to I.S. 1977-19/0.

M-56. Galvanised iron pipes and fittings

- 56.1.** Galvanised iron pipes shall be of the medium type and of required diameter and shall comply with I.S. 1239-1979. The specified diameter of the pipes shall refer to the inside diameter of the bore, clamps, screw and all galvanised iron fittings shall be of the standard 'R' or equivalent make.

M-57. Bib cock and stop cock

- 57.1.** A bib cock is a draw off tap with a horizontal inlet and free outlet A stop cock is a valve with suitable means of connection for insertion in a pipe line for controlling or stopping the flow.
- 57.2.** They shall be of screw down type and of brass chromium plated and of diameter as specified in the description of the item. They shall conform to I S. 781-1977 and they shall be of best Indian make. They shall be polished bright.
- 57.3.** The minimum finished weight of bib cock and stop cock shall be as given below :

Diameter	Bib Cock	Stop Cock	Diameter	Bib Cock	Stop Cock
8 mm	0.25 Kg.	0.25 Kg.	15 mm	0.40 Kg.	0.40 Kg.
10 mm	0.30 Kg.	0.35 Kg.	20 mm	0.75 Kg.	0.75 Kg.

M-58. Gun metal wheel valve

- 58.1.** The gun metal wheel valve shall be of approved quality. These shall be of gun metal fitted with wheel and shall be of gate valve opening full way and of the size specified. These shall conform to I.S. 778-1971.

M-59. White glazed porcelain wash basin

- 59.1.** Wash basin shall be of white porcelain first quality best Indian make and it shall conform to I.S. 2556 (Part -IV) -1972 and I.S. 771-1979. The size of the wash basin shall be as specified in item. Wash basin shall be of one piece construction with continued over flow arrangements All internal angles shall be designed so as to facilitate cleaning. Wash basin shall have single tap hole as specified. Each basin shall have a circular waste hole which is either riveted or beveled internally with 65 mm. diameter at top and 10 mm. depth to suit the waste fitting. The necessary stud slot to receive the bracket on the under side of the basin shall be provided Basin shall have an internal soap holder which shall fully drain into the bowl.
- 59.2.** White glazed pedestal of the quality and colour as that the basin shall be provided where specified in the item. It shall be completely recessed at the back for reception of supply and wash pipe. It shall be capable of supporting the basin rigidly and adequately and shall be so designed as to make the height from the floor the floor to top of the rim of basin 750 mm. to 800 mm. as directed.

M-60. European type water closet/with low flushing

- 60.1.** The European type water closet shall be white glazed porcelain first quality and shall be of wash down type conforming to I.S. 2556-1973 and I.S. 771-1979.
- 60.2.** 'S' trap shall be provided as required with water seal not than 50 mm. The solid plastic seat and cover shall be of best Indian make conforming to I.S 2548-1980. They shall be made of moulded synthetic materials which shall be tough and hard with high resistance to solvents and shall be free

from blisters and surface defects and shall have chromium plated brass hinges and rubber buffer of suitable size.

M-61. Orissa type water closet

- 61.1.** The Specification of Orissa type white glazed water closet of first quality shall conform to I.S. 2256 (Part-III) -1981 and relevant specification of Indian type water closet except that pan will be with the integral squatting pan of size 580 mm x 400 mm with raised footrest.

M-62. Indian type water closet

- 62.1.** The Indian type white glazed water closet of first quality shall be of size as specified in the item and conforming to I.S. 771-1979 and I.S. 2556 – (Part-II) 1981. Each pan shall have integral flushing. It shall also have an inlet at back and front for connecting flush pipes as directed. The inside of the bottom of the pan shall have sufficient slope from the front towards the outlet and surface shall be uniform and smooth. Pan shall be provided with 100 mm. diameter 'P' or 'S' trap with approximately 50 mm. Water seal and 50 mm. diameter vent horn.

M-62. A. Foot Rests

- 62.A.1.** A pair of white glazed earthen ware rectangular foot to minimum size 250 mm. x 130 mm. x 20 mm shall be provided with the water closet.

M-63. Glazed Earthen Ware Sink

- 63.1.** The glazed earthen-ware sink shall be of specified size, colour and quality. The sink shall conform, to I.S. 771 Part – II – 1979. The brackets for sinks shall conform to I.S 775-1970.
- 63.2.** The pipes shall conform to I.S. 1239-part-I 1973 and I.S. 404-1962 for steel and lead pipes respectively. 32 mm. brass waste coupling of standard pattern with brass chain and rubber plug shall be provided with sink.

M-64. Glazed earthen-ware Lipped type flat back urinal/corner type urinal

- 64.1.** The lipped type urinal shall be flat back or corner type as specified in the item and shall conform to I.S 771-1979. It shall be of best Indian make and size as specified and approved by the Engineer-in-charge. The flat back of corner type urinal must be of 1st quality free from any defects, cracks etc.

M-65. Low level Enamel flushing tank

- 65.1.** The low level enamel flushing tank shall be of 15 liters capacity. It shall conform to I S 774-1971. The flushing cistern shall be of best quality and free from any defects. The flushing tank shall have outlet 32 mm. diameter. The outlet shall be connected with W.C. pan by lead pipe or P.V.C. pipe as specified. The flushing tank shall be provided with inlet and outlet for fixing G.I. inlet pipes and over-flow pipes. The flushing cistern shall be provided with chromium plated handle for flushing. The flushing tank shall be provided with bracket of cast iron so that it can be fixed on wall at specified height. The brackets shall conform to I.S. 775-1970.

M-66. Cast iron flushing cistern.

- 66.1.** The cast iron flushing cistern shall be of 15 liters capacity. It shall conform to I.S. 774-1971. The flushing cistern shall be of best quality free from any defects. The flushing cistern shall have outlet of 32 mm diameter. The lead pipe shall conform to I.S 404 (Part-I) - 1962; For fixing G.I. inlet pipes and overflow pipe 20 mm. dia. inlet and outlet shall be provided. The flushing cistern shall be provided with galvanised iron chain and pull of sufficient length and shall be got approved from the Engineer-in-charge. The cast iron flushing cistern shall be painted with one coat of anticorrosive paint and two coats of primers. The flushing cistern shall be fixed on two C I brackets. The C I brackets shall conform to I S 775-1970.

M-67. Flush cock

67.1. Half turn flush cock (Heavy weight) shall be of gun metal chromium plated of diameter as specified in the description of the item. The flush cock shall conform to relevant Indian Standard.

M-68. Cast iron pipes and fittings.

68.1. All soil water, vent and anti syphonage pipes and fitting shall conform to I S.1729-1964. The pipes shall have spigot and socket ends with head on spigot end. The pipes and fitting shall be true to shape smooth, cylindrical, their inner and outer surfaces being as nearly as practicable concentric. They shall be sound and nicely cast and shall be free from cracks, laps, pinholes or there imperfection and shall be neatly dressed and carefully fettled.

68.2. The end of pipes and fittings shall be reasonable square to their axis.

68.3. The sand of cast iron pipes shall be of the diameter as specified in the description and shall be in lengths of 1.5 M., 1.8 M. including socket ends of the pipe unless shorter lengths are either specified or required at junctions etc. The pipes and fittings shall be supplied without ears unless specified or directed otherwise.

68.4. Tolerances :

68.4.1. The Standard weights and thickness of pipes shall be as shown in the following table A tolerance up to minus 10 per cent may however be -allowed against these standard weights

Sr. No.	Nominal dia. of Bore	Thickness	Overall		
			1.5 m long	1.8 m long	2 m. long
1.	75 mm	5.0 mm	12.83 Kg.	16.52 Kg.	18.37 Kg.
2.	100 mm	5.0 mm	18.14 Kg.	21.67 Kg.	24.15 Kg.

68.4.2. A tolerance up to minus 15 percent in thickness and 20 mm. length will be allowed For fittings tolerance in lengths shall be plus 25 mm. and minus 10 mm.

68.4.3. The thickness of fittings and their socket and spigot dimensions shall conform to the thickness and dimensions specified for the corresponding sizes of straight pipes. The tolerance in weights and thickness shall be the same as for straight pipes.

M-69. Nahni Trap

69.1. Nahni trap shall be of cast iron and shall be sound and free from porosity or other defects which affect serviceability The thickness of the base metal shall not be less than 6.5 mm The surface shall be smooth and free .form craze, chips and other flaws or any other kind of defects which affect serviceability The size of nahni trap shall be specified and shall be of self cleaning design.

69.2. The Nahni trap shall be of-quality approved by the Engineer-in-charge and shall generally conform to the relevant Indian Standards.

69.3. The Nahni trap provide shall be with deep seal, minimum 50 mm. except at places where trap with deep seal cannot be accommodated. The cover shall be cast iron perforated cover shall be provided on the trap of appropriate size.

M-70. Gully Trap

70.1. Gully trap shall conform to I.S. 651-1980. If shall be some, free from defects such as fire-cracks or hair cracks. The glaze of the traps shall be free from crazing. They shall give a sharp clear note when struck with light hammer. There shall be no broken blisters.

70.2. The size of the gully trap shall be as specified in the item.

70.3. Each gully trap shall have one C.I. grating of square size corresponding to the dimensions, of inlet of gully trap. It will also have a water tight C.I. cover with frame inside dimensions 300 mm. x 300

mm. the cover with frame inside dimensions 300 mm. x 300 mm. the cover and weighing not less than 4.53 Kg. and the frame not less than 2.72 Kg. The grating cover and frame shall be of sound and good casting and shall have truly square machined seating faces.

M 71. Glazed Stone Ware pipe And Fittings

71.1. The pipes and fittings shall be of best quality as approved, by the Engineer-in-charge. The pipe shall be of best quality manufactured from stone- ware of fire clay, salt glazed thoroughly burnt through the whole thickness, of a close, even texture, free from air blows, fire blisters, cracks and other imperfections, which affect the serviceability. The inner and outer surfaces shall be smooth and perfectly glazed. The pipe shall be capable to withstand pressures or 1.5 M lead without showing sign of leakage. The thickness of the wall shall not be less than 1/12th of the internal dia. The depth of socket shall not be less than 38 mm. The socket shall be sufficiently large to allow a joint of 6 mm. around the pipe.

71.2. The pipes shall generally conform to relevant I S 651-1980.

M-72. Wall Peg Rail

72.1. The aluminum wall peg rail shall have three aluminum pegs approved quality and size. It shall be fixed on teakwood plank of size 450 mm x 75 mm x 20 mm. The teakwood shall be French polished or oil painted as specified.

M-73. G.I. Water Spot

73.1. The G.I. pipes of 40 mm dia shall be of medium quality and specials shall be of 'R' brand or equivalent brand of best approved quality

73.2. The pipe shall have length as required for the thickness of wall in which it is fixed and at outside end tee bend cut at half the length shall be provided and at other end coupling shall be provided to have better fixing. The water spout shall be provided as per detailed drawing or as directed.

M-74. Asbestos Cement pipe (A.C. pipe)

74.1. The asbestos cement pipe of diameter as specified in the description of the item shall conform to I.S. 1626-1980. Special like bends, shoes, cowls, etc. shall conform to relevant Indian Standards. The interior of pipe shall have smooth finish, regular surface and regular internal diameter. The tolerance in all dimensions shall be as I.S. 1626-part-I-1980.

M-75. Crydon Ball valve

75.1. Ball valve of screwed type including polythene float and necessary level etc shall be of the size as mentioned in the description of item and shall conform to I.S 1703-1977

M-76. Bitumen Felt For Water proofing And Damp Proofing

76.1. Bitumen felt shall be on the fiber bases and shall be of type 2, self finished felt grade-2 and shall conform to I.S. 1322-1970

M-77. Selected Earth

77.1. The selected earth shall be that obtained from excavated material or shall have to be brought from outside as indicated in the items If item does not indicate anything the selected earth shall have to be brought from outside.

77.2. The selected earth shall be good yellow soil and shall be got approved from the Engineer-in-charge. In no case black cotton soil or similar expansive and shrinkable soil shall be used. It shall be clean and free from all rubbish and perishable materials, stones or brick bats. The clods shall be broken to a size of 50 mm or less. Contractor shall make his own arrangement at his own cost for land for borrowing selected earth. The stacking of material shall be done as directed by the

Engineer-in-charge in such a way not to interfere with any construction all activities and in proper stacks.

- 77.3.** When excavated material is to be used only selected stuff got approved from the Engineer-in-charge shall be used. It shall be stacked separately and shall, comply with all the requirements of selected earth mentioned above.

M-78. Barbed Wire

- 78.1.** The barbed wire shall be of galvanized steel and it shall generally conform to I.S. 278-1978. The barbed wire shall be of types-I whose nominal diameter for line wire shall be 2.5 mm. and point wire 2.24 mm. The nominal distance between two barbs shall be 75 mm unless otherwise specified in the item. The barbed wire shall be formed by twisting together two line wires. One containing the barbs. The size of the line and point wires and barb spacing shall be as specified above. The permissible deviation from the nominal diameter of the line wire and point wire shall not exceed ± 0.08 mm
- 78.2.** The barbs shall carry four points and shall be formed by twisting two point wires, each two turns tightly round one line wire making altogether four complete turns. The barbs shall have a length of not less than 13 mm and not more than 18 mm. The point shall be sharp and cut at an angle not greater than 35 degree of the axis of the wire forming the barbs.
- 78.3.** The line and point wires shall be circular in section, free from scale and other defects and shall be uniformly galvanized. The line wire shall be in continuous length and shall not contain any welds other than those in the rod before it is drawn. The distance between two successive splices shall not be less than 15 meters.
- 78.4.** The lengths per 100 Kg. of barbed wire I.S. type I shall be as under:
- | | | |
|--------------------|-------------------|---------------------|
| Nominal 1000 meter | Minimum 934 meter | Maximum 1066 Meter. |
|--------------------|-------------------|---------------------|

Item No. 1 :- Excavation for foundation upto 1.5 m depth (Executed With Manual Labour) including sorting out and stacking of useful materials and disposing off the excavated stuff upto 50 Meter lead. (A) Loose or soft soil.

➤ **All sorts of soil**

Any soil which generally require close application of picks or jumpers or scarifiers to loosen it stiff clay, gravel and stone etc. fall under this category.

1.0. General

1.1. Any soil which generally yields to the application of pickaxes and shovels, phawaras rakes or any such ordinary excavating implement or organic soil, gravel silt, sand turf loam, clay, peat etc. fall under this category.

2.0. Clearing the site

2.1. The site on which the structure is to be built shall be cleared, and all obstructions loose stone, materials and rubbish of all kind bush wood and trees shall be removal as directed The materials so obtained shall be property of the Government and shall be conveyed und stacked as directed with all lead. The roots of the trees coming in the sides shall be cut and coated with a hot asphalt

2.2. The rate of side clearance is deemed to be included in the rate of earth work for which no extra will be paid.

3.0. Setting out

After clearing the site the centre lines will be given by the Engineer-in-charge. The contractor shall assume full responsibility for alignment, elevation and dimension of each and all 'parts of the work. Contractor shall supply labours materials, etc. required for setting out the reference marks and bench 'marks and shall maintain them as long as required and directed.

4.0. Excavation

The excavation in foundation shall be carried out in true line and level and shall have the width and depth as shown in the drawings or as directed. The contractor shall do the necessary shoring and shutting or providing necessary slopes to a safe angle, at his own cost. The payment for such precautionary measures shall be paid separately it not specified. The bottom of the excavated area shall be leveled both longitudinally and transversely as directed by removing and watering as required no. earth filling will be allowed for brining it to level, if by mistake or any excavation is made deeper or wider than, that shown on the plan or directed. The extra depth or width shall be made up with concrete of same proportion as specified for the foundation concrete at the cost of the contractor. The excavation **upto 1.5 mt. depth** shall be measured under this item.

5.0. Disposal of the excavated stuff

5.1. The excavated stuff of the selected type shall be used in filling the trenches and plinth or leveling the ground in layers including ramming and watering etc.

5.2. The balance of the excavated quantity shall be removed by the contractor from the site of work to a place as directed with lead up to all lead and lift.

6.0. Mode of measurements & payment

6.1. The measurement of excavation in trenches for foundation shall be made according to the sections of trenches shown on the drawing or as per sections given by the Engineer-in-charge. No payment shall be made for surplus excavation made in excess of above requirements or due to stopping and sloping back as found necessary on account of conditions of soil and requirements of safety.

6.2. The rate shall be for a unit of **one cubic meter**.

Item No. 2 :- Excavation for foundation for depth from 1.5 m to 3.0 mt (Executed With Manual Labour) including sorting out and stacking of useful materials and disposing off the excavated stuff upto 50 Meter lead.(A) Loose or soft soil.

1.0. All sorts of soil

Any soil which generally require close application of picks or jumpers or scarifiers to loosen it stiff clay, gravel and stone etc. fall under this category.

2.0. Workmanship

The relevant specifications of **Item No. 1** shall be followed except that the excavation work shall be carried out for all sorts of soil with all lead and lift from 1.5 Mt. to 3.0 mt. depth.

3.0. Mode of measurements & payment

3.1. The relevant specifications of **Item No. 1** shall be followed

3.2. The excavation work of from 1.5 Mt. to 3.0 mt. depth shall be measured under this item.

3.3. The rate shall be for a unit of one **cubic meter**.

Item No. 3 :- Providing and laying controlled cement concrete M.150 for curing complete excluding cost of formwork and reinforcement for reinforced concrete work in (A) Foundations, footings, Base of columns and Mass concrete.

1.0. Materials

- 1.1. Water shall conform to M-1. Cement shall conform to M-3. Sand shall conform to M-6. Grit shall conform to M-8. Coarse aggregate shall conform M-12.
- 1.2. The shuttering to be provided shall be of ordinary timber plank and shall conform to M-26.
- 1.3. The dimensions of scantlings and battens shall conform to the design. The strength of the wood shall not be less than that assumed in the design.

2.0. General

- 2.1. The concrete mix shall be designed from preliminary tests. The proportion of the concrete mix shall be 1:2:4 (1 cement : 2 coarse sand : 4 graded stone aggregate 20 mm. nominal size) by volume concrete work shall have exposed concrete surface or as specified in the item.
- 2.2. The proportioning of cement and aggregates shall be done by weight and necessary precautions shall be taken in the production to ensure that the required work cube strength is attained and maintained. The controlled concrete shall be in grades of M-100, M-150, M-200, M-250, M-300, M-350 & M-400 with prefix controlled added to it. The letter M refers to mix and the numbers specify 28 days works cube compressive strength of 150 mm. cubes of the mix expressed in Kg./cm.
- 2.3. The proportion of cement, sand and coarse aggregate shall be determined of weight. The weigh batch machine shall be used for maintaining proper control over the proportion of aggregates as per mix design. The strength requirements of different grades of concrete shall be as under:

Grade of Concrete	Compressive strength of 15 cms. cubes in kg/cmt. at 28 days, conducted in accordance with I.S. 516-1959.	
	Preliminary test Min.	Work Test Min.
M 150	200	150
M 200	260	200
M 250	320	250
M 300	380	300
M 350	440	350
M 400	500	400

In all cases, the 28 days compressive strength specified in above be the criteria for acceptance or rejection of the concrete. Where the strength of a concrete mix as indicated by tests, lies in between the strength of any two grades specified in the above table, such concrete shall be classified in for purpose as concrete belonging to the lower of the grades between which its strength lies.

3.0. Workmanship

- 3.1. The proportions for ingredients chosen shall be such that concrete has adequate workability for conditions prevailing on the work question and can be properly compacted with means available except where it can be shown to the satisfaction of the Engineer-in-charge, that supply of properly graded aggregate of uniform quality can be maintained till the completion of work, grading of aggregate shall be controlled by obtaining the coarse aggregates in different sizes and bending them in the right proportions as required. Aggregates of different sizes shall be stocked in separate stock piles. The required quantity of material shall be stock piled several hours, preferably a day before use. The grading of coarse and fine aggregate shall be checked as frequently as possible, the frequency for a given job being determined by Engineer-in-charge to ensure that the suppliers are maintaining the uniform grading as approved for samples used in the preliminary tests.
- 3.2. In proportioning concrete, the quantity of both cement and aggregate shall be determined by weight. Where the weight of cement is determined by accepting the maker's weight per bag, a reasonable number of bags shall be weighted separately to check the net weight. Where cement is weighted from bulk stocks at site and not by bags, it shall be weighed separately from the aggregate. Water, shall either be measured by volume in calibrated tanks or weighed. All measuring equipment shall be maintained in clean and serviceable condition. Their accuracy shall be periodically checked.
- 3.3. It is most important to keep the specified water cement ratio constant and at its correct value. To this end, moisture content in both fine and coarse aggregates shall be determined by the Engineer-in-charge according to the weather conditions. The amount of mixing water shall then be adjusted to compensate for variations in the moisture content. For the determination of moisture content in the aggregates I.S. 2386 (Part-III) shall be referred to. Suitable adjustments shall also be made in the weights of aggregates due to variation in their moisture content. Minimum quantity of cement to be used in controlled concrete shall not be less than 220 kg./m³ in plain concrete and not less than 250 kg/m³ in reinforced concrete.
- 3.4. The form work shall conform to the shape lines and dimensions as shown on the plans and be constructed as to remain sufficiently rigid during the placing and compacting of the concrete. Adequate arrangements shall be made by the contractor to safe-guard against any settlement of the form-work during the course of concreting and after concreting. The form work of shuttering, centering, scaffolding, bracing etc. shall be as per design.

4.0. **Clearing and Treatment of forms:**

- 4.1. All rubbish, particularly chipping shaving and saw dust shall be removed from the interior of the form before the concrete work is placed and the-form in contact with concrete shall be cleaned and thoroughly wetted or treated. The surface shall be then coated with soap solution applied before concreting is done. Soap solution for the purpose shall be prepared by dissolving yellow soap in water to get consistency of paint. Alternatively a coat of raw linseed oil shall be applied after thoroughly cleaning the surface. Care shall be taken that the coating does not get on construction joint surface and reinforced bars..

5.0 **Stripping time:**

- 5.1. In normal circumstances and where ordinary cement is used forms may be struck after expiry of following periods.
- (a) Sides of walls columns and vertical faces of beams.....24 to 48 hours.
 - (b) Beam soffits, (props, left under).....7 days.
 - (c) Removal of props slabs:
 - (i) Slabs spanning up to 4.5. m.....7 days.
 - (ii) Spanning over 4.5 mm.....14 days.
 - (d) Removal of props t beams and Arches:
 - (i) Spanning up to 6 mm.....14 days.
 - (ii) Spanning over 6 m.....21 days.

6.0 **Procedure when removing the form work :**

- 6.1. All form work shall be removed without such shock or vibrations as would damage the reinforced concrete surface. Before the soffits form work and struts are removed, the soffits and the concrete surface shall be exposed where necessary in order to ascertain that the concrete has sufficiently hardened.

7.0 **Centering:**

- 7.1. The centering to be provided shall be got approved. It shall be sufficiently strong to ensure absolute safety of the form work and concrete work before, during and after pouring concrete. Watch should be kept to see that behavior or centering and form work is satisfactory during concreting. Erection should also be such that it would allow removal of forms in proper sequence without damaging either the concrete or the forms to be removed.
- 7.2. The props of centering shall be provided on firm foundation or base of sufficient strength to carry the loads without any settlement.
- 7.3. The centering and form work shall, be inspected and approved by the Engineer-in-charge before concreting. But this will not relieve the contractor of his responsibility for strength, adequacy and safety of form work and centering. If there is a failure of form work or centering, contractor shall be responsible for the damages to property.

8.0 **Scaffolding:**

- 8.1. All scaffolding, hoisting arrangements and ladders etc. required for the facilitating of conceding shall be provided and removed on completion of work by contractor at his own expense. The scaffolding, hoisting arrangements and ladders etc. shall be strong enough to with stand all live, dead and impact loads expected to act and shall be subject to the approval of the Engineer-in-charge. However contractor shall be solely responsible for the safety of the scaffolding, hoisting arrangement, ladders, work and workman etc.
- 8.2. The scaffolding, hoisting arrangements and ladder shall allow easy approach to the work spot and afford easy inspection.
- 8.3. The rate is applicable to all condition of working and height up to 4 mts. The rate shall include the cost of materials and labour for various operations involved such as :
- (a) Splayed edges, notching, allowance for overlaps and passing at angles, battens centering, shuttering propping, bolting, wedging easing, striking and removal.
 - (b) Filleting to form stop chamfered edges or splayed external angles not exceeding 20 mm: width to beams, columns and the like.
 - (c) Temporary openings in the forms for pouring concrete, if required removing rubbish etc.
 - (d) Dressing with oil to prevent adhesion of concrete with shuttering and.
 - (e) Raking or circular cutting.

9.0 **Re-Use:**

- 9.1. Before re-use, all form shall be inspected by Engineer-in-charge and their suitability ascertained. The forms shall be scarred, cleaned and joints are gone over, repaired where required. Inside surface shall be retreated to prevent adhesion of concrete.

10.0. **Mode of measurement & payment**

- 10.1. The consolidated cubical contents of concrete work as specified in item shall be measured. No deduction shall be made for
- (a) Ends of dissimilar materials such as joints, beams, posts, girders, falters, purling trusses, corbels and steps etc. up to 500 Sq. Cm. in section.
- 10.2. Form work shall be measured as the area in square meters to shuttering in contract with concrete except in the case of inclined member and portion of curved profile and upper side in which case on area of underside shall be measured for payment.
- 10.3. Form work to secondary beams shall be measured up to the sides of main beams but no deduction shall be made from the form work of the main beam at the inter section point. No deduction shall be made from the form work of a column at inter section of beams.
- 10.4. The rate includes cost of all materials labour, tools and plant required for mixing, placing in position, vibrating and compacting, finishing, as directed, curing and all other incidental expenses for producing concrete of specified strength. The rate includes the cost of form work.
- 10.5. The rate shall be for a unit of **one cubic meter**.

Item No. 4 :- Providing and laying controlled cement concrete M 250 and curing complete including the cost of form work but excluding the cost of reinforcement for reinforced concrete work in. (A) Foundation footing, base of columns & mass concrete...

The work shall be executed as per specification of **Item No. 3** except for the item is work of **Providing and laying controlled cement concrete M.250 and curing complete including the cost of formwork and excluding reinforcement for reinforced concrete work in (A) Foundations, footings, and Mass concrete..**

Item No. 05 :- Providing and laying cement concrete 1:3:6 (1-Cement : 3- coarse sand : 6- hand broken stone aggregates 40 mm nominal size) and curing complete excluding cost of formwork in (A) Foundation and Plinth.

1.0. Materials

1.1. Water shall conform to M-1. Cement shall conform to M-3. Sand shall conform to M-6. Hand broken stone aggregate 40 mm. nominal size shall conform to M-12.

2.0. Workmanship

2.1. General

2.1.1. Before stating concrete the bed of foundation trenches shall be cleared of all loose materials, leveled, watered and rammed as directed

2.2. Proportion of Mix:

2.2.1. The proportion of cement, sand and stone aggregate shall be one part of cement. 3 parts of coarse sand and 6 parts of **hand broken** stone aggregates and shall be measured by volume.

2.3. Mixing:

2.3.1. The concrete shall be mixed in a mechanical mixer at the site of work. Hand mixing may however be allowed for smaller quantity of work if approved by the Engineer-in-charge. When hand mixing is permitted by the Engineer-in-charge in case of break-down of machineries and in the interest of the work, it shall be carried out on a water tight platform and care shall be taken to ensure that mixing is continued until the mass is uniform in colour and consistency, However in such case 10% more cement than otherwise period 1 1/2 to 2 minutes. The quantity of water shall be just sufficient to produce a dense concrete of required workability for the purpose.

2.4. Transporting & Placing the Concrete:

2.4.1. The concrete shall be handed from the place, of mixing to the final position in not more than 15 minutes by the method as directed and shall be placed into its final-position, compacted and finished within 30 minutes of mixing with water i.e. before the setting commences.

2.4.2. The concrete shall be laid in layers of 15 cms. to 20 cms.

2.5.1. The concrete shall be rammed with heavy iron rammers and rapidly to get the required compaction and to allow all the interstices to be filled with mortar.

2.6. Curing:

2.6.1. After the final set, the concrete shall be kept continuously wet if required by pounding for a period of not less then 7 days form the date of placement.

3.0. Mode of measurement and payment

3.1. The concrete shall be measured for its length, breadth and depth, limiting dimensions to those specified on plans or as directed

3.2. The rate shall be for a unit of **one cubic meter**.

Item No. 6 :- Provinding and Laying controlled cement concrete M-250 & curing complete including the cost of form work but excluding cost of reinforcement concrete work in Beams, Girders and Cantilever up to floor for PLINTH BEAMS...

The work shall be executed as per specification of **Item No. 3** except for the item is work of **Provinding and Laying controlled cement concrete M-250 & curing complete including the cost of form work but excluding cost of reinforcement concrete work in Beams, Girders and Cantilever up to floor for PLINTH BEAMS..**

Item No. 07:- Brick work using common burnt clay building bricks having crushing strength not less than 35 kg./Sq.Cm. in foundation and plinth in Cement Mortar 1:5. (1-Cement : 5 -fine sand)(B) Conventional.

1.0. Materials

Water shall conform to M-1. Cement shall conform to M-3. Sand shall conform to M-6. Bricks shall conform to M-15. Cement mortar shall conform to M-11.

2.0. Workmanship

2.1. Proportion:

2.1.1. The proportion of the cement mortar shall be 1:6 (1 cement : 6 fine sand) by volume.

2.2. Wetting of bricks:

2.2.1. The bricks required for masonry shall be thoroughly wetted with clean water for about two hours before use or as directed. The cessation of bubbles, when the bricks are wetted with water is as indication of through wetting of bricks.

2.3. Laying:

2.3.1. Bricks shall be laid in English bond unless directed otherwise. Half or cut bricks shall not be used except when necessary to complete to bond; closures in such case shall be cut to required size and used near the ends of walls.

2.3.2. A layer of mortar shall be spread on full width for suitable length of the lower course. Each brick shall first be properly bedded and set home by gently tapping with handle of trowel or wooden mallet. Its inside face shall be flushed with mortar before the next brick is laid and pressed against it. On completion of course, the vertical joints shall be fully filled from the top with mortar.

2.3.3. The walls shall be taken up truly in plumb. All courses shall be laid truly horizontal and all vertical joint shall be truly vertical. Vertical joints in alternate course shall generally be directly one over the other. The thickness of brick course shall be kept uniform.

2.3.4. The brick shall be laid with frog up wards. A set of tools comprising of wooden straight edges, man son's spirit level, square half meter rub, and pins, string and plumb shall be kept on the site of work for frequent checking during the progress of work.

2.3.5. Both the faces of walls of thickness greater than 23 cms. shall be kept in proper place. All the connected brick work shall be kept not more than one meter over the rest of the work. Where this is not possible, the work shall be raked back according to bond (and not left toothed) at an angle not steeper than 45 degrees.

2.3.6. All fixtures, pipes, outlets of water, hold fasts of doors and windows etc. which are required to be built in wall shall be embedded in cement mortar.

2.4. Joints:

2.4.1. Bricks shall be so laid that all joints are quite flush with mortar. Thickness of joints shall not exposed 12 mm. The face joints shall be raked out as directed by raking tools daily during the progress of work, when the mortar is still green so as to provide key for plaster or pointing to done.

2.4.2. The face of brick shall be cleaned the very day on which the work is laid and all mortar dropping removed.

2.5. Curing:

- 2.5.1.** Green work shall be protected from rain suitably. Masonry work shall be kept moist on all the faces for a period of seven days. The top of masonry work shall be kept well wetted at the close of the day.

2.6. Preparation of foundation bed:

- 2.6.1.** If the foundation is to be laid directly on the excavated bed, the shall be leveled, cleared of all loose materials, cleaned and wetted before stating masonry, If masonry is to be laid on concrete footing, the top of concrete shall be cleaned and moistened. The contractor shall obtain the engineer's approval for the foundation bed before foundation masonry is started. When pucca flooring is to be provided flush with the top to plinth, the inside plinth offset shall be kept lower than the outside plinth top by the thickness of the flooring.

3.0. Mode of measurements & payment

- 3.1.** The measurements of this item shall be taken for the brick masonry fully completed in foundation up to plinth. The limiting dimensions not exceeding those shown on the plinths or as directed shall be final. Battered tapered and curved portions shall be measured net.
- 3.2.** No deduction shall be made from quantity of brick work nor any extra payment made for embedding in masonry of marking holes in respect of following item.
- (1) Ends of joints, beams, posts, girders, rafters, purlins trusses corbel, steps etc. where cross sectional area does not exceed 500 sq.cm.
 - (2) Opening not exceed in 1000 sq.cm.
 - (3) Wall plate sand bed plates bearing of slab, chhajjas and like whose thickness does not exceed 10 cms. and the bearing does not extend the full thickness of wall.
 - (4) Drainage holes and recesses for cement concrete blocks to embed hold fasts for doors, window etc.
 - (5) Iron fixtures, pipes up to 300 mm. dia. hold fasts of doors, and window built into masonry and pipes etc. for concealed wiring.
 - (6) Forming charges of section not exceeding 350 sq.cm. in masonry.
- 3.3** Apparatuses for fire places shall not be deducted nor shall extra labour required to make splaying of jumps, throating and making trenches over the aperture be paid for separately.
- 3.4.** The rate shall be for a unit of one **cubic meter**.

Item No. 8 :- Filling available excavated earth (excluding rock) in trenches. plinth, sides of foundations etc. in layers not exceeding 20 cm.in depth consolidating each disposed layer by ramming and watering..

1.0 WORKMANSHIP

- 1.1. The earth to be used for filling shall be free from salts, organic or other foreign matter all clots of earth shall be broken.
- 1.2. As soon as the work in foundation has been completed and measured the site of foundation shall be cleared of all debris brick bats mortar dropping etc. and filled with earth in layers not exceeding 20 cms. each layer shall be adequately watered, rammed and consolidated before the succeeding layer is laid. The earth shall be rammed with iron rammers where feasible and with the ends of crow-bars, where rammer cannot be used.
- 1.3. The plinth shall be similarly filled with earth in layers not exceeding 20 cms adequately watered and consolidated by ramming with iron or wooden rammers. When filling reaches finished level the surface shall be flooded with water for at least 24 hours and allowed to dry and then rammed and consolidated.
- 1.4. The finished level of filling shall be kept to shape intended to be given to floor.
- 1.5. In case of large heavy duty flooring like factory flooring, the consolidation may be done by power rollers, where so specified. The extent of consolidation required shall also be as specified.

2.0. Mode of Measurements & Payment

- 2.1. The payment shall be made for filling in plinth and trenches. No deduction shall be made for shrinkage or voids, if consolidated as instructed above.
- 2.2. The rate shall be for a unit of one cubic meter.

Item No. 09 : Applying general insecticide pest control treatment to floors, cupboards etc including labour materials etc. complete. Using Imidacloprid 30.5 SCas Per IS 6313 part -II(0.075% concentration by mass) is recommended 10.5ml chemical diluted with 5 liters of water application 0.5 litre chemical /Sqm of surface is recommended as per I.S...

1.0 MATERIALS

The chemicals used for the soil treatment shall be only one of the following with concentration shown against each in aqueous emulsion.

	Chemicals	Concentration
1	Aldrin or other same this properties	0.50% (By Weight)
2	Heptachlor	0.50% (By Weight)
3	Chlordane	1.00% (By Weight)

2.0 WORKMANSHIP

- 2.1 The chemicals barrier shall be complete and continuous under whole of the structure to be protected.
- 2.2 The bottom and the sides of foundations up to a height of 30 cms from the bottom of excavation made for masonry foundation and for basement column pits shall be treated with the chemical emulsion at the rate 5 liters/sq.meters of the surface area.
- 2.3 The chemical treatment shall be carried out when the surface is quite dry. Chemical treatment shall not be carried out when it is raining or when the soil wet with rain or sub soil water.
- 2.4 Once formed, treated soil barriers shall be not disturbed. If by chance, treated soil barriers and disturbed, immediately steps shall be taken to restore the continuation and compactness of the barrier system.
- 2.5 The treatment against termite infection shall remain fully effective for a period not less than 10 years from date of issue of the final certificate to completion of work. If at any time during this period, any defects in treatment are revealed or any evidence of infection in any part of the building or structure is noticed, the contractor shall be rectify the concerned failure to do so, the Engineer-in-charge any get the same rectified through any other agency at Contractor's risk and cost, any decision of Engineer-in-charge as to the cost payable by contractor for the same shall be binding to the contractor.

- 2.6 A Guarantee bond on appropriately stamped paper shall be given by the contractor to the Department in the manner and form prescribed below.

FORM OF GUARANTEE BOND

I / We _____ (Contractor) here by guarantee that work will remain unaffected and will not be in anyway damaged by termite or any other germs of similar types. For a period for **10 years** after completion of the work of anti-termite as per the terms and conditions of the contract and damage that might be caused on account of termite and or other similar type of germs and hereby Guarantee to make good any loss of damages suffered by the Govt. of Gujarat and further guarantee to redo effective work without claiming any extra cost.

- 2.7 This guarantee shall remain in force for the period of 10 years from the completion of the work under the contract and it shall remain binding to the contractor for period of 10 years.

- 2.8 The deposit at the rate of 50% of the cost of this item from the running and final bills shall be recovered and remained for the first one year after completion of the work or at least on monsoon season passed which ever is later and 10% shall be retained for the balance of the guarantee period and shall be refunded only after completion of the guarantee period.

3.0 MODE OF MEASUREMENT AND PAYMENT

- 3.1. The length and breadth shall be measured correct to a cm. as per the dimensions of sanctioned plans. No deduction shall be made nor extra paid for any opening for pipes etc. up to 0.1 sq. mt. The rate shall include the cost of all labour and materials required for the operation involved for satisfactory completion of this item. The sides of the trenches 30 cms, each side and bottom shall be measured under this item.

- 3.2. The rate shall be for a unit of One sq. meter.

Item No. 10 :- Providing and Laying controlled cement concrete M-150 and with curing etc.complete. Including the cost of formwork but excluding the cost of reinforcement for R.C.C Plinth Slab.

The work shall be executed as per specification of **Item No. 3** except for the item is work of **Providing and Laying controlled cement concrete M-150 and with curing etc.complete. Including the cost of formwork but excluding the cost of reinforcement for R.C.C Plinth Slab..**

Item No. 11 :- Providing and laying controlled cement concrete M.250 and curing complete including the cost of formwork but excluding reinforcement for reinforced concrete work in (C)Slabs, landing, shelves, Balconies, Lintels, Beams, Girders and Cantilever Beams at FF.

The work shall be executed as per specification of **Item No. 3** except for the item is work of **Providing and laying controlled cement concrete M.250 and curing complete including the cost of formwork but excluding reinforcement for reinforced concrete work in (C)Slabs, landing, shelves, Balconies, Lintels, Beams, Girders and Cantilever Beams at FF..**

Item No. 12 :- Providing and Laying controlled cement concrete M-250 and curing etc.comp including the cost of formwork but excluding the cost of reinforcement for Vertical Fins All Floor.

The work shall be executed as per specification of **Item No. 3** except for the item is work of **Providing and Laying controlled cement concrete M-250 and curing etc.comp including the cost of formwork but excluding the cost of reinforcement for Vertical Fins All Floor..**

Item No. 13 :- **Providing and Laying controlled cement concrete M-250
Finishing smooth with curing etc.comp including the cost
of formwork but excluding the cost of reinforcement for
RCC work in SLAB at FF level.**

The work shall be executed as per specification of **Item No. 3** except for the item is work of **Providing and Laying controlled cement concrete M-250 Finishing smooth with curing etc.comp including the cost of formwork but excluding the cost of reinforcement for RCC work in SLAB at FF level..**

Item No. 14 :- Providing ISI Mark T.M.T. bar Fe - 500D reinforcement for R.C.C work including bending, binding and placing in position complete. For All Floor..

1.0. GENERAL

This work shall consist of furnishing and placing coated, or uncoated or high strength deformed reinforcement, bars (intentioned) of the shape and dimensions shown on the drawings and conforming to these specifications or as approved by the Engineer in charge.

2.0. MATERIAL

2.1. TMT Bars

Reinforcements may be either T.M.T. tensile steel, confirms to IS 1786-2008 bars. They may be uncoated or coated with epoxy or with approved protective coatings.

2.2. T.M.T. bars reinforcement for R.C.C. work shall conform IS 432 (Part II) 1982 (Reaffirmed 1995) and shall be of tested quality. It shall also comply with relevant part of IS 456-2000.

2.3. All reinforcement shall be clean and free from dirt, paint, grease or oil, all scale or loose or thick rust at the time of placing.

2.4. All steel shall be procured from original producers no re-rolled steel shall be incorporated in the work.

2.5. Only new steel shall be delivered to the site every bar shall be inspected before placing to its position and defective brittle or burnt bar shall be discarded cracked ends of bars shall be discarded.

3.0. Pitch

3.1. Distance between bars shall be as specified in drawings and as directed by the Engineer in charge all bars shall be placed at an accurate distance from each other and shall be bind tightly to maintain the desired pitch Suitable means shall be provided for holding bars securely in position.

4.0. Binding wire

4.1. Mild steel binding wire shall be of 1.63 mm or 1.22 mm (16 to 18 gauge diameter and shall conform IS 280-2006.

4.2. The use of black wire will be permitted for binding reinforcement bars. It shall be free from dirt, paint, grease or oil, oil scale or loose or thick rust and any other undesirable coating which may prevent adhesion of cement mortar at the time of binding.

4.3. Only new binding wire shall be delivered to the site all binding wire shall be inspected before binding to its position and defective brittle, rusted, used wire, shall be discarded.

5.0. PROTECTION OF REINFORCEMENT

5.1. Uncoated reinforcing steel shall be protected from rusting or chloride contamination. Reinforcements shall be free from rust, mortar, loose mill scale, grease, oil or paints. This may be ensured either by using reinforcement fresh from the factory or thoroughly cleaning all reinforcement to remove rust using any suitable method such as sand blasting, mechanical wire brushing, etc. as directed by the Engineer. Reinforcements shall be stored on bricks, racks or platforms and above the ground in a clean and dry condition and shall be suitably marked to facilitate inspection and identification.

5.2. Portions of uncoated reinforcing steel and dowels projecting from concrete shall be protected within one week after initial placing of concrete with a brush coat of neat cement mixed with water to a consistency, of thick paint. This coating shall be removed by lightly tapping with a hammer or other tool not more than one week before placing of the adjacent pour of concrete. Coated reinforcing steel shall be protected against damage to the coating. If the coating on the bars is damaged during transportation or handling and cannot be repaired, the same shall be rejected.

6.0. Workmanship

- 6.1. The work shall consist of furnishing and placing reinforcement to the shape and dimensions shown as on the drawings or as directed by The Engineer in charge.
- 6.2. Reinforcing steel shall conform accurate to the dimensions given in the bar bending schedules shown on relevant drawing

7.0. BENDING OF REINFORCEMENT

- 7.1. Bar bending schedule shall be furnished by the Contractor and got approved by the Engineer before start of work.
- 7.2. Reinforcing steel shall conform to the dimensions and shapes given in the approved bar bending Schedules.

7.3. Bars shall be bent cold to the specified shape and dimensions or directed by the Engineer using a proper bar bender operated by hand power to obtain the correct radius of bends and shape.

Bars shall not be bent or straightened in a manner that will damage parent material or the coating bars bent during transport or handling shall, be straightened before being used on work and shall not be heated to facilitate straightening.

8.0. PLACING OF REINFORCEMENT

8.1. The reinforcement cage should generally be fabricated in the yard at ground level, and then shifted and placed in position. The reinforcement shall be placed strictly, in accordance with the drawings and shall be assembled in position, only when structure is otherwise ready for placing of concrete. Prolonged time gap, between assembling of reinforcements and casting of concrete, which may result in rust formation on the surface, shall not be permitted.

8.2. Reinforcement bars shall be placed accurately in position as shown on the drawings. The bars, crossing one another shall be tied together at every intersection with binding wire (annealed), conforming to IS:280 to make the skeleton of the reinforcement rigid such that the reinforcement does not get displaced during placing of concrete, or any other operation. The diameter of binding wire shall not be less than 1 mm.

8.3. Bars shall be kept in position usually by the following methods:

In case of beam and slab construction, industrially produced polymer cover blocks of thickness equal to the specified cover shall be placed between the bars and formwork subject to Satisfactory evidence that the polymer composition is not harmful to concrete and reinforcement. Cover blocks made of concrete may be permitted by the Engineer, provided they have the same strength and specification as those of the member.

8.4. In case of dowels for Columns and walls the vertical reinforcement shall be kept in position by means of timber templates with slots in them accurately, or with cover blocks tied to the reinforcement timber templates shall be removed after the concreting has progressed up to a level just below their location.

8.5. Layers of reinforcements shall be separated by spacer bars at approximately One meter intervals. The minimum diameter of spacer bars shall be 12 mm or: equal to maximum size of main reinforcement or maximum size of coarse aggregate, whichever is greater. Horizontal reinforcement shall not be, allowed to sag between supports.

8.6. Necessary stays, blocks, metal chairs, spacers, metal hangers supporting wires etc, or other subsidiary, reinforcement shall be provided to fix the reinforcements firmly in its correct position.

8.7. Use of pebbles, broken stone, metal pipe, brick, mortar or wooden blocks etc as devices for positioning reinforcement shall not be permitted.

8.8. Bars coated with epoxy or any other approved protective coating shall be placed on supports that do not damage the coating. Supports shall be installed in a manner such that planes of weakness are not created in hardened concrete. The coated reinforcing steel shall be held in place by use of plastic or plastic coated binding wires especially manufactured for the purpose.

8.9. Placing and fixing of reinforcement shall be inspected and approved by the Engineer before concrete is deposited.

9.0. Lapping

9.1. All reinforcement shall be furnished in full lengths as indicated on the drawing. No splicing of bars, except where shown on the drawing; will be permitted without approval of the Engineer. The lengths of the splice shall be as indicated on drawing or as approved by the Engineer. Where practicable, overlapping bars shall not touch each other, and shall be kept apart by 25 mm or 1 1/4 times the maximum size of coarse aggregate, whichever is greater, If this is not feasible, overlapping bars shall be bound with annealed steel binding wire, not less than 1 mm diameter and twisted tight in such a manner as to maintain minimum clear cover to the reinforcement from the concrete surface. Lapped splices shall be staggered or located at points, along the span where stresses are low.

10.0. Welding

10.1 Splicing by welding of reinforcement will be permitted only if detailed on the drawing or approved by the Engineer. Weld shall develop an ultimate strength equal to or greater than that of the bars connected.

10.2. While welding may be permitted for T.M.T. reinforcing bars conforming to IS:432, welding of deformed bars conforming to IS: 1786 shall in general be prohibited. Welding may be permitted in case of bars of other than S 240 grade including special. Welding grade of S 500D grade bars conforming to IS:1786, for which necessary chemical analysis has been secured and the carbon equivalent (CE) calculated from the chemical composition using the formula:

$$CE = C + \frac{Mn}{6} + \frac{Cr + Mg + V}{5} + \frac{Ni + Cu}{15}$$

is 0.4 or less.

10.3. The method of welding shall conform to IS:2751 and IS:9417 and to any supplemental specifications to the satisfaction of the Engineer

10.4. Bars shall be bent cold to the specified shape and dimensions or as directed by Engineer in charge using the proper bender tool, operated by hand or power to attain proper radius of bends. Bars shall not be bend or straightened in a manner that will injure the material. Bars bent during transport or handling shall be straightened before being used in the work. Bars shall not be heated to facilitate bending

10.5. Unless otherwise specified a 'U' type hook at the end of each bar shall invariably be provided to main reinforcement. The radius of the bane shall not be less then twice the diameter of the round bar and the length of the straight part of the bar beyond the end of the curve shall be at least four times of the diameter of the round bar. In case of bars which are not round and in case of deformed bars, the diameter shall be taken as the diameter of circle having an equivalent effective area. The hooks shall be suitably encased to prevent any spiting of the concrete

10.6. All reinforcement bars shall be accurately placed in exact position shown on the drawings and shall be securely held in position during placing of concrete by annealed binding wire not less than 1 mm in size and by using say blocks or metal chairs spacers, metal hangers, supporting wires or other approved devices at sufficiently close intervals, Bars shall not be allowed to sag between supports not displaced during concreting or any other operations of the work All devices used for positioning shall be of not corrodible material wooden and metal supports shall not extended to the surface of the concrete, except where shown in drawings. Placing bars on layers of freshly laid concrete as the work progresses for adjusting bar spacing shall not be allowed. Pieces of broken stone or brick and wooden blocs shall not be used Layers of bars shall be separated by spacer bars pre-cast mortar blocks or other approved devices. Reinforcement after bending placed in position shall be maintained in a clean condition until completely embedded in concrete, Special care shall be exercised to prevent any displacement of reinforcement in concrete already placed. To prevent reinforcement form corrosion, concrete cover shall be provided as indicated on drawings. All bars protruding from concrete and to which other bars are to be sliced and which are likely to be exposed for a period exceeding 10 days shall be protected by a thick coat of neat cement grout

10.7. Bars crossing each other where required shall be secured by binding wire (annealed) of size not less than 1 mm in such a manner that they do not slip over at the time of fixing and concreting

As far possible bars of full length shall be used in case this is not possible, overlapping of bars shall be done as directed by the Engineer in charge When practicable overlapping bars shall

not touch each other, but be kept apart by 25 mm Where no feasible overlapping bars shall be bound with annealed wires not less than 1 mm thick twisted tight The overlaps shall be staggered for different bars and located at points along the span where neither sheer not bending moments is maximum.

10.8. Whenever indicated on drawing or desired the Engineer in charge bars shall be jointed by coupling which shall have a cross section sufficient to transmit the full stresses of bars The end of the bars that are jointed by coupling shall be upset for sufficient length so that the effective cross section at the base of threads is not less than the normal cross section of the bar. Threads shall be standards threads Steel for coupling shall conform to IS 226

10.9. When permitted or specified on the drawings joints of reinforcement bars shall butt-welded so as to transmit their full stresses Welded joints shall preferably be located at points when steel will not be subject to more than 75 percent of the maximum permissible stresses and welds so staggered that at any one section not more than 20 percent of the rods are welded Only electric are welding using a process which excludes air form the molten metal and conforms to any or other special provisions for the work shall be accepted Suitable means shall be provided for holding bars securely in position during welding It shall be ensured that no voids are left in welding and when welding is done in two or three stages previous surface shall be cleaned properly Ends of bars shall be cleaned of all loose scale rust stages paint and other foreign matter before welding Only competent welders shall be employed on the work. The M S electrodes used for welding shall conform IS 814 Welded pieces of reinforcement shall be tested. Specimen shall be taken form the actual site and their number shall frequency to test shall be as directed by the Engineer in charge

11.0 MODE OF MEASUREMENTS & PAYMENT

11.1. For the purpose of payment the bar shall be measured correct up to 10 mm length and weight payable works out at the rate specified below

Sr. No	Diameter of steel	weight of steel per running meter	Sr. No	Diameter of steel	weight of steel per running meter
1	6 mm	0.22 Kg / Rmt	8	20 mm	2.47 Kg / Rmt
2	8 mm	0.39 Kg / Rmt	9	22 mm	2.98 Kg / Rmt
3	10 mm	0.62 Kg / Rmt	10	25 mm	3.85 Kg / Rmt
4	12 mm	0.89 Kg / Rmt	11	28 mm	4.83 Kg / Rmt
5	14 mm	1.21 Kg / Rmt	12	32 mm	6.31 Kg / Rmt
6	16 mm	1.58 Kg / Rmt	13	36 mm	7.99 Kg / Rmt
7	18 mm	2.00 Kg / Rmt	14	40mm	9.86 Kg / Rmt

11.1. Excess consumption over 5% will be charged at penal rate.

11.2. Reinforcement shall be measured in length including hooks, if any, separately for different diameters as actually used in work, excluding overlaps. From the length so measured, the weight of reinforcement shall be calculated in tonnes on the basis of IS: 1732. Wastage, overlaps, couplings, welded joints, spacer bars, chairs, stays, hangers and annealed steel wire or other methods for binding and placing shall not be measured and cost of these items shall be deemed to be included in the rates for reinforcement..

11.3. The contract unit rate for coated/uncoated reinforcement shall cover the cost of material, fabricating, transporting, storing, bending, placing, binding and fixing in position as shown on the drawings as per these specifications and as directed by the Engineer, including all labour, equipment, supplies, incidentals, sampling, testing and supervision.

The unit Rate for coated reinforcement shall be deemed to also include cost of all material, labour, tools and plant, royalty, transportation and expertise required to carry out the work. The rate shall also cover sampling, testing and supervision required for the work.

11.4. The rate shall be for a unit of **One Kg.**

Item No. 15 :- Brick work using common burnt clay building conventional type bricks having crushing strength not less than 35 Kg./Sqcm. in super structure in cement mortar 1:5 (1 cement : 5 fine sand) Work In Super Stcture above plinth Level up to floor two level including the cost of all materials and labour charges etc. complete.

1.0. Materials

Bricks shall conform to M-15. Cement mortar shall conform to M-11.

2.0. Workmanship

2.1. Proportion:

2.1.1. The proportion of the cement mortar shall be 1:6 (1 cement : 6 fine sand) by volume.

2.2. Wetting of bricks:

2.2.1. The bricks required for masonry shall be thoroughly wetted with clean water for about two hours before use or as directed. The cessation of bubbles, when the bricks are wetted with water is as indication of through wetting of bricks.

2.3. Laying:

2.3.1. Bricks shall be laid in English bond unless directed otherwise. Half or cut bricks shall not be used except when necessary to complete to bond, closures in such case shall be cut to required size and used near the ends of walls.

2.3.2. A layer of mortar shall be spread on full width for suitable length of the lower course. Each brick shall first be property bedded and set home by gently tapping with handle of trowel or wooden mallet. Its inside face shall be flushed with mortar before the next brick is laid and pressed against it. On completion of course, the vertical joints shall be fully filled from the top with mortar.

2.3.3. The walls shall be taken up truly in plumb. All courses shall be laid truly horizontal and all vertical joint shall be truly vertical. Vertical joints in alternate course shall generally be directly one over the other. The thickness of brick course shall be kept uniform.

2.3.4. The brick shall be laid with frog up wards. A set of tools comprising of wooden straight edges, mason's spirit level, square half meter rub, and pins, string and plumb shall be kept on the site of work for frequent checking during the progress of work.

2.3.5. Both the faces of walls of thickness greater than 23 cms. shall be kept in proper place. All the connected brick work shall be kept not more than one meter over the rest of the work. Where this is not possible, the work shall be raked back according to bond (and not left toothed) at an angle not steeper than 45 degrees.

2.3.6. All futures, pipes, outlets of water, hold fasts of doors and windows etc. which are required to be built in wall shall be embedded in cement mortar.

2.4. Joints:

2.4.1. Bricks shall be so laid that all joints are quite flush with mortar. Thickness of joints shall not exposed 12 mm. The face joints shall be raked out as directed by raking tools daily during the progress of work, when the mortar is still green so as to provide key for plaster or pointing to done.

2.4.2. The face of brick shall be cleaned the very day on which the work is laid and all mortar dropping removed.

2.5. Curing:

- 2.5.1.** Green work shall be protected from rain suitably. Masonry work shall be kept moist on all the faces for a period of seven days. The top of masonry work shall be kept well wetted at the close of the day.

2.6. Preparation of foundation bed:

- 2.6.1.** If the foundation is to be laid directly on the excavated bed, it shall be leveled, cleared of all loose materials, cleaned and wetted before starting masonry. If masonry is to be laid on concrete footing, the top of concrete shall be cleaned and moistened. The contractor shall obtain the engineer's approval for the foundation bed before foundation masonry is started. When pucca flooring is to be provided flush with the top to plinth, the inside plinth offset shall be kept lower than the outside plinth top by the thickness of the flooring.
- 2.7.** The frames of doors, windows, cupboards etc. shall be housed into the brick work at the correct location and level as directed. The heavy steel doors, window frames etc. shall be built in with work, but for ordinary steel doors and windows required opening for frames, hold-fasts etc. shall be in the wall and frame embedded later on in order to avoid damage to the frames.
- 2.8.** Necessary scaffolding shall be provided. The supports of the scaffolding shall be sound and strong tied, together with horizontal pieces over which the scaffolding plunks shall be fixed. Simple scaffolding shall be allowed normally. In this case scaffolding hole shall rest in hole header horizontal course only. Minimum number of holes be left in brick work for supporting horizontal scaffolding poles. The contractor is responsible for providing and maintaining sufficiently strong scaffolding so as to withstand all loads likely to come upon it.
- 2.9.** For the face of brick work, where plastering is to be done, joints shall be raked out to a depth not less than thickness of joints. The face of brick work shall be cleaned and mortar dropping removed on very same day that brick work is laid.

3.0. Mode of measurements & payment

- 3.1.** The masonry work of G.F. & First floor shall be measured and paid under this item rate includes cost of all materials & labour.
- 3.2.** Brick work in parapet shall be included in the corresponding masonry item of floor immediately below the floor above which the parapet is built.
- 3.3.** No deduction shall be made from quantity of brick work nor any extra payment made for embedding in masonry of marking holes in respect of following item.
- (1) Ends of joints, beams, posts, girders, rafters, purlins trusses corbel, steps, etc. where cross sectional area does not exceed 500 sq.cm.
 - (2) Opening not exceed in 1000 sq.cm.
 - (3) Wall plate sand bed plates bearing of slab, chhajjas, and like whose thickness does not exceed 10 cms. and the bearing does not extend the full thickness of wall.
 - (4) Drainage holes and recesses for cement concrete blocks to embed hold fasts for doors, window etc.
 - (5) Iron fixtures, pipes up to 300 mm. dia. hold fasts of doors, and window built into masonry and pipes etc. for concealed wiring.

(6) Forming charges of section not exceeding 350 sq.cm. in masonry.

(7) Apparatuses for fire places shall not be deducted nor shall extra labour required to make splaying of jumps, throating and making trenches over the aperture be paid for separately.

3.4. The rate shall be for a unit of **one cubic meter**.

Item No. 16 :- Providing 15mm thick cement plaster in single coat on Rough (Similar)side of single or half brick walls for interior plastering upto floor two level and finished with floating coat of neat cement slurry (i) Cement mortar 1:3 (1-cement:3-sand).

1.0. Materials

1.1. Water shall conform to M-1. The cement mortar of proportion **1:3** shall conform to M-13.

2.0. Workmanship

2.1. Scaffolding:

Wooden bullies, bamboos, planks, trestles and other scaffolding shall be sound. These shall be properly examined before erection and use. Stage scaffolding shall be provided for ceiling plaster which shall be independent of the walls.

2.2. Preparation of back ground :

2.2.1. The surface shall be cleaned of all dust, loose mortar droppings, traces of algae, efflorescence and other foreign matter by water or by brushing. Smooth surface shall be toughened by wire brushing if it is not hard and by hacking if it is hard. In case of concrete surface, if a chemical retarded has been applied to the form work, the surface shall be roughened by wire brushing and all the resulting dust and loose particles cleaned off and care shall be taken that none of the readers if left on the surface. Trimming of projections on brick/concrete surfaces where necessary shall be carried out to get an even surface.

2.2.2. Raking of joints in case of masonry where necessary shall be allowed to dry out for sufficient period before carrying out the plaster work.

2.2.3. The work shall not be soaked but only damped evenly before applying the plaster. If the surface becomes dry, such area shall be moistened again.

2.2.4. For external plaster, the peasting operation shall be started from top floor and carried downwards. For internal plaster, the plastering operations may be-started wherever the building frame and cladding work are ready and the temporary supports of the ceiling resting on the wall of the floor have been removed. Ceiling plaster shall be completed before starting plaster to walls.

2:3. Application of plaster :

2.3.1. The plaster about 15x15 cms. shall be first applied horizontally and vertically at not more than 2 meters intervals over the entire surface to serve as gauge. The surfaces of these gauges shall be truly in plane of the finished plastered surface. The mortar shall then be applied in uniform surface slightly more than the specified thickness, then brought to a true surface by working a wooden straight edge reaching across the gauges with small upward and sideways movements at a time. Finally, the surface shall be finished off true with a trowel or wooden float according as a smooth or a smooth or a sandy granular texture is required Excessive troweling or overworking the float shall be avoided. All corners, arises, angles and junctions shall be truly vertical or horizontal as the case may be and shall be carefully finished. Hounding or chamfering, corners, arises junctions etc. shall be carried out with proper templates to be size required.

2.3.2. Cement plaster shall be used within half an hour after addition of water and mortar or plaster which is partially set shall be rejected and removed forthwith from the site.

- 2.3.3.** In suspending the work at the end of the day, the plaster shall be left out clean to the line both horizontally and vertically, when recommencing the plaster, the edges of the old work shall be scraped clean and wetted with cement putty before plaster is applied to the adjacent areas to enable the two to properly join together. Plastering work shall be closed at the end of the day on the body of the wall and nearer than **15 cm.** to any corners or arises. It shall not be closed on the body of features such as plaster bands and cornices not at the corners or arises. Horizontal joints in plaster work shall not also occur on parapet tops and copings as these invariably lead to leakage. No portion of the surface shall be left out initially to be packed up later on.
- 2.3.4.** Each coat shall be kept damp continuously till the next coat is applied or for a minimum period of 7 days. Moistening shall commence as soon as plaster is hardened sufficiently. Soaking of walls shall be avoided and only as much water as can be readily absorbed shall be used, excessive evaporation on the sunny or windward side of building in hot air or dry weather shall be prevented by hanging matting or gunny bags on the outside of the plaster and keeping them wet.
- 2.3.5.** The plastering work shall be in single coat on rough side of half brick wall for interior plastering up to floor two level, finished even and smooth **in C.M. 1:3.**
- 2.3.6** The coat of cement and fine sand mortar of proportion 1:1 (15 mm thick about) shall be applied to the plastered surface with a trowel to provide uniform texture while the base coat is still plastic.
- 2.3.7.** In any continuous face of wall the finishing treatment should be carried out continuously and day to day breaks made to coincide with architectural breaks in order to avoid unsightly Junctions
- 2.3.8. Curing :** All the plaster work shall be kept damp continuously for a period 7 days.
- 2.3.9.** Providing necessary grooves between structural members as directed by Engineer in charge.
- 3.0. Mode of measurements & payment**
- 3.1.** The rate shall include the cost of all materials, labour and scaffolding etc. involved in the operations described under workmanship.
- 3.2.** All plastering shall be measured in square meters unless otherwise specified. Length breadth or height shall be measured correct to a centimeter.
- 3.3.** Thickness of the plaster shall be exclusive of the thickness of the key i.e. grooves or open joints in brick work, stone work etc. or space between laths. Thickness of plaster shall be average thickness with minimum **15 mm** at any point on this surface.
- 3.4.** This item includes plastering for all floors.
- 3.5.** The measurement of wall plastering shall be taken between the walls or partition (dimensions before plastering being taken) for length and from the top of floor or skirting to ceiling for height. Depth of cover of cornices if any shall be deducted.
- 3.6.** Soffits of stairs shall be measured as plastering on ceilings, following soffits shall be measured separately.

- 3.7.** For jambs, soffits, sills etc. for openings not exceeding 0.5 sq. met each in area for ends of joints beams, posts, girders, steps etc. not exceeding 0.5 sq.mt each in area and for openings exceeding 0.5. sq.mt and not exceeding 3.00 sq.mt. in each area deductions and additions shall be made in the following manners.
- (a) No deductions shall be made for ends of joints, beams, posts etc. and openings not exceeding 0.5 sq. mt each and no addition shall be made for reveals, jambs, soffits, sills etc. of these openings, for finish to plaster around ends of joints, beams posts etc.
- (b) Deduction for openings exceeding 0.5 sq. mt but not exceeding 3 sq.mt. each shall be made as follows and no addition shall be made for ravel, jambs, soffits, sills etc. of these openings, (i) When both faces of all wall are plastered with same plaster, deduction shall be made for one face only, (ii) When two faces of wall are plastered with different types of plasters or if one face is plastered and the other pointed, deductions shall be made from the plaster or pointing on the side of frame for door, window etc. on which width of reveals is less than that on the other side but no deductions shall be made on the other side. Where width of reveals on both faces of all are equal, deductions of 50% of area of opening on each face shall be made from areas of plaster and / or pointing as the case may be.
- 3.8.** For openings having door frames equal to or projecting beyond the thickness of wall, full deduction for opening shall be made from each plastered face of the wall.
- 3.9.** In case of openings of area above 3 sq.mt. each, deduction shall be made for openings but jambs, soffits sand sills shall be measured.
- 3.10** The payment shall be made for a unit of 1.0 sq.mt of work done over an above the finishing of work of base coat.
- 4.0.** The rate shall be for a unit of **One sq. meter.**

Item No. 84 :- Providing and applying on wall exterior/ interior of Heritage surface texture granules finish of Bakelite Hylam Limited (No.21-3005, 3006, 3007, 3008, 3013, 3014, 3015 and 3016) trowelled over 20 mm thick sand faced cement plastered (Two coat of 12 mm in CM 1:3 & 8 mm coat in CM 1:1) sub strata to get an average finish coat thickness of 0.08 to 1.2 mm comprising of three components viz. Dry granules, Granules, bonding agent and top coat of glossy finish (Dry granules shall be made from Silica sand, pigments, chiefly inorganic) homopolymer emulsion mix etc, of Bakelite Hylam product bonding agent made of acrylic copolymer emulsion, broad spectrum fungicide of Bakelite Hylam product etc and top coat made from solvent based acrylic polymer of Bakelite Hylam product including scaffolding.

1.0 Scope of work : The item of Heritage Granular or surface texture wall finish in two layer.

2.0 Materials: The finishing material shall be of Heritage Granular or Flakies Textured 20 mm thick plastering shall be in C.M. 1:3.

3.0 Workmanships :

The work shall be special nature and shall be carried out with wall exterior/ interior of Heritage surface texture granules finish of Bakelite Hylam Limited (No.21-3005, 3006, 3007, 3008, 3013, 3014, 3015 and 3016) trowelled over 20 mm thick sand faced cement plastered (Two coat of 12 mm in CM 1:3 & 8 mm coat in CM 1:1) sub strata to get an average finish coat thickness of 0.08 to 1.2 mm comprising of three components viz. Dry granules, Granules, bonding agent and top coat of glossy finish (Dry granules shall be made from Silica sand, pigments, chiefly inorganic) homopolymer emulsion mix etc, of Bakelite Hylam product bonding agent made of acrylic copolymer emulsion, broad spectrum fungicide of Bakelite Hylam product etc and top coat made from solvent based acrylic polymer of Bakelite Hylam product including scaffolding.

Existing plaster on brick masonry walls half brick masonry walls stone masonry walls etc shall be removed up to the limits and extent specified in the drawings or as indicated by the Engineer-in-charge.

Dismantling and removal operations shall be carried out with such equipment and in such a manner as to leave undisturbed, adjacent walls platforms door windows and other structures and any other work to be left in place.

4.0 Mode of measurements and Payment:

The rates for heritage plaster shall include cost of providing all required materials.

The measurement and payment shall be on Sq.m. basis.

The rate shall be for a unit of **One Square meter**.

Item No. 18 :- Providing and Fixing Machine Cut free edges,Pre Mirror Polished Green Marble Stone slab 16mm to 18 mm thick in single piece) for For Doors & windows sill,jambs & Cladding as per design incl. full moulded round front edge and 1cm both side nosing on 20 mm thick cement mortar 1:6 (1 - cement : 6 coarse sand) jointed with grey cement slurry including rubbing, polishing & Finishing etc. complete..

General

This work shall consist of providing and fixing polished Green Marble stone 16mm to 18mm thick in windows and doors jambs & sills with moulding and polishing of the stone as per design of the shape and dimensions shown on the drawings and conforming to these specifications or as approved by the Engineer in charge.

1.0 MATERIAL

Water shall confirm to M-1. Cement Mortar shall confirm to M-11. Marble slab shall confirm to M-51. Sand shall conform to M-6.

1.0 MARBLE SLAB

- 1.1. Marble slab shall be hard even sound, and regular in shape and generally uniform in colour. The colour of the stone shall generally be green. Only approved coloured shall not be allowed for use. They shall be without any soft veins cracks or flaws Marble slab shall be hard, even, and regular in shape and it should without fault.
- 1.2. The size of the Marble slab to be used as approved by Engineer in charge or Architect. However smaller sizes will be allowed to be used to the extent of maintaining required pattern. Thickness shall be as specified. For Doors / Windows sill & jambs cladding, risers the Marble slab shall be in single piece.
- 1.3. Tolerance of minus 30 mm. on accounts of chisel dressing of edges shall be permitted for length as well as breadth. Tolerance in thickness shall be +3 mm.
- 1.4. The edges of Marble slab shall be truly chiseled and table rubbed with coarse sand before paving. All angles and edges of the stones shall be true, square and free chipping and surface shall be true and plain.
- 1.5. The Marble slab shall have machine cut free edges with half round pipe moulding mirror polished surface. When brought on site. The stones to be used for flooring dado, skirting, sink, veneering, sills, steps etc.

2.0 WORKMANSHIP

- 2.1 Marble slab shall be of approved quality shall be laid evenly to level and slope as directed by Engineer in charge over a bed of a base layer consisting of cement mortar 1:6 (1 cement: 6 coarse sand by volume) or Lime Mortar 1:1.5 (1 lime : 1.5 lime putty by volume).
- 2.2 Marble slab shall be laid evenly as per detailed drawing or as directed by Engineer in charge. Width, length and shape of stone shall be as per pattern shown in detailed drawing.
- 2.3. Cement and sand for base layer shall be mixed in proportions of 1:6 (1 cement : 6 coarse sand by volume). Cement and sand shall be proportioned by volume after making due allowance for bulking. The required quantity of water shall then be added and the mortar mixed to produce workable consistency before mixing platform shall be thoroughly cleaned before changing from one type of cement to another.

- 2.4. The mixing for base layer shall be done intimately. The operation shall be carried out on clean water tight platform and cement sand shall be first mixed dry in the required proportion to obtain uniform colour and then the mortar shall be mixed for at least two minutes after addition of water. In case of cement mortar, that has suffered because of evaporation of water the same shall be re-tempered by adding water as frequently as needed to restore the requisite consistency but its re-tempering shall be permitted only within thirty minute from the time of addition to water at the time of initial mixing.
- 2.5. Cement and sand for base layer shall be mixed in proportion as specified in the item, Cement and sand shall be proportioned by volume after making due allowance for bulking. The required quantity of water shall then be added and the mortar mixed to produce workable consistency.
- 2.6. Curing shall be started as soon as the mortar used for finished has hardened sufficiently no to be damaged when watered. It shall be kept wet for a period of at least 7 days. During this period, it shall be suitably protected from all damages.
- 2.7. During hot weather, all finished or partly finished work shall be covered or wetted in such manner as will prevent rapid drying of the flooring work.
- 2.8. Joints of Marble slab flooring shall be through and continuous throughout the building as directed by Engineer in charge.
- 2.9. Joints shall be filled with a stiff mixture of gray cement slurry.
- 2.10. The Marble slab flooring work shall be finished by rubbing and mirror polishing after the work of flooring is set properly.

3.0 MODE OF MEASUREMENT & PAYMENT :

- 3.1. The unit rate Green Marble stone slab flooring shall include the cost of all materials, tools and plant required for mixing, laying of base layer in true level and slope as required applying & placing stones in position, finishing, curing etc. flooring all over the length of walls and corners and sill of doors etc. and all other incidental expenses for producing flooring work to complete the structure or its components as shown on the drawings and according to these specifications. They shall also include the cost of making, fixing and removing of all scaffolding and forms required for the work. The rate includes cost of mirror polishing of flooring and dado work.
- 3.2. The rate shall include the cost of all materials and labours involved in all the operations described above. The Green marble stone slab flooring shall be measured in Square meter correct to 2 places of decimal. Length and breadth shall be measured to correct to a centimeter and between the finished the finished face of the skirting, dado or wall plaster and no deduction shall be made nor extra paid for any opening in floors or areas up to 0.1 square meter.
- 3.3. The rate shall be for a unit of **one Square meter**.

Item No. 19 :- Providing and fixing safety grills of Required pattern for Windows, Door using required size of MS polished bars at specified spacing inserted and welded from inside to rectangular box type frame CRC Pipes of Required Size at required spacing as per design and hold fastening with coach bolts including one coat of primer and two coats of matt finished oil painting etc complete...

1.0 Scope of work : The item of safety grill required pattern for windows / Ventilator / Door using 16mm dia. comprises of M.S. polished bars, CRC pipe and oil painting work.

2.0 Materials: The M.S. bars, CRC pipe and all the fixture and fastening shall be of standard approved quality.

3.0 Workmanship : The item covers the requirement of preparation of Safety grills of required pattern for windows / Ventilator / Door using M.S polished bars / pipes / M.S. angles / flats of size and at required spacing as per drawings as per design and hold fastening with coach bolts including one coat of primer and two coats of matt finished oil painting shall be of approved quality by the Engineer-in-charge.

4.0 Mode of measurements and Payments:

The rates for safety grills for windows / Ventilator / Door shall be includes cost of providing all required materials and painting etc. keeping in position as directed.

The dimension of the safety grill for windows / Ventilator / Door shall be measured clear size of the windows / Ventilator / Door.

The rate shall be for a unit of **One Kg.**

Item no. 20 :- Providing and laying water proofing treatment with chaina mosaic tiles flooring over avg 40 mm C.C. 1:2:4 {1 Cement : 2 sand : 4 Kapachi / Gritt 6 to 12 mm size} bedding for maintaining slope for plain and curve surface & 12 mm to 20 mm of broken piece of ceramic / glazed tiles (one for more color as directed) to be laid over cement mortar bedding of C M 1:3 (1 cement : 3 sand) containing one Kg of water proofing materials per bag of O P C at plain or / and slopes and to be tempered to bring mortar ceramic up to surface with using white cement and colour pigment including rounding of junctions and extending them up to 15 cm along the wall and curing with bends any patterns or design as per drawing and cleaning by using oxalic acid etc complete.

1.0 MATERIAL - WATER

- 1.1 Water shall not be salty brackish and shall be clean, reasonably clear and free objectionable quantities of silt and traces of oil injurious alkalis salts organic matter and other deleterious material which will either weaken the mortar of concrete or cause efflorescence or attack the steel in R.C.C. container for transport storage and huddling of water shall be clean. Water shall conform to the Standard Specification in I.S. 455 - 1978.
- 1.2 If required by the Engineer in charge, it shall be tested by comparison with distilled water compression shall be made by means of standard cement tests for soundness, time of setting and mortar strength as specified in I.S. 269 - 1976. Any indication of unsoundness change in time of setting by 50 minutes or more or decrease of more than 10 percent strength of mortar prepared with distilled water sample when compared with the result obtained with mortar prepared with distilled water shall be sufficient cause for rejection of water under test.
- 1.3 Water for curing, mortar concrete or masonry should not be too acidic/too alkaline.
- 1.4 It shall be free of elements which significantly affect the hydration reaction or otherwise interface with the hardening of mortar or concrete during curing or those which produce objectionable stains or other unsightly deposits on concrete or mortar surfaces.
- 1.5 Hard and bitter water shall not be used for curing.
- 1.6 Potable water will generally found suitable for curing mortar or concrete.

2.0 CEMENT

- 2.1 Cement shall be ordinary Portland slag cement as per I.S. 1624 - 1974 or Portland slag cement as per I.S.455-1976.

- 2.2 Cement shall be stored above the ground level in perfectly and dry and water tight sheds. Wherever bulk storage containers are used, there capacity should be sufficient to cater to the requirements at site and should be cleaned at least once every 3 to 4 months. The aggregate shall be stored in such a way as to prevent admixture of foreign materials. Different size of fine or coarse aggregate shall be stored in separate stock piles sufficiently away from the each other to prevent inter mixing the materials.

3.0 SAND

- 3.1 Sand shall be natural sand, clean, well graded, hared, strong, durable and gritty particular free from immures amounts of dust, clay, kankar, modules, soft or flaky particles shall alkali salts, organic matter, learn mica or other deleterious substance and shall be got approved from the Engineer in charge. The sand shall not contain more than 8 percent of slit as determined by field test if necessary, the sand

COARSE SAND - The fineness modules of coarse sand shall not be less than 2.5 and shall not exceed 3.0. The sieve analysis of coarse sand be as under :

I.S. Sieve Designation	% by wt. passing
4.75 mm	100
2.36 mm	90 to 100
1.18 mm	70 to 100
600 MC	30 to 100
300 MC	85 to 70
150 MC	00 to 50

- 3.2 **FINE SAND** :The fineness modules shall not exceed 1.0 the sieve analysis of fine sand be as under:

I.S. Sieve Designation	% by wt. passing
4.75 mm	100
2.36 mm	100
1.18 mm	70 to 100
600 MC	40 to 85
300 MC	05 to 50
150 MC	00 to 10

- 3.3 Materials shall be stored as to prevent their deterioration of their quality and fitness for the work. Any material which has deterioration or has been damaged

or is otherwise considered defective by the Engineer in charge shall not be used in the work.

1.4 WATER PROOFING COMPOUND

Water proofing compound shall be of approved quality and make as approved by Engineer in charge.

1.5 BRICK BATS

Brick bat aggregates shall be broken from well burnt or slightly over burnt and dense bricks it shall be homogeneous in texture roughly cubical in shape clean and free from dirt or any other foreign material brick bats shall be of 12 to 20 mm nominal size unless otherwise specified in the item the under burnt or over burnt bricks bats shall not be used.

1.6 CHINA MOSAIC TILE PIECES

China mosaic tiles pieces shall be of 50 mm to 90 mm nominal size, tiles pieces shall be made from hard and good quality of tiles.

1.7 WHITE CEMENT

White cement shall be of approved make it shall confirm definition of I.S. 8042-E-1978 the sample of white cement shall be approved by Engineer in charge.

WORKMANSHIP

A First of all surface of the entire terrace shall be cleaned by thoroughly brooming and then by wire brushes. All the loose material, dust and debries shall be removed thoroughly from the entire surface of the terrace.

All joints and cracks shall be racked off and cut in trench which shall be filled by neat cement slurry admixed with water proofing compound. The joints with parapet shall be racked up to 30 cm height and shall be applied by neat cement slurry admixed with water proofing compound.

Neat cement slurry shall be prepared and a water proofing compound of approved make shall be mixed with the slurry in proportion specified by the manufacturer of the compound and shall be laid through out the surface of the terrace by the use of brushes mala etc. Cement slurry shall be prepared by adding adequate quantity of water so as to spread it uniformly on the surface.

B 50mm thick Cement concrete 1:2:4 (1 part of cement and 2 part of coarse sand and 4 part coarse aggregate 20mm nominal size by volume) admixed with water

proofing compound of approved make in specified proportion) of specified thickness shall be laid (Specification of C.C. 1:2:4 shall be followed for the execution of this layer) all over the surface of the terrace in true level and required slope including rounding of junctions of walls and slabs.

- C** After two days of proper curing applying a second coat of cement slurry on entire surface of the terrace.
- D** The entire surface shall be finished with 20 mm thick C.M. 1:3 and China mosaic tilling in true level and slope as directed by Engineer in charge and finally finishing the surface with trowel with white cement slurry (Specification of white glazed tiles flooring shall be followed for the execution of this item).
- E** Finishing the surface with 20 mm thick C.M. 1:3 and China mosaic tilling and finally finishing the surface with trowel with white cement slurry.
- F** After two days proper curing the terrace shall be flooded for 15 days.

7.0 MODE OF MEASUREMENT AND PAYMENT

- 7.1** The unit rate of flooring shall include the cost of all materials, tools and plant required for mixing, laying of base layer in true level and slope as required applying and placing broken pieces of china mosaic tile in position, compacting, finishing, curing, providing treatment of 30 cm high allover the length of parapets and corners and sill of doors etc. and all other incidental expenses for producing flooring work to complete the structure of its components as shown on the drawings and according to these specifications. They shall also include the cost of making, fixing of all scaffolding and forms required for the work.

The rate of plastering shall include the cost of all labour, materials, tools and plants, scaffolding and all incidental expenses as described herein above.

- 7.2** The plaster work shall be measured for its length and width, limiting dimensions to those specified on plan or as directed. The rate shall be for a unit of one Square Meter.
- 7.4** A guarantee bond on appropriately stamped paper shall be given by the contractor to the Department in the manner and form prescribed below.
- 7.3** The payment will be made on **Square Meter** basis of the finished work.

FORM OF GUARANTEE BOND

Contractor I / We _____) here by guarantee that work will remain unaffected and will not be in anyway damaged by water rain and will not leak from surface for a period for 5 years after completion of the work of water proofing treatment as per the terms and conditions of the contract and damage that might be caused on account of water rain and or other similar type of dampness or leakage from walls or above floor.

The guarantee shall remain in force for the period of 5 years from the completion of the work under the contract and it shall remain binding to the contractor for period of 5 years.

The deposit at the rate of 20% of the cost of this item from the running and final bills shall be recovered and remained for the first one year after completion of the work or at least on monsoon season passed which ever is later and 10% shall be retained for the balance of the guarantee period and shall be returned only after completion of the guarantee period.

MODE OF MEASUREMENT AND PAYMENT

The length and breadth shall be measured correct to cm. as per the dimension of the sanctioned plants. No deduction shall be made nor extra for paid for any opening for pipes etc. upto 0.1 sq.mt. The rate shall include the cost of all labour and materials required for the operation involved. For satisfactory completion of work & measurement shall be paid on unit of Sq.m. of finished work.

Item No. 21 :- Wall painting (Two coats) with plastic emulsion paint of approved brand and manufacture on undecorated wall surface to give an even shade including thoroughly brushing the surface free from mortar droppings and other foreign matter and sand papered smooth. including Applying two coats of Birla or Asian acrylic lapy (putty) & two coats of primer of approved brand and manufacture on new wall surface to give an even shade including thoroughly brushing the surface free from mortar dropping and other foreign matter and sand papered smooth....

1.0. Materials

Water shall be conform M-1. The **plastic emulsion paint** shall conform to I.S.: 5411-1969 (Part-I) and as approved by the **consultant architect**.

The paint's colour, quality, brand and make shall be as approved by the **consultant architect**.

The sample shall have to be approved by the **consultant architect** before execution on site.

2.0. Workmanship

The painting work shall be for subsequent coat of **plastic emulsion paint** of approved brand & manufactures.

The painting shall be done as per the approved design and drawings supplied by the **consultant architect**.

2.1. Scaffolding : Wherever scaffolding is necessary it shall be erected in such a way that as far as possible on part of scaffolding shall rest against the surface to be white or colour washed. A properly secured strong and well tied suspended platform (Zoola) may be used for white washing. Where ladders are used pieces of old gunny bags shall be tied at top and bottom to prevent scratches to the floors and walls. For white washing of ceilings, proper stage scaffolding shall be erected where necessary.

2.2. Preparation of surface : The undecorated surface to be distempered shall be thoroughly brushed from dust, dirt, grease, mortar dropping and other foreign matter and sand papered smooth. New plaster surface shall be allowed to dry for at least 2 months before applications of distemper.

2.2.1. All unnecessary nails shall be removed. Pitting in plaster shall be made good with plaster again with a fine grade sand paper and made smooth. A coat of distemper shall be applied over the patches. The surface shall be allowed to dry thoroughly before the regular coat of distemper is allowed. The surface affected by moulds, moss, fungi, algae lichens, efflorescence etc. shall be treated in accordance with I.S; 2395 (Part 01) 1966. Before applying distempering, any unevenness shall be made good by applying putty made of plaster of pairs mixed with water on entire surface including filling up the undulation and then sand papering the same after it is dry.

2.3. Preparation of Mix :

This shall be done as per manufacture's instructions. The thinning of emulsion is to be done with water and not with turpentine. The quantity of thinner to be added shall be as per manufacturer instructions.

2.4. Application :

- 2.4.1.** Before pouring into small containers for use, the paint shall be stirred thoroughly in item container. When applying also, the paint shall be continuously stirred in the smaller container, so that its consistency is kept uniform.
- 2.4.2.** The paint shall be laid on evenly and smoothly by means of crossing and laying off the crossing and consist of covering the area over with paint, brushing the surface hard for the first time over and then, brushing alternately in opposite direction two or three times and then finally brushing lightly in direction at right angles to the same. In this process, no brush Marks shall be left after the laying off is finished. No hair marks from the brush or clogging of paint puddles in the corners of panels, angles of moldings, etc. shall be left on the work. The full process of crossing and laying off will constitute one coat.
- 2.4.3.** The paint shall be applied with brush or rollers. For undecorated surfaces, the surface shall be treated with minimum two coat of cement water proofing paint. The second or subsequent coat shall not be started until the proceeding coat as become sufficiently hard to resist marking by brushing being used.
- 2.4.4.** The surface on finishing shall present a flat velvety smooth finish. It shall be even and uniform in shade without patches, brush marks, paint drops etc.

2.5. Precautions :

- (a) Old brushes if they are to be used with emulsion paints shall be completely dried of turpentine or oil paint by washing in warm soap water. Brushes shall be quickly washed in water immediately after use and kept immersed in water fusing break periods to prevent the paint from hardening on the brush.
- (b) In the preparation of wall for plastic emulsion painting, no oil base petals shall be sued in filling cracks, holes etc.
- (c) Splashes on floors etc. shall be cleaned out without delay as they will be difficult to remove after hardening.
- (d) Washing or surfaces treated with emulsion paint shall not be done within 3 to 4 weeks of application.

- 2.6. Protective payment :** The surface of doors, windows, floors, articles, of furniture etc. and such other parts of the building not to be white washed shall be protected from being splashed upon. Such surfaces shall be cleaned of white wash splashed if any.

3.0. Mode of measurements and payment

- 3.1.** All the work shall be measured in the decimal system as under:

- (a) Dimensions shall be measured to the nearest 0.01 m.
- (b) Area in individual item shall be worked out to the nearest 0.01 sq.m.

All the work shall be measured in sq.mt. Deductions for jambs, soffits, sills etc. for openings not exceeding 0.5 sq.mt. each in area, for ends of joists, posts, beams, girders, steps etc. not exceeding 0.5 sq.mt. each in area and for openings exceeding 0.5 sq.mt. and not exceeding 3.0. sq.mt. each in area, deductions and additions shall be made as under.

- 3.2.** No deductions shall be made for ends of joists, beams, posts, etc. and openings not exceeding 0.5 sq mt. each. No addition shall be made for reveals, jambs, soffits, sills etc. of these openings not for finish around ends of joints, beams, posts etc.

- 3.3.** No deductions for openings exceeding 0.5 sq.mt. but not exceeding 3 sq.mt. each shall be made as follows and no addition will be made for reveals, jambs, soffits etc. of these openings :
- (a) When both the faces of walls are provided with finish, deduction shall be made for one face only.
 - (b) When each face of wall is provided with different finish, deduction shall be made for that side of frame for door, windows, etc. on which width of reveals is less than that of the other side. Where width of reveals on both faces of wall are equal, deduction of .50% of area of opening on each face shall be made from total area of finish.
 - (c) When only one face of wall is treated and the other face is not treated, full deduction shall be made if the width of reveal on the treated side is less than that on the untreated side, but if the width of the reveal is equal or more than on the untreated side neither deductions nor additions to be made for reveals, jambs, soffits, sills etc.
- 3.4** In case of area of openings exceeding 3 sq. mt. each, deductions shall be made for openings but jambs, soffits, sills shall be measured.
- 3.5.** No deductions shall be made for attachment such as casing, conducts, pipe, electric wiring and the like.
- 3.6.** Corrugated surfaces shall be measured flat as fixed and not girth. The quantities so measured shall be increased by the following percentage and the resultant shall be included with the general areas:
- (a) Corrugated steel sheets..... 14%
 - (b) Corrugated A.C. sheets..... 20%
 - (c) Semi corrugated A.C. Sheets..... 10%
 - (d) Nainital pattern roof (Plain sheeting sheets)..... 10%
 - (e) Naintial pattern roof (with corrugated sheets)..... 25%
- 3.7.** Cornices and other wall features, when they are not picked out in a different finish/colour shall be girthed and included in the general area.
- 3.8** Extra payment shall be done on ceiling and sloping roofs.
- 3.9.** The rate shall include the cost of ail materials, labour, scaffolding, protective measures etc. involved in all the operations described above.
- 4.0** The rate shall be for a unit of **One sq. meter**.

Item No. 22 :- Providing and fixing to wall ceiling and floor 10.0 Kg. F/Cm² working pressure poluthene pipes of the following outside Dia. Low density, complete with special falnge compression type fittings, wall clipsetc. including making good the wall ceiling and floor.(G)110 mm..

1.0. Materials

1.1. The low density polythene pipe of specified diameter with **10.0 Kg./Sq.cm.** working pressure shall conform to I.S. 3076-1968. The specials and fittings required shall be of best quality.

2.0. Workmanship

2.1. The P.V.C. pipes of specified diameter shall be fixed as directed. Due to thermal expansion of rigid P.V.C. pipes, due allowance shall be made particularly in over ground pipe lines for any change in length of pipe line which may occur during installation or when pipe line which may occur during installation or when pipe line is in service.

2.2. Above ground installation of rigid P.V.C. pipe should be under taken after preparations are observed for their protection against direct sun rays and mechanical damage.

2.3. The rigid P.V.C. pipe lines should not be kept exposed above ground when it passes through public places, railway lines, road side and foot paths.

2.4. P.V.C. pipes shall be supported at the following intervals :

-20 mm. dia 500 mm. -25 mm. dia 750.mm. -32 mm. dia.900 mm.

2.5. Closer support spacing shall be provided if recommended by the manufacture.

2.6. The guide lines indicated by the manufacturer regarding handling, transportation, storing, laying and jointing pf pipes shall be kept in view during execution.

2.7. P.V.C. pipes shall be fixed on wall with wooden plugs and suitable plastic clamps.

2.8. Jointing the pipes :

2.8.1. The pipes and sockets shall be accurately cut. The ends of the pipes and fittings should be absolutely free from dirt and dust. The outside surface of the pipes and the inside of the fittings shall then be roughened with emery paper, and then solvent cement joint. Since solvent cement is aggressive to P.V.C. care must be taken to avoid applying excessive cement to the inside of pipe sockets as any surplus cement cannot be wiped of after jointing. Empty solvent cement tins, brushes, rags, or paper impregnated with cement should not be buried in the trenches. They should be gathered not left scattered about, as-they can prove to be a hazard to animals, which may chew them.

2.8.2. If any manufacturer recommends its own methods of jointing the same shall be adopted after necessary approval from the Engineer-in-charge.

2.9. Laying pipes in Trenches :

2.9.1. The pipes shall be laid over uniform relatively soft fine trained soil found to be free of presence of hard object such as large flints, rocky projections, large tree roots etc. The width of the trenches shall be minimum width required for working.

2.9.2. The pipes laid underground shall not be less than one meter from the ground level. The pipe shall be positioned in the trenches so as to avoid any induced stressed due to deflection. Any deviation required shall be obtained by using proper type of rubber ring joints.

3.0. Mode of measurements & payment

- 3.1.** The description of the item shall, unless otherwise stated be held to include where necessary conveyance and delivery, handling, unloading, storing fabrication, hoisting, all labour for finishing to required shape and size, setting, fitting in position straight, cutting and waste return of packing etc.
- 3.2.** The length shall be measured on running meter basis of finished work. The length shall be taken along the centre line of the pipe and fittings. The pipes fixed to wall, ceiling, floors etc shall be measured and paid under this item.
- 3.3.** All the work shall be measured in decimal system as fixed in its place, subject to tolerance given below unless otherwise stated.
(i) Dimension shall be measured to the nearest 0.01 meter. (ii) Area shall be worked out to the nearest 0.01 sq. meter.
- 3.4.** All measurements of cutting shall unless otherwise stated be held to include the consequent waste
- 3.5.** In case of fitting of unequal bore, the targets bore shall be measured for the test.
- 3.6.** Testing of pipe lines fittings, and joints include for providing all plant appliances necessary for obtaining access to the work to be tested and carrying out the tests
- 3.7.** The rate includes P.V.C. pipes with screwed socket joints. to gather with all fittings (such as bends, sockets springs, elbows, test, crosses, short pieces, clamps and plugs, unions etc.) and fixing complete with clamping wall hooks, wooden plug etc. and also curing, screwing and waste and for making forged (or hand made) bends on piping as required. Connector shall be inserted where required or directed. The rate also includes cutting through walls, floors etc. and their making good and painting exposed threads with anti-corrosive paint as above and testing where tubes are to be fixed to wall, ceiling and flooring, the rates shall not include painting of pipes, providing sleeves and sand filling under floor for which separate payment shall be made.
- 3.8.** The unit rate shall be for a unit of **One running meter.**

Item No. 23 :- SIGNAGES ON WALL

Providing, Fabricating & Fixing wall signage's using 304 grade Stainless steel brushed steel finish plate of 1.5 mm thick fixed on a wall using s.s studs including punched (laser cut) lettering carried out on s.s plate of required size and text as directed by Engineer over the S.S plate etc complete.

In general the work shall be carried out as per the standard specifications of P.W.D. / C.P.W.D., relevant drawings and as per the instructions of Engineer in charge. The work shall be carried out & paid as per site conditions and as described in item description.

The signage system shall be placed in such a way to identify and direct a user to their desired destination. The signage shall be placed efficiently so that the signage does not generate confusion, frustration, or cause pedestrian traffic problems.

The effective signage shall have following criteria:

- Noticeable - the sign should be easily recognizable from its background.
- Readable - text should be easily read with good color contrast and sized in relation to its intended viewing distance.
- Provide clear, concise, "easy-to-understand" information - minimal text with the use of graphic symbols helps to convey the message efficiently.

Quality of Manufacture

All signs must comply with State laws, codes and regulations and all municipal ordinances or regulations in effect at the time the work is performed.

A. MATERIALS

All materials should be new and free from defects.

1. Aluminum

- Thickness, size and type as specified in the sign type drawings.
- All seems to be straight and symmetrical.
- Finish: hard-coat anodized colour as per drawing.

2. Fastenings

- All screws, nuts, bolts, and fastenings devices shall be stainless steel, or cadmium-plated non-corrosive material.
- All anchorage and fastenings of miscellaneous metal items shall be structurally adequate and finished to match surface.

3. Electrical

- Electrical parts and materials shall be in accordance with national electrical codes, applicable local codes and should be so labeled.
- Suitable and approved disconnect switches shall be provided.

Location to be as inconspicuous as possible and approved by EIC.

- Electrical service will be provided at the location and voltage specified. Extensions of wiring, conduit and transformation of voltages, if required, and final connections shall be part of this section. Verify exact location of existing stubs and junction boxes.
- Signs shall provide an evenly distributed lighted surface equal to an intensity hereinafter specified. Lighted letters shall be of equal intensity and shall be the same as all other letters.
- Signs shall be complete with all necessary lamps, tubes, ballasts, transformers, sockets and internal wiring as required or complete.
operable units. Use of LED lights is preferred.
- All light sources shall be of outdoor type OR as specified on drawings.

4. Plastics

- Thickness, color and type as specified in the sign type drawings.
- Material to be free from scratches or defects and be clean and edges finished per manufacturer's instructions.
- Sheet materials and sampling shapes shall be of thickness recommended by sign fabricator to produce straight or evenly curved surfaces, free from waviness, wrinkles or other deformation except as otherwise herein specified or indicated on drawings.

5. Flexible Materials

- Thickness, size and type as specified in the sign type drawings.
- Fastening devices to meet manufacturer recommendations. Seam placement to be straight and symmetrical.

6. Coatings and Finishes

- All aluminum, metal and fasteners shall be finish coated with an appropriate primer and color coat with corrosion inhibitors guaranteed against fading, chipping, cracking, peeling and discoloration. Color as specified in sign type drawings.
- All flexible face coatings shall be guaranteed against fading, discoloration and mildew.
- All holes, penetrations and cut edges of pre-finished metals must be free of burrs, primed and painted to maintain a corrosion-proof finish.

7. Miscellaneous Materials

- Any metal hardware used for construction not previously covered shall be of stainless steel, aluminum or steel with galvanized coating.
- Wood, fiber glass, brick, stainless steel or any other material must be of top grade quality and as specified on drawings.

B. WORKMANSHIP

Any work required under this section that is not described in detail shall be constructed in accordance with approved shop drawings.

1. Accuracy of Work

All work shall be fabricated and erected square, plumb, straight and true. Cut-out letters, numbers and images shall be cut to continuous, sharp even line of profile as indicated on drawings. Provide all supporting and anchoring means as required for proper installation.

All curved areas to be true. No kinks, creases, oil-canning or dimpling will be accepted

2. Exposed Metal Surfaces

Exposed metal surfaces shall be reinforced, braced and securely fastened to provide rigid assembly. Sign faces shall be free of all holes except those required to install letters or weep-holes. Service access doors shall be concealed wherever possible. Flush-butt locked seams and fillers shall be metal screwed and bolted on filler edges to provide smooth faces free of unsightly rivets. All steel items exposed to the weather and all other steel items as indicated or specified shall be galvanized or ground and painted with zinc-chromate primer and finish coat.

3. Exposed Joints

Exposed joints should be continuously welded, ground and polished smooth and shall not be visible. Mitered corners shall be snug, neat and tight fitting in an even, smooth plane.

4. Exterior Cabinets and Frames

Exterior cabinets and frames shall be fastened with stainless steel screws of countersunk, or nuts and bolts as indicated in the drawing. The inside of exterior signs shall be rainproof. Signs shall be provided with weep-holes in bottom edging, of sufficient size to allow full drainage of any condensate moisture collected in the sign.

5. Aluminium in Contact with Ferrous Metals

Aluminium in contact with ferrous metals shall be separated with a heavy coating of bit mastic paint or sheet neoprene.

6. Accessories, Anchorage, Mounting Devices and Spacers

Accessories, anchorage, mounting devices and spacers shall be guaranteed non-staining to adjacent walls and sign finished for a period of five (5) years from final acceptance. Ferrous mountings may be sleeved with non-ferrous metal covers matching adjacent finishes, cemented on with non-hydroscopic glue, or other suitable protective measures may be proposed to comply with this guarantee.

C. INSTALLATION

All signs shall be in place as indicated on the drawings or where directed by the designee. Signs shall be secured with studs, toggle bolts, expansion bolts, or methods as approved on shop drawings specified hereinafter and of sizes required to assure rigid attachment. Survey of ground conditions related to soil content, density and compaction are the responsibility of the installer prior to submitting a bid. Removal and/or replacement of asphalt, concrete, existing footings and poles are the responsibility of the installer unless otherwise specified on drawings.

F. GUARANTEE AND SERVICE

Contractor shall furnish a written guarantee to the effect that all material and work furnished under this section is guaranteed for one (1) year to be free from defects and faulty workmanship, and that any defective material or work shall be promptly repaired or replaced without additional cost to the U of M or designee. Contractor shall, during the first year of operation, fully maintain and service the signs, making regular inspections, and servicing and replacing tubes and electrical equipment as may be necessary to maintain the signs in operation

without additional cost to the U of M or designee. Any guarantees for additional time or services as required in other sections of this document or as noted on specifications are to be in addition to this section.

G. PROTECTION

All exposed surfaces shall be protected until final acceptance of the work in a manner sufficient to prevent damage or discoloration. Any work damaged or discolored in any way before final acceptance of the work shall be replaced without additional cost to the designee.

H. CLEAN-UP

During the process of the work, the premises shall be kept reasonably free of all debris and waste materials resulting from the work under this section. Upon completion and before final acceptance of work, all debris, rubbish, leftover materials, tools and equipment shall be removed from the site.

I. FINAL CLEANING

Final cleaning of all surfaces shall be carefully done strictly in accordance with the manufacturer's instructions.

C. FABRICATION METHODS

1. Digital Printing

Computer generated artwork printed directly (or applied) to second surface of clear acrylic substrate. Print quality should be higher resolution using UV-stable inks. Color management software should be used for consistent color reproduction.

2. Silk-screening

Silk-screen ink applied to second surface of clear acrylic substrate. This is an economical method for producing custom background colors. Silk-screened text and/or graphics should only be considered for permanent signs where large quantities are needed.

3. Engraving

The engraving process is commonly used to create tactile (raised) text and graphics through the layering of material. Subsurface text and graphics are created by engraving into the front face of the material. Reverse-engraved text and graphics are created by engraving the backside of material with a clear face and a colored back and then paint filling the engraved areas. These engraving methods can be used alone or in combination.

4. Braille

Use the Raster™ Method patented process for placing Braille dots on architectural signs using a special carbide engraving bit, manual insertion device (Raster™ Pen) or automated insertion device (Auto-Raster™) and UV stable clear acrylic Rasters™.

5. Vinyl

Pressure sensitive vinyl letters and graphics are computer generated and cut for accuracy. Vinyl can be applied first surface or second surface and is easily changeable. Vinyl can be used indoors and outdoors and is an economical choice for certain sign type applications.

6. Painting

Spray paint for consistent, even color and coverage. To maintain the quality of the signage the following points may be considered: No screws, nuts, bolts, welding marks, cutting marks, edge of the MS sections should be prominently visible from the outside. All details should be worked out from the inside.

Provide grooves to have the fixing details embedded so that they are not prominently visible from outside. Place visible hinges, screws inside these grooves. A beading shall be provided to cover the groove.

Do not use putting and patching up to cover up misalignments in the panel sizes. Make use of jigs, fixtures and guides while fabricating the parts so that all of them match and align properly.

Do not use hand painting to finish the surface. The paint should be sprayed in the factory in proper painting booths and not at site. This way you can maintain the required finish (glossy, matt, shiny or dead matt) consistently all over the signage.

Do not directly paint the MS components - that are prone to rusting. Mild Steel (MS) parts have to be properly treated according to procedure and then only the final coat of finish should be applied. All Screws, nuts and bolts that are exposed to outside preferably should be Stainless Steel Fasteners that are Cold Forged.

Mode of Measurement and Payment:

The rate includes cost of all materials, tools, plants and labour involved in satisfactory completion of work etc. complete.

The rate shall as per actual work done.

The work shall be carried out as per detailed drawings and as directed by Engineer in charge. Measurements shall be as per description.

The rate shall be a unit of one **No.**

Item No. 24 :- Providing and fixing in position collapsible steel shutters with vertical channels 20 x 10 x 2 mm braced with flat iron diagonals 20 x 5 mm size with top and bottom rails of T_rin 40x 40 x 6 mm with 38mm dia, steel pulleys complete with bolts, nuts, locking arrangements, stoppers handles including applying a priming coat of red lead paint..

1.0. Materials

The collapsible steel shutters shall conform to M-33 and Primer of red lead paint.

2.0. Workmanship

J-rails shall be fixed to the floor and to the lintel at top by means of Anchor bolts, embedded in cement concrete of floor and lintel. The anchor bolts shall be placed approximately at 45 mm. centers alternatively in groove shall be formed along the runner for the purpose. The collapsible gate shall fixed at the sites by fixing the double channels in the T-iron rail and also by hold fasts bolted to the end double channel and fixed in the masonry of the side walls or the otherwise. In case where the collapsible gate is not required to the lintel beams or slop above, a toe iron suitably designed may be fixed at the top embedded in masonry and provided with necessary clamps and roller arrangement at the top.

All the adjoining work damaged while fixing of gate shall be made good to match the existing work without any extra payment. All the members of the collapsible gate including. T-iron shall be thoroughly cleaned of rust, scales dust etc. and given a priming coat of red lead, before fixing them in position.

3.0. Mode of measurement and payment

3.1. The collapsible steel shutters shall be measured in sq.meter. The height of the gate shall be measured as the length of double channels and breadth from outside to outside of the end fixed double channels in open position of the gate. The rate includes providing handles, arrangements stoppers etc. and providing & applying primer coat etc. complete satisfactory of item as directed by Engineer in charge.

3.2. The rate shall be for a unit of one sq.meter.

Item No. 25 :- Providing & fixing of reinforcement bars (reinforcement bars shall be paid extra under relevant item of work) after drilling the hole of required diameter & depth ,cleanning of the same ,providing /filling the hole with Injection Mortar (HIT HY 150 of Hilti or pproved equivalant),inserting reinforcement bar etc. complete dSper Manufacturers & architects instruction.The work shall be carried out by the technical workmens/agency approved by the manufacturer and under technical supervision of Manufacturer of Injection grout including all materials,tool tackles ,labour etc.complete. (a) 10/12 mm. dia.bar -Holes 14mm/16mm dia Depth 300 mm.

1.0. Materials

- 1.1.** Supplying Mechanical stud anchors (Nut Version) HSA of sizes M8 (75 mm long)/M10 (90 mm long) / M12 (100 & 150 mm long)/ M16 (140 mm long)/ M20 (170 mm long) of HILTI India Pvt. Ltd. or approved make. The anchor should be of cold formed carbon steel anchor, A4, Galvanized/Stainless steel and can be used for two embedment depths.
- 1.2** Supplying Plastic light duty impact anchors HPS-1 of HILTI India Pvt. Ltd or approved make for size ranges from 4-8 mm dia. (50 to 110 mm long). The anchor should be made of polyamide sleeve PA6 grade with 4 way expansion and galvanized coated.
- 1.3** Supplying heavy duty injection adhesive for rebar fixing in Wet/Dry conditions HILTI HIT-RE 500 for dia. up to 40mm of HILTI India Pvt. Ltd. or approved make. The system should be made of two foils consisting of resin and Hardener foil pack. The system can be used for rebar fixing or threaded rods viz HAS-E rods. The rate of Threaded rods used if any and reinforcements will be included.
- 1.4** Supplying medium to heavy duty injection adhesive for rebar fixing in Dry conditions HILTI HIT-HY 150 for dia. upto 25mm of HILTI India Pvt. Ltd. or approved make. The system should be made of two foils consisting of resin and Hardener foil pack. The system can be used for rebar fixing or threaded rods viz HAS-E rods. The installation and the setting instructions should be strictly followed as per the manufacturer's recommendations. The rate of Threaded rods used if any and reinforcements will be included.
- 1.5** Supplying light duty injection adhesive for fixing in hollow bricks, standard bricks, masonry, etc with HILTI HIT-HY 70 of HILTI India Pvt. Ltd. or approved make. The system should be made of two foils consisting of resin and Hardener foil pack. The system can be used for rebar fixing or threaded rods viz HAS-E rods. The installation and the setting instructions should be strictly followed as per the manufacturer's recommendations. The rate of Threaded rods used if any and reinforcements will be included.

2.0 MODE OF MEASUREMENT & PAYMENTS

- 2.1** The rate shall be for a unit of one **number** basis.

Item No. 26 : Demolition of Brick work and stone masonry including stacking of serviceable materials and disposal of unserviceable materials with all lead and lift.(ii) In Cement Mortar..

1.0. Workmanship

- 1.1. The demolition shall consist of demolition of one or more parts of the building as specified or shown in the drawings. Demolition implies taking up or down or breaking up. This shall consist of demolishing whole or part of work including all relevant items as specified or shown in the drawings.
- 1.2. The demolition shall always be planned before hand shall be done in reverse order to the one in which the structure was constructed. This scheme shall be got approved from the Engineer-in-charge before starting the work. This however will not absolve the contractor from the responsibility of proper and safe demolition.
- 1.3. Necessary propping, shoring and under pinning shall be provided for the safety of the adjoining work or property, which is to be left intact, before dismantling and demolishing is taken up and the work shall be carried out in such a way that no damage is caused to the adjoining property.
- 1.4. Wherever required, temporary enclosures or partitions shall also be provided. Necessary precautions shall be taken to keep the dust nuisance down as and where necessary.
- 1.5. Dismantling shall be commenced in a systematic manner. All materials which are likely to be damaged by dropping from a height or demolishing roof, masonry etc. shall be carefully dismantled first. The dismantled articles shall be properly stacked as directed.
- 1.6. All materials obtained from demolition shall be the property of Government unless otherwise specified and shall be kept in safe custody until handed over to the Engineer-in-charge.
- 1.7. Any serviceable materials, obtained during dismantling or demolition shall be separated out and stacked properly as directed with all lead and lift. All unserviceable materials, rubbish etc., shall be stacked as directed' by the Engineer-in-charge.
- 1.8. On completion of work, the site shall be cleared of all debris rubbish and cleaned as directed.

2.0. Mode of measurements and payment

- 2.1. Measurements of all work except hidden work shall be taken before demolition or dismantling and no allowance for increase in bulk shall be allowed. The demolition of lime concrete shall be measured under this item. Specification for deduction for voids, openings etc. shall be on same basis as that employed for construction of work.
- 2.2. All work shall be measured in decimal system as fixed in its place subject to the following limits; unless otherwise stated hereinafter : (a) Dimensions shall be measured to the nearest 0.01 mt. (b) Area shall be worked out to the nearest 0.01 sq.mt. (c) Cubical contents shall be worked out to the nearest 0.01 Cu.m.

- 2.4.** The unserviceable materials shall be stacked as directed by Engineer-in-charge with all leads and lifts.
- 2.5.** The rate shall include cost of all labour involved and tools used in demolishing and dismantling including scaffolding. The rate shall also include the charges for separating out and stacking the serviceable materials properly and disposing the unserviceable materials with all lead and lift. The rate also includes for temporary shoring for the safety of the portion not required to be pulled down or of adjoining property and providing temporary enclosures or portions where considered necessary.
- 2.6.** The rate shall be for a unit of one **cubic meter**.

Item No. 27 : Dismantling doors, windows, ventilators etc. (wood or steel) shutters including chowkhats architraves, holdfasts and other attachment etc. complete and stacking them within all lead and lift.(ii) Exceeding 3 Sq.M. in area.

1.0. Workmanship

The relevant specifications of **Item No. 26** shall be followed except that the door, windows, ventilators etc. (wood or steel) shutters including chowkhats, architraves, hold fasts and other attachments etc. are to be dismantled.

2.0. Mode of measurements & payment

2.1. The relevant specifications of **Item No. 26** shall be followed.

2.2. The doors, windows, ventilator etc. not exceeding 3 sq. mt. in area (each) including shutters and chowkhats. Architraves, hold fasts and other attachments to frames etc. will be mantled and measured under this item.

2.3. The rate includes stacking the serviceable materials as and where directed with all leads and lifts.

2.4. The rate shall be for a unit of one **each**.

Item No. 28 : Demolition including stacking of serviceable materials and disposal of unserviceable materials with all load and lift. (i) R.C.C. work.

➤ **Scope**

This work shall consist of dismantling and removing existing culverts, bridges, pavements, kerbs and other structures like guard-rails, fences, utility services, manholes, catch basins, inlets etc. from the right of way which in the opinion of the Engineer interfere with the construction of road or are not suitable to remain in place, disposing of the surplus / unsuitable materials and backfilling to after the required compaction as directed by the Engineer.

Existing culverts, bridges, pavements and other structures which are within the highway and which are designed for removal shall be removed upto the limits and extent specified in the drawings or as indicated by the Engineer-in-charge.

Dismantling and removal operations shall be carried out with equipment and in such a manner as to leave undisturbed, adjacent pavement, structure and any other work to be left in place.

All operations necessary for the removal of any existing structure which might endanger new construction shall be completed prior to the start of new work.

➤ **Dismantling Culverts and Bridges**

The structures shall be dismantled carefully and the resulting materials so removed as not to cause any damage to the part of the structure to be retained and any other properties or structures nearby.

Unless otherwise specified, the superstructure portion of culverts/ bridges shall be entirely removed and other parts removed upto at least 600mm below the sub-grade, slope face or original ground level whichever is the lowest or as necessary depending upon the interference they cause to the new construction. Removal of overlying or adjacent materials, if required in connection with the dismantling of the structures, shall be incidental to this item.

Where existing culverts/ bridges are to be extended or otherwise incorporated in the new work, only such part or parts of the existing structure shall be removed as are necessary and directed by the Engineer to provide a proper connection to the new work. The connecting edges shall be cut, chipped and trimmed to the required lines and grades without weakening or damaging any part of the structure to be retained. Due care should be taken to ensure that reinforcing bars which are to be left in place so as to project into new work as dowels or ties are not be injured during removal of concrete.

Pipe culverts shall be carefully removed in such a manner as to avoid damage to the pipes.

Steel structures shall unless otherwise provided be carefully dismantled in such a manner as to avoid damage to members thereof. If specified in the drawing or directed by the Engineer that the structure is to be removed in a condition suitable for re-erection, all members shall be match marked by the contractor with white lead paint before dismantling end pins, nuts, loose plates, etc. shall be similarly marked to indicate their proper location, all pins, pin holes and machined surface shall be painted with a mixture of white lead and tallow and all loose parts shall be securely wired to adjoined members or packed in boxes.

Timber structures shall be removed in such a manner as to avoid damage to such timber or lumber having salvage value as is designated by the Engineer.

➤ **Dismantling Pavements and Other structures**

In removing pavements, kerbs, gutters and other structures like guard rails, fences, manholes, catch basins, inlets etc. where portions of the existing construction are to be left in the finished work the same shall be removed to an existing joint or out and chipped to a true line with a face perpendicular to the surface of the existing structure. Sufficient removal shall be made to provide for proper grades and connections with the new work as directed by the Engineer.

All concrete pavements, base course in carriageway and shoulders etc. designed for removal shall be broken to pieces whose volume shall not exceed 0.02 cubic metre and used with the approval of the Engineer or disposed of.

➤ **Back-filling**

Holes and depressions caused by dismantling operations shall be backfilled with excavated or other approved materials and compacted to required density as directed by the Engineer.

➤ **Disposal of Materials**

All surplus materials shall be taken over by the Contractor which may either be re-used with the approval of the Engineer or disposed of with all lead and lifts.

➤ **Measurements for Payment**

The work of dismantling shall be paid for in units indicated below by taking measurements before and after, as applicable.

(i)	Dismantling brick/stone masonry / concrete (Plain and reinforced)	Cubic Metre
(ii)	Dismantling flexible and cement concrete pavement	Cubic Metre
(iii)	Dismantling steel structure.	Tonne
(iv)	Dismantling timber structure	Cubic Metre
(v)	Dismantling pipes, guard rails, kerbs, gutters and fencing.	Linear Metre
(vi)	Utility services	No.

➤ **Rate**

The contract unit rates for the various items of dismantling shall be payment in full for carrying out the required operations including full compensation for all labour, materials, tools, equipment, safeguards and incidentals necessary to complete the work. The rates will include excavation and backfilling to the required compaction and for handling, giving credit towards salvage value disposing of the dismantled materials within all lead and lifts.

➤ Payment shall be made on **Cum** basis.