

Name of work :- C.R. to Rajkot Kalawad Road SH-25 K.M. 26/0 to 48/7
(Providing MSS Paver Patta work Bet. K.M. 26/0 to 38/0)

TEST SCHEDULE

| It. No. | Type of Test | Frequency of testing (As per most specification for rc |
|---------|-----------------------------|--|
| 1 | 20mm Seal Surface | |
| | FOR TACK COAT | |
| | i) Binder Temnperature | At Regular close interval |
| | ii) Rate of Spread of binde | Two Test per day |
| | FOR PAVER ITEMS | |
| | (B.S. Crushed metal Grit) | |
| | i) Aggregate impact value | Upto 100 Cum 1 Test |
| | ii) Flakiness Indes | 101 to 500 CUM 3 Test |
| | iii) Gradation | 501 to 1500 Cum 5 Test |
| | | 1501 to 5000 Cum 7 Test |
| | iv) Abrasion | Minimum 1 test One for each source of su |
| | v) Stripping Value | |
| | vi) Water absorption | |
| | vii) Crushing strength | |
| | viii) Temperature of binder | At Regular close interval |
| | | at application |
| | ix) Binder Contents | Two test per day per plant |
| | x) Gradation at plant site | Two test per day per plant |
| | xi) Rate of spread of mater | Regular control through joints on materials |
| | | and layer thickness |
| | | |
| | | No. of Tanker No. of Test |
| xii) | Quality of Binder | 1 to 10 1 |
| | Asphalt | |
| | | 11 to 20 2 |
| | | 21 to 50 3 |
| | | 51 to 100 4 |
| | | Above 100 tankers, 1-test per each 50 tankers |

Expenditure for test should be borne by the department, but all materials required for test should be supplied by the contractor to the department from which materials utilized for work. One Percent of estimated cost put to tender will be recovered from the contractor's bill as testing charges.

Deputy Executive Engineer
Jamnagar (R&B)Sub-Dn.
Jamnagar.

Executive Engineer
Jamnagar (R&B)Divisio
Jamnagar.

oad and

pply

in

Name of work :- C.R. to Rajkot Kalawad Road SH-25 K.M. 26/0 to 48/7
(Providing MSS Paver Patta work Bet. K.M. 26/0 to 38/0)

TESTING SCHEDULE

Statement showing laboratory test to be carried out during Execution of work as per Circular No. Govt/R&B Deptt. Gandhinagar No. S.S.R./2083/5411/Date 20-2-82.

| Sr. No. | Tender It. No. | Description of Item in brief. | Details of Materials to be tested | Nature of Lab test | Frequency of test | Remarks. |
|---------|----------------|-------------------------------|--|---|---|----------|
| 1 | 2 | 3 | 4 | 5 | 6 | 7 |
| 1 | | 20mm Mixed Seal Surface. | B.S. Crushed Metal 11.20 to 5.60 2.80 to 5.60 Stone Dust. | 1) Flakiness Index 2) Impact Value 3) Gradation 4) Water absorption 5) Specific Gravity 6) Crushing Strength 7) Abrasion test 8) Stripping Value | Upto 100 Cum. 1 Test 101 to 500 Cum 3 Test 501 to 1500 Cum 5 Test 1501 to 5000 Cum 7 Test Minimum 1 Test (One For Each Source of Supply) | |

Note :- One Percent of Estimated cost put to tender will be recovered from the contractor's bill for testing charges. The Testing Materials shall be provided on laboratory site free of cost by the Contractor.

Deputy Executive Engineer
Jamnagar (R&B) Sub-Dn.
Jamnagar.

Executive Engineer
Jamnagar (R&B) Division
Jamnagar.