

GENERAL TECHNICAL SPECIFICATIONS

FOR ROAD / BRIDGE WORKS

Name of Work-Resurfacing of Chhodavadi Kariya Road
Ch.00/000 to 6/915 Km. Ta.Bhesan
Dist.Junagadh

SPECIFICATION INDEX

Sr No. of the Aplicable in the schedule "B" of the tender	Specifi - cation Referanace	Description of Item	Page No.
1	MORD	Clearing and grubbing of road land incl.uprooting rank vegetation, grass, bushes, shurbs, saplings and trees girth upto 300mm removal of stumps of trees cut earlier and disposal of unserviceable materials © By mechanical means in area of Light jungle.	
2	MORD	Earthwork for embankment including breaking clods, dressing with all lead and lift and including watering rolling and consolidation of subgrade in layers at O.M.C. to required dry density including filling the depression which occur during the process using power roller 8T to 10T. (E) From Borrow area within 3.0KM. lead	
3	MORD	Box cutting the road surface to proper slope and camber for making a base for road work including removing the excavated stuff and depositing on the road side slopes as directed upto all lead.	
4	MORD	Earthwork in cutting in all sorts of soil and soft Murrum including conveying and putting the stuff, in spoil bank maintaining minimum distanace of five meter between top edge of cutting and top of spoil bank.	
5	MORD	Suplying and stacking of Hard Murrum/ stone dust /binding materials on road site including filling measure boxes with all lead and.lift.	
6	MORD	Scarifying graveled macadam or Bitumen macadam surface 6cm to 10cm depth including stacking useful materials on road side and disposing off remaining stuff.	

7	MORD	Granular Sub-base Construction of 100mm Granular Sub base Grade-II C.B.R. not less than 30% by providing coarse graded materials, consisting B.T. crushed stone aggregate & combination of sand stone dust/grit spreading in uniform layers with mortar grader on prepared surface mixing by mix in place method with rotavator at OMC to required density including filling the depression which occur during the process using vibratory roller 8 T to 10 T complete as per clause 401.	
8	MORD	WBM Grading-2 Providing and laying Spreading and Compacting B.T.M.C. stone aggregate of 63 mm to 45mm size to WBM II 225mm thick in three layers (75mm Each) including spreading in uniform thickness hand packing rolling with vibratory roller 8-10 tones to proper grad and camber applying and brooming requisite type of screening /binding /filler materials to fill up the interstices of coarse aggregate watering and compacting to the required density. Grading - II using screening type- A [13.20 mm agg.]	
9	MORD	Providing and laying evenly priming coat with emulsion SS-1 at rate of 7.5 Kg/10 Sqm etc.complete	
10	MORD	Providing and laying Bituminous Grout 37.5mm thick compacted with asphalt VG-30 grade at the rate of 1.99% by weight of total mix with RS1 tack coat at 2.50 Kg/10 Sqmt. On existing B.T/ Metal. surface and using B.T. chips of required gradation including cleaning & heating the aggregate and asphalt by Drum Mix Plant & spreading the same by paver finisher & consolidation with vibratory road roller including providing all materials, equipments, tools, plants, fire wood, kerosene, oil and labor charges etc. comp. (using by contractor own machineries)	

11	MORD	Providing and laying 37.5 mm thick Bituminous Macadam (B.M.) in one layers on the existing B.T. surface using stone chips as per gradation and using Emulsion RS1 for tack coat at rate of 2.5 kg/ 10 sq.m. on B.T. surface and Bitumen VG-30 34KG/MT by weight of total mix by using stone chips as per MORT & H specification including heating asphalt and aggregates by Drum mix plant and spreading by paver finisher to the required grade, level and alignment and rolled including consolidation with vibratory road roller as per clauses 501.6 and 501.7 to achieve the desired compaction and providing, operating plant machineries, equipments, tools, plants, oil fire wood, kerosene and all labour charges etc. complete.	
12	MORD	Providing and laying 20 mm thick average Mix sealsurface using stone chips dust as per gradation and using bitument for mixing VG-30 at the rate of not less than 50.90Kg / M.T. on BT surface using stone chips as per M.O.R.T.H specification including heating the asphalt and aggregates by Hot Mix Plant and spreading the same by paver finisher including consolidation with Vibratory Roller and providing, operating plant machineries, equipment, tools, plants, oil, fire wood, kerosene and all labour charges etc. complete.	
13	MORD	Excavation for foundation upto all depth including sorting out and stacking of useful materials and disposing of the excavated stuff upto all lead. Dense or hard soil.	
14	MORD	Providing and laying rubble for apron (Each stone weighting not less than 40kg) including and packing and filling in the interstices with quarry spall.	
15	MORD	Providing and laying cement concrete 1:3:6 (1- Cement : 3- coarse sand : 6- hand broken stone aggregates 40 mm nominal size) and curing complete excluding cost of formwork in (A) Foundation and plinth	

16	MORD	Providing and casting in situ ordinary cement concrete M-150 mix and providing necessary pin headers including shuttering, scaffolding, laying vibrating, curing and finishing complete Without V-Grooves For all Hieght.	
17	MORD	Construction of concrete road using tremix system with 20cm/15cm thick controlled M-250 concrete mixing conplast P-211 water reduction admixture @ 100ml/bag of cement and hardner 62.50ml. /bag using fixing and removing "C" channels of required road depth levelling if placed concrete with surface vibrator, finishing the surface with power floater and towel tight brooming as directed with providing expansion joints 20x200mm and contraction joints 20x20mm using concrete cutter machine etc. complete.[PQC]	
18	MORD	Providing and fixing in position FE 500D TMT bar reinforcement including cutting, bending and tying complete as per detailed drawings. (A) R.C.C. Kerb. (B) R.C.C. Footpath. (C) R.C.C. Approach slab. (D) Wearing Coat.	
19	MORD	Filling available excavated earth (excluding rock) in trenches plinth sides of foundation etc. in layers not exceeding 20cm in depth consolidating each deposited layer by ramming and watering.	
20	MORD	Supplying and fixing reinforced concrete heavy duty non-pressure pipes with collars for culverts including setting and joining the pipes in C.M. 1:2 watering and laying (To level of slops of I.S. 458/1971 Class NP3 casted by vertically vibrated technology of following internal diameter. 600mm dia.	
21	MORD	Supplying and fixing reinforced concrete heavy duty non-pressure pipes with collars for culverts including setting and joining the pipes in C.M. 1:2 watering and laying (To level of slops of I.S. 458/1971 Class NP3 casted by vertically vibrated technology of following internal diameter. 900mm dia.	

22	MORD	Dismantling the existing structure including removing and stacking the dismantled materials as and where directed. Stone/Rubble masonry.	
23	MORD	Dismantling the existing structure including removing and stacking the dismantled materials as and where directed. RCC Work.	
24	MORD	Providing and placing in position FE 500D TMT Bar reinforcement including cutting, bending, hooking, and taying complete as per detail drawing. (C) Balanced cantiliver box type super structure.	
25	MORD	Providing and fixing Precast cement concrete Hectometer as per IRC type design incl. painting, lettering etc. fixing in C.C. 1:5:10.	
26	MORD	Providing and fixing Precast cement concrete Guard stone as per I.R.C. type design including white washing etc. complete. Fixing in Earth	
27	MORD	Providing and fixing ordinary Kilometer stone of pre-cast C.C. 1:2:4 including necessary reinforcement as per I.R.C. type design in C..C. 1:4:8 including painting lettering etc. complete.	
28	MORD	Providing and fixing 5th Kilometer stone of pre-cast C.C. 1:2:4 including necessary reinforcement as per I.R.C. type design in C..C. 1:4:8 including painting lettering etc. complete.	

29	MORD	<p>Village/Bump Ahead sign. : Providing and fixing sign boards made out of 2mm Aluminium sheet size 90x60 cms. Rectangle as per the design of IRC-67-1977 pre treated with phospheting process and acid etching coated with one coat of apoxy primer and two coats of best quality epoxy paint reflectorised with retro reflective sheeting as per latest MOST specification letter and numbers should be as per IRC:30-1968, 3.1 Mt. long (2 nos) stand post and frame fabricated from suitable size iron angle of 50x50x5mm, painted with best quality epoxy coating in black and white bends, the details of symbole on inscription/numerals for each board shall be as per the instruction of the Engineer in charge. The fixing at site shall be in C.C 1:2:4 block of size 45x45x60cms. for each leg including excavation curring etc. complete under the supervision of engineer in charge (A) Engineer Grade.</p>
30	MORD	<p>Hazard Marker sign : Providing and Fixing sign boards made out of 2mm aluminum sheet : size 90*30 cms. rectangle as per design / Drawing attached (IRC). Pretreated with phospheting process and acid etching : coated with one coat of epoxy primer and two coats of best quality epoxy paint: reflectorised with retro reflective sheeting as per latest M.O.S.T specification: 3.1 M. long (2 nos) stand post and frame fabricated from suitable size iron angle of 35*35*3mm and 50*50*5mm : painted with best quality epoxy coatings in black and white bends the details of symbole or inscription / numerals for each board shall be as per the instruction of engineer in charge the fixing at site shall be in 1:2:4 CC block of size 45*45*60 cms for each leg: including excvation curing etc. comp.under the supervision of engineer-in-charge.(B) Engineering Grade</p>

31	MORD	<p>Chevron sign :-Providing and fixing sign boards madeout of 1.5mm aluminium sheet / 3mm ACP (Aluminum composite Panel); size 60x50cm rectangular as per design of IRC-67-2012. Pre treated with phospheting process & acid etching; coated with one coat of epoxy primer and two coats of best quality epoxy paint; reflectorised with High Intensity Prismatic Grade retro reflectivesheeting of Type-4 as per ASTM D-4956 and latest M.O.S.T.Specifications; 3.3 mtr long stand post of Iron Angle 75 x 75 x 6mm /65NB Circular MS Pipe as required and frame fabricated from suitable size iron angle of35x35x3mm; painted with bestquality epoxy coatings in black and white bends. the details of symbol or inscription /numerals for each board shall be as per the instruction of engineer in charge. The fixing at site shall be in 1:2:4 CC block of size 45 x 45 x 60 Cms. for each leg including excavation, curing etc.complete under the supervision of engineer in charge. A warranty for 7 years for the Retro reflective sheeting from original manufacturer & a certified copy of 3 year outdoor exposure test report from third party test lab for the product offered shall be submitted by contractor. (A) Class-B Type-4 Retro Reflective sheeting</p>
----	------	---

32	MORD	<p>Cautionary Warning Sign : Providing and fixing sign boards made out of 2mm Aluminium sheet size 90x90x90 cms. Equilateral triangle as per the design of IRC-67-1977 pre treated with phospheting process and acid etching coated with one coat of apoxy primer and two coats of best quality epoxy paint reflectorised with retro reflective sheeting as per latest MOST specification 3.1 Mt. long stand post and frame fabricated from suitable size iron angle of 35x35x3mm, 75x75x6mm. as required painted with best quality epoxy coating in black and white bends the details of symbole for each board shall be as per the instruction of Engineer in charge the fixing at site shall be in 1:2:4 CC block of size 45x45x60cms. for each leg including excavation curring etc. complete under the supervision of engineer in charge (A) Engineering Grade.</p>
33	MORD	<p>Citizen's information Board. Providing and fixing of typical MMGSY information board as per instruction. Two MS sheets of 3 mm thick, of 900 mm x 750mm size fixed at top & bottom duly rivetted with MS angles of 25 x 25 x 5 mm thick M.S angle shall be welded by two vertical M.S angle of 5 mm thick to 75 mm x 75 mm of 12 SWG square tubes posts duly embedded in cement concrete M-15 grade blocks of 600mm x 600mm x 750mm, below ground level. The letters & figure of any shade reflectorised with High Intensity Prismatic Grade Retro Reflective Sheeting of Type-4 as per ASTM D-4956 and latest MORD specifications; All sections of framed posts and steel tube will be painted with primer and two coats of epoxy paints as per drawing Clause 1701 and Annexure 1700.1 (10.16). (A) Class-B High intensity Grade Retro Reflective sheeting.</p>

34	MORD	<p>Road Marking with Hot Applied paints with reflectorising glass beads on bitumin surface providing and laying a hot applied thermoplasting compound 2.5mm thick including reflectorising glass beads @250 gm per sq.mtr area, thickness of 2.5mm is excluding of surface applied glass beads as per IRC:35-2015 the finished surface to be level, uniform and free from streaks and holes, zebra patta/bump/centerline/edge line/ cut patta. the while color marking should provide liminance coefficient on cement road shall be min. 130 mcd/m²/lux and asphalt road shall be min 100 mcd/m²/lux during the survice life during the date the marking should meet the performanace criteria for night time reflectivity, wet reflectivity and skid resistance as mentioned in the section-15 of IRC 35-2015 warranty for retroreflectivity shall be two years.</p>
35	MORD	<p>Cat Eye / Road Stud / RPM: Supplying Raised Pavement Markers made of polycarbonate and ABS moulded body and reflective panels with Micro prismatic lens (No Glass bead lens) capable of providing total internal reflection of the light entering the lens face and shall support a load of 13635 kgs. tested in accordance to ASTM D 4280 Type H and complying to Specifications of Category A of MORTH Circular No RW/NH/33023/10-97 & DO III Dt 11.06. 1997. The height, width and length shall not exceed 20 mm, 130 mm and 130 mm and with minimum reflective area of 13 Sqcm on each side and the slope to the base shall be 35 +/- 5 degree. The body of the marker should having finger grip for easy and accurate placement and application with epoxy / bituminous Adhesive as recommended by the manufacturer of the marker. The color of the marker should be as per the IRC 35-2015 and as directed by Engineer-in . (A) Engineer Grade</p>

36	MORD	<p>STOP SIGN:-Providing and fixing sing boards made out of 2mm aluminium sheet; size 90 * 90cms rectangle as per the design of IRC-67-1977 pre treated with phospheting process & acid teching; coated with one coat of epoxy primer and two coats of best quality epoxy paint; reflectorised with retro reflective sheeting as per latest M.O.S.T. Specifications; 3.1m long stand post and frame fabricated from suitable size iron angle of 35 * 35 * 3mm * 75 * 75 * 6mm as required; painted with best quality epoxy coatings in black and white bends. the details of symbol for each board shall be as per the instruction of engineer in charge. The fixing at site shall be in 1:2:4 CC block of size 45 * 45 * 60cms for each leg. including excavation curing tec. complete under the supervision of engineer in charge. (A) Engineer Grade</p>
37	MORD	<p>Direction sign (Junction board):-Providing and fixing sign boards made out of 2mm aluminium sheet; size 244 * 122cms rectangle as as per the design of IRC-67-1977 pre treated with phospheting process & acid etching; coated with one coat of epoxy primer and two coats of best quality epoxy paint; reflectorised with retro reflective sheeting as per latest M.O.S.T. Specifications; Letters and numerals should be as per IRC-30-1968, 3.1m long (2 nos) stand post and frame fabricated from suitable size iron angle of 50 * 50 * 5mm 75 * 75 * 6mm as required; painted with best quality epoxy coatings in black and white bends. the details of symbol or inscription / numerals for each board shall be as per the instruction of engineer incharge. The fixing at site shall be in 1:2:4 CC block of size 45 * 45 * 60cms for each leg. including ploto under the supervision of engineer in charge. (A) Engineer Grade (VR)...</p>

38	MORD	Distance Informatory/ Destubatuib sign: Providing and fixing sign boards made out of 2mm aluminium sheet; size 180 x 120cms. rectangle as as per the design of IRC-67-1977 pre treated with phospheting process & acid etching; coated with one coat of epoxy primer and two coats of best quality epoxy paint; reflectorised with retro reflective sheeting as per latest M.O.S.T. Specifications; Letters and numerals should be as per IRC-30-1968, 3.1m long (2 nos) stand post and frame fabricated from suitable size iron angle of 50 x 50 x 5mm 75 x 75 x 6mm as required; painted with best quality epoxy coatings in black and white bends. the details of symbol or inscription / numerals for each board shall be as per the instruction of engineer in charge. The fixing at site shall be in 1:2:4 CC block of size 45 x 45 x 60cms. for each leg. including excavation curing etc. complete under the supervision of engineer in charge. (A) Engineer Grade
39	MORD	Diversion sign board :-Providing & Fixing sign boards made out of 2mm aluminium sheet, size 180 x 60 cms. rectangle as per the attached drawing pre treated with phospheting process & acid etching. coated with one coat of epoxy priemr and two coats of best quality epoxy paint reflectorised with retro reflective sheeting as per latest M.O.S.T. Specifications; Letters and numerals should be as per IRC-30-1968, 3.1m long (2nos) stand post and frame fabricated from iron angle of 35x35x3mm, 50x50x5mm painted with best quality epoxy coatings in blak and white bends. The fixing at site shall be in 1:2:4 CC block of size 45 x 45x 60cms for each leg, including excavation curing etc. complete under the supervision of engineer in charge. (A) Engineer Grade (VR)...

Deputy Executive Engineer
Panchayat R&B Sub Division
Junagadh-2

Executive Engineer
Panchayat R&B Division
Junagadh

GENERAL TECHNICAL SPECIFICATIONS

1.0 General :

All Measurements shall be made in metric system. Different items of work shall be measured in accordance with the procedures set forth in relevant sections read in conjunction with General Conditions of contract. The same shall not however apply in the case of lump-sum items. All measurements and computations ; unless other wise indicated, shall be carried nearest to be following limits :

- (i) Length and breadth.....10mm
- (ii) Height, depth or thickness of earthwork,
Sub-base, bases surfacing, and structural members.....5mm
- (iii) areas..... 0.01 Sq.Metre.
- (iii) Cubic contents.....0.01 Cubic Metre.

In recording dimensions of work the sequence of length, width and height or depth or thickness shall be followed.

2.0. Measurement of lead for Materials :

Where lead is specified in the contract for construction materials, the same shall be measured as described hereunder.

Lead shall be measured over the shortest practicable route and not the one actually taken and the decision of the Engineer-in-charge in this regards shall be taken as final. Distance up to and including 100 metres shall be measured in units of 50 metres, exceeding 100 metres but exceeding 1 Km. in units of 100 metres, and exceeding 1 Km. in units of 500 metres. The half and greater than half of the units shall be reckoned as one and less than half of the units ignored. In this regard, the source of the materials shall be divided into suitable blocks and for each block the distance from the centre of the block to the centre of placing pertaining to that block shall be taken as the lead distance.

3.0 Surface Regularity of sub grade and Pavement courses :

The surface regularity of completed sub-base courses and wearing surface in the longitudinal and transverse direction shall be within the tolerances indicated in Table below. The longitudinal profile shall be checked with a 3 metre long straight edge, at the middle of each traffic lane along a line parallel to the centre line of the road. The transverse profile shall be checked with a set for three camber boards at intervals of 10 metres.

PERMITTED TOLERANCES OF SUB REGULARITY FOR PAVEMENT COURSE.

Sr.	Type of construction	Longitudinal Profile with 3 metre straight edge.					Cross Profile
		Maximum permissible undulation in mm	Maximum number of undulation permitted in any 300 m. length exceeding in				Maximum permissible variation from specified profile camber themplate mm
1	2	3	4	5	6	7	8
1	Earth sub grade	36	30	-	-	-	15
2	Granular/lime Cement stabilized sub base.	23	-	30	-	-	12
3	Water Bound Macadam with nominal size metal (20-50)mm	18	-	-	30	-	8
4	Semi Dense carpet @ @	15	-	-	-	20	6

Notes:

- These are for machine laid surfaces. If laid manually, due to unavoidable reason, tolerance up to 50 percent above these values in the columns may be permitted. However, this relaxation does not apply to the values of maximum undulation for longitudinal and cross profiles mentioned in columns 3 and 8 in the table.
- Surface evenness requirements in respect of both the longitudinal and profiles should be simultaneously satisfied.
- Rectification** : Where the surface irregularity of sub grade and the various pavement courses fall out side the specified tolerances, the contractor shall be liable to rectify these in the manner described below and to the satisfaction of the Engineer- in-Charge at this own cost.

(i) **Sub grade**; Where the surface is high, it shall be trimmed and suitably compacted. Where the same is low, the deficiency shall be corrected by adding fresh material. The degree of compaction and the type of material to be used shall conform to the specified requirements.

(ii) **Granular/Sub Base**: Same as at (i) above except that the degree of compaction and the type of material to be used shall conform to the specified requirements.

(iii) **Lime/Cement stabilized soil sub-Base**: For lime/ cement treated materials where the surface is high, the same shall be suitably trimmed while taking care that the material below is not disturbed due to this operation. However where the surface is low, the same shall be corrected as described here in below.

For cement treated material, when the time elapsed between detection of irregularity and the time of mixing of the material, is less than 2 hours, the surface shall be scarified to a depth of 50mm, supplemented with freshly mixed material as necessary and recomposed to the relevant specification. When this time is more than 2 hours, the full depth of the layer shall be removed from the pavement and replaced with fresh material, to specification. In either case, the area treated shall not be less than 5 metres wide. This also applies to lime treated material except that the time criterion shall be 3 hours instead of 2 hours.

(iv) **Water Bound Macadam Base** : Where the surface is high or low, that top 75mm shall be scarified, reshaped with added material as necessary and re compacted. The area treated at a place shall not be less than 5 metres long and 2 metres wide.

(v) **Bituminous Construction** : For bituminous construction other than wearing course, where the surface is low, the deficiency shall be corrected by adding fresh material and re compaction to specifications, Where this surface is high, the full depth of the layer shall be removed and replaced with fresh material and compacted to specifications. For wearing course, where the surface is high or low, the full depth of the layer shall be removed and replaced with fresh material and compacted to specifications in all cases where the removal and replacement of a bituminous layer is involved, the area treated shall not be less than 5 metre long and not less than 1 lane wide.

4.0 Quality Control Test during Construction. :

The materials supplied and the works carried out by the Contractor shall conform to the enclosed relevant specifications. For ensuring the requisite quality of construction, the materials and works shall be subjected to quality control test as described hereinafter, by the Engineer-in-charge. The testing frequencies set forth are the desirable minimum and the Engineer-in-charge shall have the full authority to carry out test as frequently as he may deem necessary to satisfy that the materials at work comply with the appropriated specification. Test procedures for the various quality control tests are indicated in the respective sections of the specification or for certain tests within this section. Where no specific testing procedure is mentioned, the test shall

be carried out as per prevalent accepted engineering practice to the directions of the Engineer-in-charge.

5.0 Tests of Earthwork for Embankment Construction :

5.1 Borrow Materials:

- (a) Sand content (IS: 2720 Part IV)

Two test per 8000 Cubic metres of soil.

- (b) Plasticity Test (IS: 2720 Part-V)

Each type to be tested. Two tests per 8000 Cubic Metres of soil.

- (c) Density test (IS: 2720 part-VII)

Each soil type to be tested. Two test per 8000 Cubic Metres of Soil.

- (d) Moisture Content Test (IS: 2720 Part-II)

One test for every 250 Cubic Metres of soil.

5.2 Compaction Control :

Control shall be exercised by taking at least one measurement of density for each 1000 square metres of compacted area, or closer as required to yield the maximum number of test results for evaluating day's work on statistical basis. The determination of density shall be accordance with IS: 2720 (Part XXVIII). Test locations shall be chosen only through random sampling techniques. Control shall be not being based on the result of any one test but on the mean value of set of 5-10 density determinations. The number of tests in one set of measurements shall be 5 as long as it is felt that sufficient control over borrow material and the method of compaction is being exercised. If considerable variations are observed between individual density results, the minimum number of tests in one set of measurement shall be increase to 10. The acceptance of work shall be subject to the condition that the mean dry density equals or exceeds the specified density and the standard deviation for any set of result is below 0.08 gm/cc. However for earthwork in shoulders and in top 500 mm portion of the embankment below the sub grade, at least one density measurement shall be taken for every 500 square metres of the compacted area provided further that the number of the test in each set of measurement shall be at least 10. In other respects, the control shall be similar to that described earlier.

6. Following materials shall conform to the Indian Standards shown against them;

- (1) Cement IS: 269
- (2) Sand for masonry IS: 2116
- (3) Sand for concrete IS: 383
- (4) Course aggregate. IS: 383
- (5) Mild Steel. IS: 432
- (6) High yield strength deformed bars
 - (a) Hot Rolled. IS: 1139
 - (b) Cold Twisted. IS: 1786

7. Barrel thickness of pipes of different class shall be under:

Sir No	Internal Diametre of pipes in MM	Barrel thickness (in mm)		
		NP1	NP2	NP3
1	80	25	25	-
2	100	25	25	-
3	150	25	25	-
4	250	25	25	-
5	300	30	30	-
6	350	32	32	75
7	400	32	32	75
8	450	35	35	75
9	500	-	35	75
10	600	-	40	80
11	700	-	40	80
12	800	-	45	90
13	900	-	50	100
14	1000	-	55	100
15	1100	-	60	115

16	1200	-	65	115
----	------	---	----	-----

Special conditions for Bituminous surface work with use of Drum mix plant, paver finisher.

1. The hot mix plant and accessories to be used for the work shall be in conformity with the specification prescribed vide Govt of India. Ministry of Transport Circular No. RQ/RMP/ 1613784 Dt. 1-1-87 The plant shall be equipped with all units and accessories as per latest IS 3066 / 1965, as amended from time to time. The contractor will have to modify their plants suitably within a period of six months from the date of issue of latest I.S. Specification of codes.
2. The work of laying aggregate mixed with bitumen shall start on site of work only after 8.00 hours in the morning and continue up to 17.00 hours in winter season and up to 18.30 hours in summer No work shall be done except during the period mentioned above and also on Sundays and National holidays viz. 26th January, 15th August & 2nd October.
3. Quantity of bituminous aggregate mix to be laid shall be restricted to 250 tones per day for 30/40 capacity plant and may be more or less depending upon the rated capacity of the plant.
4. The work of laying asphalt mix shall start latest within 60 days from the date of issue for work order except when work is closed for few days due to breakdown of machinery and during such period the contractor has not shifted paver plant to any other paver work not carried out by the same plant and will be completed as per time limit. Reasons for delay in starting of work after 60 days shall result into sufficient cause for laying compensation for disproportionate progress. However , the period from 15 th June to 15th October monsoon shall not be counted for the purpose of disproportionate progress and consequent cause for levy of compensation. The contractors shall commence the work of laying payment on the before the last date of the period. The contractors shall commence the work of laying pavement on or before the last date of the period mentioned above falling which he shall pay for every day that he shall delay the commencement of the work as above in accordance with clause 2 of the contract.

કોન્ટ્રાક્ટર ૬૦ દિવસની અંદર કામ શરૂ કર્યા પછી ગોડુક કામ કરીને નીચે દર્શાવેલ સંજાગા. સિવાય કામ અધેરા મેકશે તો જે દિવસથી કામ અધુરું મુકે તે દિવસથી કામ શરૂ કરે ત્યાં સુધી રૂા. ૫૦૦/- લેખે વળતર વસુલ કરવામા આવશે.

(૧) મશીનરી બ્રેકડાઉન થયેલ હોય અને તેટલા જ જુજ સમય પુરતુ કામ બંધ રહેલ હોય.

(ર) મશીનરી બ્રેકડાઉન સમય દરમિયાન પેવર પ્લાન્ટ પણ ત્યાથી ખસેડવામા આવેલ ન હોય અથવા ત. જ પ્લાન્ટ પ.વર થી અન્યજગ્યાઅ. કામગીરી કરવામા આવી ન હોય.

5. The contractor shall invariable get the job mix formula for the mix approved by the Engineer in charge before starting the work.

6. These special conditions shall be applicable to the specifications of all the items included in this contractor where work is to be carried out with Hot mix plant and paver finisher.

SCHEDULE OF WORK TO BE EXECUTED SHALL BE AS UNDER

Time Limit:

Sir No Period

Description of items to be executed

1.	Month..... Month	1. Collection of Materials on site
2	From month 2 to 4 month	2.Erection of Plant machinery as required
3 &	From Month..... to month	3.Laying of asphaltting work carpet & seal coat flushing of sand over surface, side with filling with earth as required and directed.

ANNEXURE - 1

TECHNICAL REQUIREMENTS OF HOT MIX PLANT

Composition of plant : The hot mix plant shall confirm generally to IS Specification No. IS 3066 / 1965 as amended from time to time and shall be equipped with the following arrangements :

- 1. Cold Aggregate Feeder :** The cold aggregate feeder shall have minimum three independent bins or compartment, each provided with accurate mechanical pre determined rate to the cold elevator or to some intermediate conveyor or directly into the dryer. The feeder shall provide for the adjustment of total and proportional feed and shall be capable of being locked in any setting.
- 2. Dryer :** The dryer shall be capable of continuously agitating the aggregates while heating to the desired temperature. At the discharge end of the dryer or any other suitable location, means shall be provided for ascertaining the temperature of the heated aggregate.
- 3. Screening Unit and Gradation Control :** The dried aggregate shall be screened into not less than three size. The plant shall include means for accurately proportioning each bin size of aggregate either by weight or volumetric measurement. When the gradation control is by volume, the unit shall include a feeder mounted under the compartment bins. Each bin shall have an accurately controlled, individual gate to form an orifice for proportioning the material drawn from each respective bin compartment. The orifice shall have mechanical adjustment and provided with a lock indicators shall be provided on each gate to show the opening in centimetres.
- 4. Mixer Unit :** The plant shall include a mixer of an approved twin shaft pug mill type capable of producing a uniform mix. If not enclosed, the mixer box shall be equipped with a dust hood to prevent loss of fines.
- 5. Mineral filler supply Unit :** There shall be a independent arrangement to feed mineral filler directly into the pugmill. The hopper to bin for mineral filler shall provide for the adjustment to proportion the feed with the aggregate and bitumen feed and shall be capable of being locked in any setting.
- 6. Bitumen Heating:** A heating system for bitumen always with effective and positive control of temperature shall be provided, to maintain proper temperature and for allowing continuous circulation between storage tanks and proportioning units during the entire opening period. Suitable arrangements shall be provided for recording the temperature at the tank and in the circulation system.
- 7. Synchronization:** For synchronization of Aggregate. Bitumen and filler feeds satisfactory means shall be provided to afford positive inter- locking control between the flow of aggregates

from the bins or compartment, flow of bitumen from the tank and flow the tank and flow of mineral filler.

VISCOSITY GRADE BITUMEN

Brief Back Ground :

Bitumen is a thermoplastic material and its stiffness is dependent on temperature. The temperature versus stiffness relationship of Bitumen is dependent on source of Crude and method of refining. Bureau of Indian Standards (BIS) first time introduced paving grade Bitumen specifications IS:79-1950 in the year 1950 based on penetration. Based on this classification, the Bitumen were classified into five grades : S35, S435, S65, S90 & S-200.

BIS first revised the IS : 73-1950 specifications in the year 1962 based on penetration. In IS : 73-1961 specifications only eight parameters were considered for specifications.

BIS revised IS : 73-1961 specification in year 1992 for waxy and non waxy crude based on penetration. In this revision, BIS introduced four additional qualification tests like penetration ratio, paraffin wax content, viscosity at 60 & 135 Degree C and retained penetration after thin film oven test. In case of non-waxy crude an additional grade S55 (50/60 penetration) was also introduced. However, in case of non-waxy crude only four grades A35, A55, A65 & A90 were specified.

To improve the quality of the Bitumen, BIS revised IS : 73-1992 specifications based on Viscosity grading (Viscosity at 60 Degree C) in July'2006. As per this specifications there are four grades VG-10, VG-20, VG-30 & VG-40. Few qualification tests like specific gravity, water content, ductility, loss on heating & Farass breaking point were removed from IS : 73-1992 specifications as these tests do not have any relationship either with the quality or performance of the Bitumen.

Introduction of Viscosity Grade Bitumen :

India has embarked upon massive and unprecedented road construction & improvement programme involving huge investments It has also to maintain a vast road network of over 33 lakh KM. The durability of the road surfaces depends largely on the type and quality of Bitumen used and quality control exercised in the production, transportation, mixing, laying and compaction.

Traditionally, we have been using Penetration Grade Bitumen in Bituminous mixes. The Bituminous surfacing was showing rutting at higher temperatures, cracking at lower temperatures and raveling due to fatigue. The life of Bituminous surfacing on National Highways varied from 3-4 years requiring frequent repairs and renewals. To achieve durable pavements, use of Modified Bitumen

was introduced in late nineties. The cost of Modified Bitumen is about 30 to 40 per cent higher than the cost of Bitumen as well as the construction of pavement with Modified Bitumen requires higher level of care & quality control during the entire process right from production of Modified Bitumen to laying and compaction. The latest instruction is "**Viscosity Grade Paving Bitumen**" which is designed to take care of lowest temperature (responsible for cracking) and maximum temperature (responsible for rutting). The BIS has issued IS 73 specification for this type of Bitumen in July 2006. In view of the importance of Bitumen in road construction and maintenance, it is necessary that appropriate grade of Bitumen most suited for our environment are used and adequate quality control is exercised at each stage.

Viscosity Grading of Bitumen :

Paving grade Bitumen's are categorized according to Viscosity (degree of fluidity) grading. The higher the grade, the stiffer the Bitumen. In Viscosity Grade, Viscosity tests are conducted at 60 degree C and 135 degree C, which represent the temperature of road surface during summer (hot climate, similar to northern parts of India) and mixing temperature respectively. The Penetration at 25 degree C, which is annual average pavement temperature, is also retained.

VG-10 BITUMEN :

VG-10 is widely used in spraying applications such as surface dressing and paving in very cold climate in lieu of old 80/100 Penetration grade. It is also used to manufacture Bitumen Emulsion and Modified Bitumen products.

VG-20 BITUMEN :

VG-20 is used for paving in cold climate & high altitude regions, for eg. Northern regions.

VG-30 BITUMEN :

VG-30 is primarily used to construct extra heavy duty Bitumen pavements that need to endure substantial traffic loads. It can be used in lieu of 60/70 Penetration grade.

VG-40 BITUMEN :

VG-40 is used in highly stressed areas such as intersections, near toll booths and truck parking lots in lieu of old 30/40 Penetration grade. Due to its higher Viscosity, stiffer Bitumen mixes can be produced to improve resistance to rutting and other problems associated with higher temperature and heavy traffic loads.

TABLE : VISCOSITY GRADE (VG) BITUMEN SPECIFICATION AS PER IS 73:2006

Characteristics	VG-10	VG-20	VG-30	VG-40
Absolute Viscosity, 60 degreeC, poises, min	800	1600	2400	3200
Kinematics, Viscosity, 135 degree C, CST, min	250	300	350	400
Flash, point, C, min	220	220	220	220
Solubility in trichloroethylene, %, min	99.0	99.0	99.0	99.0

Penetration at 25 degree C	80-100	60-80	50-70	40-60
Softening point, C, min	40	45	47	50
Tests on residue from thin film over test / RTFOT :				
I. Viscosity ratio at 60 degree C , max	4.0	4.0	4.0	4.0
II. Ductility at 25 degree C, cm, min, after thin film over test	75	50	40	25

FREQUENTLY ASKED QUESTIONS

1. What is the difference between Penetration & Viscosity Grade ?

Penetration Grade classifications based on the Penetration value (degree of hardness) (Test conditions : 25 degree C, 100 gm, 5 sec) while VG system is based on absolute Viscosity (degree of Flow Resistance) of the Bitumen samples measured in Poise (Test conditions : @ 60 degree C, 300 mm Hg vacuum). It also includes Kinematics Viscosity measured in cst @ 135 degree C.

2. Benefits / advantages of VG Bitumen over Penetration Grade – explain.

- ◆ VG system is based on fundamental engineering parametre (not empirical)
- ◆ Viscosity is measured at 60 degree C and 135 degree C, which takes care of both low and high temperature susceptibility of the binder, which is not possible with Penetration value @ 25 degree C. Hence, pavement engineers, contractors / consultants can have better understanding about the binder's performance in the field.
- ◆ Any two same Viscosity Grade Bitumen would give similar rutting performance in hot summer unlike Penetration Grade.
- ◆ Grater ease of handling to customers as Viscosity Value at two different temperatures (@ 60 degree C and @ 135 degree C) is available, which would enable users to measure accurate mixing and compaction temperatures.
- ◆ Minimum specified Kinematics Viscosity value @ 135 degree C helps to minimize the potential of tender mixes during construction.
- ◆ Viscosity Graded Bitumen's are suitable for a wide range of temperature; 25 degree C for raveling / fatigue cracking, 60 degree C for rutting and 135 degree C for construction (mixing and compaction).
- ◆ IS 73-2006 has only 7 tests to evaluate a sample compared to 14 tests in Penetration Grade system. This reduces time and cost of testing without sacrificing its quality.

3. What are the limitations of Penetration Grade ?

- ◆ This gradation is based on an empirical test and not a fundamental test; it doesn't provide any relevance with field performance of the sample.
- ◆ Two samples having same Penetration value may show different behavior at high and low temperatures.

- ◆ No Bitumen Viscosity is available near Bitumen mixing and compaction temperatures for the guidance of end users.
- ◆ Penetration grading doesn't control the temperature susceptibility of Bitumen. Highly thermal susceptible Bitumen's are not desirable because they are soft at high service temperature and very stiff at low service temperature.
- ◆ It cannot be used effectively for Polymer modified Bitumen.

4. Is VG Bitumen is the demand / requirement of users or the statutory bodies ? Why there is a need to shift from Penetration to Viscosity Grade Paving Bitumen ?

Penetration test was developed in an era of significantly lower pavement loading. In the past, truck weights were less than 30 tons with tyre pressure at 75 PSI. Today truck weights yields a 40% increase in the stresses applied to the pavement and is further aggravated by heavy traffic and change in weather conditions. Therefore, to cope up with the change in conditions, there is a need to shift from Penetration to Viscosity Grade Paving Bitumen. Both user agencies and statutory bodies are enforcing suppliers to supply VG Bitumen.

5. Pavement made of VG Bitumen has longer durability than Penetration Grade Bitumen and why ?

The pavement made from VG Bitumen will have better performance, because Viscosity value measured at 60 degree C correlated well with rutting behavior and Viscosity value at 135 degree C gives sufficient idea about the mixing and compaction temperature and as a result pavement life is improved.

6. Can we use VG 30 Bitumen in high temperature zones where the critical highway temperature is > 60 degree C ?

Yes, VG 30 can be used in high temperature zones as it has good thermal susceptibility.

7. Why there is a delay in introducing Viscosity Grade Bitumen in India despite declaring the spec by BIS in 2006.

- ◆ For decades, Indian customers have been using Penetration Grade Bitumen, customers are yet to be educated fully about the new specification and its benefits. In India, Bitumen market is driven by customers to a large extent like any other market.
- ◆ Additionally, there are other typical issues like user agencies demand for Penetration Grade Bitumen to complete the existing contracts, simultaneous, production of two grades at refineries and associated technical, logistical, administrative issues, etc.

In view of above, there is a delay in introducing Viscosity Grade Bitumen in the market.

8. Is VG Bitumen the ultimate solution for pavement failures ?

VG Bitumen is not the ultimate solution; it is an initial step to understand the binder performance in the field. Inline with international trend (AASHTO M320-05 specification- Super pave performance grading is being followed by USA, Europe etc.), we need to move towards performance grading system to understand the pavement failure due to binders. It is obvious that pavement design also needs due consideration.

9. Why minimum limit to absolute Viscosity @ 60 Deg C prescribed ? Is it ok to keep Min limit ?

The Temperature of 60 degree C is the near maximum Bituminous pavement temperature on a hot summer day, when rutting is likely to occur. It is useful to determine the stiffness (in terms of absolute Viscosity) of Bitumen at 60 degree C so that we can specify its minimum stiffness to ensure adequate resistance to rutting during hot summer. Pavement rutting is the most prevalent problem in India.

10. What is the relevance of Ductility Test @ 25 Deg C on residue of TFOT ?

Thin film Oven Test (TFOT) is nothing but the simulation of aging condition during mixing and compaction. If material shows good ductile characteristics after TFOT, it implies that binder can be laid nicely on the road and will not age (deteriorate) much during mixing and compaction.

11. Number of tests for VG Bitumen is less than Penetration Grade, how this would assure / control quality of Bitumen.

Some of the tests given in old Penetration Grade specification are the repetition of checking one parametre by different methods and some are redundant. For e.g. ductility measurement before and after TFOT. Ductility measurement after TFOT itself ensures the ductile property; there is no need to check it before TFOT. Penetration ratio, paraffin wax content and fraass breaking point tests are redundant as these properties have been taken care in new Viscosity Grade specifications.

12. Do we have ready-made chart to use various Bitumen Grades as per the temperature zones ?

Ideally, selection of Bitumen Grade should be based on high and low pavement. temperatures (climatic conditions). For practical consideration, selections need to be based on air temperatures, Weather data can be obtained from IMO (Indian Meteorological Organization) for the purpose of understanding region wise requirement of binder grades. Selection criteria for VG paving Bitumen based on climatic conditions is tabulated below :

S.No.	Lowest Daily Mean Air Temperature, C	< 25 Deg. C	20 to 30 Deg. C	> 30 Deg. C
1.	More than -10 Deg. C	VG-10	VG-20	VG-30
2.	- 10 Deg. C or lower	VG-10	VG-10	VG-20

13. What is the effect of using VG-10 Bitumen in hot climate areas ? What is the right grade to be used in this area ?

Due to high temperature in hot climatic areas, use of VG-10 would not provide good rutting resistance. Based on the highest daily mean air temperature which good rutting resistance. Based on the highest daily mean air temperature which generally ranges from 30 to 44 Deg. C, VG-30 Bitumen can be used in this area.

14. Is there any difference in process for manufacturing VG Bitumen over Penetration Grade ?

Yes, process parameters need to be modified to produce VG Bitumen. It is produced by blowing Bitumen with air.

15. How to measure Viscosity at 60 Deg. C ? What type of equipments and which manufactures do you recommend ?

A vacuum capillary tube viscometre is used to perform the Viscosity test at 60 Deg. C. Viscosity test equipment consists of i.e Calibrated Cannon-Manning Viscosity tube, ii. Oil bath maintained at 60 Deg. C, iii. Vacuum pump and iv. Vacuum gauge, controller, thermometer, stop watch. Viscosity tube to be imported through Indian distributor and remaining items are easily available in India. Generally Cannon Manning vacuum capillary viscometre, Cannon Fenske viscometre and Brookfield viscometre are used to measure the Viscosity.

Ref :

- (1) Ministry of Shipping, Road Transport & Highway, Govt. of India letter No. RW/NH-33041/3/2001 S & R (R) Vol. III Dt.4/8/08.
- (2) Ministry of Shipping, Road Transport & Highway, Govt. of India letter No. RW/NH-33041/3/2001 S & R (R) Vol. III Dt.4/2/09.
- (3) Indian Oil Corporation Ltd. letter dated 27/7/09.

ITEM NO.1

Clearing and grubbing of road land incl. uprooting rank vegetation, grass, bushes, shrubs, saplings and trees girth upto 300mm removal of stumps of trees cut earlier and disposal of unserviceable materials © By mechanical means in area of Light jungle.

201. CLEARING AND GRUBBING

201.1. Scope

Clearing and grubbing shall be performed less than one month in advance of earthwork operations and shall consist of cutting, trimming, removing and disposing of all materials such as trees, tree branches, bushes, shrubs, stumps roots, grass, weeds, anthills, jungle top organic soil not exceeding 150 mm in thickness, rubbish, loose stones, boulders, etc. which are undesirable and unsuitable for use in the works, from the designated area of road land, embankment slopes, drains, cross-drainage structures and such other areas as specified on the drawings or from areas as directed by the Engineer. It shall include grubbing, necessary excavation, backfilling of pits resulting from uprooting of trees and stumps to required compaction, handling, salvaging, removal and disposal of cleared materials in accordance with the requirements of these Specifications.

Reclearing of the site of any vegetation, grass shrubs before commencement of work shall be carried out as directed by the Engineer and shall be incidental to the work of clearing and grubbing.

201.2. Preservation of Property / Amenities

Roadside trees, shrubs, any other plants, pole lines, fences, signs, monuments, buildings, pipelines, sewers and all highway facilities within or adjacent to the road which are not to be disturbed shall be protected from injury or damage by providing and installing suitable safeguards as shown in the drawing or as approved by the Engineer.

During clearing and grubbing the Contractor shall take all adequate precautions for preservation of all vegetation adjacent to road land against soil erosion, water pollution, etc. and where required, shall undertake additional works to that effect. Before start of operations, the Contractor shall submit to the Engineer for approval, his work plan including the procedure to be followed for disposal of waste materials, etc. and the schedule for carrying out additional work where required.

201.3. Conservation of Top-soil

The top-soil removed during clearing and grubbing of site, if suitable for re-use shall be transported, conserved and stacked as directed by the Engineer. This shall be incidental to the work.

201.4. Methods, Tools and Equipments

Only such methods, tools and equipment as are approved by the Engineer shall be adopted for the work. If the area has thick vegetation/roots/trees, a crawler or dozer shall be used for clearance purposes. All trees, stumps, etc. falling within excavation and fill line shall be cut to such depth below ground level that in no case these fall within 500 mm of the sub grade. Also, all vegetation such as roots, under-growth, grass and other deleterious matter unsuitable for re-use in the embankment/sub grade shall be removed between fill lines to the satisfaction of the

Engineer. On areas beyond these clearing limits trees and stumps required to be removed shall be cut down to 500 mm below ground level so that these do not present an unsightly appearance.

All branches of trees extending above the roadway shall be cut or trimmed so as to provide a clear height of 5 m above the road surface and shoulders.

All excavations below the general ground level arising out of the removal of trees, stumps etc. shall be filled with material conforming to prescribed requirements and compacted to specified density, given by the Engineer.

201.5. Removal of Ant-hills

Ant-hills both above and below the ground, as are liable to collapse and obstruct free subsoil water flow shall be removed by excavating to a suitable depth as directed by the Engineer. The excavated ant-hills material shall be carted away from the site. Cavities in the ground due to removal of ant-hills shall be filled with approved material and compacted to specified densities, as directed by the Engineer.

201.6 Disposal of Materials

All materials including trees, stumps, etc. arising from clearing and grubbing operations shall be the property of Government and shall be disposed off by the Contractor as here-in-after provided or as directed by the Engineer.

Trunks, branches and stumps of trees shall be cleaned of limbs and roots and stacked. Also boulders, stones and other materials usable in road construction shall be neatly stacked as directed by the Engineer. Stacking of stumps, boulders, stones etc. shall be done at specified spots with all lifts and upto a lead of 1000 m.

All products of clearing and grubbing which cannot be used or auctioned shall be cleared away from the roadside in a manner as directed by the Engineer. Care shall be taken to see that unsuitable waste materials are disposed off in such a manner that there is no likelihood of these getting mixed up with the materials meant for embankment, sub grade and road construction or cause undesirable environmental conditions.

201.7. Measurements for Payment

Clearing and grubbing for road embankment, drains and cross-drainage structures shall be measured on area basis in terms of hectares. Clearing and grubbing of borrow areas shall be incidental to embankment construction and the rates quoted for the embankment construction shall be inclusive of it.

Cutting of trees upto 300 mm in girth including removal of stumps and roots, and cutting/trimming of branches of trees extending above the roadway shall be considered incidental to the clearing and grubbing operations. Removal of stumps of trees upto 300 mm girth left over after trees have been cut by any other agency of the Contractor or Government shall also be considered incidental to the clearing and grubbing operations.

Cutting, including removal of stumps and roots of trees of girth above 300 mm and backfilling to required compaction and removal of stems and roots of trees of girth above 300 mm diameter left over after trees have been cut by any other agency or the government shall be measured in terms of number according to the sizes given below:

- (i) Above 300 mm to 600 mm
- (ii) Above 600 mm to 900 mm
- (iii) Above 900 mm to 1800 mm
- (iv) Above 1800 mm to 2700 mm
- (v) Above 2700 mm to 4500 mm
- (vi) Above 4500 mm

For this purpose, the girth shall be measured at a height of 1 m above ground or at the top of the stump, if the height of the stump is less than 1 m from the ground.

Where the proposed work site passes through dense forest area, clearing and grubbing including cutting of trees of all girths and removal of their roots and stumps, etc. for construction of road embankment, drains and cross-drainage structures shall be measured on area basis.

201.8 Acceptance

Acceptance of clearing and grubbing shall be based on visual inspection of the work for compliance with the above specifications to the satisfaction of the Engineer.

201.9 Rate

201.9.1. The Contract unit rates for the various items of clearing and grubbing shall be paid/payable in full for carrying out the required operations including full compensation for all labour, materials, tools, equipment and incidentals necessary to complete the work. These will also include removal of stumps and roots of trees less than 300 mm in girth as well as stumps left over after cutting of trees carried out by another agency of the Contractor or Government, excavation and backfilling to required density, where necessary, and handling, salvaging, piling and disposing of the cleared materials with all lifts and upto a lead of 1000 m.

201.9.2. The Contract unit rate for cutting (including removal of stumps and roots) of trees of girth above 300 mm and removal of stems and roots of trees of girth above 300 mm left over after trees have been cut by any other agency or the government shall include excavation and backfilling to required compaction, handling, salvaging, piling and disposing of the cleared materials with all lifts and upto a lead of 1000 m as directed by the Engineer.

201.9.3. Where a Contract does not include separate items of clearing and grubbing, the same shall be considered incidental to the earthwork items and the Contract unit prices for the same shall be considered as including clearing and grubbing operations.

ITEM NO.2

Earthwork for embankment including breaking clods, dressing with all lead and lift and including watering rolling and consolidation of subgrade in layers at O.M.C. to required dry density including filling the depression which occur during the process using power roller 8T to 10T. (E) From Borrow area within 3.0KM. lead

1. The land width on which the earth work is to be done shall be cleared of all trees having a girth of 30cm and loss, loose stones, vegetation, bushes, stumps and all other objectionable materials. All the materials cleared will be the property of Government. Useful material shall be arranged in convenient stack the road boundary or as directed at places within 50 metres lead, and handed over to the department in convenient section. Unsuitable material shall be burnt or otherwise disposed off by the contractor at own cost without causing any nuisance inconvenience or damage to the works property or people in the neighborhood. In all cases the materials shall be disposed off in a neat manner.

2. After cleaning the site, the alignment of the road shall be properly set out true to line, curves, slopes grade and sections as shown on the plan or directed by the Engineer-in-charge. The contractor shall provide all labors and materials such as lime, string, pegs, nails, bamboos, stones, mortar, concrete etc. Required for setting out, establishing Bench Marks and giving profiles. The contractor shall be responsible for maintaining the B.M.S. profiles alignment and other marks long they are required for the work in the opinion of the Engineer-in-charge. If the contractor defaults in this respect they may be restored by the department at the cost of the contractor.

3. When an existing embankment is to be widened, continuous, horizontal benches, each at least 0.3 metre wide shall be cut into the existing slope for ensuring adequate bond with the fresh embankment materials to be added. The material obtained from the cutting of benches can be utilized in the widening of the embankment. The dumping of material from trucks for widening operation shall be avoided except in difficult circumstances when the extra width is too narrow to permit the movement of any other type of hauling equipment.

4. The soil to be used for embankment shall be free from trees, stumps, root, rubbish or any other objectionable materials. Only materials considered suitable by the Engineer-in-charge shall be used for the construction and that considered unsuitable shall be disposed off as directed by him. The selection of materials to be used in the construction of embankment shall be made after soil survey and investigations are carried out by the Department. The embankment shall consist of earth available from road-side borrow pits on either side with all lead and lifts. And within land width in the manner specified in Para 11. Below. The road, if any required for the purpose of haulage of earth by men, animals or vehicles will be constructed. (If not existing) and maintained by the contractor at his own cost.

5. Department is extended all necessary co-operations in helping contractor to get borrow from near by Government or Panchayat land, if available. However department is not responsible if not such area is made available to the contractor and in the case, contractor will have to make his own arrangement to get borrow area for borrowing earth of the quantity even by making temporary arrangement with the private land owners.

6. The Embankment shall be constructed in uniform layer not exceeding 250mm in loose thickness. The soil shall be spread uniformly over the entire width of the embankment unless otherwise directed by the Engineer-in-charge. All clods of hard lumps of earth shall be broken to have maximum size of 15 cm. When being placed in the embankment a maximum of size 5 cm when being placed in the top 45 cm. of embankment. The work of next layer shall be allowed only after the first layer has been thoroughly compacted.

7. Where an embankment is to be placed on sloping ground shall be balanced in the step of trenches of broken up in such a manner that the new material shall have perfect bond with the existing surface. Where the embankment is to be placed over an existing road surface, the surface shall be scarified to minimum depth of a 5 cm. so as to provide ample bond between the old and new material. However when the embankment is to be placed over and old concrete pavement and lies within 1 metre of new sub grade level, the pavement shall be broken up in pieces not to exceed 0.1 m and may be metre of new sub grade left under the new embankment. If the existing road surface is of granular or bituminous type and lies within 1 mt. of the new sub grade level, the same shall be scarified to a depth of minimum 50mm. so as to provide ample bond between the old and the new material.

8. To avoid interference with contraction of abutment, wing walls or return walls of culvert/bridge structures, the contractor shall at point to be determined by the Engineer-in-charge, suspend work on embankment forming approaches to such structures, until such time as the construction of the latter is sufficiently advanced to permit the completion of approaches without the risk of interference of damage to the bridge work, unless directed otherwise the filling around culverts, bridge and other structures upto a distance of twice the height of the embankment from the back of the embankment shall be carried out independent of the work on the main embankment. The fill material shall not be placed against any abutment or wing wall unless permission has been given by the Engineer-in-charge but in any case not until the concrete or masonry has been in position for 14 days, the embankment shall be brought up simultaneously in equal layer on each side of the structure to avoid displacement and unequal pressure. The sequence of work in this regard shall be got approved from the Engineer-in-charge. Where the provision of any filter medium is specified behind the abutment, the same shall be laid in layers with the laying of fill material. The material used for the filter shall conform to the requirements for filler medium and will be paid extra in the relevant item.

9. The embankment shall be finished in conformity with the alignment, level, cross section and dimensions shown on the plans or as directed by the Engineer-in-charge. Where the alignment of the road is in a curve, the top of the embankment shall be formed with the super elevation and the increased width shown on the drawing or as the Engineer-in-charge may direct. Finishing operation shall include the work of shaping and dressing the shoulder, road bed and the slopes to conform to the cross section.

10. The earthwork measurement shall be paid on cross sectional measurements and computing the volumes of earth work in cubic metres by average area method. The contractor shall sign day to day leveling work and also original cross sections, longitudinal section etc. in token of his acceptance. The working section both longitudinal and cross of the ground shall be taken by the Engineer-in-charge before the actual work has started. The contractor or his authorized representative shall attend day to day leveling work and sign with date the field book daily, in token of his acceptance, if there is any disagreement, the contractor shall inform of it in writing to the officer concerned with specific reference to the sections before starting further work. Once the work is started, no cognizance of any complaint will be taken merely not signing to level book shall not be deemed as disagreement. The Executive Engineer shall also verify leveling work to the extent of 5% before commencement of earth work and on finalization. The contractor shall maintaining the embankment by filling in ruts, rain cuts, depression due to shrinkage etc. to proper formation and grade till this item is finally measured and accepted by the Department. The measurements shall be the on compacted earth work. Deduction of 15% for shrinkage shall be made from gross measured quantity if measured before first monsoon and 10% if measured after

one or more monsoon have been passed over the earth embankment. However the contractor shall have to bear loss of deformation etc. If any due to all settlements as well as other type of deformation etc. if any, that might have taken place at the time of taking measured of the item.

11. If usable approved material is available within the land width of road, the same shall be permitted for used in the road embankment subject to the following conditions:-

(i) The borrow pits will be so excavated as to form a road side longitudinal gutter to drain the water, interrupted by such gutter.

(ii) The width of the drain shall be restricted to 1.5mts. only the depth will be restricted to such grade so as to drain the water efficiently. All balance quantity of earth shall be brought from distant borrow areas only.

(iii) If there is top layer of black cotton or other objectionable soils, the same shall be removed and disposed off elsewhere and usable material found at the lower level will only be used in the earthen embankment, if the contractor choose to utilize this material.

(iv) the drain should be aligned along the boundry of the land width of the road. Not pit, other than this drain shall be dug within 5 metres of the toe to the final section of the road embankment.

(v) No borrow pits shall be allowed in the length in which earth obtained for cutting from cutting is specified to be used in embankment.

12 The rate of earthwork includes cleaning jungles, dog belling fixing profiles, erecting necessary pillars or stones for bench mark for leveling purpose, excavating earth from borrow pits, bracking clods, conveying and spreading earth in layers with all lead and lift, finishing the entire embankment and incidentals necessary to complete the work to the specifications. The cutting stuff of cutting in ordinary soil, soft murrum, soft rock, hard murrum and hard rock shall utilised in embankment costruction under this item within the lead specified in the particulars item. No Payment shall be made under this item for the cutting stuff used in embankment but labour for cutting will be paid as per specifications in the particulars item, and only balance quantity of earthwork from borrow areas will be pain in this item.

ITEM NO.3

Box cutting the road surface to proper slope and camber for making a base for road work including removing the excavated stuff and depositing on the road side slopes as directed upto all lead.

Specification No. 162 and 553 of P.W.D. Hand book volume II and the following additional specifications be applicable here.

1. Cutting shall be done in proper grade & camber as per measurements given, Care must be taken the tall slopes are evenly and truly dressed. Cutting shall be done to the exact depth required and shall be as per formation level in proper grade and the camber. If extra depth of cutting is done due to negligence of contractor the same shall be refilled with approved quality of materials duly consolidated to the satisfaction of the Engineer-in-charge (Without extra cost) Box cutting for soling and metalling in required width the depth shall be done

2. The stuff received from the cutting shall be utilized for filling cuts and correcting side slopes of bank with all lead and lift as directed. Useful stuff shall be careful stacked separately as directed.

3. The measurement shall be taken as per cross section measurement of the cutting based on length, breadth, depth measured with tape at every 25 metres interval.

4. The payment shall be made on cmt. basis.

ITEM NO.4

Earthwork in cutting in all sorts of soil and soft Murrum including conveying and putting the stuff, in spoil bank maintaining minimum distance of five meter between top edge of cutting and top of spoil bank.

1. The land width required for the roadway gutter side slopes and catch water gutters shall be cleared of all trees having a girth of 30 cms. and less loose stones. vegetation bushes stumps and all other objectionable materials. The roots of trees and stumps shall be removed to a depth of 30 cms below the grade information and slopes and excavation filled up with excavated materials and compacted. All the materials cleared will be the property of Government. Useful materials shall be arranged in convenient stacks along the road boundary or as directed as places within 50 mts. lead, and handed over to the department in convenient sections. Unsuitable material shall be burnt or otherwise disposed off by the contractor at his own cost without causing any nuisance, inconvenience or damage to the work, property or people in the neighborhood. If the contractor and royalty etc. If any paid by him without claiming compensations. In all cases, the materials shall be disposed of in a neat manner.

2. After ceasing the site, the alignment of the road shall be properly set out true to lines, curves slope, grades and section as shown on the plans or directed by the Engineer in charge. The contractor shall provide all labour and establishing bench marks and giving profiles. The contractor shall be responsible for maintaining the B.Ms profiles alignments and other stakes and marks as long as then are required for the work in the opinion of the Engineer, If the contractor defaults in this respect even after the direction by the Engineer within the specified time, they may be resorted by the Engineer at the levels etc. If there is any disagreement the contractor shall inform of it in writing to the Officer concerned with the specific reference to the sections before starting further work. Once the work has started, no cognizance of any complaint shall be taken Merely not signing of the book shall not be deemed as disagreement.

3. Profiles of the section including the road side gutters to be excavated shall be laid at suitable intervals of 10m to 50 m or other intervals as directed by Engineer to conform to the curved or straight alignment, sections grades and used shall be set up with the toe line marked on each side. The road way section shall first be excavated with vertical side for each lift and the sides slopes for that lift shall be excavated in steps. These steps shall be smoothened to the required slope when the excavation reaches the road formation. The contractor shall on no account excavate beyond the slopes or below the specified grade unless so directed by the Engineer in writing. If excavation is done below the specified level or out side the section, it shall not be paid for and the contractor shall be required to fill up at his won cost such extra excavation in the road portion, with approved materials of the embankment grade in layers, watered and fully compacted to attain maximum density laid down for the embankment in its relevant item. The Engineer may require measurement ridges and dead man to be left at specified intervals or places and kept intact till order to be removed for the purpose to check measurements. The excavation shall be finished neatly smoothly and evenly to the correct lines, curves, grades. If loose shall be scarified, watered and compacted to the same density as the embankment, The section side slopes and catch water gutter shall be maintained by the contractor at his own cost in such a way that the formation and gutters will be drained by providing for necessary idversions etc. and not damaged due to obstruction of any drainage, Necessary passages shall be provided for leading away seepage, spring , surface flow or rainwater safely without damaging the work. If any damageoccurse dure to default of the contractor in this respect he shall make good the damage at his own cost, If it is necessary in the execution of the work to interrupt existion surface drainage , irrigation channels , sewers or under drainage, temporary arrangements shall be provide till such time as is necessary. The contractor at his own cost shall make the existing work or work in hand caused as a result of his operations or negligence shall be made good by the contractor at his own cost. Road side gutters shall be excavated to the specified sections and shall be measured along with the main cutting in cubic metres.

4. If slides occur in the cutting they shall be removed as ordered by the Engineer. If finished slopes slide into the roadways before the final acceptance of the work. Such slides shall be removed by the contractor and shall be paid for at the contract rate for the class of excavation involved provided the slides are not due to any negligence of the contractor, The classification of the material in slides shall conform to its conditions at the time of removal and payment made accordingly regardless of its prior condition. Care shall be taken to see that excavation is arranges in a safe way so that there will be no risk to the workmen by lider, falling materials. boulders and collapsing sides etc.

5. If there is traffic nearby or if there are towns and villages in the neighbrohood. barricades and or trafic, signals shall be provided day and night for the duration of the work in such a way as to revent accidents. Warning signals shall be dispayed at 7mt. from the danger poing on both sides

giving sufficient warning. If necessary, signalers shall be stationed at each end to regulate traffic where it is heavy. Measures shall be taken to see that the excavation does not affect or damage adjoining structures or properly, If there is damage to property, injury to workers, the members of the public, animals etc., due to the negligence of the contractor, he will be responsible and liable to all the consequences including compensation.

6. All the excavated materials shall be property of Govt. When the useful excavated material is to be used in embankment within a lead of 200 metre an all lift, it shall be directly deposited at the required location in specified layers. No handing or conveyance charges shall be paid if the material is temporarily deposited elsewhere and the drainage in any way. If no Govt. land is available but the excavated useful stuff is to be stacked temporarily before use under the same agreement, the contractor shall make his own arrangements for the stacking of this material not required for use on embankment or unsuitable materials may be used on his own to uniformly widen embankment to flatten slopes and to fill low places in the road land. if so permitted by the Engineer. Material not required for any use whatsoever maybe disposed of by the contractor at his own cost in manner approved by the Engineer. The excavated material shall not be deposited within 3 m. from the top edge if slope or toe of the bank. The lead shall be measured from the junction point of cutting and embankment up to 200 mt. on either side.

7. If the contractor does not wish to utilise the quantity of cutting within the specitied lead for any reason, then he may do the embankment work with the earth from other sources (except borrow pits in the length of the road where cutting stuff is to e utilized) but in that case the full or part quantity on acceptable quality stuff for which payment is made or to be made will be duducted from the net quantity of the earth work in the embankment arrived at, within the chainage measured as above.

8. The contract rate shall be a unit of one cubic metre for the start mentioned in the wording of the item of excavation acceptably completed. limited to the dimensions shown on the plans or as directed by the Engineer. Excavation shall be measured in its original positions by taking cross sections before the work starts and after it is entirely completd. The quality shall be worked by the average end area method. When the classification of the strata changes, the contractor shall bring this to notice of the Engineer. who will then verify and if necessary take levels for the changed strata for purpose of measurement.

(b) In spoil Bank : Specification shall be as per Item 2(a) except that the excavated stuff shall be deposited in spoil Bank instead of using same in road embankment.

ITEM NO.5

Supplying and stacking of Hard Murrum/ stone dust /binding materials on road site including filling measure boxes with all lead and lift.

1. The quarry spauls shall be approved quarry as approved by the Ex. Engineer prior to collection. Filling of boxes. shall no be allowed till the metal is broken to the specified site.
2. The quarry spaul be as uniform in size as possible. The quarry spaul shall be hard, tough, solid, durable of black trap quarry of close texture, free from decay and weathering. The stone shall be angular and roughly cubical in shape and round elongated or flaky materials shall be rejected . No sound or long rubble or angular chips smaller than specified size shall be allowed,
3. All unsound , whethere or disintegrated stone obtained from the under surface layer of the quarry of other layers of boulders shall be rejected.
4. Wherever any doubt as to whether above requirement are stisfy in whole or part of the collection it shall be got sereened by the contractor if so ordered by the Excutive Engineer, and for which no extra payment shall be claimed by the contractor.
5. Any collection which does not fully satisfy the above requirements is liable to be rejectied all together.
6. Stacking shall be made by the contractor by steel pharas of 2 m x 1.5 m 0.5 m and no deduction of voids shall be made from the gross measurements.
7. Regular stack shall be made by the contractor on a fairly level ground. All the stack shall be marked by white wash immediately on being measuered and recorded by the Engineer in charge.
8. The rate includes blasting the rock, if any breaking the quarry spauls, stacking measureing in pharas etc. complete.
9. The rate shall as per actual requirements and any materials in excess shall Be have to be transported by the contractor at the places directed by the Executive Engineer at the risk and cost of the contractor.

10. While stacking materials the depositing should commence at one end of the km, and carried continuously towards the other end unless the Executive Engineer shall direct otherwise and as a rule measurements shall be taken after metal for half kilometre or km, has been fully collected. Any fraction of these distance shall be not be measured up,
11. The measurements shall be recorded in on Cum. basis & be paid accordingly.

ITEM NO.6

Scarifying graveled macadam or Bitumen macadam surface 6cm to 10cm depth including stacking useful materials on road side and disposing off remaining stuff.

1.0 The layer of the existing layer metaling shall be excavated and shall be screened on site of work. Stacking of 75 % of metal obtained from screening shall be done by filling in the standard steel boxes of 2m x 1.5m x 0.5 m size deductions for voids shall be made form the gross measurements. Where any doubt exist as to whether the quantity of stack of material in any hectometre is not confirming with cubical content of the standard pharas (2m x 1.5m x 0.5m) shall be got corrected by the Engineer-in-charge for which no extra payment shall be claimed by the contractor. If the quantity of metal in any stack in a particular hectometre is found to be less then the standard measurements viz. 1.5 cmt. the entire collection in the hectometre shall be paid on the be is of the quantity so found. Regular stack shall be done by you the contractor on a fairly level ground stacking of the metal shall be done in a manner as directed by the Engineer-in-charge.

2.0 The remaining material except 75 % of metal obtained from screening process shall be used in embankment with all lead and lit. It shall be directly deposited at the required location in specified layers No. handling or conveyance charge shall be paid if the material is temporarily deposited else where and subsequently convey to site of duposition. The sequence of operations should be arranged property. M material not required for any use what so ever may be disposed off by the contractor at his own cost in manner approved by the Engineer-in-charge. The material utilised in the embankment it will be deducted from the net quantity of earthwork in embnkment arrived at within the chainage measured.

3.0 The payment shall be made on sq.mt. basis, the contractor shall maintain all stacks in regular and proper size till thw hole materials shall not be measured and finally accepted by the Department. The spreading of materials shall not be allowed till the materials are fully stacked and completed kilometre wise.

4.0 The rate includes the cost of scarifying macadam, screeing, diposting, conveyance with all lead and lift filling the boxes including all labour, tools, equipments and all other incidental expenses.

ITEM NO.7

Granular Sub-base

Construction of 100mm Granular Sub base Grade-II C.B.R. not less than 30% by providing coarse graded materials, consisting B.T. crushed stone aggregate & combination of sand stone dust/grit spreading in uniform layers with mortar grader on prepared surface mixing by mix in place method with rotavator at OMC to required density including filling the depression which occur during the process using vibratory roller 8 T to 10 T complete as per clause 401.

401. GRANULAR SUB-BASE

401.1. Scope

This work shall consist of laying and compacting well-graded material on prepared subgrade in accordance with the requirements of these Specifications. The material shall be laid in one or more layers as sub-base or lower sub-base and upper sub-base (termed as sub-base here-in-after) as necessary according to lines, grades and cross-sections shown on the drawings or as directed by the Engineer.

401.2. Materials

401.2.1. The material to be used for the work shall be natural sand, gravel, crushed stone, depending upon the grading required. The material shall be free from organic or other deleterious constituents and conform to one of the three gradings given in Table 400.1. The grading to be adopted for a project shall be as specified in the Contract.

TABLE 400.1 : GRADING FOR GRANULAR SUB-BASE MATERIALS

IS Sieve Designation	Per cent by Weight Passing the IS Sieve		
	Grading I	Grading II	Grading III
75.0 mm	100	-	-
53.0 mm	-	100	-
26.5 mm	55-75	50-80	100
9.50 mm	-	-	-
4.75 mm	10-30	15-35	25-45
2.36 mm	-	-	-
0.425 mm	-	-	-
0.075 mm	<10	<10	<10

- Notes: (1) The material passing 425 micron (0.425 mm) sieve for all the three gradings when tested according to IS:2720 (Part 5) shall have liquid limit and plasticity index not more than 25 and 6 per cent respectively.
- (2) On clayey subgrades, the per cent passing IS Sieve 0.075 mm shall not exceed 5.

401.3. Strength of Sub-base

When directed by the Engineer, this shall be verified by performing CBR tests in the laboratory as required on specimens remoulded at field dry density and moisture content and any other tests for the “quality” of materials, as may be necessary.

401.4. Construction Operations

401.4.1. Preparation of subgrade: Immediately, prior to the laying of sub-base, the subgrade already finished to Clause 303 shall be prepared by removing all vegetation and other extraneous matter, lightly sprinkled with water if necessary and rolled with two passes of 80-100 kN smooth wheeled roller.

The sequence of construction operations shall be such that the construction of granular subbase layer shall match the construction of the adjoining layer in the shoulders, as per Clause 407.4.1.

401.4.2. Spreading and compacting: The sub-base material of grading specified in the Contract shall be spread on the prepared subgrade with the help of suitable tractor-towed appliances, for maintaining the required slope and grade during the operation or other means as approved by the Engineer.

When the sub-base material consists of combination of materials mentioned in Clause 401.2.1, mixing shall be done mechanically by the mix-in-place method or by an approved mixing plant.

Manual mixing shall be permitted only where the width of laying is not adequate for mechanical operations, as in small-sized jobs. The equipment used for mix-in-place construction shall be a tractor-towed rotavator or similar approved equipment capable of mixing the material to the desired degree. If so desired by the Engineer, trial runs with the equipment shall be carried out to establish its suitability for the work.

Moisture content of the loose material shall be checked in accordance with IS:2720 (Part 2) and suitably adjusted by sprinkling additional water from a truck mounted or trailer mounted water tank and suitable for applying water uniformly and at controlled quantities to variable widths of surface or other means approved by the Engineer so that, at the time of compaction, it is from 1 per cent above to 2 per cent below the optimum moisture content corresponding to IS:2720 (Part

7). While adding water, due allowance shall be made for evaporation losses. After water has been added, the material shall be processed by mechanical or other approved means, like, tractor-towed disc harrows, rotavators until the layer is uniformly wet.

Immediately thereafter, rolling shall start. If the thickness of the compacted layer does not exceed 100 mm, a smooth wheeled roller of 80 to 100 kN weight may be used. For a compacted single layer upto 225 mm the compaction shall be done with the help of a vibratory roller of minimum 80 to 100 kN static weight. Rolling shall commence at the lower edge and proceed towards the upper edge longitudinally for portions having unidirectional crossfall and superelevation and shall commence at the edges and progress towards the centre for portions having crossfall on both sides.

Each pass of the roller shall uniformly overlap not less than one-third of the track made in the preceding pass. During rolling, the grade and crossfall (camber) shall be checked, with the help of templates and straight edge, and any high spots or depressions, which become apparent, corrected by removing or adding fresh material. The speed of the roller shall not exceed 5 km per hour.

Rolling shall be continued till the density achieved is atleast 100 per cent of the maximum dry density for the material determined as per IS:2720 (Part 7). The surface of any layer of material on completion of compaction shall be well closed, free from movement under compaction equipment and from compaction planes, ridges, cracks or loose material. All loose, segregated or otherwise defective areas shall be made good to the full thickness of layer and re-compacted.

401.5. Aggregate Plugs

When the granular sub-base is extended over the full formation, as shown on the drawings, the exposed edges shall be protected with suitable aggregate plugs, 200 to 300 mm wide, as specified on the drawings.

401.6. Surface Finish and Quality Control of Work

The surface finish of construction shall conform to the requirements of Clause 1802.

Control on the quality of materials and works shall be exercised by the Engineer in accordance with Section 1800.

401.7. Arrangements for Traffic

During the period of construction, arrangement of traffic shall be maintained in accordance with Clause 111.

401.8. Measurements for Payment

Granular sub-base shall be measured as finished work in position in cubic metres.

The protection of edges of granular sub-base extended over the full formation as shown in the drawing shall be considered incidental to the work of providing granular sub-base and as such no extra payment shall be made for the same.

401.9. Rate

The Contract unit rate for granular sub-base shall be payment in full for carrying out the required operations including full compensation for:

- (i) making arrangements for traffic to Clause 111 except for initial treatment to verges, shoulders and construction of diversions;
- (ii) furnishing all materials to be incorporated in the work including all royalties, fees, rents where necessary and all leads and lifts;
- (iii) all labour, tools, equipment and incidentals to complete the work to the Specifications;
- (iv) carrying out the work in part widths of road where directed; and
- (v) carrying out the required tests for quality control.

ITEM NO.8

WBM Grading-2

Providing and laying Spreading and Compacting B.T.M.C. stone aggregate of 63 mm to 45mm size to WBM II 225mm thick in three layers (75mm Each) including spreading in uniform thickness hand packing rolling with vibratory roller 8-10 tones to proper grad and camber applying and brooming requisite type of screening /binding /filler materials to fill up the interstices of coarse aggregate watering and compacting to the required density. Grading - II using screening type- A [13.20 mm agg.]

404.1 SCOPE

This work shall consist of clean, machine crushed B.T. stone aggregates mechanically interlocked by rolling and bonding together with screening, binding material where necessary and water laid on a properly prepared sub grade/ sub bases base or existing pavement, as the case may be and finished in accordance with the requirements of these specifications and in close conformity with the lines, grades, cross-sections and thickness as per approved plans or as directed by the Engineer.

404-2. Materials

404.2.1 Coarse aggregates

Coarse aggregates shall be either crushed or broken stone, crushed slag, overburnt (Jhama) brick aggregates or any other naturally occurring aggregates such as kankar and laterite of suitable quality. Materials other than crushed gravel / shingle is used, not less than 90 percent by weight of the gravel / shingle pieces retained on 4.75mm sieve shall have at least two fractured faces. The aggregates shall conform to the physical requirements set forth in Table 400-8. The type and size range of the aggregate shall be specified in the contract or shall be as specified by the Engineer. If the water absorption value of the coarse aggregate is greater than 2 percent, the soundness test shall be carried out on the material delivered to site as per IS:2386 (Part-5).

**TABLE 400-8. PHYSICAL REQUIREMENTS OF COARSE AGGREGATES FOR
WATER BOUND MACADAM FOR SUB-BASE / BASE COURSES**

<u>S.No. Test</u>	<u>Test Method</u>	<u>Requirement</u>
1. *** Los Angeles	IS:2386	40 percent (Max)
Abrasion value	(Part-4)	
or		
Aggregate	IS: 2386	30 percent (Max)
Impact value	(Part-4) or IS:5640*	
2. Combined		
Flakiness and	IS:2386	30 percent (Max)
Elongation -	(Part- 1)	
Indices (Total)**		

* Aggregate which get softened in presence of water shall be tested for impact value under wet conditions in accordance with IS:5640.

** The requirement of flakiness index and elongation index shall be enforced only in the case of Crushed broken stone and crushed slag.

*** In case water bound macadam is used for sub-base, the requirements in respect of Los Angeles Value and Aggregate impact value shall be relaxed to 50 percent and 40 percent maximum respectively.

404.2.2 Crushed or broken stone

The crushed or broken stone shall be hard, durable and free from excess flat, elongated, soft and disintegrated particles, dirt and other deleterious material.

404.2.3. Crushed slag :

Crushed slag shall be made from air-cooled blast furnace slag. It shall be of angular shape, reasonably uniform in quality and density and generally free from thin, elongated and soft pieces, dirt or other deleterious materials. The weight of crushed slag shall not be less than 11.2 kN per m³ and the percentage of glossy material shall not be more than 20. It should also comply with the following requirements:

- (i) Chemical stability : To comply with requirement of appendix of BS : 1047
- (ii) Sulphur content : Maximum 2 per cent
- (iii) Water absorption : Maximum 10 per cent

404.2.4. Overburnt (Jhama) Brick aggregates :

Jhama brick aggregates shall be made from overburnt bricks or brick bats and be free from dust and other objectionable and deleterious materials. This shall be used only for road stretch when traffic is low.

404.2.5. Grading requirement of Coarse aggregates :

The coarse aggregates shall conform to one of the Gradings given in Table 400-9 as specified.

404.2.6. Screenings:

Screenings to fill voids in the coarse aggregate shall generally consist of the same material as the coarse aggregate. However, where permitted, predominantly non-plastic material such as murrum or gravel (other than rounded river borne material) may be used for this purpose provided liquid limit and plasticity index of such material are below 20 and 6 respectively and fraction passing 75 micron sieve does not exceed 10 per cent.

TABLE 400-9 : GRADING REQUIREMENTS OF COARSE AGGREGATES

Grading	Size Range	IS Sieve	Per cent by
---------	------------	----------	-------------

No.		Designation	weight passing
1.	63 mm to 45 mm	75 mm	100
		63 mm	90-100
		53 mm	25-75
		45 mm	0-15
		22.4 mm	0-5
2.	53 mm to 22.4 mm	63 mm	100
		53 mm	95-100
		45 mm	65-90
		22.4 mm	0-10
		11.2 mm	0-5

Note : The compacted thickness for a layer shall be 75mm.

Screenings shall conform to the grading set forth in Table 400–10. The quantity of screenings required for various grades of stone aggregates are given in Table 400–11. The table also gives the quantities of materials (loose) required for 10 m² for sub-base / base compacted thickness of 75 mm.

The use of screenings shall be omitted in the case of soft aggregates such as brick metal, kankar, laterites etc. as they are likely to get crushed to a certain extent under rollers.

404.2.7 Binding Material :

Binding material to be used for water bound macadam as a filler material meant for preventing ravelling, shall comprise of a suitable material approved by the Engineer having a Plasticity Index (PI) value of less than 6 as determined in accordance with IS:2720 (Part 5).

The quantity of binding material where it is to be used will depend on the type of screening. Generally, the quantity required for 75 mm compacted thickness of water bound macadam will be 0.06 – 0.09 m³ / 10 m².

TABLE 400 – 10. GRADING FOR SCREENINGS

Grading Classification	Size of Screenings	IS Sieve Designation	Per cent by weight passing the IS sieve
A	13.2 mm	13.2 mm	100
		11.2 mm	95-100
		5.6 mm	15-35
		180 micron	0-10
B	11.2 mm	11.2 mm	100
		9.5 mm	80-100
		5.6 mm	50-70
		180 micron	5-25

TABLE 400 – 11. APPROXIMATE QUANTITIES OF COARSE AGGREGATES AND SCREENINGS REQUIRED FOR 75 MM COMPACTED THICKNESS OF WATER BOUND MACADAM (WBM) SUB-BASE / BASE COURSE FOR 10 M² AREA

Classification	Size Range	Compact thickness	Loose Qty.	Screenings			
				Stone screening		Crushable type such as murrum or gravel	
				Grading classification and size	For WBM sub-base / base course (loose Qty)	Grading classification and size	Loose Qty.
Grading 1	63mm to 45 mm	75 mm	0.91 to 1.07m ³	Type A 13.2 mm	0.12 to 0.15 m ³	No uniform	0.22 to 0.24 m ³
- do -	- do -	- do -	- do -	Type B 11.2 mm	0.20 to 0.22 m ³	- do -	- do -
Grading 2	53mm to 22.4 mm	75 mm	- do -	- do -	0.18 to 0.21 m ³	- do -	- do -

The above mentioned quantities should be taken as a guide only, for estimation of quantities for construction etc.

Application of binding materials may not be necessary when the screenings used are of crushable type such as murrum or gravel.

404.3 Construction Operations

404.3.1 Preparation of base :

The surface of the sub grade sub-base/base to receive the water bound macadam course shall be prepared to the specified grade and camber and cleaned of dust, dirt and other extraneous material. Any ruts or soft yielding places shall be corrected in an approved manner and rolled until firm surface is obtained.

Where the WBM is to be laid on an existing metalled road, damaged area including depressions and potholes shall be repaired and made good with the suitable material. The existing surface shall be scarified and re-shaped to the required grade and camber before spreading the coarse aggregate for WBM.

As far as possible, laying water bound macadam course over an existing bituminous layer may be avoided since it will cause problems of internal drainage of the pavement at the interface of two courses. It is desirable to completely pick out the existing thin bituminous wearing course where water bound macadam is proposed to be laid over it.

404.3.2 Inverted Choke / Sub surface Drainage layer

If water bound macadam is to be laid directly over the subgrade, without any other intervening pavement course, a 25 mm course of screenings (Grading B) or coarse sand shall be spread on the prepared subgrade before application of the aggregates is taken up. In case of a fine sand or silty or clayey subgrade, it is advisable to lay 100 mm insulating layer of screening or coarse sand on top of Fine grained soil, the gradation of which will depend upon whether it is intended to act as a drainage layer as well. As a preferred alternative to inverted choke, appropriate geosynthetics performing functions of separation and drainage may be used over the prepared subgrade as directed by the Engineer. Section 700 shall be applicable for use of geosynthetics.

404.3.3 Lateral Confinement of Aggregates

For construction of WBM, arrangement shall be made for the lateral confinement of aggregates. This shall be done by building adjoining shoulders along with WBM layers. The practice of constructing WBM in a trench section excavated in the finished formation must be completely avoided.

Where the WBM course is to be constructed in narrow widths for widening of an existing pavement, the existing shoulders should be excavated to their full depth and width upto the sub grade level except where widening specifications envisages laying of a stabilised sub base using in situ operations in which case the same should be removed only upto the sub base level.

404.3.4 Spreading coarse aggregates:

The coarse aggregates shall be spread uniformly and evenly upon the prepared sub grade/sub-base/ in the required quantities from the stock piles to proper profile by using templates placed across the road about. 6 m apart, in such quantities that the thickness of each compacted layer is not more than 75 mm. In no case shall these be dumped in heaps directly on the area where there are to be laid nor shall their hauling over a partly completed base be permitted. Wherever possible approved mechanical devices such as aggregate spreader shall be used to spread the aggregates uniformly so as to minimize the need for manual rectification afterwards.

No segregation of coarse aggregate shall be allowed and the coarse aggregates, as spread shall be of uniform gradation with no pockets of fine material.

The surface of the aggregate spread shall be carefully checked with templates and all high or low spots remedied by removing or adding aggregates as may be required. The surface shall be checked frequently with a straight edge while spreading and rolling so as to ensure a finished surface as per approved drawings.

The coarse aggregate shall not normally be spread more than 3 days in advance of the subsequent construction operations.

404.3.5 Rolling:

Immediately following the spreading of the coarse aggregate, rolling shall be started with three wheeled power rollers of 80 to 100 kN capacity or tandem or vibratory rollers of 80 to 100 kN static weight. The type of roller to be used shall be approved by the Engineer based on trial run.

Except on super elevated portions and carriageway with unidirectional cross-fall, where the rolling shall proceed from inner edge to the outer, rolling shall begin from the edges gradually progressing towards the centre. First the edge/edges shall be compacted with roller running forward and backward. The roller shall then move inward parallel to the centre line of the road, in successive passes uniformly overlapping preceding tracks by at least one half width.

Rolling shall be carried out on courses where coarse aggregates of crushed / broken stone are used, till the road metal is partially compacted. This will be followed by application of screening and binding material where required in Clauses 404.3.6 and 404.3.7.

However, where screenings are not to be applied as in the case of aggregates like brick metal laterite and kankar for the sub base construction, the compaction shall be continued until the aggregates are thoroughly keyed. Rolling shall be continued and light sprinkling of water shall be done till the surface is well compacted. Rolling shall not be done when the sub grade is soft or yielding or when it causes a wave-like motion in the sub grade or sub base course.

The rolled surface shall be checked transversely with templates and longitudinally with 3 m. straight edge. Any irregularities exceeding 12mm shall be corrected by loosening the surface, adding or removing necessary amount of aggregates and re-rolling until the entire surface conforms to desired camber and grade. In no case shall the use of screenings be permitted to make up depressions.

Material which gets crushed excessively during compaction or becomes segregated shall be removed and replaced with suitable aggregates.

404.3.6 Application of screenings:

After the coarse aggregate have been rolled to Clause 404.3.5, screenings to completely fill the interstices shall be applied gradually over the surface. These shall not be damp or wet at the time of application. Dry rolling shall be done while the screenings are being spread so that vibrations of the roller cause them to settle into the voids of the coarse Aggregate. The screenings shall not be dumped in piles but be spread uniformly in successive thin layers either by the spreading motion & of hand shovels or by mechanical spreaders or directly from tipper with suitable grit spreading arrangement Tipper operating for spreading the screenings shall be equipped with pneumatic tyres and operated so as not to disturb to coarse aggregates.

The screenings shall be applied at a slow and uniform rate (in three or more applications) so as to ensure filling of all voids. This shall be accompanied by dry rolling and brooming with mechanical brooms, hand brooms or both. In no case shall the screenings be applied so fast and thick as to form cakes or ridges on the surface in such a manner as would prevent filling of voids or prevent the direct bearing of the roller on the coarse aggregate. These operations shall continue until no more screenings can be forced into the voids of the coarse aggregate.

The spreading, rolling and booming of screenings shall be carried out in only such lengths of the road which could be completed within one day's operation.

404.3.7 Sprinkling of water and grouting :

After application of screenings, the surface shall be copiously sprinkled with water, swept and rolled. Hand brooms shall be used to sweep the wet screenings into voids and to distribute them evenly. The sprinkling, sweeping and rolling operation shall be continued, with additional screenings applied as necessary until the coarse aggregate have been thoroughly keyed, well-bonded and firmly set in its full depth and a grout has been formed of screenings. Care shall be taken to see that the sub base or sub grade does not get damaged due to the addition of excessive quantities of water during construction.

In case of lime treated soil sub-base, construction of water bound macadam on top of it shall be taken up after curing as per Clause 402.3.9 and as directed by the Engineer.

Application of binding material : After the application of screenings in accordance with Clauses 404.3.6 and 404.3.7, the binding material where it is required to be used (Clause 404.2.7) shall be applied successively in two or more thin layers at a slow and uniform rate. After each application, the surface shall be copiously sprinkled with water, the resulting slurry swept in with hand brooms or mechanical brooms to fill the voids properly and rolled during which water shall be applied to the wheels of the rollers if necessary to wash down the binding material sticking to them. These operations shall continue until the resulting slurry after filling of voids, form a wave ahead of the wheels of the moving roller.

404.3.8 Setting and drying :

After the final compaction of water bound macadam course, the pavement shall be allowed to dry overnight. Next morning hungry spots shall be filled with screenings or binding material as directed, lightly sprinkled with water if necessary and rolled. No Traffic shall be allowed on the road until the macadam has set. The Engineer shall have the discretion to stop hauling traffic from using the completed water bound macadam course, if in his opinion it would cause excessive damage to the surface.

The compacted water bound macadam course should be allowed to completely dry and set before the next pavement course is laid over it.

404.4 Surface Finish and Quality Control of Work

404.4.1 The surface finish of construction shall conform to the requirements of Clause 902.

404.4.2 Control on the quality of materials and works shall be exercised by the Engineer in accordance with Section 900.

404.4.3 The water bound macadam work shall not be carried out when the atmospheric temperature is less than 10° C in the shade.

404.4.4 Reconstruction of defective macadam :

The finished surface of water bound macadam shall conform to the tolerance of surface regularity as prescribed in Clause 902. However, where the surface irregularity of the course exceeds the tolerances or where the course is otherwise defective due to sub grade soil mixing, with the aggregates, the course to its full thickness shall be scarified over the affected area, reshaped with added material or removed and replaced with fresh material as applicable and re-

compacted. The area treated shall not be less than 10 sq.m. In no case shall depressions be filled up with screenings or binding material.

404.5 Arrangement for Traffic

During the period of construction, the arrangement for traffic shall be done as per Clause 112.

404.6 Mode of Measurement & payment

Water bound macadam shall be measured as finished work in position in **cubic meters**.

404.7 RATE

The Contract unit rate for water bound macadam sub-base/base course shall be payable in full for carrying out the required operations including full compensation for all components listed below including arrangement of water used in the work as approved by the Engineer.

- (i) Making arrangements for traffic to Clause 112 except for initial treatment to verges, shoulders and construction of diversions;
- (ii) Supplying all materials to be incorporated in the work including all royalties, fees, rents where applicable with all leads and lifts,
- (iii) All labour, tools, equipment and incidental to complete the work to the Specifications
- (iv) Carrying out the work in part widths of the road where required and
 - (i) Carrying out the required tests for quality control.

ITEM NO.9

Providing and laying evenly priming coat with emulsion SS-1 at rate of 7.5 Kg/10 Sqm etc.complete

502. PRIME COAT OVER GRANULAR BASE

502.1. Scope

This work shall consist of the application of a single coat of low viscosity liquid bituminous material to a porous granular surface preparatory to the superimposition of bituminous treatment or mix.

502.2. Materials

502.2.1. Primer: The choice of a bituminous primer shall depend upon the porosity characteristics of the surface to be primed as classified in IRC:16. These are:

- (i) Surfaces of low porosity; such as wet mix macadam and water bound macadam.

- (ii) Surfaces of medium porosity; such as cement stabilized soil base; and
- (iii) Surfaces of high porosity; such as, a gravel/soil-aggregate base.

502.2.2. Primer viscosity: The type and viscosity of the primer shall comply with the requirements of IS:8887, as sampled and tested for bituminous primer in accordance with these standards. Guidance on viscosity and rate of spray is given in Table 500.1.

TABLE 500.1 : REQUIREMENTS OF VISCOSITY AND QUANTITY OF LIQUID BITUMINOUS MATERIALS FOR PRIMING

Porosity	Type of Surface	Kinematics Viscosity of Primer at 60°C (Centistokes)	Saybolt Furol Viscosity at 60° C (Seconds)	Quantity per 10 sqm (kg)
Low	WBM/WMM	30-60	14-238	7-10
Medium	Stabilized Base	70-140	33-66	9-12
High	Gravel Base	250-500	117-234	12-15

502.2.3. Choice of Primer: The primer shall be Slow Setting Bitumen Emulsion Grade SS-1, complying with IS:8887 or as specified in the Contract or as directed by the Engineer. The use of medium curing cutback as per IS:217 shall be restricted only for sites at sub-zero temperatures or for emergency applications.

502.3. Weather and Seasonal Limitations

Bituminous primer shall not be applied to a wet surface (see Clause 502.4.2) or during a dust storm or when the weather is foggy, rainy or windy or when the temperature in the shade is less than 10° C. Surfaces which are to receive emulsion primer should be damp, but no free or standing water shall be present.

502.4. Construction

502.4.1. Equipment : The primer distributor shall be a self-propelled or towed bitumen pressure sprayer equipped for spraying the material uniformly at specified rates and temperatures. Hand spraying of small areas, inaccessible to the distributor, or in narrow strips shall be permitted with a pressure hand sprayer. Use of a hand held perforated canister shall, however, not be permitted.

502.4.2. Preparation of road surface: The surface to be primed shall be prepared in accordance with Clause 501. Immediately prior to applying the primer, the surface shall be carefully swept clean of dust and loose particles, care being taken not to disturb the interlocked aggregate. This is best achieved when the surface layer is slightly moist (lightly sprayed with water and the surface allowed to dry) and the surface should be kept moist until the primer is applied.

502.4.3. Application of Bituminous Primer: The bituminous primer shall be sprayed/distributed uniformly over the dry surface, prepared as per Clause 502.4.2, using self-propelled or towed sprayer, capable of supplying primer at specified rates and temperature so as to provide a uniformly unbroken spread of primer. If the surface to be primed is so dry or dusty as to cause freckling of bituminous material, it shall be lightly and uniformly sprinkled with water immediately prior to priming; however, the bituminous material shall not be applied till such time as no surface water is visible. The primer shall be applied at the rate as specified in Table 500.1.

Temperature of application of a primer need only be high enough to permit the primer to be effectively sprayed through the jets of the spray bar and to cover the granular base surface uniformly in the desired quantity. For a bituminous emulsion primer, the range of spraying temperature shall be 20° C to 60° C and for cutback 50° C - 80° C if Medium Curing grade is used.

The primer coat shall be applied only on the topmost water bound macadam or any granular layer, over which the bituminous base course/wearing course is to be laid.

502.4.4. Curing of primer and opening to traffic: A primed surface shall be allowed to cure for at least 24 hours or such other period as is found to be necessary to allow all the volatiles to evaporate before any subsequent surface treatment or mix is laid. Any unabsorbed primer shall be blotted with an application of sand, using the minimum quantity possible. A primed surface shall not be opened to traffic other than that necessary to lay the next course. A very thin layer of clean sand may be applied to the surface of the primer, to prevent the primer picking up under the wheels of the paver and the trucks delivering bituminous material to the paver.

502.4.5. Tack Coat: Over the primed surface, a tack coat should be applied in accordance with Clause 503.

502.5. Quality Control of Work

For control of the quality of materials supplied and the works carried out, the relevant provision of Section 1800 shall apply.

502.6 Arrangements for Traffic

During construction operations, arrangements for traffic shall be made in accordance with the provisions of Clause 111.

502.7. Measurement for Payment

Prime Coat shall be measured in terms of surface area of application in square metres.

502.8. Rate

The contract unit rate for prime coat shall be payment in full for carrying out the required operations including full compensation for all components listed in Clause 401.9 (i) to (v) and as applicable to the work specified in these Specifications.

ITEM NO.10

Providing and laying Bituminous Grout 37.5mm thick compacted with asphalt VG-30 grade at the rate of 1.99% by weight of total mix with RS1 tack coat at 2.50 Kg/10 Sqmt. On existing B.T/ Metal. surface and using B.T. chips of required gradation including cleaning & heating the aggregate and asphalt by Drum Mix Plant & spreading the same by paver finisher & consolidation with vibratory road roller including providing all materials, equipments, tools, plants, fire wood, kerosene, oil and labor charges etc. comp. (using by contractor own machineries)

(Read as “ Viscosity Grade bitumen VG-10” inplace of “ Penetration grade 80/100” and “ Viscosity Grade bitumen VG-30” inplace of “ Penetration grade 60/70”)

Scope :

The work shall consist of construction, in a single course, of compacted crushed aggregates premixed with a bituminous binder, to serve as base / binder course, laid immediately after mixing on a base prepared previously in accordance with the requirement of these specifications and in conformity with the lines, grades and cross-sections shown on the drawing or as directed by the Engineer.

Built-up grout shall be used in a single course in a pavement structure.

Materials :

Bitumen : The Bitumen shall be paving bitumen of suitable penetration grade VG-10 as per IS 73. The actual grade of bitumen to be used shall be decided by the Engineer appropriate to the region, traffic, rainfall and other environmental conditions Guidelines on selection of the grade of bitumen are given in Appendix-4.

Aggregates :-

The aggregates shall consist of crushed stone of type black trap only. They shall be clean, strong, durable, of fairly cubical shape and free from desegregated pieces, organic or other deleterious matter and adherent coating the bitumen shall preferably be treated with anti-stripping agents of approved quality in suitable doses as Appendix-5. The aggregates shall satisfy the physical requirements set forth in Table.

PHYSICAL REQUIREMENTS OF AGGREGATES FOR BITUMINOUS GROUT.

Sr, No.	Test	Test Method	Requirement
01	Los Angeles Abrasion Value.	IS : 2386(Part – 4)	40 % Maximum
02	Aggregate Impact Value.	IS : 2386(Part – 4)	30 % Maximum

03	Flakiness and Elongation indices (Total)**	IS : 2386(Part – 1)	30 % Maximum
04	Coating and stripping of bitumen aggregate mixtures.	AASHTO T 182	Minimum retained coating 95 %.
05	Soundness (i) Loss with sodium sulphate 5 cycles. (ii) Loss with Magnesium sulphate 5 cycles.	IS : 2386(Part – 5)	12 % Maximum
06	Water absorption.	IS : 2386(Part – 3)	2 % Maximum

- Aggregates may satisfy requirements for either of the two tests.
- To determine this combined proportion, the flaky stone from a representative sample should first be separated out. Flakiness index is weight of flaky stone metal divided by remaining(non flaky) stone metal elongation index is weight of elongated particles divided to total non flaky particles. The value of flakiness index and elongation index to found are added up.

Proportioning of materials :

The bitumen content for premixing shall be 1.99 percent by weight of the total mix except when otherwise directed by the engineer.

The maximum compacted thickness of a layer shall be 100 mm.

The quantities of aggregates to be used shall be sufficient to yield the specified thickness after compactions.

AGGREGATE GRADING FOR BITUMINOUS GROUT.

IS Sieve Designation	Percent by weight passing the sieve.
53.0 mm.	100
26.5 mm.	75-100
22.4 mm.	50-85
13.2 mm.	20-40
5.6 mm.	5-20
2.8 mm.	0-5

Variation in proportioning of material : The contractor shall have the responsibility for ensuring proper proportioning of materials and producing a uniform mix A variation in binder content +0.3 % by weight of total mix shall blow ever be permissible for individual specimens taken for quality control test vide Section 900.

Construction Operations :

Weather and seasonal limitations : The work of laying shall not be taken up during rainy or foggy weather or when the base course is damp or wet, or during dust storm or when atmosphere temperature in shade is 10 degree C or less.

Preparation of base : The work shall consist of preparation and existing granular or black topped surface bituminous course. The work shall be performed on such widths and lengths as shown in applicable drawing or as directed by the Engineer. The existing surface shall be firm and clean, and treated with prime or tack coat as shown on the drawings as otherwise stated in the contract.

Materials :

For scarifying and re-laying granular surface : The materials used shall be coarse aggregate salvaged from scarification of the existing granular base course supplemented by fresh coarse aggregates and screenings so that aggregates and screening thus supplemented correspond to Clause 404 : Water macadam or Clause 406 Wet Mix Macadam, as the case may be.

For patching potholes and scaling cracks : Where the existing surface to be overlaid is bituminous. Any existing potholes and cracks shall be repaired and sealed in accordance with Clauses 3004.2 and 3004.3 or as directed by the Engineer.

For profile corrective course : A profile corrective course for correcting the existing pavement profile shall be laid to varying thickness as shown on the Drawings. Or as indicated in the Contract Documents. The profile corrective course shall be laid to tolerances and densities as specified for wearing course if a single layer or base course, if it is to be covered with a wearing course layer.

Profile corrective course and its application : The type of material for use as a profile corrective course shall be as shown on the drawing. If it is to be laid as part of the overlay/strengthening course, the profile corrective course material shall be of the same specification as that of the overlay/strengthening course. However, if provided as a separate layer, it may be of the same specification as the layer over which it is to be laid or intermediate between underlying layers, as shown on the Drawings.

Surface Levels

The levels of the sub grade different pavement courses as constructed, shall not vary from those calculated with reference to the longitudinal and cross profile of the road, shown on the drawings or as directed by the engineer beyond the tolerances mentioned in Table 900-1.

Bituminous materials shall not be applied to a wet surface or during a dust storm or when the weather foggy, rainy or windy or when the temperature in the shade is less than 10°C where the tack coat consists of emulsion, the surface shall be slightly damp, but not wet. Where the tack coat is of cutback bitumen, the surface shall be dry.

Construction Equipment :

The tack coat distributor shall be self propelled or towed bitumen pressure sprayer, quipped for spraying the material uniformly at a specified rate. Hand spraying of small areas, inaccessible to the distributor, or in narrow strips, shall be sprayed with a pressure and sprayer, or as directed by the Engineer. 503-4.2 of MORTH Specification Preparation of base : The surface on which the tack coat is to be applied shall be clean and free from dust, dirt and extraneous materials, and be otherwise prepared in accordance with the requirements of Clauses 501.8 and 902 as appropriate

immediately before the application of the tack coat, the surface shall be swept clean with a mechanical broom, and high pressure air jet, or by other means as directed by the Engineer.

Application of tack coat :

The application of tack coat shall be at the rate specified in the contract, and shall be applied uniformly, if rate of application of tack coat is not specified in the contract then it shall be at the rate specified in TABLE 500-2 OF MORTH Specification. The normal range spraying.

TABLE 500-2, RATE OF APPLICATION OF TACK COAT

The VG-10 asphalt at the rate of 2.5 kg. per 10 sq. m. on BT surface and 4.00kg/10sqm on WBM surface shall be used for tack coat temperature for a bituminous emulsion shall be 20°C to 70° C and for a cutback, 50°C to 80° C if RC-70/MC -70 is used. Where geosynthetic is proposed for use, the provisions of Clauses 703.3.2 and 703.3.4 of MORTH specification shall apply. The method of application of the tack coat will demand on the type of equipment to be used, size of nozzles, pressure at the spray bar, and speed of forward movement. The contractor shall demonstrate at a spraying trial, that the equipment and method to be used is capable of producing a uniform spray, within the tolerances specified.

Where the material to receive an overlay is a freshly laid bituminous layer, that has not been subjected to traffic or contaminated by dust, a tack coat is not mandatory where the overlay is completed within two days.

Curing of tack coat : The tack coat shall be left to cure until all the volatiles have evaporated before any subsequent construction is started. No pany or vehicles shall be allowed on the tack coat other than those essential for the construction.

Quality control of work : TOLERANCES IN SURFACE LEVELS

1. Sub grade	1.20 mm.
	25 mm.
2. Sub-base 4-10 mm.	
a) flexible pavement	-20 mm.
b) concrete pavement.	-6 mm.
(Dry lean concrete of rolled concrete)	-10mm.
3. Base-course for flexible pavement.	
a) Bituminous course.	+6 mm.
	+6 mm.
b) Other than bituminous.	+10 mm.
(i) Machine laid.	-10 mm.
(ii) Manually laid,	

	+15 mm. -15 mm.
4. Wearing course for flexible pavement.	
a) Machine laid.	+6 mm.
b) Manually laid	-6 mm. +10 mm. -10 mm.
5. Cement concrete pavement.	+5 mm. -6 mm.

TACK COAT

Scope

This work shall consist of the application of a single coat of high viscosity liquid bituminous material to an existing bituminous road surface preparatory to be superimposition of a bituminous mix when specified in the Contract or instructed by the Engineer.

Materials

The binder used for tack coat shall be bitumen VG-10 complying with ISS 8887 of a type and grade as specified in the Section 600 of MORTH specification contract or as directed by the Engineer. The use of cutback bitumen as per IS 217 shall be restricted only for sites at sub-zero temperatures or for emergency applications as directed by the Engineer.

Weather and Seasonal Limitations

For control of the quality of materials supplied and the works carried out the relevant provisions of Section 900 shall apply.

Specifications : The rate shall cover the provision of tack coat at 0.25 kg. / 0.40kg per square metre with the provision that the variation in actual quantity of bitumen used will assessed and the payment adjusted accordingly.

Preparation and transport of mix :

Bituminous grout mix shall be prepared in abet mix plant of adequate capacity and capable of yielding a mix of proper and uniform quality, with thoroughly coated aggregates.

The plant shall be drum mix type. The plant shall have coordinated set of essential units capable of producing uniform mix within the job mix formula such as laid down in Appendix-A.

- (a) In case of drum mix plant, the cold feed system shall have variable speed conveyors/or other suitable devices for regulating the accurate proportion/Control Cabin.
- (b) Bitumen Control Unit : Capable of measuring/metreing and spraying required quantity of bitumen at specified temperature with automatic synchronization of bitumen and aggregate feed.
- (c) Filter System : A fines feeder system suitable to receive bagged or bulk supply of filter materials and its incorporation to the mix in the correct quantity shall be necessary auxiliary.

- (d) Dust control : A suitable built in Dust control equipment for the dryer to contain the exhaust of the dust in to atmosphere for environmental control whoever so specified by the Engineer.
- (e) Suitable auxiliary Bitumen : Boiler of adequate capacity with self heating arrangement and temperature control device. The boiler should be fitted with temperature indicating instructs.

The temperature of binder at the time of mixing shall be in range of 150°C to 163°C and that of the aggregate in the range of 155°C to 163°C provided that the difference in temperature between the binder and aggregate at no time exceeds 14°C.

Mixing shall be through to ensure that a homogeneous mixture is obtained in which all particles of the aggregates are coated uniformly and then discharged temperature of mix shall be between 130°C to 160°C.

The mixture shall be transported from the mixing plant to the point of use in suitable tipper vehicles. The vehicles employed for transport shall be clean and be covered in transit of so directed by the Engineer. Any tipper causing excessive segregation of materials by its spring suspension or other contributing factors or that which shows undue shall be removed from the work unit such conditions are corrected.

Spreading : The mix transferred from the tipper at site to the paver shall be spread immediately by means of self propelled mechanical paver with suitable screeds capable of spreading, tamping and finishing the mix true to the specified lines, grads and cross sections. The paver finisher shall have the following essential features.

- (a) Loading hoppers and suitable distributing mechanism.
- (b) All drives having hydrostatic drive/control.
- (c) The machine shall have a hydraulically extendable screed for appropriate width requirement.
- (d) The screed shall have tamping and vibrating arrangement for initial compacting to the layer as it is spread without rutting of otherwise marrying surface, it shall have adjustable amplitude and variable frequency.
- (e) The paver shall be equipment with necessary control mechanism so as to ensure that the finished surface is free from surface blemishes.
- (f) The paver shall be fitted with an electronic sensing device for automatic leveling and profile control within the specified tolerances.
- (g) The screed shall have the internal heating arrangement.
- (h) The paver shall be capable of laying either 2.5 to 4.0 m. width of 4.0 to 7.0 m. width as stipulated in the Contract.
- (i) The paver shall be so designed as to eliminate skidding/slippage of the tyres during operation.

However, in restricted location and in narrow widths where the available plant cannot be operated in the opinion of the Engineer, he may permit manual laying of the mix.

The temperature of the mix at the time of laying shall be in the range 120° C to 160°C. In multi layer construction, the longitudinal joint in one layer shall offset that the layer below by about 150 mm. However, the joint in the top-most layer shall be at the lane line of the pavement.

Longitudinal joints and edges shall be constructed true to the delineating line parallel to the center line of the road. All joints shall be cut vertical to the full thickness of the previously laid

mix and surface painted with hot bitumen before placing fresh material. Longitudinal and transverse joints shall be offset by at least 250 mm. from those in the lower course and the joint on the top-most layer shall not be allowed to fall within the wheel path. All transverse joints shall be cut vertically to the full thickness of the previously laid mix with asphalt cutter/pavement breaker and surface painted with hot bitumen before placing fresh materials. Longitudinal joints shall be preferably hot joints. Cold longitudinal joints shall be properly heated with joint heater to attain a suitable temperature of about 80°C before laying of adjacent materials.

Compaction : After the spreading of mix, rolling shall be done by 80 to 100 KN. Vibratory roller. Rolling shall start as soon as possible after the material has been spread deploying 3 sets of rollers as the rolling is to be completed in limited time frame. The roller shall move at a speed not more than 5 km/h. Rolling shall be done with care to avoid unduly roughening of pavement surface.

Rolling of the longitudinal joints shall be done immediately behind the paving operation. After this the rolling shall commence at the edges and progress towards the center longitudinally except that on super elevated and unidirectional cambered portions, it shall progress from the lower to the upper edge parallel to the center line of the pavement.

The initial or break-down rolling shall be done with 80-100KN. Static weight static weight smooth wheel roller (3wheels or tandem) as soon as it is possible to roll the mix without cracking the surface or having the mix pick up on the roller wheels. The second or intermediate rolling shall follow the break down rolling with vibratory roller of 80 to 100 KN. Static weight of pneumatic tyred roller of 150 to 250 kn. Weight with minimum 7 wheels and minimum tyre pressure of 0.7 Mpa. As closely as possible to the paver and be done while material is still workable enough for removal of roller marks, with 60 to 80 Kn. Tandem roller. During the final rolling, vibratory system shall be switched off. The joints and edges shall be rolled with a 80 to 100 kn. Static roller.

When the roller has passed over the whole area once, any high spots or depressions which become apparent shall be corrected by removing or adding mix material. The rolling shall then be continued till the entire surface has been rolled to 95 percent of the average laboratory density (obtained from Marshall specimens compacted as defined in Table(500-10), there is no crushing of aggregates and all roller marks have been eliminated. Each pass of the roller shall uniformly overlap not less than one-third of the track made in the preceding pass. The roller wheel shall be kept damp if necessary to avoid bituminous materials from sticking to the wheels and being packed up. In no case shall fuel, lubricating oil be used for this purpose, nor excessive water poured on the wheels.

Rolling operations shall be completed in every respect before the temperature of the mix falls below 100°C.

Roller(s) shall not stand on newly laid materials while there is a risk that surface will be deformed thereby. The edges along and transverse of the bituminous grout laid and compacted earlier shall be cut to their full depth so as to expose fresh surface which shall be painted with a thin surface coat of appropriate binder before the new mix is placed against it.

Surface Finish and Quality Control of Work.

The surface finish of constructing shall conform to the requirements of Clause 902. Control on the quality of materials and works shall be exercised by the Engineer in accordance with Section 900.

The built up spray grout shall be provided with next surfacing without any delay. If there is to be any delay, the curse shall be covered by a seal coat to the requirement of Clause 613 before allowing any traffic over it. The seal coat in such cases shall be considered incidental to the work and shall not be paid for separately.

Arrangements for Traffic.

During the period of construction, arrangement of traffic shall be done to Clause 112 of MORTH specification.

Passage of Traffic along a part of the Existing Carriageway under Improvement.

For widening/strengthening existing carriageway where part width of the existing carriage way proposed to be used for passage of traffic, treated shoulders shall be provided on the side on which work is not in progress. The treatment to the shoulder shall consists of providing at least 150 mm. thick granular base course covered with bituminous surface dressing in a width of at least ~~xxxx~~ and surface shall be maintained throughout the period during which traffic uses the same to the satisfaction of the engineer. The continuous length in which such work shall be carried out, would be limited normally to 500 m. at a place. However, where work is allowed by the Engineer in longer stretches passing places at least 20m. long with additional paved width of 2.5 m shall be provided at every 0.5 km. interval.

In case of widening existing two lane to four lane, the additional two lanes would be constructed first and the traffic diverted to it and only there after the required treatment to the existing carriageway would be carried out. However, in case where on the request of the contractor, work on existing two lane carriageway is allowed by the Engineer with traffic using part of the existing carriageway, stipulations as in para above shall apply.

After obtaining permission of the Engineer, the treated shoulder shall be dismantled the debris disposed of and the area cleared as per the direction of the Engineer.

MEASUREMENTS FOR PAYMENT

The payment shall be made on the tonnage (MT) basis of the weight of mix of aggregates and bitumen. For the purpose, the contractor shall have to install a weight bridge of suitable capacity for the purpose of weighment of dumpers at suitable place at his cost as directed weight of empty and weight of loaded dumper will be recorded in bound and numbered register on plant site.

Department will be free to get some loaded dumpers test checked at other weight bridge. Weight bridge will be periodically got calibrated and verified from weight and measure authorities.

For the purpose of application of tack coat, if the theoretical area as per sanctioned estimate for basis of tone differs with the actual area of work done in the field, the reduction in or addition to payment shall have to be exceed respectively.

Weight of mix materials will be done in presence or responsible person, not less than the rank of supervisor of department and the measurement shall be recorded by the Deputy Executive or Assistant Engineer or Addl. Asst. Engineer. If so authorized, Record of each dumper will be maintained separately in bound and numbered register, which will be maintained by the departmental representative and signed by the contractor, proper gate pass system shall be established for the vehicle coming to the plant site and out going from the plant site. The location

of the kilometre, hectometre and metre in which individual dumper are unloaded shall be recorded carefully.

Rate :

The contract unit rate for the work shall be payment in full for carrying out the required operations including full compaction for.

- (i) Making arrangements for traffic to Clause 112 of MORTH specification except or initial treatment to verge, shoulders and construction of diversion.
- (ii) preparation of base except for laying of profile corrective course
- (iii) but including filling of potholes.
- (iii) Providing all materials to be incorporated in the work including arrangement for stock yards, all royalties, fees, rents where necessary and all leads and lift.
- (iv) All labor, tools, equipment, plant including installation of hot mix plant, power supply units and all machineries, incidental to complete the work to the specifications.
- (v) Carrying out the work in part widths of the road where directed.
- (vi) Carrying out all tests for control of quality.

ITEM NO.11

Providing and laying 37.5 mm thick Bituminous Macadam (B.M.) in one layers on the existing B.T. surface using stone chips as per gradation and using Emulsion RS1 for tack coat at rate of 2.5 kg/ 10 sq.m. on B.T. surface and Bitumen VG-30 34KG/MT by weight of total mix by using stone chips as per MORT & H specification including heating asphalt and aggregates by Drum mix plant and spreading by paver finisher to the required grade, level and alignment and rolled including consolidation with vibratory road roller as per clauses 501.6 and 501.7 to achieve the desired compaction and providing, operating plant machineries, equipments, tools, plants, oil fire wood, kerosene and all labour charges etc. complete.

(Read as “ Viscosity Grade bitumen VG-10” in place of “ Penetration grade 80/100” and “ Viscosity Grade bitumen VG-30” in place of “ Penetration grade 60/70”)

504.1. Scope

This work shall consist of construction in a single course having 37.50 mm thickness of compacted crushed aggregates premixed with a bituminous binder on a previously prepared base to the requirements of these Specifications.

504.2. Materials

504.2.1. Bitumen: The bitumen shall be paving bitumen of viscosity Grade complying with Indian Standard Specifications for “Paving Bitumen” IS:73, or Modified Bitumen conforming to Clause 512 or as directed by the Engineer. Further guidelines on the choice of bitumen depending on the maximum and minimum annual temperatures (T_{max} and T_{min}) in the area are given at ***Annexure-500.2.***

504.2.3. Aggregate grading and binder content: When tested in accordance with IS:2386 (Part 1) (wet sieving method), the combined aggregate grading for the particular mixture shall fall within the limits shown in Table 500.4. The type and quantity of bitumen are also indicated in Table 500.4.

TABLE 500.4 : COMPOSITION OF BITUMINOUS MACADAM

IS Sieve (mm)	Cumulative Per cent Passing by Weight of Total Aggregate
26.5	100
19	90-100
13.2	56-88
4.75	16-36
2.36	4-19
0.3	2-10
0.075	0-5
*Bitumen content, % by weight of total mixture	3.3-3.5
Bitumen Penetration Grade	35 to 90

* For conditions in cooler areas of India or where the per cent passing 0.075 mm sieve is on the higher side of the range, appropriate bitumen contents may be upto 0.5 per cent higher, subject to the approval of the Engineer.

The binder content shall be within a tolerance of ± 0.3 per cent by weight of total mixture when individual specimens are taken for quality control tests in accordance with the provisions of Section 1800.

504.3. Construction Operations

504.3.1. Weather and seasonal limitations: Laying of bituminous mixtures shall not be carried out when the air temperature at the surface over which it is to be laid is below 10° C or when the wind speed at any temperatures exceeds 40 km/hr at 2 m height unless specifically approved by the Engineer. Laying shall be suspended while free-standing water is present on the surface to be covered, or during rain, fog and dust storms. After rain, the surface shall be left to dry before laying shall start.

504.3.2. Preparation of the base: The base on which bituminous macadam is to be laid shall be prepared, shaped and compacted to the required profile in accordance with Clause 501, as appropriate, and a prime coat, on granular base shall be applied in accordance with Clause 502 where specified, or as directed by the Engineer.

504.3.3. Tack Coat: A tack coat in accordance with Clause 503 shall be applied as specified in the Contract or as directed by the Engineer.

504.3.4. Preparation and transportation of mix: Bituminous Macadam shall be prepared in a hot mix plant of adequate capacity and capable of yielding a mix of proper and uniform quality with thoroughly coated aggregates. Appropriate mixing temperatures are given in Table 500.7 of these Specifications; the difference in temperature between the binder and aggregate should at no time exceed 14° C. In order to ensure uniform quality of the mix and better coating of aggregates, the hot mix plant shall be calibrated from time to time. A batch type or continuous type or a spot mixer may be used for preparation of mix as decided by the Engineer. If a continuous mixing plant is to be used for mixing, the Contractor must demonstrate by laboratory analysis that cold feed combined grading is within permissible grading limits and binder content is in compliance to job mix formula. The maximum permitted variation in binder content shall be 0.3 per cent.

Bituminous Macadam shall be transported in clean insulated vehicles and unless otherwise agreed by the Engineer, shall be covered while in transit or awaiting tipping. Subject to the approval of the Engineer, a thin coating of diesel or lubricating oil may be applied to the interior of the vehicles to prevent sticking and to facilitate discharge of the material. Any tipper causing excessive segregation of materials by its spring suspension or other contributing factors or that which shows undue delay shall be removed from the work until such conditions are corrected.

504.3.5. Spreading: Except in areas where a mechanical paver cannot access, premixed bituminous macadam shall be spread, leveled, and tamped by an approved self-propelled paving machine. As soon as possible, after arrival at site, the materials shall be supplied continuously to the paver and laid without delay.

The rate of delivery of material to the paver shall be regulated to enable the paver to operate continuously. The travel rate of the paver and its method of operation shall be adjusted to ensure an even and uniform flow of bituminous material across the screed, free from dragging, tearing and segregation of the material. In areas with restricted space where a mechanical paver cannot be used, the material shall be spread, raked and leveled with suitable hand tools by experienced staff and compacted to the satisfaction of the Engineer.

However, in restricted locations and in narrow widths where the available plant cannot be operated in the opinion of the Engineer, he may permit manual laying of the mix.

504.3.6. Compaction: After the spreading of mix, rolling shall be done by 80 to 100 kN static weight rollers or other approved equipment. Rolling shall start as soon as possible after the material has been spread deploying a set of rollers as the rolling is to be completed in limited time frame. The roller shall move at a speed not more than 5 km/hr. Rolling shall be done with care to avoid unduly roughening of the pavement surface.

Rolling shall commence at the edges and progress towards the centre longitudinally except that on superelevated and uni-directional cambered portions, it shall progress from the lower to the upper edge parallel to the centerline of the pavement.

The initial or break-down rolling shall be done with 80 to 100 kN static weight rollers, as soon as it is possible to roll the mix without cracking the surface or having the mix pick up on the roller wheels. The second or intermediate rolling shall follow the break-down rolling with vibratory roller of 80 to 100 kN static weight or a suitable pneumatic tyred roller as closely as possible to the paver and be done while the paving mix is still at a temperature that will result in maximum density. The final rolling shall be done while material is still workable, as per the temperatures given in Table 500.5. The joints and edges shall be rolled with a 80 to 100 kN static weight roller.

When the roller has passed over the whole are once, any high spots or depressions which become apparent shall be corrected by removing or adding mix material. The rolling shall then be continued till there is no crushing of aggregates and all roller marks have been eliminated. Each pass of the roller shall uniformly overlap not less than one-third of the track made in the preceding pass. The roller wheel shall be kept damp if necessary to avoid bituminous material from sticking to the wheels and being picked up. In no case shall fuel, lubricating oil be used for this purpose, nor excessive water poured on the wheels. The initial wetting of the roller wheels should be done outside the compaction area.

Rolling operations shall be completed in every respect before the temperature of the mix falls below the rolling temperature given in Table 500.5.

TABLE 500.5 : MANUFACTURING AND ROLLING TEMPERATURES

Bitumen viscosity	Bitumen Mixing(°C)	Aggregate Mixing(°C)	Mixed Material (°C)	Laying (°C)	Rolling (°C)
35	160-170	160-175	170 maximum	140 minimum	100 minimum
65	150-165	150-170	165 maximum	130 minimum	100 minimum
90	140-160	140-165	155 maximum	130 minimum	100 minimum

Roller(s) shall not stand on newly laid material while there is a risk that surface will be deformed thereby. The edges along and transverse of the bituminous macadam laid and compacted earlier shall be cut to their full depth so as to expose fresh surface which shall be painted with a thin surface coat of appropriate binder before the new mix is placed against it, as per Clause 504.3.7.

Where Modified Bitumen is used, the manufacturing and rolling temperatures shall be as per Clause 512.4.2.

504.3.7. Joints: For single-lane road construction, only transverse joints are made, while for double-lane road construction, longitudinal joints have also to be made in addition to transverse joints. While forming joints it is necessary that the premixed material shall be fully compacted and the joint made flush by cutting back the exposed joint for a distance equal to the specified layer thickness, to a vertical face, discarding all loosened material. The vertical face shall be coated completely with 80/100 penetration grade hot bitumen, or cold-applied bitumen, or polymer modified adhesive bitumen tape with a minimum thickness of 2 mm, before the adjacent width is laid.

504.4. Surface Finish and Quality Control of Work

The surface finish of the completed construction shall conform to the requirements of Clause 1802. For control of the quality of materials supplied and the works carried out, the relevant provision of Section 1800 shall apply.

504.5. Protection of the Layer

The bituminous macadam shall be covered with either the next pavement course or wearing course, as the case may be, within a maximum of forty-eight hours. If there is to be any delay on account of the construction procedure adopted by the Contractor, the course shall be covered by a seal coat to the requirement of Clause 509 before opening to any traffic. The seal coat in such cases shall be considered incidental to the work and shall not be paid for separately.

504.6. Arrangements for Traffic

During the period of construction, arrangements for traffic shall be made in accordance with the provisions of Clause 111.

504.7. Measurements for Payment

[The work shall be measured as finished work in by weight in metric tones as provided in the Contract.](#)

504.8. Rate

The contract unit rate for the work shall be payment in full for carrying out the required operations including full compensation for:

- (i) Making arrangements for traffic to Clause 111 except for initial treatment to verges, shoulders and construction of diversions;
- (ii) Preparation of base;
- (iii) Providing all materials to be incorporated in the work including arrangement for stockyards, all royalties, fees, rents where necessary and all leads and lifts;
- (iv) Mixing, transporting, laying and compacting the mix, as specified;
- (v) All labour, tools, equipment, plant including laying trials, if directed by the Engineer, installation of hot mix plant, power supply units and all machineries, incidental to complete the work to the Specifications;
- (vi) Carrying out the work in part widths of the road where directed;
- (vii) Carrying out all tests for control of quality;
- (viii) The rate shall cover the provision of bitumen at 3.4 per cent of weight of total mix, with the provision that the variation of quantity of bitumen will be assessed and the payment adjusted as per the rate of bitumen quoted; and
- (ix) The rates for premixed material shall include for all wastage in cutting of joints etc.

503.1. Scope

This work shall consist of the application of a single coat of low viscosity liquid bituminous material to an existing bituminous road surface preparatory to the superimposition of a bituminous mix, when specified in the Contract or instructed by the Engineer.

503.2. Materials

503.2.1. Binder: The binder used for tack coat shall be Rapid Setting Bitumen Emulsion Grade RS-1 complying with IS:8887 or as specified in the Contract. The use of cutback bitumen (Medium Curing grade) as per IS:217 shall be restricted only for sites at sub-zero temperature or for emergency applications as directed by the Engineer.

503.3. Weather and Seasonal Limitations

Bituminous material shall not be applied to a wet surface or during a dust storm or when the weather is foggy, rainy or windy or when the temperature in the shade is less than 10° C. Where

the tack coat consists of emulsion, the surface shall be slightly damp, but not wet. Where the tack coat is of cutback bitumen, the surface shall be dry.

503.4. Construction

503.4.1. Equipment: The tack coat distributor shall be a self-propelled or towed bitumen pressure sprayer, equipped for spraying the material uniformly at a specified rate. Hand spraying of small areas, inaccessible to the distributor, or in narrow strips, shall be permitted with a pressure hand sprayer, or as directed by the Engineer.

503.4.2. Preparation of base: The surface on which the tack coat is to be applied shall be clean and free from dust, dirt, and any extraneous material, and be otherwise prepared in accordance with the requirements of Clause 501. Immediately before the application of the tack coat, the surface shall be swept clean with a mechanical broom, or by other means as directed by the Engineer.

503.4.3. Application of binder: The binder shall be sprayed on the base at the rate specified in Table 500.2. The normal range of spraying temperature for a bituminous emulsion shall be 20° C – 60° C and for a cutback 50° C – 80° C if Medium curing grade is used. It shall be the responsibility of the Contractor to carefully handle the inflammable bituminous cutback material so as to safeguard against any fire mishap. The binder shall be applied uniformly with the aid of either self-propelled or towed bitumen pressure sprayer capable of spraying bitumen at specified rates and temperature so as to provide a uniformly unbroken spread of bitumen. Work should be planned so that no more than the necessary tack coat for the day's operation is placed on the surface.

TABLE 500.2 : RATE OF APPLICATION OF TACK COAT

Type of Surface	Quantity of BituminVG-10 in kg per square metre area
(i) Normal bituminous surfaces	0.25
(ii) Dry and hungry bituminous surfaces	0.25 to 0.30
(iii) Granular surfaces treated with primer	0.25 to 0.30
(iv) Cement Concrete Pavement	0.30 to 0.35

503.4.4 Curing of tack coat: The tack coat shall be left to cure until all the volatiles have evaporated before any subsequent construction is started. No plant or vehicles shall be allowed on the tack coat.

503.5. Quality Control of Work

For control of the quality of materials supplied and the works carried out, the relevant provisions of Section 1800 shall apply.

503.6. Arrangements for Traffic

During the period of construction, arrangements for traffic shall be made in accordance with the provisions of Clause 111.

503.7. Measurements for Payment

Tack coat shall be measured in terms of surface area of application in M.T.

503.8 Rate

The contract unit rate for tack coat shall be payment in full for carrying out the required operations including for all components listed in Clause 401.9 (i) to (v) and as applicable to the work specified in these Specifications

501.6 Compaction

Bituminous materials shall be laid and compacted in layers which enable the specified thickness, surface level, regularity requirements and compaction to be achieved.

Compaction of bituminous materials shall commence as soon as possible after laying. Compaction shall be substantially completed before the temperature falls below the minimum rolling temperatures stated in the relevant part of these Specifications. Rolling of the longitudinal joints shall be done immediately behind the paving operation. After this, rolling shall commence at the edges and progress towards the centre longitudinally except that on super elevated and unidirectional cambered portions, it shall progress from the lower to the upper edge parallel to the centre line of the pavement. Rolling shall continue until all roller marks have been removed from the surface. All deficiencies in the surface after laying shall be made good by the attendants behind the paver, before initial rolling is commenced. The initial or breakdown rolling shall be done with 8-10 tonnes dead weight smooth-wheeled rollers. The intermediate rolling shall be done with 8-10 tonnes dead weight or vibratory roller or with a pneumatic tyred roller of 12 to 15 tonnes weight having nine wheels, with a tyre pressure of at least 5.6 kg/sq.cm. The finish rolling shall be done with 6 to 8 tonnes smooth wheeled tandem rollers.

Where compaction is to be determined by density of cores the requirements to prove the performance of rollers shall apply in order to demonstrate that the specified density can be achieved. In such cases the Contractor shall nominate the plant, and the method by which he intends to achieve the specified level of compaction and finish at temperatures above the

minimum specified rolling temperature. Laying trials shall then demonstrate the acceptability of the plant and method used.

Bituminous materials shall be rolled in a longitudinal direction, with the driven rolls nearest the paver. The roller shall first compact material adjacent to joints and then work from the lower to the upper side of the layer, overlapping on successive passes by at least one-third of the width of the rear roll or, in the case of a pneumatic tyred roller, at least the nominal width of 300 mm.

In portions with super-elevated and uni-directional camber, after the edge has been rolled, the roller shall progress from the lower to the upper edge.

Rollers should move at a speed not more than 5 km per hour. The roller shall not be permitted to stand on pavement which has not been fully compacted, and necessary precautions shall be taken to prevent dropping of oil, grease, petrol or other foreign matter on the pavement either when the rollers are operating or standing. The wheels of rollers shall be kept moist with water, and the spray system provided with the machine shall be in good working order, to prevent the mixture from adhering to the wheels. Only sufficient moisture to prevent adhesion between the wheels and rollers and the mixture should be used. Surplus water shall not be allowed to stand on the partially compacted pavement.

Rolling shall be continued until the specified density is achieved, or where no density is specified, until there is no further movement under the roller. The required frequency of testing is defined in Clause 903.

501.7 Joints

Where longitudinal joints made in pre-mixed bituminous materials, the materials shall be fully compacted and the joint made flush in one of the following ways; only method (iii) shall be used for transverse joints

- (i) by heating the joints with an approved joint heater when the adjacent width is being laid, but without cutting back or coating with binder. The heater shall raise the temperature of the full depth of material, to within the specified range on minimum rolling temperature and maximum temperature at any stage for the material, for a width not less than 75 mm. the Contractor shall have equipment available, for use in the event of a heater breakdown, to form joints by method (iii);
- (ii) by using two or more pavers operating in echelon, where this is practicable and in sufficient proximity for adjacent widths to be fully compacted by continuous rolling.

(iii) by cutting back the exposed joint, for a distance equal to the specified layer thickness, to a vertical face, discarding all loosened material and coating the vertical face completely with 80/100 penetration grade hot bitumen, or cold-applied bitumen, or polymer modified adhesive bitumen tape with a minimum thickness of 2mm, before the adjacent width is laid.

All joints shall be offset at least 300 mm from parallel joints in the layer beneath or as directed, and in a layout approved by the Engineer. Joints in the wearing course shall coincide with either the lane edge or the lane marking, which ever is appropriate. Longitudinal joints shall not be situated in wheel track zones.

501.8.8.2. Rate for premixed bituminous material:

The contract unit rate for premixed bituminous material shall be payment in full for carrying out the required operations including full compensation for, but not necessarily limited to:

- (i) Making arrangements for traffic to Clause 112 except for initial treatment to verge, shoulders and construction of diversion;
- (ii) Preparation of the surface to receive the material.
- (iii) Providing all materials to be incorporated in the work including arrangement for stock yards, all royalties, fees, rents where necessary and all leads and lifts;
- (iv) Mixing, transporting, laying and compacting the mix, as specified.
- (v) All labour, tools, equipment, plant including installation of hot mix plant, power supply units and all machinery, incidental to complete the work to these Specifications;
- (vi) Carrying out the work in part width of the road where directed;
- (vii) Carrying out all tests for control of quality; and
- (viii) The rate shall cover the provision of bitumen at the rate specified in the contract, with the provision that the variation in actual percentage of bitumen used will be assessed and the payment adjusted accordingly.
- (ix) The rates for premixed material are to include for all wastage in cutting of joints etc.

- (x) The rates are to include for all necessary testing, mix design, transporting and testing of samples, and cores. If there is not a project specific laboratory, the Contractor must arrange to carry out all necessary testing at an outside Laboratory, approved by the Engineer, and all costs incurred are deemed to be included in the rate quoted for the material.
- (xi) The cost of all plant and laying trials as specified to prove the mixing and laying methods is deemed to be included in the Contractor's rates for the material.

ITEM NO.12

Providing and laying 20 mm thick average Mix seal surface using stone chips dust as per gradation and using bitument for mixing VG-30 at the rate of not less than 50.90Kg /M.T. on BT surface using stone chips as per M.O.R.T.H specification including heating the asphalt and aggregates by Hot Mix Plant and spreading the same by paver finisher including consolidation with Vibratory Roller and providing, operating plant machineries, equipment, tools, plants, oil, fire wood, kerosene and all labour charges etc. complete.

(Read as " Viscosity Grade bitumen VG-10" inplace of " Penetration grade 80/100" and " Viscosity Grade bitumen VG-30" inplace of " Penetration grade 60/70")

509. MIX SEAL SURFACING

509.1. Scope

509.1.1. This work shall consist of the preparation, laying and compaction of mix seal surfacing material of 20 mm thickness composed of graded aggregates premixed with a bituminous binder on a previously prepared surface, in accordance with the requirements of these Specifications, to serve as a wearing course. No Mix Seal Surfacing layer shall, however, be placed directly over WBM base.

509.1.2. Mix Seal surfacing shall be of Type A or Type B as specified in the Contract documents.

509.2. Materials

509.2.1. Binder: The provisions of Clause 508.1.2.1. shall apply.

509.2.2. Coarse aggregates: The provisions of Clause 508.1.2.2. shall apply.

509.2.3. Fine aggregates: The fine aggregates shall consist of crushed rock, quarry sands, natural gravel/sand or a mixture of both. These shall be clean, hard, durable un-coated, mineral particles, dry and free from injurious, soft or flaky particles and organic or deleterious substances.

509.2.4. Aggregate gradation: The coarse and fine aggregates shall be so graded or combined as to conform to one or the other gradings shown in Table 500.15 as specified in the contract.

TABLE 500.15 : AGGREGATE GRADATION

IS Sieve Designation (mm)	Cumulative per cent by weight of Total Aggregate Passing	
	Type A	Type B
13.2 mm	-	100
11.2 mm	100	88-100
5.6 mm	52-88	31-52
2.8 mm	14-38	5-25
0.090 mm	0-5	0-5

509.2.5. Proportioning of materials: The total quantity of aggregates used for Type A or B close-graded premix surfacing shall be 0.27 cu.m per 10 sq.m area. The quantity of binder used for premixing in terms of straight-run bitumen shall be 22 kg and 19 kg per 10 sq.m area for Type A and Type B surfacing respectively.

509.3. Construction Operations

The provisions of Clauses 508.1.3.1 to 508.1.3.5 shall apply, except that the laying of Mix Seal Surfacing shall be carried out by a mechanical paver.

509.4. Opening to Traffic

Traffic may be allowed after completion of the final rolling when the mix has cooled down to the surrounding temperature. Excessive traffic speeds should not be permitted.

509.5. Surface Finish and Quality Control of Work

The surface finish of construction shall conform to the requirements of Clause 1802. For control on the quality of materials supplied and the works carried out, the relevant provisions of Section 1800 shall apply.

509.6. Arrangements for Traffic

During the period of construction, arrangements for traffic shall be in accordance with the provisions of Clause 111.

509.7. Measurements for Payment

Mix Seal surfacing, Type A or B shall be measured as finished work, for the area specified to be covered, in square metres at a specified thickness. The area shall be the net area covered, and all allowances for wastage and cutting of joints shall be deemed to be included in the rate.

509.8. Rate

The contract unit rate for Mix Seal Surfacing, Type A or B shall be payment in full for carrying out the required operations including full compensation for components listed in Clause 504.8, as applicable to the work specified in these Specifications.

Payment shall be made on Metric tone Basis

ITEM NO.13

Excavation for foundation upto all depth including sorting out and stacking of useful materials and disposing of the excavated stuff upto all lead. Dense or hard soil.

1. Excavation for structures shall consist of the removal of material for the construction of foundations for culverts, retaining walls, cut of walls pipe culverts and other similar structures, in accordance with the requirements of these specification and the lines and dimensions shown on the drawing or as indicated by the Engineer in charge. The work shall include all necessary sheeting shorting. ba\ racing draining an pumping and the removal of all logs stumps ,grubs and other deleterious matter and obstructions necessary for placing the foundations, trimming bottoms of excavations backfilling and clearing up the site and the disposal of all surplus material.
2. After the site has been cleared the limits of excavation shall be set out true to lines, curves and slopes.
3. Excavation shall be taken to the width of the lowest step of th footing. The contractor at his own expense shall put up necessary shoring, trutting and planking or cut slopes to a safer angle or both with due-regard to the safety of persons and works and to the satisfaction of the enginner in charge.
4. The depth to which the excave on is to be carried out shall be as shown, on the drawings. unles the type of material encountered is such as to require changes. in which case the depth shall be as ordered by the Engineer in charge.

5. Where waters is met with in excavation due to stream flowm seepage springs , raing or ther reasons, the contractor shall take adequate measures such as bailing pumping , constructing , diversion channels drainage channels and other necessary work to keep the foundation trenches dry when so required and to protect green concrete/masonry against damage by erosion or sudden rising of wate level. The method to be accepted in the regard and other details there of shall be left to the choice of the contractor but subject of approval of the engineer in charge. Approval of the Engineer in charge shall, however not relieve the contractor of the responsibility for the adequancy of dewatering and protection arragements and for the quality an safety of the work.

6. Pumping from the interior of any foundation enclosures shall be done in such manner as to preclude the prossibility of the movement of water through anyfresh concrete. No pumping shall be permitted durring the placing of concrete or for any period of at leasst 24 hours thereafter, unless it is done from a sitable sump separated from the concrete work by a water tight wall or other similar means.

7. The botton of the foundation shall be leveled both longitudinally and transversely or stepped as directed by the Engineer in charge. Before footing is laid, the surface shall be slightly watered and remmed. In the event of excavation having been made deeper than that shown on the drawings or as otherwise oredered by the Engineer in charge, the extra depth shall be made up with concrete or masonry of the foundation grade at the cost of the contractor , Ordinary filling shall not be used for the purpose of bringing the foundation oto level. If there are any slip or blows in the excavation these shall be removed by the contractor at his own cost.

8. Near towns , villages and all frequented plances , trenches and foundation pits shall be securely fenced, provided with proper caution signs and marked with red lights at night to avoid accidents. The contractor shall gbe required to take adequate protective measures to see that the excavation operation do not affect or damage adjoining structures.

9. Backfilling shall be done with approved material after concrete or masonry is full set and carried out in such a way as not to cause under thrust on any part of the structure. All space btween foundation masonry or concrete and the sides of excavation shall be refilled to the original surface, maing due allowance for settlement in 250 mm loose layers. Which sahil be watered and compacted.

10. All the excavated materials shall be the property of the Govtrnment where the excavated material is directed to be used in the construction of embankment , it shall be directly deposied at the required locations.
11. All useful materials, not intended for use in the bank, shall bestacked neatly on Government land as directed by the Engineer in charge within 50 metres lead. Unsuitable and surplus materials not intended for use in any part of the road shall be disposed off as directed by the Engineer in charge.
12. Excavation for structures shall be measured in cubic metres for each class of material encontered , limited to the dimensions shown on the drawings or as directed by the Engineer in charge Excavation over increased width , cutting of slopes, shoring , shattering and planking shall be deemed as convenience for the contractor in executing the work and shall not measured and paid for separately.
13. The contract until rate fore for the items for excavation for structures shall be paid in full for carrying out the required operations including.
- (1) Setting out
 - (2) Construction of necessary shoring and bracing and their subsequent removal :
 - (3) Removal of all longs stumps , grubs and other deleterious matter and obstructions for pacing the foundations including trimming of bottoms of excavation :
 - (4) Foundation sealing dewatering including pumping.
 - (5) Backfilling clearing up the site and disposal of all surplus material within all lifts and leads upto 100 metres :
 - (6) All lobour, material, tools, equipment, safeguards and incidentals necessary to completed the work to the specification .
14. Excavation shall be for ordinary soil such as vegetable or organic soil, turt slit, and loam , clay mud, plat, black cotton soil, soft shale or soft murrum a mixture of these and similar material which yields other ordinary application of pick and shovel rake of other ordinary digging equipment. Removal of gravel or any other nodular material having diametre in any one direction not exceeding 75 mm occurring in such strata shall bedeemed to be covered under this category.

The classification of excavation shall be decided by the Engineer in charge and his decision shall be final and binding on the contractor,

(B) -DO- in dense or hard soil

Specifications shall be same except that the work shall be carried out in strata like dense or hard soil. The work shall be carried out in workmanship like manner.

Useful material available from excavation should be stacked properly and reused as directed and remaining materials should be disposed as directed. Rate should be paid on cubic metre basis.

ITEM NO.14

Providing and laying rubble for apron (Each stone weighting not less than 40kg) including and packing and filling in the interstices with quarry spall.

1. The work shall consist of laying boulders directly on the prepared surface for protection against scour.

2. The stones used in apron shall be sound, hard, durable & fairly regularly in shape, Stone subject to marked deterioration by water or weather shall not be used. The thickness and shape of apron shall be as indicated on the drawings or as directed by the Engineer-in-charge. The surface on which the apron is to be laid shall be leveled and prepared for the length and width as shown on the drawings. The size of stone shall

be as large as possible & weight shall be as specified in the item but in no case any fragment shall weight less than 40kg. The specific gravity of stone shall be as high as possible and it shall not be less than 250. To ensure regular and orderly disposition of the full intended quantity of stone in the apron, template cross walls in dry masonry shall be built about a metre wide and to the full height of the specified thickness of the apron at intervals of 30 metres and all along the length and width of the apron. Within these walls, the stone then shall be hand-packed.

3. Payment shall be made on CMT basis of chata, the materials shall have to be stacked at site before laying. Preparation of base for laying bedding shall be deemed incidental to the work Nothing shall deducted for voids.

4. The rate shall include cost of materials, labour & tools to complete the job.

ITEM NO.15

Providing and laying cement concrete 1:3:6 (1-Cement : 3- coarse sand : 6- hand broken stone aggregates 40 mm nominal size) and curing complete excluding cost of formwork in (A) Foundation and plinth.

MATERIALS : Specification for all the ingredients to be used shall be as per the details in the central specification for materials attached.

PROPORTION : The concrete shall consist of the part of cement, sand and metal as per 1:40 to 63mm. size) the above description of items.

MIXING : Mixing of the materials shall be done as for specified volume metre proportion as a possible after water is added, so that every place of aggregate is uniformly coated by cement plaster. The concrete must be used immediately after it is prepared and in any case shall not be used after the cement has attained final set. Generally concrete prepared before more than half an hour shall not be permitted to be used.

LAYING : Consolidation shall be rapidly carried out sufficient labour being employed to permit of ramming reading be spreading etc. being compacted within as short items as possible causing the mortar to cream up in no case shall ramming be prolonged after the cement has been to take its initial sets.

CURING : As soon as the concrete has set sufficiently i.e. after about an hour of laying the surface must be protected from rapid curing out by being covered with at sand wet sunny of where possible curing shall done by forming the shall be allowed pools of water by means of sand pollics. The curing shall be continued or atleast 10 (ten) days broadly two or three weeks and where possible for longer period. The rate includes all necessary equipment, labour etc. payment shall be made on cubic measurement of cement concrete. The entire work shall be carried out as per the specification of the PWD Hand book Vol.1 Page No. 166 to the satisfaction of the Engineer-in-Charge.

PAYMENT : The Payment will be made on Cmt. Basis of the finished work.

RATE : The Unit Rate for concrete shall include the cost of material, labour, tools and plants. Required for mixing, placing in position, compacting, finishing, curing and all other incidental expenses for producing concrete of specified grade to complete structure or its components as shown on drawing including cost of formwork.

ITEM NO.16

Providing and casting in situ ordinary cement concrete M-150 mix and providing necessary pin headers including shuttering, scaffolding, laying vibrating, curing and finishing complete Without V-Grooves For all Height.

1. In case of ordinary concrete, mix is not required to be designed by preliminary tests and proportion of cement, fine aggregate and coarse aggregates are specified by volume as given in table below for different grades of concrete designed as ordinary M. 100. , M. 150, M.200 and M.250.

2. In the designation of a concrete mix. letter “M” refers to the mix and the number the specified 28 days works cube compressive strength of that mix on 150mm cubes expressed in kg./cm².

3. The ordinary concrete mix shall generally be specified by volume. For cement which normally comes in bags and is used by weight, volume shall be worked out taking 50kg. of cement as 0.035 cubic metre in volume. While measuring aggregate by volume, shaking, ramming or hammering shall not be done. Proportioning of sand shall be as per its dry volume. In case it is dump, allowance for “bulking” shall be made as per IS: 2386 (Part-III).

4. Ingredients required for ordinary concrete containing one 50 kg bag of cement of different proportions of mix shall be as given in Table below.

TABLE

Grade of Concrete	Mix By Volume	Total quantity of dry aggregates by volume per 50 Kg. of cement, to be taken as sum of the individual volumes of fine and coarse aggregates max.,	Proportion of fine aggregate to coarse aggregate	Quantity of water per 50 kg. of cement max.
1	2	3	4	5
Ordinary M.100	Litres 1:3:6	300	General 1:2 for fine aggregate to coarse aggregate by volume but subject to a upper limit of 1:1.1/2 & 2 lower limit of 1:3	Litres 34
M.150	1:2:4	220		32
M.200	1:1 ½:3	160		30
M.250	1:1:2	100		27

NOTE:- The proportions of the aggregates shall be adjusted from upper limit to lower limit progressively as the grading of the fine aggregates becomes finer & the maximum size of coarse aggregate becomes larger.

Example:- For an average grading of fine aggregate (that is Zone II of IS: 383-1963) the proportions shall be 1: 1 1/2, 1:2 and 1:3 for maximum size of aggregates 10mm, 20mm, and 40mm respectively (after carrying out sieve analysis).

Note-2 A mix leaner than M.100 (1:3:6) may be used for non-structural parts, if provided in the contract. In such case gading of aggregates shall be by volume. Other requirements for mixing, placing & curing shall be the same.

5. Following shall be the maximum nominal size of coarse aggregate, for the different items of work:

Sr. No.	Item of Construction	Maximum nominal size of coarse aggregate
(i)	R.C.C. well curb, R.C.C. well steining and R.C.C. Piles	40mm
(ii)	R.C.C. well steining	63mm
(iii)	Well cap or pile cap; solid type piers, abutment and wing-walls, and their pier caps	40mm
(iv)	R.C.C. Works in cross girders deck slab, wearing coars, kewrb, light posts, blast walls, approach slab etc. and hollow type piers, abutments, wing-walls and their pier caps.	20mm
(v)	R.C.C. bearings	20mm
(vi)	For any other item of construction not covered by item (i) to (v)	As specified on the drawing or as desired by the Engineer- in-charge in case it is not specified on drawing.

For heavily reinforced concrete members as in the case of ribs of main beams nominal maximum size of aggregate shall usually be restricted to 5 mm. Less than the minimum lateral clear distance between the main bars or 5mm less than the minimum cover to the reinforcement, whichever is the smaller.

6. Fine aggregate shall be clean, hard, coarse sand, It shall be free from dust and such other substances. The sand be got approved by the Engineer-in-charge.

7. All materials shall be stored as to prevent their deterioration or instruction of their quality and fitness for the work. Any material which has deteriorated or has been damaged or is otherwise considered defective by the Engineer-in-charge shall not be used in the works.

8. Cement shall be stored above the ground level in perfectly and water tight shed. Wherever bulk storage containers are used, their capacity should be sufficient to cater to the requirements at site and should be cleaned at least once every 3 to 4 months. The aggregate shall be stored in such a way as to prevent admixture of foreign materials. Different size of fine or coarse aggregate shall be stored in separate stock-piles sufficiently away from the each other to prevent intermixing the materials.

9. The water for mixing shall be potable water to satisfaction of the Engineer-in-charge. The quantity of water shall be just sufficient to produce a dense concrete of required workability for the job.

10. For all work concrete shall be mixed in a mechanical mixer which along with other accessories shall be kept in first class working condition and so maintained through the construction. Mixing shall be continued till materials are uniformly distributed and uniform colour of the entire mass is obtained and each individual particle of the coarse aggregate show complete coating of mortar containing its proportionate amount of cement, In no case shall the mixing be done for less than 2 minutes after all ingredients have been put into the mixer.

11. When hand mixing is permitted by the Engineer-in-charge for small jobs or for certain other reasons. It shall be done on a smooth watertight platform large enough to allow efficient turning over of the ingredients of concrete before and after adding water. Mixing platform shall be so arranged that no foreign materials shall get mixed with concrete nor does the mixing water flow out. Cement in required number of bags shall be placed in a uniform layer on top of the measured quantity of fine and coarse aggregate, which shall also be spread in a layer of uniform thickness on the mixing platform. Dry coarse and fine aggregate and cement shall then be mixed thoroughly by turning over to get a mixture of uniform colour. Enough water shall then be added gradually through a rose can and the mass turned over till a mix of required consistency is obtained. In hand mixing quantity of cement shall be increased by 10 per cent above that specified.

12. Mixers which have been out of use for more than 30 minutes shall be thoroughly cleaned before putting in a new batch. Unless otherwise agreed to be the Engineer-in-charge, the first batch of concrete from the mixer shall contain only two thirds of normal quantity of coarse aggregate. Mixing plant shall be thoroughly cleaned before changing from one type of cement to another.

13. The method of transporting and placing concrete shall be approved by the Engineer-in-charge. Concrete shall be so transported and placed that no contamination, segregation or loss of its constituent materials takes place. All form work and reinforcement contained in it shall be cleaned and made free from standing water, dust, snow or ice immediately before placing of concrete. No concrete shall be placed in any part of the structure until the approval of the Engineer-in-charge has been obtained.

14. If concreting is not started within 24 hours of the approval given, it shall have to be obtained again from the Engineer-in-charge. Concreting being given, it shall proceed continuously over the area between construction joints. Fresh concrete shall not be placed against concrete which has been in position for more than 30 minutes unless a proper construction joint is formed. Concrete shall be compacted in its final position within 30 minutes of its discharge from the mixer unless carried in properly design agitators, operating continuously, when this time shall be with 2 hours of the addition of cement to the mix and within 30 minutes of its discharge from the agitator. Except where otherwise agreed to be the Engineer-in-charge, concrete shall be deposited in horizontal layers to a compacted depth of not more than 0.45 metre when internal vibrators are used and not exceeding 0.30 metre in all other cases.

15. Unless otherwise agreed to by the Engineer-in-charge concrete shall not be dropped into place from a height exceeding 2 metres. When trunking or chutes are used they shall be kept clean and used in such a way as to avoid segregation. When concreting has to be resumed on a surface which has hardened, it shall be roughened, swept, clean, thoroughly wetted and covered with a 13 mm thick layer of mortar composed of cement and sand in the same ratio as in the concrete mix itself. This 13mm layer of mortar shall be freshly mixed and placed immediately before placing of new concrete. Where concrete has not fully hardened, all laitance shall be removed by scrubbing the wet surface with wire or bristle brushes, care being taken to avoid dislodgement of any particles of coarse aggregate. The surface shall then be thoroughly wetted, all free water removed and then coated with neat cement grout. The first layer of concrete to be placed on this surface shall not exceed 150mm in thickness, and shall be well rammed against oldwork particular attention being given to corners and close spots.

16. All concrete shall be compacted to produce a dense homogeneous mass with the assistance of vibrators, unless otherwise permitted by the Engineer-in-charge for exceptional cases, such as concreting under water, where vibrators can not be used, Sufficient vibrators in serviceable condition shall be kept at site so that spare equipment is always available in the event of break downs.

17.. immediately after compaction, concrete, shall be protected against harmful effects of weather, including rain, running water, shocks, vibration, traffic, rapid temperature changes, frosts and driving out process. It shall be covered with wet sacking, hessian or other similar absorbent material approved by the Engineer-in-charge soon after the initial set, and shall be kept continuously wet for a period of not less than 14 days from the date of placement. Masonary work over the foundation concrete may be started after 48 hours of its laying but the curing of concrete shall be continued for a minimum period of 14 days.

18. Formwork shall include all temporary or permanent forms required for forming the concrete, together with all temporary construction required for their support. Formwork shall however be divided into following two district categories:-

(1) Shuttering i.e. form work required for forming the concrete.

(2) Scaffolding i.e. form work required for supporting shuttering.

Forms for shuttering shall be constructed only in metal suitable lined. Forms for scaffolding shall be constructed for metal or timber. Both shuttering and scaffolding shall be of substantial rigid construction and shuttering shall be true to shape and dimensions shown on the drawings. All bolts and rivets shall be counter-sunk and well ground to provide a smooth, level surface.

19. Forms shall be mortar-tight and shall be made sufficiently rigid by the use of ties and bracings to prevent any displacement or sagging between supports. They shall be strong enough to withstand all pressure, ramming and vibration, without deflection from the prescribed line occurring during and after placing the concrete. Screw jacks or hard wood wedges where required shall be provided to make up any settlement in the form work either before or during the placing of concrete. Suitable camber shall be provided in horizontal members of structure, specially in long spans to counteract the effects of any fixed loads to provide such camber. Forms shall be so constructed as to be removable in sections in the desired sequence, without damaging the surface of concrete or disturbing other sections. Unless otherwise specified or directed, chamfers or fillets of sizes 25mm x 25mm shall be provided at all angles of formwork to avoid sharp corners.

20. The inside surface of shuttering shall, except in the case of permanent form work or where otherwise agreed to by the Engineer-in-charge, be coated with an approved material to prevent adhesion of concrete to the formwork. Release agents shall be applied strictly in accordance with the manufacturer's instructions and shall not be allowed to come into contact with any reinforcement or prestressing tendons and anchorages. Different release agents shall not be used in formwork for concrete which will be visible in the finished works.

21. Special measures shall be taken to ensure that the formwork does not hinder the shrinkage of concrete because without these cracking could occur before the formwork is removed. Wherever applicable arrangements must be made to ensure that the formwork does not restrain the shortening and hogging of the beams or slabs during tensioning of the tendons. The formwork should take due account of the calculated amount of positive or negative camber so as to ensure the correct final shape of the structures having regard to the deformation of falsework, scaffolding or propping and the instantaneous or deferred deformation due to various causes affecting prestressed structures. Where there are re-entrant angles in the concrete sections the formwork should be removed at those sections as soon as possible after the concrete has set in order to avoid cracking due to shrinkage of concrete. Formwork shall be tight enough to prevent

any appreciable loss of cement during vibrations, suitable tolerances should be provided in the formwork. Immediately before concreting all forms shall be thoroughly cleaned. Contractor shall give the Engineer-in-charge due notice before placing any concrete in the forms to permit him to inspect and accept the formwork and forms as to their strength alignment and general fitness, but such inspection shall not relieve the contractor of his responsibility for safety of men, machinery, materials and or results obtained.

22. The Engineer-in-charge shall be informed in advance by the contractor of his intention to strike any formwork. While fixing the time for removal of formwork, due consideration shall be given to local conditions, character of the structure, the weather and other conditions that influence the setting of concrete and of the materials used in the mix. Where field operations are controlled by strength tests of concrete, the removal of the load-supporting or soffit forms may commence when concrete has attained strength equal to at least twice the stress to which the concrete will be subjected at the time of striking props including the effect of any further addition of loads. When field operations are not controlled by strength tests of concrete the vertical forms of beams, columns and walls may be removed after 2 days. The props of slabs and beams may be removed after 14 and 21 days respectively. All formwork shall be removed without causing any damage to the concrete. Centering shall be gradually and uniformly lowered in such a manner as to permit the concrete to take stresses due to its own weight uniformly and gradually. Where internal metal ties are permitted, they or their removable parts shall be extracted without causing any damage to the concrete and remaining holes filled with mortar. No permanently embedded metal part shall have less than 25 mm. cover to the finished concrete surface. Where it is intended to reuse the formwork, it shall be cleaned and made good to the satisfaction of the Engineer-in-charge.

23. Immediately after the removal of forms, all exposed bars or bolts passing through the concrete member and used for shuttering or any other purposes shall be cut inside the concrete member to a depth of at least 25mm. below the surface of the concrete and the resulting holes be filled by cement mortar. All fins caused by form joints, all cavities produced by the removal of form ties and all other holes and depressions, honeycomb spots, broken edges or corners and other defects, shall be thoroughly cleaned, saturated with water and carefully pointed and rendered true with mortar of cement and fine aggregate mixed in the proportions used in the grade of concrete that is being finished and of as dry as consistency as is possible to use, considerable pressure shall be applied in filling and pointing to ensure thorough filling in all voids, surface which have been pointed shall be kept moist for a period of twenty four hours. If rock pockets/ honeycombs, in the opinion of the Engineer-in-charge are of such an extent or character as to affect the strength of the structure materially or to endanger the life of the steel reinforcement, he may declare the concrete defective and require the removal and replacement of the portions of the structure affected.

24. In the case of reinforced concrete work workability shall be such that the concrete surrounds and properly grips all reinforcement. The degree of consistency, which shall depend

upon the nature of work and methods of vibration of concrete shall be determined by regular slump testes. Following slump shall be adopted for different types of works.

Type of work		Where vibrators are used	Slumps Where vibrators are not used
(i)	Mass concrete in R.C. C. foundations, footings and retaining walls	10mm to 25mm	80mm
(ii)	Beams, slabs and columns simply reinforced	25m to 40mm	100mm to 120mm
(iii)	Thin R.C.C. section or section with congested steel	40mm to 50mm	125mm to 150mm

25. Works strength tests shall be made in accordance with IS:516. Each test shall be conducted on ten specimens, five of which shall be tested at seven days and the remaining five at 28 days. The samples of concrete shall be taken on each day of concreting and cubes shall be made at the rate of one for every 5 cubic metre of concrete or a part thereof. However, if concreting done in a day in less than 15 cubic metree, the minimum number of cubes can be reduced to 6 with the specific permission of the Engineer-in- charge, similar works tests shall be carried out whenever the quality and grading of materials is charged irrespective of the quantity of concrete proud. The number of specimens may be suitably increased as deemed necessary by the Engineer-in- charge when procedure of tests given above reveal a poor quality of concrete and in other special cases.

26. The average strength of the group of cubes cast for each day shall not be less than the specified works cube-strength. 20 per cent of the cubes cast for each day may have values less than the specified strength, provided the lowest value is not less than 85 per cent of the specifies strength.

27. R.C.C. work shall have exposed concrete surface. Centering design and its erection shall approved by he Engineer-in- charge. One carpenter with helper will invariably be kept present throughout the period of concreting. Movement of labour and other persons shall be totally prohibited over reinforcement laid in position. For access to different parts, suitable mobile platforms shall provided so that steel reinforcement in position is not disturbed. For ensuring proper cover, motar blocks of suitable size shall be cast and tied to the reinforcement. Timber, kapchi, or matal pieces shall not be used for this purpose. Concreting of important structural members shall always be done in the presence and under the supervision of department person not below the rank of Astt. Engineer/ Addi-Astt. Engineer Overseer or as instructed by the

Engineer-in-charge. After removal of form work checks that concrete produced is of good quality. Plastering shall not be allowed to the exposed faces of concrete.

28. In reinforced concrete the volume occupied by reinforcement shall not be deducted. The slab shall be measured as running continuously through and the beam as the portion below the slab.

29. All necessary labour, materials equipment, etc. for sampling, preparing test cubes, curing etc., shall be provided by the Contractor. Testing of the materials and concrete may be arranged by Engineer-in-charge in an approved laboratory at the cost of the contractor.

30. The payment will be made on cmt. basis of the finished work.

31. The unit rate for concrete shall include the cost of all materials, labour, tools and plan required for mixing, placing in position, vibrating and compacting finishing as per directions of the Engineer-in-charge, curing and all other incidental expenses for producing concrete of specified strength to complete the structure or its components as shown on the drawings and according to these specifications. The rate shall also include the cost of making/fixing and remixing of all centers and forms required for the work.

ITEM NO.17

Construction of concrete road using tremix system with 20cm/15cm thick controlled M-250 concrete mixing conplast P-211 water reduction admixture @ 100ml/bag of cement and hardner 62.50ml./bag using fixing and removing "C" channels of required road depth levelling if placed concrete with surface vibrator, finishing the surface with power floater and towel tight brooming as directed with providing expansion joints 20x200mm and contraction joints 20x20mm using concrete cutter machine etc. complete.[PQC]

MATERIALS :

Water:

- 1.1 Water shall not be salty or brackish and shall be clean, reasonably clear and free from objectionable quantities of silt and traces of oil and injurious alkalis, salts, organic matter and other deleterious material which will either weaken the mortar or concrete or cause efflorescence or attack the steel in R.C.C. Container for transport, storage and handling of water shall be clean. Water shall conform to the standards specified in LS. 456-1978.
1. If required by Engineer-in-charge it shall be tested by comparison with distilled water. Comparison shall be made by means of standard cement tests for soundness, time of setting and mortar strength as specified in LS. 269-1976. Any indication of unsoundness, change in time of setting by 30 minutes or more or decrease of more than 10 per cent in strength of mortar prepared with water sample when compared with the results obtained with mortar prepared with distilled water shall be sufficient cause for rejection of water under test.

2. Water for curing mortar, concrete or masonry should not be too acidic or too alkaline. It shall be free of elements which significantly affect the hydration reaction or otherwise interfere with the hardening of concrete during curing or those which produce objectionable stains or other unsightly deposits on concrete or mortar surfaces.
3. Hard and bitter water shall not be used for curing.
4. Potable water will be generally found suitable for curing mortar or concrete.

Cement:

Cement shall be ordinary Portland slag cement as per I.S. 269-1976 or Portland slag cement as per I.S. 455-1976.

Sand:

mm Sand shall be natural sand, clean, well graded, hard strong durable and gritty particle free from injurious amounts of dust clay, kankar nodules, soft or flaky particles shale, alkali; salts organic, matter, loam, mica or other deleterious substance and shall be got approved from the Engineer-in-charge. The sand shall not contain more than 8 percent of silt as determined by field test, if necessary the sand shall be washed to make it clean.

nn Coarse Sand:

The fineness modulus of coarse sand shall not be less than 2.5 and shall not exceed 3.0.

The sieve analysis of coarse shall be as under:

I. S. Sieve Designation	Percentage by weight passing Sieve	I. S. Sieve Designation	Percentage by weight passing Sieve
----------------------------	--	----------------------------	--

4.75 mm	100	600 micron	30-10
2.36 mm	90 to 100	300 micron	5-70
1.18 mm	70 to 100	150 micron	0-50

A Fine Sand:

The fineness modulus shall not exceed 1.0. The sieve analysis of fine sand shall be as under

I. S. Sieve Designation	Percentage by weight passing Sieve	I. S. Sieve Designation	Percentage by weight passing Sieve
4.75 mm	100	600 micron	40-85
2.36 mm	100	300 micron	5-50
1.18 mm	70 to 100	150 micron	0-10

Stone Grit:

1.1 Grit shall consist of crushed or broken stone and be hard strong, dense, durable, clean, of proper gradation and free from skin or coating likely to prevent adhesion of mortar. Grit shall generally be cubical in shape and as far as possible flaky elongated pieces shall be avoided. It shall generally comply with the provisions of I.S. 383-1970. Unless special stone of particular quarries is mentioned, grit shall be obtained from the best black trap or equivalent hard stone as approved by the Engineer-in-charge. The grit shall have no deleterious reaction with cement.

1.2 The grit shall conform to the following gradation as per sieve analysis:

I.S. Sieve Designation	Percentage by weight passing through sieve
12.50 mm	100%
10.00 mm	85-100%
4.75 mm	0-20%
2.36 mm	0-25%

1.3 ~~The crushing strength of grit will be such as to allow the concrete in which it is used to built-up the specified strength of concrete.~~

1.4 The necessary tests for grit shall carried out as per the requirements of I.S. 2386 (Parts I to VII) 1963, as per instructions of the Engineer-in-charge. The necessity of test will be decided by the Engineer-in-charge.

Stone Aggregate for Concrete:

- 1.1 Coarse aggregate shall be machine crushed stone of black trap or equivalent and be hard, strong, dense, durable, clean and free from skin and coating likely to prevent proper adhesion of mortar.
- 1.2 The aggregate shall generally be cubical in shape. Unless special stones of particular quarries are mentioned aggregates shall be machine crushed from the best black trap or equivalent hard stone as approved. Aggregate shall have no deleterious reaction with cement. The size of the coarse aggregate for plain cement concrete and ordinary reinforced cement concrete shall generally be as per the table given below. However in

case of reinforced cement concrete the maximum limit may be restricted to 6 mm. less than the minimum lateral clear distance between bars or 6 mm. less than the cover, whichever is smaller.

TABLE

I.S. Seive	Percentage passing for single sized aggregates of Nominal size			I.S. Seive	Percentage passing for single sized aggregates of Nominal size		
	40 mm	20 mm	10 mm		40 mm	20 mm	10 mm
80 mm	-	-	-	12.50 mm	-	-	-
63 mm	100	-	-	10 mm	0.5	0.02	0.30
40 mm	85-100	100	-	4.75 mm	-	0.5	0.5
20 mm	0-20	85-100	100	2.35 mm	-	-	-
16 mm	-	-	85-100				

Note: This percentage may be varied some what by Engineer-in-charge when considered necessary for obtaining better density and strength of concrete.

- 1.3 The grading test shall be taken in the beginning and at the change of source of materials. The necessary test indicated in I.S. 383-1970 and I.S. 456-1978 shall have to be carried out to ensure the acceptability. The aggregates shall be stored separately and handled in such a manner as to prevent the intermixing of different aggregates. If the aggregates are covered with dust, they shall be washed with water to make them clean

CONPLAST-P.211 water reducing concrete admixture & Recron-35 fibbers shall be of approved quality. Colpor-200 expansion joints materials shall be of approved quality.

WORKMANSHIP

- [i] 200mm thicker M-250 grade concrete is being placed over the prepared sub-base Conplast P.211 (Water reducing concrete admixture) @ 100 Mt. per bag of cement and Racron-3s fibers Polyester fibre of Reliance or equivalent make at 125 Gms per bag of cement shall be used in M-250 concrete mix. [The specification of concrete is as Given below]

- [ii] Leveling of the surface is done using TREMIX surface vibrator. The vibrator runs over channels, placed as per required level and slope and simultaneously level surface of the concrete.
- [iii] Vacuum dewatering follows the leveling of concrete. The purpose of vacuum processing is to provide quicker setting and high early strength by removing surplus water from the concrete. The process is followed as per instruction of site Engineer in charge & attached guide line.
- [iv] Immediately after dewatering, the surface is floated with a skim power floater as per instruction of Engineer-in-charge. The surface shall be prepared as per requirements and instructions. For smoother surface requirement, the surface is trowel with same machine mounted with trowel ling blades. If required floor hardener "Nitoflor Hardtop" a Fostoc product shall be used at the rate of 3 to 5 Kg/Sqm to get hard wearing surface.

- [v] Construction joints upto 1/4 of the slab depth are cut afterwards. They give clear and straighter theoretical cracking line in the case of unexpected stresses. m Groove cutting is done within 48 hours from casting at the floor.
- [vi] After surface vibrator and finishing the surface with power floater and trowel light brooming on the surface, expansion joint size 20 x 200 MM shall be provided with filling the expansion joints having size 20 x 20 MM by using COLPOR-200 as per manufacturers specification and directed by Engineer-in-charge. The expansion joints filled with Nitoseal-200.
- [vii] Making a construction joints by cutting of joints of size 3 MM x 20 MM by using of concrete cutter machine construction joint are filled with "MITOSEAL-280" an esoteric cold applied joint sealant, which ensures performance of expected functions at the joints.
- [viii] Concrete should be cured in normal way (Water pending) or the surface is covered with a plastic sheet or gunny bags. In any method, the surface should be always kept wet with water. Curing must be done for atleast 14 days or as per directed by Engineer-in-charge.
- [ix] The machineries used for the above process shall be of standard technical specification attached separately herewith. (i.e. surface vibrator, vacuum pump,suction mal top cover, filter pad, skim floater etc.)
- [x] The Workmanship and process for vacuumed dewatering, water cement ratio concrete placing, surface vibration and vacuum processing floating. Trowel ling and curing shall be carried out as per attached literatures and as per instruction of Engineer-in-charge.
- [xi] The dowel bars of 30mm CRS reinforcement bars of 450mm long shall be field in 32mm dia G.I. pipe cap at free end with filling grade etc. in longitudinal joints at 30cm centre to centre
and transverse joints at 30 mt. interval as directed engineer in charge.

ATTACHED ADDED TECHNICAL SPECIFICATION

A. SURFACE VIBRATOR

Beam Lengths (meters) :4.2 meters

Weights (Kgs) : 41 Kgs

Beam Spacing (mm) : 300

Beam Height (mm) : 100

Vibrator Unit : Elecrctically operated on 3 Phase V, 415V, 50Hz. A.C. Supply

Power input (Walls) : 450

Vibrator (Vib/min) : 2860

Rated current (Amp.) :1.5

Centrifugal Force (N) : 1350-4600

Weight (Kg) :19

B. VACUUM PUMP

Drive : Electrically operated on 3 Phase V, 415V,50Hz. A.C. Supply

Power (Kw) : 4

Current : 7.5

Pump Capacity (Lit/Min) : 1850

Max. Vacuum(mm Hg) : 680(90%)

Overall Length (mm) : 1300

Overall Width (With empty Tank): 125

C. SUCTION MAT TOP COVER

Length : 6 Width
: 4 Weight (Kg) :
31

D. FILTER PAD

Length / Pieces (Mt.) : 6
Width : 1.2

Weight (Kg) : 4

E. SKIM FLOATER

Supply : 3 Phase V, 415V,50 Hz.A.C.Supply
Power (Kw) : 2.1/1.8

Current(Amp.) : 6/4

Motor Speed (rpm) : 3000/1500

Final Speed (rpm) : 115/57

Working Diameter (mm) : 1000

Max.Reach (Meter) : 3

Diameter of Floating Disc(mm):985

Weight of Floating Disc(Kg) :16

MODE OF MEASUREMENT :

- [i] The rate shall be include all materials, formworks, machineries and labour charges.
- [ii] The rate shall be for a unit of One Sq.m.

Specification of ordinary C.C. M-250

1 In case of ordinary concrete, mix is not required to be designed by preliminary tests and proportions of cements fine aggregates and coarse aggregates are specified by volume as given table for different grades of concrete designed as ordinary M-100, M -150, M-200, and M-250

2. In the designation of a concrete mix, letter 'M' refers to the mix and the specified 28 days works cube compressive strength of that mix on 150 mm cubes expressed in Kg/Cm² 3. The ordinary concrete mix shall generally be specified by volume. For cement which Normally comes in bags and is used by weight volume shall be worked out taking 50 kg. Of cement as 0.035 cubic meter in volume. While measuring aggregate by volume, shaking, ramming or hammering shall not be

done. Proportioning of sand shall be as per its dry volume. In case it is dump allowance for "Bulking" Shall be made as per IS: 2386 (Part - III)

4. Ingredients required ordinary concrete contracting one 50kg bag of cement of different.

Proportions mix shall be as given in table below.

TABLE

Grade of Concrete	Mix by Volume	Total quantity of dry aggregates by volume	Proportion of grade coarse of aggregate	Quantity of water
------------------------------	--------------------------	---	--	------------------------------

		per 50kg. of cement to be taken as sum of the individual volumes of fine and coarse aggregates max		per 50 kg of cement max
1	2	3	4	5
(1 Cubic Meter means 1000 Liters)				
Ordinary	Liters			Liters
M-100	1:3:6	300	Generally 1:2 for fine aggregate to coarse aggregate by volume but subject to a upper limit of 1:1 ½ & a lower limit of 1:3	34
M-150	1:2:4	220		32
M-200	1:1.1/2 :3	160		30
M-250	1:1:2	100		27

Note-1 The proportion of the aggregates shall be adjusted from upper limit to lower limit progressively as the grading of the fine aggregates finer & the maximum size of coarse aggregates becomes larger

Example:- For an average grading of fine aggregate (That is zone II of IS: 383 1963) The proportion shall be 1:1 1/2 , 1:2 and 1:3 for maximum size of aggregate 10mm 20mm and 40mm respectively (after carrying out sieve analysis)

Note-2 A mix leaner than M-100 (1:3:6) may be use non structural parts, it provided, if provided in the contract in such case grading of aggregate shall be by volume. Other requirement for mixing placing & curing shall be the same

5. Following shall be the maximum nominal size of coarse aggregate for the different items of work

Sr. No.	Item of construction	Maximum nominal size of coarse aggregate
---------	----------------------	--

(i)	RCC well curb, RCC well staining and RCC pipes	40 mm
(ii)	RCC well staining	63 mm
(iii)	Well cap or pile cap, solid type piers abutments and wing walls and their pier caps	40 mm
(iv)	RCC works in cross girders deck slab, wearing coarse curb, light, ballast walls, approach slab etc and hollow types pier, abutments wings walls and their pier caps	20 mm

(v)	R.C.C. bearings	20 mm
(vi)	For any other item of construction not covered by items (i) to (v)	As specified on the drawing or as desired by the Engineer - in -charge in case it is not specified on drawing.

For heavily reinforced concrete members as in case of ribs of main beams nominal maximum size of aggregate shall usually be restricted to 5 mm less than the minimum lateral clear distance the main bars or 5mm less then minimum cover reinforcement, whichever is the smaller.

6. Fine aggregate shall be clean hard coarse sand. it shall be free from dust and that substance. The sand shall be got approved by Executive -in-charge.
7. All materials shall be stored as to prevent their deterioration or intrusion of their quality and fineness for the work, any materials which has deteriorated or has been damaged or otherwise considered defective by the Engineer -in-charge shall not be used in the works.
8. Cement shall be stored above the ground level in perfectly dry and water tight sheds. Whatever bulk storage containers are used. Their capacity should be sufficient to cater to the requirements at site and should be cleaned at least once every 3 to 4 months. The aggregate shall be stored in such a way as to prevent admixture of foreign materials. Different sizes of coarse aggregate shall be stored in separate stock -piles sufficiently away from the catch other to prevent intermixing the materials
9. The water for mixing shall be potable water to satisfaction for the Engineer-in-charge. The quantity of water shall be just sufficient to produce a dense concrete of required work ability the job.
10. For all work concrete shall be mixed in a mechanical mixer which with accessories shall be kept first class working condition and so maintained throughout the construction. Mixing shall be continued till material are uniformly distributed and uniform color of the entire mass is obtained and each individual particle of the coarse aggregate show complete coating of mortar containing its proportionate amount of cement in no case shall the mixing be done for less then 2 minutes after all ingredients have been put into the mixer.

11. When hand mixing is permitted by the Engineer -in-charge for small jobs or for certain reasons it shall be done on smooth a water tight platform large enough to allow sufficient turning or of the ingredient concrete before and adding water. Mixing platform shall be so arranged than no foreign material shall get mixed with concrete not does the mixing water flow out. Cement in required number of bags shall get placed in a uniform layer on top of the measured quantity of fine and coarse aggregate, which shall also be spread in layer of uniform thickness by turning over to

get mixture of uniform color. Enough water shall than be added gradually thoroughly through a rose can and the mass turned over till a mix for required consistency is obtained. In hand mixing quantity of cement shall be increased by 10 percent above that specified.

12. Mixers which have been out of use for more than 30 minutes shall thoroughly clean before putting in a new batch. Unless otherwise agreed by the Engineer -in-charge, the first batch of concrete from the mixer shall contain only two thirds of normal quantity of coarse aggregate Mixing plant shall be thoroughly cleaned before changing from one type of cement of another.

13. The method of transporting and placing concrete shall be approved by the Engineer -in-charge. Concrete shall be so transported and placed that no contamination segregation or loss of its constituent material takes place all form work and reinforcement contained in it shall be cleaned and made free from standing water, dust, snow or ice immediately before placing of concrete .No concrete shall be placed in any part of the structure until the approval of the Engineer-in-charge has been obtained.

14. In concrete is not started within 24 hours of the approval being given, it shall have to be obtained again from the Engineer-in-charge, Concreting than shall proceed continuously over the area between construction points. Fresh concrete shall not be placed against concrete which has been in position for more than 30 minutes unless a proper construction joints is formed. Concrete shall be compacted in its final position within 30 minutes of its discharge from the mixture unless carried in properly design agitators operating continuously, when this time shall be within 2 hours of

the addition of cement to the mix and within 30 minutes of its discharge from the agitator. Except where otherwise agreed to by the Engineer-in-charge. Concrete shall be deposited in horizontal layers to a compacted depth of not more than 0.45 meter when internal vibrators are used and not exceeding 0.30 meter in all ceases.

15 Unless otherwise agreed to by the Engineer -in-charge concrete shall not be drooped

into place from a height exceeding 2 meters. When trucking or chutes are used they shall be kept clean and used in such a way as to avoid secretion when concreting has to be resumed on a surface which has hardness it shall be roughened swept clean, Thoroughly wetted and covered with a 13 mm thick layer of mortar composed of cement and sand in the same ratio as in the concrete mix

itself. This 13 mm layer of mortar shall be freshly mixed and placed immediately before placing of new concrete where concrete has not fully hardened. All laitance shall be removed by scrubbing the well surface with wire of bristle brushes care being taken to avoid dislodgement of any particles of coarse aggregate. The surface shall then be thoroughly wetted all free removed and then coated with neat cement grout. The first layer of concrete to be placed on this surface shall not exceed 150 mm, and shall be well rammed against old work particular attention being given to corner and close spots.

16. All concrete shall be compacted to produce a dense homogenous mass with the assistance of vibrators, unless otherwise permitted by the Engineer - in - charge for Exceptional cases such as concreting under water, where vibrators can not be used. Sufficient vibrators in serviceable condition shall be kept at site so that spare Equipment is always available in the event of break downs.
17. Immediately after compaction, concrete shall be protect against harmful of washer, including rain, running water shocks, vibration, traffic, rapid temperature charges frost and driving out process. it shall be covered with wet sacking, Hessian or other similar absorbent material approved by Engineer -in-charge soon after the initial set, and shall be kept continuously wet for a period of not less than 14 days from the date of placement. Masonry work over the foundation continued for a minimum period of 14 days.
18. Form work shall include all temporary or permanent forms required for forming the concrete together with all temporary construction required for their support. Form work shall however be divided into following two distinct categories.

(1) Shuttering i.e. Form work required for forming the concrete.

(2) Scaffolding i.e. from work required for supporting shuttering.

Forms for shuttering shall be constructed only in metal suitably lined. Forms for scaffolding shall be constructed of metal or limber. Both shuttering and scaffolding shall be or substantial rigid constructor and shuttering shall be true to shape and dimensions show on the drawings. All bolts and nuts shall be counter-sunk and well ground to provide a smooth, plane surface.

19. Forms shall be mortar - tight and shall be made sufficiently rigid by the use of ties and bracings to prevent any displacement or sagging between supports. They shall be Strong enough to with stand all pressure, ramming and vibration, without deflection from the prescribed lines occurring during and after placing the concrete. Screw jacks or hard wood wedges where required shall be provided to make up any statement in the form work either before of during the placing of concrete. Suitable comber shall be provided in horizontal members of structure, specially in long spans to counteract the effect of any fixed as to provide for such comber. Forms shall be so constructed as to be removable in section in the desired sequence without damaging the surface of concrete or disturbing other section. Unless otherwise specified of

directed chambers or fillets of sizes of 25mm x 25 mm shall be provided at all angles of formwork to avoid sharp corners.

20. The inside surface of shuttering shall except in the case of permanent form work of where otherwise agreed to by the Engineer -in-charge be coated with an approved material to prevent adhesion of concrete to the form work. Release agents shall be applied strictly in accordance with

the manufacture instructions and shall not be allowed to come into contact with any reinforcement or anchorages. Different release agents shall not be used in form work for concrete which will be visible in finished work.

21. Special measures shall be taken to ensure that the form work not hinder the shrinkage of concrete because without these cracking could occur before the form work is removed. Wherever applicable arrangement must be made to ensure that the form work does not restrain the shortening and hogging of the beams or slabs during tensioning of the tendons. The form work should take due account of the calculated amount of positive and negative camber so as to ensure the correct final shape of the structure having regard to the deformation of false work, scaffolding or propping and the instantaneous or deferred before the form work does not restrain the shortening and hogging of the beams or slabs during tensioning of tendons. The form work should take due account of the calculated of positive or negative camber so as to ensure the correct final shape of the structures having regard to the deformation of a false work scaffolding or propping and the instantaneous or deferred deformation due to various the form work should be removed at those section as soon as possible after concrete has set in order to avoid cranking due to shrinkage of concrete. Form work shall be tight enough to prevent any appreciable loss of cement during vibrations suitable tolerances should be provided in the form work. immediately before concreting all forms shall be thoroughly cleaned contractor shall given accept the false work and forms as their strength alignment and general fitness but such inspection shall not relieve the contractor of his responsibility for safety of machinery , materials and for results obtained.
22. The Engineer-in- charge shall be informed in advance by the contractor of his intention to strike any form work. While fixing the time for removal of form work, due consideration shall be given to local conditions, character of the structure the weather and other condition that influence the setting of concrete and of the materials used in mix, Where field operations are controlled by strength test of concrete the removal of the load supporting or soffit forms may commence when concrete has attained stress the which the concrete will be subjected at the time of staking props including the effect of any further addition of loads when field operations are not controlled by strength tests of concrete the vertical forms of beams. Column and walls may be removed after 2 days. The drops of slabs and beams may be removed after 14 and 21 days respectively. All forms work shall be removed without causing any damage to the concrete. Centering shall be gradually and uniformly lowered in such a manner as to permit concrete to take stresses due to its own weight uniformly and gradually where internal metal ties are permitted they or tier removable parts shall be extracted without causing any damage to concrete and remaining holes filled with mortar. No permanently embedded metal part

shall have less than 25 mm cover to the finished concrete surface where it is intended to re-use the form work, it shall be clean and made good to the Engineer – in – charge.

23 Immediately after removal of forms, all exposed bars or bolts passing through the cement concrete member and used for shuttering or any other purpose shall be cut inside the cement concrete member to a depth on at least 25mm. Below the surface of the concrete and the resulting holes be filled by cement mortars, all fines caused by form joints. All cavities produced by the removal to form ties and all other holes and depression honeycomb spots broken edges or corners and others detects shall be thoroughly cleaned started with water and carefully pointed and rendered true with mortar of cement and fine aggregate mixed in the proportion used in the grade of concrete that is being finished and of as dry as consistency as is possible to use. Considerable pressure shall be applied in filling and pointing to ensure thorough filling in all voids. Surface which have been pointed shall be kept moist for a period of twenty four hour if rock pocket/ honeycombs in the opinion of the Engineer – in – charge are of such an extent or character as to affect the strength of the structure materially or to endanger the life of the steel reinforcement he may declare the concrete defective required the removal and replacement of the portion of these structure affected.

23. In the case of reinforced concrete workability shall be such that the concrete surrounds and properly grips all reinforcement. The agrees of consistency which shall depend upon the nature of work and methods of concrete shall be determined by regular slump test following slump shall be adorned for different types of works.

Type of work	slumps	
	where vibrators are used	where vibrators are not used
(i) Mass concrete in R.C.C. Foundations footing and retaining walls.	10 mm to 25 mm	80 mm
(ii) Beams Slabs and columns simply reinforced...	25 mm to 40 mm	100 mm to 120 mm
(iii) Thin R.C.C. Section with congested steel	40 mm to 50 mm	125 mm to 150 mm

25. Works strength test shall be made in accordance with IS: 516 each test shall be conducted on ten specimens, five of which shall be tested at seven days and he remaining five at 28 days. The samples of concrete shall be taken on each day of concreting and cubes shall be made at the rate

of one for every 5 cubic meters of concrete or a part thereof. However, If concreting done in a day is less than 15 cubic meters the minimum number of cubic can be reduced to 6 with the specific permission of the Engineer-in-charge similar words tests shall be carried out whenever the quality

and grading of materials in charged respectively as deemed necessary by the Engineer-in –charge when procedure of tests given above reveals poor quality of concrete and other special cases.

26. The average strength of the group of Cubes cast for cash day shall not be less than the specified works cube – strength 20 per cent of the cubes cast for each day may have values less than the specific strength provided the lowest value is not less than 85 percent of the specified strength.
27. R.C.C. Work shall have exposed concrete surface. Centering design and its erection shall be approved by the Engineer-in –charge. One carpenter with helper will invariably be kept present throughout the period of concreting movement of labour and other person shall be totally prohibited over reinforcement laid in position for access to different parts suitable mobile platforms shall be provided so that steel reinforcement in position is not disturbed for ensuring proper cover mortar blocks of suitable size shall be cast and tied to the reinforcement timber kapchi or metal piece shall not be used for this purpose. Concreting of important structures members shall always be done in the presence and under the supervision of departmental person not below the rank of assistance engineer/additional assistance engineer-overseer or as instructed by the Engineer-in – charge. After removal of form work and shuttering Executive Engineer shall inspect the work and satisfy by random check that concrete produced is of good quality. Plastering shall not be allowed to the exposed faces of concrete.
28. In reinforced concrete the volume occupied by reinforcement shall not be deducted the slab shall be measured as running continuously through and the beams as the portion below the slab.
29. All necessary labour, materials equipment etc. for sampling preparing test cubes curing etc. shall be provided by the contractor. Testing of the materials and concrete may be arranged by the Engineer-in –charge in an approved laboratory at the cost of the contractor.
30. The unit rate for concrete shall include the cost of all materials, labor, tools and plants required for mixing placing in position vibrating and compacting finishing as per direction of Engineer-in –charge curing and all other incidental expenses for producing concrete of specified strength to complete the structure or its components as shown on the drawings and according to these specifications. The rates shall also include the cost of making / fixing and removing of all centers and forms required for the work.

ITEM NO.18

Providing and fixing in position FE 500D TMT bar reinforcement including cutting, bending and tying complete as per detailed drawings. (A) R.C.C. Kerb. (B) R.C.C. Footpath. (C) R.C.C. Approach slab. (D) Wearing Coat.

2.00 Materials :- T.M.T. shall conform to IS : 1786-FE 500 Mild steel binding wires shall conform to the specification.

2.1 The work shall consist of furnishing and placing reinforcement of the shape and dimensions shown on the drawing or as directed by the Engineer-in-charge.

2.2 Steel shall be clean and free from loose rust mill scale at the time of fixing in position and subsequent concreting.

2.3 Reinforcing steel shall conform accurately to the dimensions given iron bar bending schedules shown on relevant drawing. Bar shall be bent cold to the specified shape and dimensions or as directed by the Engineer-in-charge using a proper bar bender, operated by hand or power to attain proper radius of bends. Bars shall not be bent or straightened in manner that will injure the material. Bars bent during transporting or handling shall be straightened before use on work ; they shall not be invariably be provided. The radius of the bend shall not less than twice the diameter of the round bar and length of the straight part of the beyond the end of the curve shall be at least four times the diameter of the round bar. In the case which are not round and in the case of deformed bars, the diameter shall be taken as the diameter of a circle having a equivalent effective area. The work shall be suitably encased to prevent any splitting of the concrete.

2.4 All reinforcement bars shall be accurately placed in exact on the drawings, and shall be securely held in position during placing of concrete by annealed binding wire not less than 1mm, in size and conforming to IS : 280 and by using stay blocks or metal chairs, spacer, metal hangers, supporting wires or other approved device at sufficiently close intervals. Bars will not be allowed to sag between supports or displaced during concreting or any of their operations over the work. All devices used for positioning shall be non-corrodible material. Wooden and metal supports will not extend to the surface of concrete except where shown on the drawings. Placing bars on layers of freshly laid concrete as the work progress or adjusting bar will not be allowed. Pieces of broken stone or brick and wooden blocks shall not be used. Layers of bars shall be separated by spacer bars, precast mortar block, or other approved device. Reinforcement after being placed in position shall be maintained in clean condition until completely embedded in concrete. Special care shall be exercised to prevent any displacement of reinforcement in concrete already placed. To protect reinforcement from corrosion, concrete cover shall be provided as indicated on the drawing. All bars protruding from concrete and to which other bars are to be spliced and which are likely to be exposed for an indefinite period shall be protected by a thick coat of neat cement grout.

2.5. Bars crossing each other, where required shall be secured by binding wire (annealed) of size not less than 1 mm. in such a manner that they do not slip over each other at the time of fixing and concreting.

2.6. As far as possible, bars of full length shall be used. In case this is not possible, overlapping of bars shall be done as directed by the engineer-in-charge. When practicable, overlapping bar shall not touch each other, but be kept apart by 25mm or 1.25 times the maximum size of the coarse aggregate whichever is greater, by concrete between them, Where not feasible, overlapping bars shall be bound with annealed steel wire, not less than 2mm thickness twisted right. The overlaps shall be staggered for different bars and located at points, along the span where neither shear nor bending movement is maximum.

2.7. Whenever indicated on the drawings or desired by the Engineer-in-charge, bar shall be joined by couplings which shall have a cross-section sufficient to transmit the full strength of bars. The end of the bars that are joined by coupling shall be upset for a sufficient length so that the effective cross-section at the base of threads shall be standard with the threads. Steel for coupling shall conform to IS : 226.

2.8. When permitted or specified on the drawings joints of reinforcement bars shall be but welded so as to transmit their full strength. Welded joints shall preferably be located at points where steel will not be subject to more than 75 per cent of the maximum permissible stresses and shall be staggered so that at any one section not more than 20 per cent of the rods are welded. Only electric arc welding shall be used using a process which excluded air from the molten metal and conforms to any or all the special provisions for the work which will be accepted. Suitable means shall be provided for holding the bars securely in position during welding. It must be ensured that no voids are left in welding and when welding is done in 2 or 3 stages, previous surface shall be cleaned properly. Ends of the bars shall be cleaned of all loose scale, rust, grease, paint and other foreign matter before welding. Only competent welders shall be employed on the work. The M.S. electrodes used for welding shall conform to IS : 814. Welded pieces of reinforcement shall be tested. Specimen shall be taken from the actual site and their number and frequency to test shall be as directed by the Engineer-in-charge.

3.00 Mode of Measurement and Payment

The rate shall be for a unit of One M.T

ITEM NO.19

Filling available excavated earth (excluding rock) in trenches plinth sides of foundation etc. in layers not exceeding 20cm in depth consolidating each deposited layer by ramming and watering.

1.0 The earth to be used for filling shall be free from salts, organic or other foreign matter, All clods of earth shall be broken.

2.0 As soon as the work in foundation has been completed and measured, the site of foundation shall be cleared of all debris, stone, mortar droppings etc. and filled with earth in layers not exceeding 20 cms. each layer shall be adequately watered, rammed and consolidated before the succeeding layers is laid, the earth shall be rammed with iron rammers where feasible and with the butt ends of crow-bars. Where rammer can not be used. With iron rammers finished level, the surface shall be flooded with water for at least 24 hours and allowed to dry and then rammed and consolidated.

3.0 The excavated stuff of the selected type shall be allowed to be used in filling the trenches and plinth under no circumstances black cotton soil be used for filling.

4.0 The payment shall be made for filling in trenches and plinth. No deduction shall be made for shrinkage of voids, if consolidated as instructed above.

5.0 The rate shall be for a unit of one cubic metre

ITEM NO.20

Supplying and fixing reinforced concrete heavy duty non-pressure pipes with collars for culverts including setting and joining the pipes in C.M. 1:2 watering and laying (To level of slopes of I.S. 458/1971 Class NP3 casted by vertically vibrated technology of following internal diameter. 600mm dia.

AND

ITEM NO.21

Supplying and fixing reinforced concrete heavy duty non-pressure pipes with collars for culverts including setting and joining the pipes in C.M. 1:2 watering and laying (To level of slopes of I.S. 458/1971 Class NP3 casted by vertically vibrated technology of following internal diameter. 900mm dia.

1. The work shall consist to furnishing and installing reinforced cement concrete pipe of the type dia metre and length required at the location shown on the drawings or as ordered by the Engineer in charge.

2. Reinforced concrete pipe shall be NP3 type conforming to the requirements of IS : 458 and shall be of dia as specified in the item each consignment of cement concrete pipes shall be inspected. If necessary and approved by the engineer in charge, either at the place of manufacture or at the site before their incorporation in the works.

NP3 , NP3 , NP1 pipes are used for RCC pipes where testing of pipes will not be feasible the contractors will have to produce a certificate from the manufacturers on company's letter head the given hereinafter form.

Production of such certificate will not however relieve the contractor from this responsibility of supplying pipes of required standard and will have to bear the loss or damage caused to the work in account of defects found subsequently during the execution It will also be necessary to purchase these pipes from manufacturere having standard equipments for carring out various test as per IS : 458 at his factory.

FORM OF CERTIFICATE FOR NP3, NP2, NP1 PIPES

We..... manufacture of RCC pipes prudude RCC pipes as per the requirement of IS : 458 and also carry out the required test at our place. We have acquired equipments for carrying out test and are prepared to carryout test at our factory sites.

We have experience of manufacturing of pies of years
The pipes supplied by us to M/s Satisfy the requirement of IS " 458.

Date

Place
.....

Manufacturer;s sign.

3. No pipe shall be placed in position until the foundations have been approved by the eingneer in charge, Where two or more pipes are to be laid adjacent to each other they shall be separated by a distace equal to at leat half the diametre of the pipe subject to minimum of 450mm. The laying of pipes on the prepared foundation shall start from the outlet and proceed toward the inlet and be completed to teh specified lines and grades. The pipes shall be fitted and matched so that when laid in works they form a culvert with a smooth uniform invert. Any pipe found defective or damaged during laying shall be removed at there cost of contractor.

4. The pipes shall be jointed either by collar joint or by flush joint in the former case the collers shall be of RCC 150 to 200 mm wide and having the same strength as the pipes to be jointed . Caulking space shall be slightly wet mix of cement and sand in the ratio of 1:2 rammed with caulking irons. Before caulking the collar shall be so placed that its centre coincides with that of pipe and an even annular space is left between the collar and the pipes. Flush joint may be shaped to form a self centering joing with a joinin space 13 cm wide, The joining space shall be filled with cement mortar, 1 cement 2. sand, mixed sufficiently dry to remain in position when forced with a trowel or rammer, Care shall be taken to fill all voids and excess mortar shall be removed. All joints shall be made with care so that their interior surface is smooth and consistent

with the interior surface of the pipes. After finishing, the joint shall be kept covered and damp for at least four day.

5. RCC pipe shall be measured along thir centre between thir inlet and outlet ends in linear metres.

6. The rate for the pipes shall include the cost of pipe including loading unloading handing storing laying in position and joining complete.

7. Payment shall be made on Running metre basis.

ITEM NO.22

Dismantling the existing structure including removing and stacking the dismantled materials as and where directed. Stone/Rubble masonry.

AND

ITEM NO.23

Dismantling the existing structure including removing and stacking the dismantled materials as and where directed. RCC Work.

202. DISMANTLING CULVERTS, SMALL BRIDGES, PAVEMENTS AND OTHER STRUCTURES

202.1. Scope

This work shall consist of removing, as hereinafter setforth, existing culverts, bridges, pavement, kerbs and other structures, like, railings, fences, utility services, manholes, catch basins, inlets etc., which are in place but interfere with the new construction or are not suitable to remain in place. It shall include salvaging and disposing of the resulting materials and backfilling the resulting trenches and pits.

Existing culverts, bridges, pavement and other structures which are within the road land and which are designated for removal, shall be removed upto the limits and extent specified in the drawings or as directed by the Engineer.

Dismantling and removal operations shall be carried out preferably with locally available tools and equipments and in such a manner as to leave undisturbed adjacent pavement, structures and any other work to be left in place. Use of specialized tools and equipments by the agency shall be incidental to this item.

All operations necessary for the removal of any existing structure which endanger new construction shall be completed prior to the start of new work.

202.2. Dismantling Culverts and Small Bridges

The structures shall be dismantled carefully and the resulting materials so removed as not to cause any damage to the serviceable materials to be salvaged, the part of the structure to be retained and any other properties or structures or utilities nearby.

Unless otherwise specified, the superstructure portion of culverts/bridges shall be entirely removed and other parts removed below the ground level or as necessary depending upon the interference they cause to the new construction. Removal of overlying or adjacent material, if required in connection with the dismantling of the structures, shall be incidental to this item.

Where existing culverts/bridges are to be widened / strengthened or otherwise incorporated in the new work, only such part or parts of the existing structure shall be removed as are necessary for execution of work shown in drawings to provide a proper connection to the new work. The connecting edges shall be cut, chipped and trimmed to the required lines and grade without weakening or damaging any part of the structure to be retained. Due care should be taken to ensure that reinforcing bars which are to be left in place so as to project into the new work as dowels or ties are not damaged during removal of concrete and protected against rusting or corrosion.

Pipe culverts shall be carefully removed in such a manner as to avoid damage to the pipes.

Steel structures shall be carefully dismantled in such a manner as to avoid damage to members thereof, if the structure is to be removed in a condition suitable for re-erection as specified in the drawings or directed by the Engineer. All members shall be match marked with white lead paint by the Contractor before dismantling. All loose parts like pins, nuts, loose plates, etc. shall be securely wired to adjacent members or packed in boxes with proper markings for the ease of identification at the time of re-erection of the structure at later stage.

Timber structures shall be removed in such a manner as to avoid damage to such timber or lumber as is designated by the Engineer to be salvaged after joint inspection by the Engineer and the Contractor or their authorized representatives.

202.3. Dismantling Pavement and Other Structures

In removing pavements, kerbs, gutters, and other structures, like, railings, fences, manholes, catch basins, inlets, etc. where portions of the existing construction are to be left in the finished work, the same shall be removed to an existing joint or cut and chipped to a true line with a face perpendicular to the surface of the existing structure. Sufficient removal shall be made to provide for proper grades and connections with the new work as directed by the Engineer.

Concrete pavements, base courses in carriageway and shoulders, etc. designated for removal shall be broken to pieces and stock piled at designated locations or as directed by the

Engineer, if the material is to be used later or otherwise, the Contractor shall arrange for disposal as stipulated in Clause 202.5.

202.4. Backfilling

Holes and depressions caused by dismantling operations shall be backfilled with excavated or other approved materials and compacted to required density conforming to these specifications, or as directed by the Engineer.

202.5 Disposal of Materials

All materials, obtained by dismantling, shall be the property of Government. Unless otherwise specified, materials having any salvage value shall be placed in neat stacks of like materials within the right-of-way, as directed by the Engineer with all lifts and upto a lead of 1000 m.

Pipe of culverts which are removed shall be cleaned and neatly piled on the right-of-way at spots designated by the Engineer with all lifts and lead upto 1000 m.

Structural steel removed from old structures shall, unless otherwise specified be stored in a neat and presentable manner in blocks at locations suitable for loading.

Timber or lumber salvaged from old structures shall have all nails and bolts removed therefrom and shall be stored in neat piles in locations suitable for loading in the right-of-way.

All materials obtained from dismantling operations which cannot be used or auctioned shall be disposed off as directed by the Engineer with all lifts and upto a lead of 1000 m.

202.6. Acceptance

Acceptance of dismantling and removal of salvaged material shall be based on visual inspection of the work and backfilling and compaction shall comply the tests specified for such work in these Specifications.

202.7. Measurements for Payment

The work of dismantling structures shall be paid for in units indicated below by taking measurements before and after, as applicable:

- (i) Dismantling brick/stone masonry/concrete (Plain and reinforced) cu.m.
- (ii) Dismantling flexible and cement concrete pavement cu.m.

(iii)	Dismantling steel structures	tonne
(iv)	Dismantling pipes, guard rails, kerbs, gutters and fencing	Linear m
(v)	Utility services	Nos./linear m

202.8. Rate

The Contract unit rates for the various items of dismantling including utility services shall be paid in full for carrying out the required operations including all labour, materials tools, equipment, safeguards and incidental expenditure for the satisfactory completion of the work. These rates will also include excavation and backfilling where necessary to the required compaction and for handling, salvaging, piling and disposing of the dismantled materials within all lifts and upto a lead of 1000 m.

ITEM NO.24

Providing and placing in position FE 500D TMT Bar reinforcement including cutting, bending, hooking, and taying complate as per detail drawing. (C) Balanced cantiliver box type super structure.

2.00 Materials :- T.M.T. shall conform to IS : 1786-FE 500D Mild steel bidning wires shall conform to the specification.

2.1 The work shall consist of furnishing and placing reinforcement of the shape and dimensions shown on the drawing or as directed by the Engineer-in-charge.

2.2 Steel shall be clean and free from loose rust mill scale at the time of fixing in position and subsequent concreting.

2.3 Reinforcing steel shall conform accurately to the dimensions given iron bar bending schedules shown on relevant drawing. Bar shall be bent cold to the specified shape and dimensions or as directed by the Engineer-in-charge using a proper bar bender, oprated by hand or power ro attain proper relduis of bends. Bars shall not be bent or straightened in manner that will injure the material. Bars bend during transporting or handaling shall be straightened before use on work ; they shall not be invariably be provided. The dius of the bend shall not less than twoce the diametre of the round bar and length of the straight part of the beyond the end of the curve shall be at lest four lest four times the diametre of the round bar. In the case which are not round and in the case of deformed bars, the diametre shall be taken as the diametre of a circle having a equivalent effective area. The work shall be suitably encased tp prevent any splitting of the concrete.

2.4 All reinforcement bars shall be accurately placed in exact on the drawings, and shall besecurely held in position during placing of concrete by annealed binding wire not less than

1mm, in size and confirming to IS : 280 and by using stay blocks or metal chairs, spacer, metal hangers, supporting wires or other approved device at sufficiently close intervals. Bars will not be allowed to sag between supports or displaced during concreting or any of their operations over the work. All devices used for positioning shall be non-corrodible material. Wooden and metal supports will not extend to the surface of concrete except where shown on the drawings. Placing bars on layers of freshly laid concrete as the work progress or adjusting bar will not be allowed. Pieces of broken stone or brick and wooden blocks shall not be used. Layers of bars shall be separated by spacer bars, precast mortar block, or other approved device. Reinforcement after being placed in position shall be maintained in clean condition until completely embedded in concrete. Special care shall be exercised to prevent any displacement of reinforcement in concrete already placed. To protect reinforcement from corrosion, concrete cover shall be provided as indicated on the drawing. All bars protruding from concrete and to which other bars are to be spliced and which are likely to be exposed for an indefinite period shall be protected by a thick coat of neat cement grout.

2.5. Bars crossing each other, where required shall be secured by binding wire (annealed) of size not less than 1 mm. in such a manner that they do not slip over each other at the time of fixing and concreting.

2.6. As far as possible, bars of full length shall be used. In case this is not possible, overlapping of bars shall be done as directed by the engineer-in-charge. When practicable, overlapping bars shall not touch each other, but be kept apart by 25mm or 1.25 times the maximum size of the coarse aggregate whichever is greater, by concrete between them. Where not feasible, overlapping bars shall be bound with annealed steel wire, not less than 2mm thickness twisted right. The overlaps shall be staggered for different bars and located at points, along the span where neither shear nor bending movement is maximum.

2.7. Whenever indicated on the drawings or desired by the Engineer-in-charge, bars shall be joined by couplings which shall have a cross-section sufficient to transmit the full strength of bars. The end of the bars that are joined by coupling shall be upset for a sufficient length so that the effective cross-section at the base of threads shall be standard with the threads. Steel for coupling shall conform to IS : 226.

2.8. When permitted or specified on the drawings joints of reinforcement bars shall be welded so as to transmit their full strength. Welded joints shall preferably be located at points where steel will not be subject to more than 75 per cent of the maximum permissible stresses and shall be staggered so that at any one section not more than 20 per cent of the rods are welded. Only electric arc welding shall be used using a process which excludes air from the molten metal and conforms to any or all the special provisions for the work which will be accepted. Suitable means shall be provided for holding the bars securely in position during welding. It must be ensured that no voids are left in welding and when welding is done in 2 or 3 stages, previous surface shall be cleaned properly. Ends of the bars shall be cleaned of all loose scale, rust, grease, paint and other foreign matter before welding. Only competent welders shall be employed on the work. The M.S. electrodes used for welding shall conform to IS : 814 welded pieces of reinforcement shall be tested. Specimen

shall be taken from the actual site and their number and frequency to test shall be as directed by the Engineer-in-charge.

3.00 Mode of Measurement and Payment

The rate shall be for a unit of One M.T

ITEM NO.25

Providing and fixing Precast cement concrete Hectometer as per IRC type design incl. painting, lettering etc. fixing in C.C. 1:5:10.

(1) Fixing in Earth :

The work shall be carried out as per the item of ordinary kilometre stone except that the size of hectometre stone shall be smaller than that of ordinary kilometre stone as per IRC 26 (type design for 200 metre stone fixing shall be in earth the measurement for payment as well as operations included in the unit rate shall be as per hectometre stone.

(2) Fixing in C.C. 1:5:10

Specification same as 11(1) above except that the indicator stone shall be fixed in C.C. 1:5::10 which will consist of one part of cement, five part of good sand and ten parts of good brick bats, Rate includes all labour and curing etc. necessary for concrete.

Payment shall be made on number basis

ITEM NO.26

Providing and fixing Precast cement concrete Guard stone as per I.R.C. type design including white washing etc. complete. Fixing in Earth.

(1) Fixing in Earth / Wearing Coat :

1. The guard stone shall be of approved quality and of 20 cm x 15 cm size and its length shall not be less than 75 cms. The top portion shall be rounded. The top 38 cm shall be chisel dressed on all sides. The size shape and dimensions of the guard stones shall be exact and shall be nearly dressed and finished.

2. The guard stone shall be fixed in position as directed by the Engineer in charge in earth / wearing coat. If the guard stone shall be fixed in wearing coat. the equivalent volume covered by the guard stones shall be given three coats of white wash. Any excavation necessary for fixing of the guard stones shall be done by the contractor at his own cost. The measurement for payment shall be per number of guard stone fixed in position.

3. Unit rate of guard stone includes the cost of all materials , laboures , tools, fixing & white washing as directed by the Engineer in charge.

(2) Fixing in C.C. 1:5:10

Specification same as 12(1) above except that the indicator stone shall be fixed in C.C. 1:5:10 which will consist of one part of cement, live part of good sand and ten parts of good brick bats. Rate includes all labour and curring etc. necessary for consrete.

ITEM NO.27

Providing and fixing ordinary Kilometer stone of pre-cast C.C. 1:2:4 including necessary reinforcement as per I.R.C. type design in C.C. 1:4:8 including painting lettering etc. complete.

1. Kilometre stone shall be of approved quality and shall be either black Rajula stone or of precast 1:2:4 RCC specified in the item.

2. The size, manner of fixing, painting and lettering of K.M. stone shall conform specification as per IRC - 8 (Type design for Highway kilometre sones) The fixing of K.M. stone shall be carried out in ordinary concrete of grade specified in the item using hand broken metal field metal or gravel, The **measurement for payment shall be made per No. of K.M. stone fixed in position.**

3. Unit rate for kilometre alone includes the cost of all materials labours tools fixing finishing curing lettering and painting as directed by the engineer in charge.

ITEM NO.28

Providing and fixing 5th Kilometer stone of pre-cast C.C. 1:2:4 including necessary reinforcement as per I.R.C. type design in C..C. 1:4:8 including painting lettering etc. complete.

The work covers the supply, painting, lettering and fixing of 5th Kilometer stone.

The dimensions of the stones and the size, colour, arrangement of letters and scripts shall be as per I.R.C. type designs. The 5th kilometer stone of approved hard stone as per IRC type design in C.C. 1:2:4 as indicated in the drawings or in the relevant I.R.C. specifications or as directed by the Engineer-in-charge. The orientation and location of the stones shall be as

indicated in the drawings or in the relevant I.R.C. Specification or as directed by the Engineer-in-charge.

The 5th Kilometer stone shall be fixed in C.C. 1:4:8 at site of work.

MEASUREMENT OF PAYMENT

The measurement will be taken in Numbers of 5th Kilometer stone fixed at site.

RATE

The contract unit rate for 5th kilometer stones shall be paid in full compensation for furnishing, all labour, materials including providing necessary reinforcement, tools, equipment and making the stones, painting and lettering and fixing at site and all other incidental costs necessary to complete the work to these specifications.

ITEM NO.29

Village/Bump Ahead sign. : Providing and fixing sign boards made out of 2mm Aluminium sheet size 90x60 cms. Rectangle as per the design of IRC-67-1977 pre treated with phospheting process and acid etching coated with one coat of epoxy primer and two coats of best quality epoxy paint reflectorised with retro reflective sheeting as per latest MOST specification letter and numbers should be as per IRC:30-1968, 3.1 Mt. long (2 nos) stand post and frame fabricated from suitable size iron angle of 50x50x5mm, painted with best quality epoxy coating in black and white bends, the details of symbole on inscription/ numerals for each board shall be as per the instruction of the Engineer in charge. The fixing at site shall be in C.C 1:2:4 block of size 45x45x60cms. for each leg including excavation curring etc. complete under the supervision of engineer in charge (A) Engineer Grade.

AND

ITEM NO.30

Hazard Marker sign :Providing and Fixing sign boards made out of 2mm aluminum sheet : size 90*30 cms. rectangle as per design / Drawing attached (IRC). Pretreated with phospheting process and acid etching : coated with one coat of epoxy primer and two coats of best quality epoxy paint: reflectorised with retro reflective sheeting as per latest M.O.S.T specification: 3.1 M. long (2 nos) stand post and frame fabricated from suitable size iron angle of 35*35*3mm and 50*50*5mm : painted with best quality epoxy coatings in black and white bends the details of symbole or inscription / numerals for each board shall be as per the instruction of engineer in charge the fixing at site shall be in 1:2:4 CC block of size 45*45*60 cms for each leg: including excvation curing etc. comp.under the supervision of engineer-in-charge.(B) Engineering Grade

801.1. General

801.1.1. The colour, configuration, size and location of all traffic signs for highways other than Expressways shall be in accordance with the Code of Practice for Road Signs, IRC: 67 or as shown on the drawings. For Expressways, the size of the signs, letters and their placement shall be as specified in the contract drawings and relevant Specifications. In the absence of any details or for any missing details, the signs shall be provided as directed by the Engineer.

801.1.2. The signs shall be either reflectorised or non-reflectorised as shown on the drawings or as directed by the Engineer. When they are of reflectorised type, they shall be of retro-reflectorised type and made of encapsulated lens type reflective sheeting vide clause 801.3, fixed over aluminium sheeting as per these Specifications.

801.1.3. In general, cautionary and mandatory signs shall be fabricated through process of screen printing. In regard to informatory signs with inscriptions, either the message could be printed over the reflective sheeting, or cut letters of non-reflective black sheeting used for the purpose which must be bonded well on the base sheeting as directed by the Engineer.

801.2 Materials

The various materials and fabrication of the traffic signs shall conform to the following requirements :

801.2.1. Concrete: Concrete shall be of the grade shown on the Contract drawings or otherwise as directed by the Engineer.

801.2.2. Reinforcing steel: Reinforcing steel shall conform to the requirement of IS: 1786 unless otherwise shown on the drawing.

801.2.3. Bolts, nuts, washers: High strength bolts shall conform to IS: 1367 whereas precision bolts, nuts, etc., shall conform to IS: 1364.

801.2.4. Plates and supports: Plates and support sections for the sign posts shall conform to IS: 226 and IS: 2062 or any other relevant IS Specifications.

801.2.5. Aluminium: Aluminium sheets used for sign boards shall be of smooth, hard and corrosion resistant aluminium alloy conforming to IS: 736 – Material designation 24345 or 1900.

801.2.6. Signs with a maximum side dimension not exceeding 600 mm shall not be less than 1.5 mm thick. All others shall be at least 2 mm thick. The thickness of the sheet be related to the size of the sign and its support and shall be such that it does not bend or deform under the prevailing wind and other loads.

801.2.7. In respect of sign sizes not covered by IRC: 67, the structural details (thickness, etc.) shall be as per the approved drawings.

801.3. Traffic Signs Having Retro-Reflective Sheeting

801.3.1. General requirements: The retro-reflective sheeting used on the sign shall consist of the white or coloured sheeting having a smooth outer surface which has the property of retro-reflection over its entire surface. It shall be weather-resistant and show colour fastness. It shall be new and

unused and shall show no evidence of cracking, scaling, pitting, blistering, edge lifting or curling and shall have the negligible shrinkage and expansion. A certificate of having tested the sheeting for these properties in an unprotected outdoor exposure facing the sun for two years and its having passed these tests shall be obtained from a reputed laboratory, by the manufacturer of the sheeting. The reflective sheeting shall be either of engineering grade material with enclosed lens or of high intensity grade with encapsulated lens. The type of the sheeting to be used would depend upon the type, functional hierarchy and importance of the road.

800.1.3.2. High intensity grade sheeting: This sheeting shall be of encapsulated lens type consisting of spherical glass lens, elements adhered to a synthetic resin and encapsulated by a flexible, transparent waterproof plastic having a smooth surface. The retro-reflective surface after cleaning with soap and water and in dry condition shall have the minimum co-efficient of retro-reflection (determined in accordance with ASTM Standard E: 810) as indicated in Table 800-1.

**TABLE 800- 1. ACCEPTABLE MINIMUM COEFFICIENT OF RETRO-REFLECTION
FOR HIGH INTENSITY GRADE SHEETING
(CANDELAS PER FLUX PER SQUARE METRE)**

Observation angle (in degrees)	Entrance angle (in degrees)	White	Yellow	Orange	Green/ Red	Blue
0.2	-4	250	170	100	45	20
0.2	+30	150	100	60	25	20
0.5	-4	95	62	30	15	7.5
0.5	+30	65	45	25	10	5.0

When totally wet, the sheeting shall now show less than 90 percent of the values of retro-reflectance indicated in Table – 800 – 1. At the end of 7 years, the sheeting shall retain at least 75 percent of its original retro-reflectance.

801.3.3. Engineering grade sheeting: This sheeting shall be of enclosed lens type consisting of microscopic lens elements embedded beneath the surface of a smooth, flexible, transparent, waterproof plastic, resulting in a non-exposed lens optical reflecting system. The retro-reflective surface after cleaning with soap and water and in dry condition shall have the minimum coefficient of retro-reflection (determined in accordance with ASTM Standard: E-810) as indicated in Table 800-2.

**TABLE 800 –2. ACCEPTABLE MINIMUM COEFFICIENT OF RETRO-REFLECTION
FOR ENGINEERING GRADE SHEETING
(CANDELAS PER LUX PER SQUARE METRE)**

Observation angle in degree	Entrance angle in degree	Whit e	Yello w	Orange	Green	Red	Blue
0.2	-4	70	50	25	9.0	14.5	4.0
0.2	+30	30	22	7.0	3.5	6.0	1.7
0.5	-4	30	25	13.5	4.5	7.5	2.0

When totally wet, the sheeting shall not show less than 90 percent of the values, of retro-reflection indicated in Table 800 -2. At the end of 5 years, the sheeting shall retain at least 50 percent of its original retro-reflectance.

801.3.4. Messages / borders: The messages (legends, letters, numerals etc.) and borders shall either be screen printed or of cut-outs. Screen printing shall be processed and finished with materials and in a manner specified by the sheeting manufacturer. Cut-outs shall be of materials as specified by the sheeting manufacturer and shall bonded with the sheeting in a manner specified by the manufacturer.

801.3.5. For screen-printed transparent coloured areas on white sheeting, the co-efficient of retro-reflection shall not be less than 50 percent of the values of corresponding colour in Table 800-1 and 2, as applicable.

801.3.6. Cut-out messages and borders, wherever used, shall be made out of retro-reflective sheeting (as per Clause 801.3.2. or 801.3.3. as applicable), except those in black which shall be of non-reflective sheeting.

801.3.7. Colour: Unless otherwise specified, the general colour scheme shall be as stipulated in IS: 5 “Colour for Ready Mixed Paints “. viz.

Blue	IS	Colour	No.166	French Blue
Red	IS	Colour	No.537	Signal Red
Green	IS	Colour	No.284	India Green
Orange	IS	Colour	No.591	Deep Orange

The colours shall be durable and uniform in acceptable hue when viewed in day light or under normal headlights at night.

801.3.8. Adhesives: The sheeting shall either have a pressure-sensitive adhesive of the aggressive –tack type requiring no heat, solvent or other preparation for adhesion to a smooth clean surface, or a tack free adhesive activated by heat, applied in a heat – vacuum applicator, in a manner recommended by the sheeting manufacturer. The adhesive shall be protected by an easily removable liner (removable by peeling without soaking in water or other solvent) and shall be suitable for the type of material of the base plate used for the sign. The adhesive shall form a durable bond to smooth, corrosion and weather resistant surface of the base plate such that it shall not be possible to remove the sheeting from the sign base in one piece by use of sharp instrument. In case of pressure-sensitive adhesive sheeting, the sheeting shall be applied in accordance with the manufacturer’s specifications. Sheeting with adhesives requiring use of solvents or other preparation for adhesive shall be applied strictly in accordance with the manufacturer’s instructions.

801.3.9. Refurbishment: Where existing signs are specified for refurbishment, the sheeting shall have a semi-rigid aluminium backing pre-coated with aggressive – tack type pressure sensitive adhesive. The adhesive shall be suitable for the type of material used for the sign and should thoroughly bond with that material.

801.3.10 Fabrication:

801.3.10.1. Surface top be reflectorised shall be effectively prepared to receive the retro-reflective sheeting. The aluminium sheeting shall be de-greased either by acid or hot alkaline etching and all scale/dust removed to obtain a smooth plain surface before the application of retro-reflective sheeting. If the surface is rough, approved surface primer may be used. After cleaning, metal shall not be handled, except by suitable device or clean canvas gloves, between all cleaning and preparation operation and application of reflective sheeting/primer. There shall be no opportunity for metal to come in contact with grease, oil or other contaminants prior to the application of retro-reflective sheeting.

801.3.10.2. Complete sheets of the material shall be used on the signs except where it is unavoidable; at splices, sheeting with pressure sensitive adhesives shall be overlapped not less than 5 mm. Sheeting with heat-activated adhesives may be spliced with an overlap not less than 5 mm or butted with a gap not exceeding 0.75 mm. Where screen printing with transparent colours is proposed, only butt jointing shall be used. The material shall cover the sign surface evenly and shall be free from twists, cracks and folds. Cut – outs to produce legends and borders shall be bonded with the sheeting in the manner specified by the manufacturer.

801.3.11. Warranty and durability: The contractor shall obtain from the manufacturer a seven-year warranty for satisfactory field performance including stipulated retro-reflectance of the retro-reflective sheeting of high intensity grade and a five year warranty for the adhesive sheeting of engineering grade and submit the same to the engineer. In addition, a seven year and a five year warranty for satisfactory in-field performance of the finished sign with retro-reflective sheeting of high intensity grade and engineering grade respectively, inclusive of the screen printed or cut out letters/legends and their bonding to the retro-reflective sheeting shall be obtained from the Contractor/supplier and passed on to the Engineer. The Contractor/supplier shall also furnish a certification that the signs and materials supplied against the assigned work meets all the stipulated requirements and carry the stipulated warranty.

Processed and applied in accordance with recommended procedures, the reflective material shall be weather resistant and, following cleaning, shall show no appreciable discolouration, cracking, blistering or dimensional change and shall not have less than 50 percent of the specified minimum reflective intensity values (Table 800-1 and 800-2) when subjected to accelerated weathering for 1000 hours, using type E or EH Weatherometre (AASHTO Designation M 268).

801.4. Installation

801.4.1. Sign posts, their foundations and sign mountings shall be so constructed as to hold these in a proper and permanent position against the normal storm wind loads or displacement of vandalism. Normally, signs with an area up to 0.9 sq. m. shall be mounted on a single post, and for greater area two or more supports shall be provided. Sign supports may be of mild steel, reinforced concrete or galvanized iron (G. I). Post-end(s) shall be firmly fixed to the ground by means of properly designed foundation. The work of foundation shall conform to relevant Specifications as specified.

801.4.2. All components of signs and supports, other than the reflective portion and G. I. posts shall be thoroughly descaled, cleaned, primed and painted with two coats of epoxy paint. Any part of mild steel (M. S.) post below ground shall be painted with three coats of red lead paint.

801.4.3. The signs shall be fixed to the posts by welding in the case of steel posts and by bolts and washers of suitable size in the case of reinforced concrete or G. I. posts. After the nuts have been tightened, the tails of the bolts shall be furred over with a hammer to prevent removal.

801.5. Measurements for Payment

The measurement of standard cautionary, mandatory and information signs shall be in numbers of different types of signs supplied and fixed, while for direction and place identification signs, these shall be measured by area in square metres.

801.6. Rate

The contract unit rate shall be payment in full for the cost of making the road sign, including all materials, installing it at the site and incidentals to complete the work in accordance with the Specifications

Payment shall made on number basis

ITEM NO.31

Chevron sign :-Providing and fixing sign boards madeout of 1.5mm aluminium sheet / 3mm ACP (Aluminum composite Panel); size 60x50cm rectangular as per design of IRC-67-2012. Pre treated with phospheting process & acid etching; coated with one coat of epoxy primer and two coats of best quality epoxy paint; reflectorised with High Intensity Prismatic Grade retro refiectivesheeting of Type-4 as per ASTM D-4956 and latest M.O.S.T.Specifications; 3.3 mtr long stand post of Iron Angle 75 x 75 x 6mm /65NB Circular MS Pipe as required and frame fabricated from suitable size iron angle of35x35x3mm; painted with bestquality epoxy coatings in black and white bends. the details of symbol or inscription /numerals for each board shall be as per the instruction of engineer in charge. The fixing at site shall be in 1:2:4 CC block of size 45 x 45 x 60 Cms. for each leg including excavation, curing etc.complete under the supervision of engineer in charge. A warranty for 7 years for the Retro reflective sheeting from original manufacturer & a certified copy of 3 year outdoor exposure test report from third party test lab for the product offered shall be submitted by contractor. (A) Class-B Type-4 Retro Reflective sheeting

1. Material & Manufacturing:

1.1 Scope

The work shall consist of fabrication, supply and installation of ground mounted traffic signs on roads. The details of the signs shall be as shown in the drawings and in conformity with the code of practice for Road signs, IRC 67-2012.

1.2 Materials

The various materials and fabrication of the traffic signs shall conform to the following requirements:

1.2.1 Concrete:

Concrete for the foundation shall be of M15 Grade as per section 1700 or the grade shown on the drawings or otherwise as directed by the Engineer.

1.2.2 Reinforcing Steel

Reinforcing steel shall conform to the requirements of IS: 1786 unless otherwise shown on the drawings

1.2.3 Bolts, Nuts and Washers

High strength Bolts shall conform to IS: 1367 whereas precision bolts, nuts, etc. shall conform to IS: 1364

1.2.4 Plates and Supports

Plates and support sections for the sign posts shall conform to IS: 226 and IS: 2062 or any other relevant IS specifications.

1.2.5 Substrate

Sign panel shall be fabricated on Aluminum sheet, aluminum composite panel, fibre glass sheeting, or sheet moulding compound. Aluminum sheets used for sign boards shall be of smooth, hard and corrosion resistance aluminum alloy conforming to IS: 736-Material Designation 24345 or 1900. Aluminum composite Material (ACM) sheets shall be sandwiched construction with a thermoplastic core of Low Density Polyethylene (LDPE) between two thick skins/sheets of aluminum with overall thickness of 3mm or 4mm (as specified in the contract), and aluminum skin thickness 0.5mm and 0.3mm respectively on both the sides.

The mechanical proportion of ACM and that of aluminum skin shall conform to the requirements given in the table 800-1, when tested in accordance with the test methods mentioned against each of them.

Table 800-1: Specifications for Aluminum Composite Material (ACM)

Sr No.	Description	Specification for 4mm		Specification for 3mm
		Standard test	Acceptable value	Acceptable value
A	Mechanical Properties of ACM			
1	Peel off strength with retro reflective sheeting. (Drum Peel Test)	ASTM D903	Min. 4 N/mm	Min. 4 N/mm
2	Tensile strength	ASTM E8	Min. 40 N/mm ²	Min. 40 N/mm ²
3	0.2% Proof Stress	ASTM E8	Min. 34 N/mm ²	Min. 34 N/mm ²
4	Elongation	ASTM E8	Min. 6 %	Min. 5 %
5	Flexural strength	ASTM C393	Min. 130 N/mm ²	Min. 120 N/mm ²
6	Shear strength with Punch shear test	ASTM D732	Min. 18 N/mm ²	Min. 18 N/mm ²
8	Properties of Aluminium Skin			
1	Tensile strength (Rm)	ASTM E8	Min. 150 N/mm ²	Min. 150 N/mm ²
2	Modulus of elasticity	ASTM E8	Min. 70,000 N/mm ²	Min. 70,000 N/mm ²
3	Elongation	ASTM E8	A50 Min. 2%	A50 Min. 2%
4	0.2 % Proof Stress	ASTM E8	Min. 110 N/mm ²	Min. 110 N/mm ²

1.2.6 Plate Thickness

Shoulder mounted ground signs with a maximum side dimension not exceeding 600 mm shall not be less than 1.5mm thick Aluminum and 3 mm thick with Aluminium Composite Material. All other signs shall be at least 2mm thick Aluminum and 4 mm thick with Aluminium Composite Material. The thickness of the sheet shall be related to the size of the sign and its support and shall be such that it does not bend or deform under prevailing wind and other loads.

1.2.7 In respect of sign sizes not covered by IRC-67, the structural details (thickness etc.) shall be as per the approved drawings or as directed by the Engineer.

1.3 Traffic signs having Retro Reflective Sheeting

1.3.1 General Requirements

The retro reflective sheeting used on the signs shall consist of white or coloured sheeting having a smooth outer surface, which has the property of retro reflection over its entire surface. It shall be weather resistant and exhibit colour fastness. It shall be new and unused and show no evidence of cracking, scaling, and pitting, blistering, edge lifting or curling and shall have negligible shrinkage or expansion. A certificate of having the sheeting tested for coefficient of retro reflection, daytime colour and luminance, shrinkage, flexibility, liner removal, adhesion, impact resistance, specular gloss and fungus resistance, 3 years outdoor weathering and its having passed these tests shall be obtained from International/Government laboratory/Institute by the manufacturer of the sheeting. The reflective sheeting shall be either of Engineering Grade material with enclosed lens, High Intensity Grade with encapsulated lens or Micro- Prismatic Grade retro reflective element material as given in Clauses 801.3.2 to 801.3.7. Guidance on the recommended application of each class of sheeting may be taken from IRC-67.

1.3.2 High Intensity Grade Sheetting

1.3.2.1 High Intensity Grade (Type III)

This sheeting shall be of encapsulated lens type consisting of spherical glass lens, elements adhered to a synthetic resin and encapsulated by a flexible, transparent water-proof plastic having a smooth surface or as an unmetallised micro prismatic reflective material elements. The retro-reflective surface after cleaning with soap and water and in dry conditions shall have the minimum coefficient of retro-reflection (determined with ASTM D:4956-09) as indicated in Table 800-2.

Table 800-2 Acceptable Minimum Coefficient of Retro-reflection for Type III High Intensity Grade Sheetting^A (Encapsulated Lens Type)
(Candelas Per Lux Per Square Metre)

Observation Angle	Entrance Angle	White	Yellow	Orange	Green	Red	Blue	Brown
0.1° ^B	-4°	300	200	120	54	54	24	14
0.1° ^B	+30°	180	120	72	32	32	14	10
0.2°	-4°	250	170	100	45	45	20	12
0.2°	+30°	150	100	60	25	25	11	8.5
0.5°	-4°	95	62	30	15	15	7.5	5.0
0.5°	+30°	65	45	25	10	10	5.0	3.5

^A Minimum Coefficient of Retro reflection (R_A) (cd.lx⁻¹.m⁻²).

^B Values for 0.1° observation angles are supplementary requirements that shall apply only when specified by the purchaser in the contract or order. When totally wet, the sheeting shall show not less than 90 percent, of the values of retro reflectance indicated in above Table. At the end of 7 years, the sheeting shall retain at least 80 percent of its original retro-reflectance.

1.3.2.2 High Intensity Micro-Prismatic Grade Sheetting (HIP) (Type IV) :

This sheeting shall be of high intensity retro-reflective sheeting made of micro-prismatic retro-reflective element material coated with pressure sensitive adhesive. The retro-reflective surface after cleaning with soap and water and in dry condition shall have the minimum co-efficient of retro-reflection (determined in accordance with ASTM D 4956-09) as indicated in Table 800-3.

Table 800-3 Acceptable Minimum Coefficient of Retro-Reflection for Type IV High Intensity Micro-prismatic Grade Sheetting^A
(Candelas Per Lux Per Square Metre)

Fluorescent Orange	Fluorescent Yellow	Fluorescent Yellow - Green	Brown	Blue	Red	Green	Orange	Yellow	White	Entrance Angle	Observation Angle
150	300	400	25	42	90	70	200	380	500	-4°	0.1° ^B
70	140	185	12	20	42	32	94	175	240	+30°	0.1° ^B
105	220	290	18	30	65	50	145	270	360	-4°	0.2°
50	100	135	8.5	14	30	25	68	135	170	+30°	0.2°
45	90	120	7.5	13	27	21	60	110	150	-4°	0.5°
22	40	55	3.5	6	13	10	28	54	72	+30°	0.5°

^AMinimum Coefficient of Retro reflection (R_A) ($\text{cd.lx}^{-1}.\text{m}^{-2}$).

^BValues for 0.1° observation angles are supplementary requirements that shall apply only when specified by the purchaser in the contract or order. When totally wet, the sheeting shall show not less than 90 percent of the values of retro reflection indicated in above Table. At the end of 7 years, the sheeting shall retain at least 80 percent of its original retro-reflectance

1.3.4 Prismatic Grade Sheeting

1.3.4.1 Prismatic Grade Sheeting (Type VIII)

The reflective sheeting shall be retro reflective sheeting made of micro prismatic retro reflective material.

The retro reflective surface, after cleaning with soap and water and in dry condition shall have the minimum co-efficient of retro reflection (determined in accordance with ASTM D: 4956-09) as indicated in Table 800-4

Table 800-4 Acceptable Minimum Coefficient of Retro-reflection for Type VIII Prismatic Grade Sheeting^A
(Candelas Per Lux Per Square Metre)

Fluorescent Orange	Fluorescent Yellow	Fluorescent Yellow - Green	Brown	Blue	Red	Green	Orange	Yellow	White	Entrance Angle	Observation Angle
300	600	800	30	45	150	100	375	750	1000	-4°	0.1° ^B
135	280	370	14	21	69	46	175	345	460	+30°	0.1° ^B
210	420	560	21	32	105	70	265	525	700	-4°	0.2°
95	200	260	10	15	49	33	120	245	325	+30°	0.2°
75	150	200	7.5	11	38	25	94	190	250	-4°	0.5°
35	69	92	3.5	5	17	12	43	86	115	+30°	0.5°

^AMinimum Coefficient of Retro reflection (RA) ($\text{cd.lx}^{-1}.\text{m}^{-2}$).

^BValues for 0.1° observation angles are supplementary requirements that shall apply only when specified by the purchaser in the contract or order. When totally wet, the sheeting shall show not less than 90 percent of the values of retro reflection indicated in above Table. At the end of 7 years, the sheeting shall retain at least 80 percent of its original retro-reflectance

1.3.4.2 Prismatic Grade Sheeting (Type IX)

The reflective sheeting shall be retro reflective sheeting made of micro prismatic retro reflective material. The retro reflective surface, after cleaning with soap and water and in dry condition shall have the minimum co-efficient of retro reflection (determined in accordance with ASTM D 4956-09) as indicated in Table 800-5

Table 800-5 Acceptable Minimum Coefficient of Retro-reflection for Type IX Prismatic Grade Sheeting^A
(Candelas Per Lux Per Square Metre)

Observation Angle	Entrance Angle	White	Yellow	Orange	Green	Red	Blue	Fluorescent Yellow-Green	Fluorescent Yellow	Fluorescent Orange
0.1° ^B	-4°	660	500	250	66	130	30	530	400	200
0.1° ^B	+30°	370	280	140	37	74	17	300	220	110
0.2°	-4°	380	285	145	38	76	17	300	230	115
0.2°	+30°	215	162	82	22	43	10	170	130	65
0.5°	-4°	240	180	90	24	48	11	190	145	72
0.5°	+30°	135	100	50	14	27	6	110	81	41
1.0°	-4°	80	60	30	8	16	3.6	64	48	24
1.0°	+30°	45	34	17	4.5	9.0	2	36	27	14

^AMinimum Coefficient of Retro reflection (R_A) ($\text{cd.lx}^{-1}.\text{m}^{-2}$).

^BValues for 0.1° observation angles are supplementary requirements that shall apply only when specified

by the purchaser in the contract or order. When totally wet, the sheeting shall show not less than 90 percent of the values, of retro reflection indicated in above Table. At the end of 10 years, the sheeting shall retain at least 80 percent of its original retro-reflectance.

1.3.4.3 Prismatic Grade Sheeting (Type XI)

Retro reflective sheeting typically manufactured as a cube corner. The reflective sheeting shall be retro reflective sheeting made of micro prismatic retro reflective material. The retro reflective surface, after cleaning with soap and water and in dry condition shall have the minimum co-efficient of retro reflection (determined in accordance with ASTM D 4956-09) as indicated in Table 800-6

Table 800-6 Acceptable Minimum Coefficient of Retro-reflection for Type XI Prismatic Grade Sheeting^A
(Candelas per Lux per Square Metre)

Observation Angle	Entrance Angle	white	Yellow	Orange	Green	Red	Blue	Brown	Fluorescent Yellow-Green	Fluorescent Yellow	Fluorescent Orange
0.1° ^B	-4°	830	620	290	83	125	37	25	660	500	250
0.1° ^B	+30°	325	245	115	33	50	15	10	260	200	100
0.2°	-4°	580	435	200	58	87	26	17	460	350	175
0.2°	+30°	220	165	77	22	33	10	7	180	130	66
0.5°	-4°	420	315	150	42	63	19	13	340	250	125
0.5°	+30°	150	110	53	15	23	7	5	120	90	45

1.0°	-4°	120	90	42	12	18	5	4	96	72	36
1.0°	+30°	45	34	16	5	7	2	1	36	27	14

^A Minimum Coefficient of Retro reflection (R) ($\text{cd.lx}^{-1}.\text{m}^{-2}$).

^B Values for 0.1° observation angles are supplementary requirements that shall apply only when specified by the purchaser in the contract or order. When totally wet, the sheeting shall show not less than 90 percent of the values, of retro reflection indicated in above Table. At the end of 10 years, the sheeting shall retain at least 80 percent of its original retro-reflectance.

1.3.5 Adhesive

The sheeting shall have a pressure-sensitive adhesive of the aggressive-tack type requiring no heat, solvent or other preparation for adhesion to a smooth clean surface, in a manner recommended by the sheeting manufacturer. The adhesive shall be protected by an easily removable liner (removable by peeling without soaking in water or other solvent) and shall be suitable for the type of material of the base plate used for the sign. The adhesive shall form a durable bond to smooth, corrosion and weather resistant surface of the base plate such that it shall not be possible to remove the sheeting from the sign base in one piece by use of sharp instrument. The sheeting shall be applied in accordance with the manufacturer's specifications.

1.3.6 Fabrication

Surface to be reflectorised shall be effectively prepared to receive the retro-reflective sheeting. The aluminium sheeting shall be de-greased either by acid or hot alkaline etching and all scale/dust removed to obtain a smooth plain surface before the application of retro-reflective sheeting. If the surface is rough, approved surface primer may be used. After cleaning, metal shall not be handled, except by suitable device or clean canvas gloves, between all cleaning and preparation operation and application of reflective sheeting/primer. There shall be no opportunity for metal to come in contact with grease, oil or other contaminants prior to the application of retro-reflective sheeting. Complete sheets of the material shall be used on the signs except where it is unavoidable. At splices, sheeting with pressure-sensitive adhesives shall be overlapped not less than 5 mm. Where screen printing with transparent colours is proposed, only butt joint shall be used. The material shall cover the sign surface evenly and shall be free from twists, cracks and folds. Cut-outs to produce legends and borders shall be bonded with the sheeting in the manner specified by the manufacturer.

1.3.7 Message / Border

The messages (legends, letters, numerals, etc.) and borders shall either be screen-printed or of cut out from durable transparent overlay or cut out from the same type of reflective sheeting for the cautionary/mandatory sign boards. Screen printing shall be processed and finished with materials and in a manner specified by the sheeting manufacturer. For the informatory and other sign boards, the messages (legends, letters, numerals etc.) and borders shall be cut out from durable transparent overlay film or cut- out from the same reflective sheeting only. Cut-outs shall be from durable transparent overlay materials as specified by the sheeting manufacturer and shall be bonded with the sheeting in the manner specified by the manufacturer. For screen-printed transparent coloured areas on white sheeting, the co-efficient of retro-reflection shall not be less than 50 per cent of the corresponding values in Tables 800-2to 800-6 as applicable. Cut-out messages and borders, wherever used, shall be either made out of retro-reflective sheeting or made out of durable transparent overlay except those in black which shall be of non-reflective sheeting or opaque in case of durable transparent overlay.

1.3.8 Color for Signs

1.3.8.1 Signs shall be provided with retro-reflective sheeting and/or overlay film/screening ink as shown on the detailed drawings. The reverse side of all signs shall be painted grey

1.3.8.2 Except in the case of railway level crossing signs (for which the colour scheme is given later) the sign posts shall be painted in 250 mm wide bands, alternately black and white. The lowest band next to the ground shall be in black

1.3.8.3 The colour of the material shall be located within the area defined by the chromaticity coordinates in Table 8.1 and comply with the luminance factor given in Table 800-7 when measured as per ASTM D:

Table 8.1 Specilication Limits (Daytime)^A								
Colour	1		2		3		4	
	x	y	x	y	X	y	x	y
White	0.303	0.300	0.368	0.366	0.340	0.393	0.274	0.329
Yellow	0.498	0.412	0.557	0.442	0.479	0.520	0.438	0.472
Green⁸	0.026	0.399	0.166	0.364	0.286	0.446	0.207	0.771
Red	0.648	0.351	0.735	0.265	0.629	0.281	0.565	0.346
Blue⁸	0.140	0.035	0.244	0.210	0.190	0.255	0.065	0.216
Orange	0.558	0.352	0.636	0.364	0.570	0.429	0.506	0.404
Brown	0.430	0.340	0.610	0.390	0.550	0.450	0.430	0.390
Fluorescent Yellow-Green	0.387	0.610	0.369	0.546	0.428	0.496	0.460	0.540
Fluorescent Yellow	0.479	0.520	0.446	0.483	0.512	0.421	0.557	0.442
Fluorescent Orange	0.583	0.416	0.535	0.400	0.595	0.351	0.645	0.355

The colours shall be durable and uniform in acceptable hue when viewed in day light or under normal headlights at night.

1.3.8.4 The mandatory and warning signs shall be provided with white background and red border. The legend/symbol for these signs shall be in black

1.3.8.5 The colours chosen for informatory or guide signs shall be distinct for different categories of roads. For National Highways and State Highways, these signs shall be of green background with white borders, legends and word messages. For Expressways these signs shall be of blue background with white border, legends and word messages.

1.3.9 Refurbishments

Where existing signs are specified for refurbishments, the sheeting shall have semi-rigid aluminum backing or materials as per clause 1.2.5, pre-coated with aggressive tack type pressure sensitive adhesive. The adhesive shall be suitable for the type of material used for the signs and should thoroughly bond with that material.

1.3.10 Sizes of Letters

1.3.10.1 Letter size should be chosen with due regard to the speed, classification and location of the road, so that the sign is of adequate size for legibility but without being too large or obtrusive. The size of the letter, in terms of x-height, to be chosen as per the design speed is given in Table 800-8.

Table 800-8 Acceptable Limits for Size of Letters and Visibility Distance

Design Speed (kmph)	Minimum 'x' Height of the Letters (mm)	Minimum Sight Distance / Clear visibility distance (m)	Maximum Distance from Centre Line (m)
40	100	45	12
50	125	50	14
65	150	60	16
80	250	80	21
100	300	90	24
120	400	115	32

The thickness of the letters and their relation to the x-height, the width and the heights are indicated in Table IV (a) of the Annexure-IV to facilitate the design of the informatory signs and definition plates.

1.3.10.2 For advance direction signs on non-urban roads, the letter size ('x' height) should be minimum of 150 mm for National and State Highways and 100 mm for other roads. In case of overhead signs, the size ('X' height) of letters may be minimum 300 mm. Thickness of the letter could be varied from 1/6 to 1/5 of the letter 'x' size. The size of the initial uppercase letter shall be 1-1/3 times x-height. In urban areas, letter size shall be 100 mm on all directional signs. For easy and better comprehension, the word messages shall be written in initial upper case letter followed by lower case letters.

1.3.10.3 Letter size on definition plates attached with normal sized signs should be 100 mm or 150 mm. In the case of small signs, it should be 100 mm. Where the message is long, as for instance in "NO PARKING" and "NO STOPPING" signs, the message may be broken with two lines and the size of letters may be varied in the lines so that the definition plate is not too large. The lettering on definition plates will be all in upper case letters.

1.3.11 Warranty and Durability

The Contractor shall obtain from the original manufacturer of the Retro Reflective sheeting for period of Seven (7) years warranty for satisfactory field performance including stipulated retro reflectance of Micro-Prismatic sheeting and a Seven years warranty for High Intensity Grade and submit the same to the Engineer. The warranty shall be inclusive of the screen printed or cut out letters/legends and their bonding to the retro reflective sheeting. The contractor shall also furnish LOT numbers and certificate that the signs and material supplied against the assigned work meet all the stipulated requirements and carry the stipulated warranty and the contractor/supplier is the authorized converter of the particular sheeting.

All the signs shall be dated during the fabrication with indelible marking to indicate the start of the warranty. The warranty shall also cover the replacement obligation by the sheeting manufacturer as well as contractor for replacement/repair/restoration of the retro reflective efficiency.

A certificate in original shall be given by the manufacturer of the sheeting that its offered retro-reflective sheeting has been tested for various parameters such as co-efficient of retro reflection, day/night time color and luminance, shrinkage, flexibility, liner removal, adhesion, impact resistance, specular gloss and fungus resistance.; the tests shall be carried out by a Government laboratory in accordance with the various ASTM procedures and the results must show that the sheeting has passed the requirements for all the above mentioned parameters. A copy of the test reports shall be attached with the certificate.

1.4 Installation

1.4.1

The traffic signs shall be mounted on support posts, which may be of GI pipes conforming to IS 1239, Rectangular Hollow Section conforming to IS 4923 or square hollow Section conforming to IS 3589. Sign posts, their foundations and sign mountings shall be so constructed as to hold these in a proper and permanent position against the normal storm wind loads or displacement by vandalism. Normally, signs with an area up to 0.9 square metre shall be mounted on a single post, and for greater area, two or more supports shall be provided. Post End(s) shall be firmly fixed to the ground by means of properly designed foundation. The work of foundation shall conform to relevant Specifications as specified.

1.4.2 All components of signs and supports, other than the reflective portion of GI posts shall be thoroughly desealed, cleaned, primed and painted with two coats of epoxy paint. Any part of post below ground shall be painted with protective paint.

1.4.3 The signs shall be fixed to the posts by welding in the case of steel posts and by bolts and washers of suitable size in the case of reinforced concrete or GI posts. After the nuts have been tightened, the tails of the bolts shall be furred over with a hammer to prevent removal.

1.5 Measurement for Payment

The measurements of standard cautionary, mandatory and information signs shall be in number of different types of signs supplied and fixed, while for direction and place identification signs, these shall be measured by per Number

1.6 Rate

The Contract unit rate shall be payment in full for the cost of making the road sign, including all materials, installing it at the site and incidentals to complete the work in accordance with the Specifications. The contract rate shall be for a unit of One Number. for completed item as directed.

ITEM NO.32

Cautionary Warning Sign : Providing and fixing sign boards made out of 2mm Aluminium sheet size 90x90x90 cms. Equilateral triangle as per the design of IRC-67-

1977 pre treated with phospheting process and acid etching coated with one coat of apoxy primer and two coats of best quality epoxy paint reflectorised with retro reflective sheeting as per latest MOST specification 3.1 Mt. long stand post and frame fabricated from suitable size iron angle of 35x35x3mm, 75x75x6mm. as required painted with best quality epoxy coating in black and white bends the details of symbole for each board shall be as per the instruction of Engineer in charge the fixing at site shall be in 1:2:4 CC block of size 45x45x60cms. for each leg including excavation curring etc. complete under the supervision of engineer in charge (A) Engineering Grade.

801.1. General

801.1.1. The colour, configuration, size and location of all traffic signs for highways other than Expressways shall be in accordance with the Code of Practice for Road Signs, IRC: 67 or as shown on the drawings. For Expressways, the size of the signs, letters and their placement shall be as specified in the contract drawings and relevant Specifications. In the absence of any details or for any missing details, the signs shall be provided as directed by the Engineer.

801.1.2. The signs shall be either reflectorised or non-reflectorised as shown on the drawings or as directed by the Engineer. When they are of reflectorised type, they shall be of retro-reflectorised type and made of encapsulated lens type reflective sheeting vide clause 801.3, fixed over aluminium sheeting as per these Specifications.

801.1.3. In general, cautionary and mandatory signs shall be fabricated through process of screen printing. In regard to informatory signs with inscriptions, either the message could be printed over the reflective sheeting, or cut letters of non-reflective black sheeting used for the purpose which must be bonded well on the base sheeting as directed by the Engineer.

801.2 Materials

The various materials and fabrication of the traffic signs shall conform to the following requirements :

801.2.1. Concrete: Concrete shall be of the grade shown on the Contract drawings or otherwise as directed by the Engineer.

801.2.2. Reinforcing steel: Reinforcing steel shall conform to the requirement of IS: 1786 unless otherwise shown on the drawing.

801.2.3. Bolts, nuts, washers: High strength bolts shall conform to IS: 1367 whereas precision bolts, nuts, etc., shall conform to IS: 1364.

801.2.4. Plates and supports: Plates and support sections for the sign posts shall conform to IS: 226 and IS: 2062 or any other relevant IS Specifications.

801.2.5. Aluminium: Aluminium sheets used for sign boards shall be of smooth, hard and corrosion resistant aluminium alloy conforming to IS: 736 – Material designation 24345 or 1900.

801.2.6. Signs with a maximum side dimension not exceeding 600 mm shall not be less than 1.5 mm thick. All others shall be at least 2 mm thick. The thickness of the sheet be related to the size of the sign and its support and shall be such that it does not bend or deform under the prevailing wind and other loads.

801.2.7. In respect of sign sizes not covered by IRC: 67, the structural details (thickness, etc.) shall be as per the approved drawings.

801.3. Traffic Signs Having Retro-Reflective Sheeting

801.3.1. General requirements: The retro-reflective sheeting used on the sign shall consist of the white or coloured sheeting having a smooth outer surface which has the property of retro-reflection over its entire surface. It shall be weather-resistant and show colour fastness. It shall be new and unused and shall show no evidence of cracking, scaling, pitting, blistering, edge lifting or curling and shall have the negligible shrinkage and expansion. A certificate of having tested the sheeting for these properties in an unprotected outdoor exposure facing the sun for two years and its having passed these tests shall be obtained from a reputed laboratory, by the manufacturer of the sheeting. The reflective sheeting shall be either of engineering grade material with enclosed lens or of high intensity grade with encapsulated lens. The type of the sheeting to be used would depend upon the type, functional hierarchy and importance of the road.

800.1.3.2. High intensity grade sheeting: This sheeting shall be of encapsulated lens type consisting of spherical glass lens, elements adhered to a synthetic resin and encapsulated by a flexible, transparent waterproof plastic having a smooth surface. The retro-reflective surface after cleaning with soap and water and in dry condition shall have the minimum co-efficient of retro-reflection (determined in accordance with ASTM Standard E: 810) as indicated in Table 800-1.

**TABLE 800- 1. ACCEPTABLE MINIMUM COEFFICIENT OF RETRO-REFLECTION
FOR HIGH INTENSITY GRADE SHEETING
(CANDELAS PER FLUX PER SQUARE METRE)**

Observation angle (in degrees)	Entrance angle (in degrees)	White	Yellow	Orange	Green/ Red	Blue
0.2	-4	250	170	100	45	20
0.2	+30	150	100	60	25	20
0.5	-4	95	62	30	15	7.5
0.5	+30	65	45	25	10	5.0

When totally wet, the sheeting shall now show less than 90 percent of the values of retro-reflectance indicated in Table – 800 – 1. At the end of 7 years, the sheeting shall retain at least 75 percent of its original retro-reflectance.

801.3.3. Engineering grade sheeting: This sheeting shall be of enclosed lens type consisting of microscopic lens elements embedded beneath the surface of a smooth, flexible, transparent, waterproof plastic, resulting in a non-exposed lens optical reflecting system. The retro-reflective surface after cleaning with soap and water and in dry condition shall have the minimum coefficient of retro-reflection (determined in accordance with ASTM Standard: E-810) as indicated in Table 800-2.

**TABLE 800 –2. ACCEPTABLE MINIMUM COEFFICIENT OF RETRO-REFLECTION
FOR ENGINEERING GRADE SHEETING**

(CANDELAS PER LUX PER SQUARE METRE)

Observation angle in degree	Entrance angle in degree	White	Yellow	Orange	Green	Red	Blue
0.2	-4	70	50	25	9.0	14.5	4.0
0.2	+30	30	22	7.0	3.5	6.0	1.7
0.5	-4	30	25	13.5	4.5	7.5	2.0
0.5	+30	15	13	4.0	2.2	3.0	0.8

When totally wet, the sheeting shall not show less than 90 percent of the values, of retro-reflection indicated in Table 800 -2. At the end of 5 years, the sheeting shall retain at least 50 percent of its original retro-reflectance.

801.3.4. Messages / borders: The messages (legends, letters, numerals etc.) and borders shall either be screen printed or of cut-outs. Screen printing shall be processed and finished with materials and in a manner specified by the sheeting manufacturer. Cut-outs shall be of materials as specified by the sheeting manufacturer and shall be bonded with the sheeting in a manner specified by the manufacturer.

801.3.5. For screen-printed transparent coloured areas on white sheeting, the co-efficient of retro-reflection shall not be less than 50 percent of the values of corresponding colour in Table 800-1 and 2, as applicable.

801.3.6. Cut-out messages and borders, wherever used, shall be made out of retro-reflective sheeting (as per Clause 801.3.2. or 801.3.3. as applicable), except those in black which shall be of non-reflective sheeting.

801.3.7. Colour: Unless otherwise specified, the general colour scheme shall be as stipulated in IS: 5 “Colour for Ready Mixed Paints “. viz.

Blue	IS	Colour	No.166	French Blue
Red	IS	Colour	No.537	Signal Red
Green	IS	Colour	No.284	India Green
Orange	IS	Colour	No.591	Deep Orange

The colours shall be durable and uniform in acceptable hue when viewed in day light or under normal headlights at night.

801.3.8. Adhesives: The sheeting shall either have a pressure-sensitive adhesive of the aggressive –tack type requiring no heat, solvent or other preparation for adhesion to a smooth clean surface, or a tack free adhesive activated by heat, applied in a heat – vacuum applicator, in a manner recommended by the sheeting manufacturer. The adhesive shall be protected by an easily removable liner (removable by peeling without soaking in water or other solvent) and shall be suitable for the type of material of the base plate used for the sign. The adhesive shall form a durable bond to smooth, corrosion and weather resistant surface of the base plate such that it shall

not be possible to remove the sheeting from the sign base in one piece by use of sharp instrument. In case of pressure-sensitive adhesive sheeting, the sheeting shall be applied in accordance with the manufacturer's specifications. Sheeting with adhesives requiring use of solvents or other preparation for adhesive shall be applied strictly in accordance with the manufacturer's instructions.

801.3.9. Refurbishment: Where existing signs are specified for refurbishment, the sheeting shall have a semi-rigid aluminium backing pre-coated with aggressive – tack type pressure sensitive adhesive. The adhesive shall be suitable for the type of material used for the sign and should thoroughly bond with that material.

801.3.10 Fabrication:

801.3.10.1. Surface top be reflectorised shall be effectively prepared to receive the retro-reflective sheeting. The aluminium sheeting shall be de-greased either by acid or hot alkaline etching and all scale/dust removed to obtain a smooth plain surface before the application of retro-reflective sheeting. If the surface is rough, approved surface primer may be used. After cleaning, metal shall not be handled, except by suitable device or clean canvas gloves, between all cleaning and preparation operation and application of reflective sheeting/primer. There shall be no opportunity for metal to come in contact with grease, oil or other contaminants prior to the application of retro-reflective sheeting.

801.3.10.2. Complete sheets of the material shall be used on the signs except where it is unavoidable; at splices, sheeting with pressure sensitive adhesives shall be overlapped not less than 5 mm. Sheeting with heat-activated adhesives may be spliced with an overlap not less than 5 mm or butted with a gap not exceeding 0.75 mm. Where screen printing with transparent colours is proposed, only butt jointing shall be used. The material shall cover the sign surface evenly and shall be free from twists, cracks and folds. Cut – outs to produce legends and borders shall be bonded with the sheeting in the manner specified by the manufacturer.

801.3.11. Warranty and durability: The contractor shall obtain from the manufacturer a seven-year warranty for satisfactory field performance including stipulated retro-reflectance of the retro-reflective sheeting of high intensity grade and a five year warranty for the adhesive sheeting of engineering grade and submit the same to the engineer. In addition, a seven year and a five year warranty for satisfactory in-field performance of the finished sign with retro-reflective sheeting of high intensity grade and engineering grade respectively, inclusive of the screen printed or cut out letters/legends and their bonding to the retro-reflective sheeting shall be obtained from the Contractor/supplier and passed on to the Engineer. The Contractor/supplier shall also furnish a certification that the signs and materials supplied against the assigned work meets all the stipulated requirements and carry the stipulated warranty.

Processed and applied in accordance with recommended procedures, the reflective material shall be weather resistant and, following cleaning, shall show no appreciable discolouration, cracking, blistering or dimensional change and shall not have less than 50 percent of the specified minimum reflective intensity values (Table 800-1 and 800-2) when subjected to accelerated weathering for 1000 hours, using type E or EH Weatherometre (AASHTO Designation M 268).

801.4. Installation

801.4.1. Sign posts, their foundations and sign mountings shall be so constructed as to hold these in a proper and permanent position against the normal storm wind loads or displacement of vandalism. Normally, signs with an area up to 0.9 sq. m. shall be mounted on a single post, and for greater area two or more supports shall be provided. Sign supports may be of mild steel, reinforced concrete or galvanized iron (G. I). Post-end(s) shall be firmly fixed to the ground by means of properly designed foundation. The work of foundation shall conform to relevant Specifications as specified.

801.4.2. All components of signs and supports, other than the reflective portion and G. I. posts shall be thoroughly descaled, cleaned, primed and painted with two coats of epoxy paint. Any part of mild steel (M. S.) post below ground shall be painted with three coats of red lead paint.

801.4.3. The signs shall be fixed to the posts by welding in the case of steel posts and by bolts and washers of suitable size in the case of reinforced concrete or G. I. posts. After the nuts have been tightened, the tails of the bolts shall be furred over with a hammer to prevent removal.

801.5. Measurements for Payment

The measurement of standard cautionary, mandatory and information signs shall be in numbers of different types of signs supplied and fixed, while for direction and place identification signs, these shall be measured by area in square metres.

801.6. Rate

The contract unit rate shall be payment in full for the cost of making the road sign, including all materials, installing it at the site and incidentals to complete the work in accordance with the Specifications

Payment shall made on number basis

33

Citizen's information Board. Providing and fixing of typical MMGSY information board as per instruction. Two MS sheets of 3 mm thick, of 900 mm x 750mm size fixed at top & bottom duly rivetted with MS angles of 25 x 25 x 5 mm thick M.S angle shall be welded by two vertical M.S angle of 5 mm thick to 75 mm x 75 mm of 12 SWG square tubes posts duly embedded in cement concrete M-15 grade blocks of 600mm x 600mm x 750mm, below ground level. The letters & figure of any shade reflectorised with High Intensity Prismatic Grade Retro Reflective Sheeting of Type-4 as per ASTM D-4956 and latest MORD specifications; All sections of framed posts and steel tube will be painted with primer and two coats of epoxy paints as per drawing Clause 1701 and Annexure 1700.1 (10.16). (A) Class-B High intensity Grade Retro Reflective sheeting.

2. Material & Manufacturing:

2.1 Scope

The work shall consist of fabrication, supply and installation of ground mounted traffic signs on roads. The details of the signs shall be as shown in the drawings and in conformity with the code of practice for Road signs, IRC 67-2012.

2.2 Materials

The various materials and fabrication of the traffic signs shall conform to the following requirements:

2.2.1 Concrete:

Concrete for the foundation shall be of M15 Grade as per section 1700 or the grade shown on the drawings or otherwise as directed by the Engineer.

2.2.2 Reinforcing Steel

Reinforcing steel shall conform to the requirements of IS: 1786 unless otherwise shown on the drawings

2.2.3 Bolts, Nuts and Washers

High strength Bolts shall conform to IS: 1367 whereas precision bolts, nuts, etc. shall conform to IS: 1364

2.2.4 Plates and Supports

Plates and support sections for the sign posts shall conform to IS: 226 and IS: 2062 or any other relevant IS specifications.

2.2.5 Substrate

Sign panel shall be fabricated on Aluminum sheet, aluminum composite panel, fibre glass sheeting, or sheet moulding compound. Aluminum sheets used for sign boards shall be of smooth, hard and corrosion resistance aluminum alloy conforming to IS: 736-Material Designation 24345 or 1900. Aluminum composite Material (ACM) sheets shall be sandwiched construction with a thermoplastic core of Low Density Polyethylene (LDPE) between two thick skins/sheets of aluminum with overall thickness of 3mm or 4mm (as specified in the contract), and aluminum skin thickness 0.5mm and 0.3mm respectively on both the sides.

The mechanical proportion of ACM and that of aluminum skin shall conform to the requirements given in the table 800-1, when tested in accordance with the test methods mentioned against each of them.

Table 800-1: Specifications for Aluminum Composite Material (ACM)

Sr No.	Description	Specification for 4mm		Specification for 3mm
		Standard test	Acceptable value	Acceptable value
A	Mechanical Properties of ACM			
1	Peel off strength with retro reflective sheeting. (Drum Peel Test)	ASTM D903	Min. 4 N/mm	Min. 4 N/mm
2	Tensile strength	ASTM E8	Min. 40 N/mm ²	Min. 0 N/mm ²
3	0.2% Proof Stress	ASTM E8	Min. 34 N/mm ²	Min. 4 N/mm ²
4	Elongation	ASTM E8	Min. 6 %	Min. 5 %
5	Flexural strength	ASTM C393	Min. 130 N/mm ²	Min. 120 N/mm ²
6	Shear strength with Punch shear test	ASTM D732	Min. 18 N/mm ²	Min. 18 N/mm ²
8	Properties of Aluminium Skin			
1	Tensile strength (Rm)	ASTM E8	Min. 150 N/mm ²	Min. 100 N/mm ²
2	Modulus of elasticity	ASTM E8	Min. 70,000 N/mm ²	Min. 70,000 N/mm ²
3	Elongation	ASTM E8	A50 Min. 2%	A50 Min. 2%
4	0.2 % Proof Stress	ASTM E8	Min. 110 N/mm ²	Min. 110 N/mm ²

2.2.6 Plate Thickness

Shoulder mounted ground signs with a maximum side dimension not exceeding 600 mm shall not be less than 1.5mm thick Aluminum and 3 mm thick with Aluminium Composite Material. All other signs shall be at least 2mm thick Aluminum and 4 mm thick with Aluminium Composite Material. The thickness of the sheet shall be related to the size of the sign and its support and shall be such that it does not bend or deform under prevailing wind and other loads.

2.2.7 In respect of sign sizes not covered by IRC-67, the structural details (thickness etc.) shall be as per the approved drawings or as directed by the Engineer.

2.3 Traffic signs having Retro Reflective Sheeting

2.3.1 General Requirements

The retro reflective sheeting used on the signs shall consist of white or coloured sheeting having a smooth outer surface, which has the property of retro reflection over its entire surface. It shall be weather resistant and exhibit colour fastness. It shall be new and unused and show no evidence of cracking, scaling, and pitting, blistering, edge lifting or curling and shall have negligible shrinkage or expansion. A certificate of having the sheeting tested for coefficient of retro reflection, daytime colour and luminance, shrinkage, flexibility, liner removal, adhesion, impact resistance, specular gloss and fungus resistance, 3 years outdoor weathering and its having passed these tests shall be obtained from International/Government laboratory/Institute by the manufacturer of the sheeting. The reflective sheeting shall be either of Engineering Grade material with enclosed lens, High Intensity Grade with encapsulated lens or Micro- Prismatic Grade retro reflective element material as given in Clauses 801.3.2 to 801.3.7. Guidance on the recommended application of each class of sheeting may be taken from IRC-67.

2.3.2 High Intensity Grade Sheeting

2.3.2.1 High Intensity Grade (Type III)

This sheeting shall be of encapsulated lens type consisting of spherical glass lens, elements adhered to a synthetic resin and encapsulated by a flexible, transparent water-proof plastic having a smooth surface or as an unmetallised micro prismatic reflective material elements. The retro-reflective surface after cleaning with soap and water and in dry conditions shall have the minimum coefficient of retro-reflection (determined with ASTM D:4956-09) as indicated in Table 800-2.

Table 800-2 Acceptable Minimum Coefficient of Retro-reflection for Type III High Intensity Grade Sheeting^A (Encapsulated Lens Type)
(Candelas Per Lux Per Square Metre)

Observation Angle	Entrance Angle	White	Yellow	Orange	Green	Red	Blue	Brown
0.1° ^B	-4°	300	200	120	54	54	24	14
0.1° ^B	+30°	180	120	72	32	32	14	10
0.2°	-4°	250	170	100	45	45	20	12
0.2°	+30°	150	100	60	25	25	11	8.5
0.5°	-4°	95	62	30	15	15	7.5	5.0
0.5°	+30°	65	45	25	10	10	5.0	3.5

^A Minimum Coefficient of Retro reflection (R_A) ($\text{cd.lx}^{-1}.\text{m}^{-2}$).

^B Values for 0.1° observation angles are supplementary requirements that shall apply only when specified by the purchaser in the contract or order. When totally wet, the sheeting shall show not less than 90 percent, of the values of retro reflectance indicated in above Table. At the end of 7 years, the sheeting shall retain at least 80 percent of its original retro-reflectance.

2.3.2.2 High Intensity Micro-Prismatic Grade Sheeting (HIP) (Type IV) :

This sheeting shall be of high intensity retro-reflective sheeting made of micro-prismatic retro-reflective element material coated with pressure sensitive adhesive. The retro-reflective surface after cleaning with soap and water and in dry condition shall have the minimum co-efficient of retro-reflection (determined in accordance with ASTM D 4956-09) as indicated in Table 800-3.

Table 800-3 Acceptable Minimum Coefficient of Retro-Reflection for
Type IV High Intensity Micro-prismatic Grade Sheeting^A

(Candelas Per Lux Per Square Metre)

Observation Angle	Entrance Angle	White	Yellow	Orange	Green	Red	Blue	Brown	Fluorescent Yellow-Green	Fluorescent Yellow	Fluorescent Orange
0.1° ^B	-4°	500	380	200	70	90	42	25	400	300	150
0.1° ^B	+30°	240	175	94	32	42	20	12	185	140	70
0.2°	-4°	360	270	145	50	65	30	18	290	220	105
0.2°	+30°	170	135	68	25	30	14	8.5	135	100	50
0.5°	-4°	150	110	60	21	27	13	7.5	120	90	45
0.5°	+30°	72	54	28	10	13	6	3.5	55	40	22

^AMinimum Coefficient of Retro reflection (R) ($\text{cd.lx}^{-1}.\text{m}^{-2}$).

^BValues for 0.1° observation angles are supplementary requirements that shall apply only when specified by the purchaser in the contract or order. When totally wet, the sheeting shall show not less than 90 percent of the values of retro reflection indicated in above Table. At the end of 7 years, the sheeting shall retain at least 80 percent of its original retro-reflectance

1.3.5 Prismatic Grade Sheeting

1.3.5.1 Prismatic Grade Sheeting (Type VIII)

The reflective sheeting shall be retro reflective sheeting made of micro prismatic retro reflective material.

The retro reflective surface, after cleaning with soap and water and in dry condition shall have the minimum co-efficient of retro reflection (determined in accordance with ASTM D: 4956-09) as indicated in Table 800-4

Table 800-4 Acceptable Minimum Coefficient of Retro-reflection for Type VIII Prismatic Grade Sheeting^A
(Candelas Per Lux Per Square Metre)

Observation Angle	Entrance Angle	White	Yellow	Orange	Green	Red	Blue	Brown	Fluorescent Yellow - Green	Fluorescent Yellow	Fluorescent Orange
0.1° ^B	-4°	1000	750	375	100	150	45	30	800	600	300
0.1° ^B	+30°	460	345	175	46	69	21	14	370	280	135
0.2°	-4°	700	525	265	70	105	32	21	560	420	210
0.2°	+30°	325	245	120	33	49	15	10	260	200	95
0.5°	-4°	250	190	94	25	38	11	7.5	200	150	75
0.5°	+30°	115	86	43	12	17	5	3.5	92	69	35

^AMinimum Coefficient of Retro reflection (RA) ($\text{cd.lx}^{-1}.\text{m}^{-2}$).

^BValues for 0.1° observation angles are supplementary requirements that shall apply only when specified by the purchaser in the contract or order. When totally wet, the sheeting shall show not less than 90 percent of the values of retro reflection indicated in above Table. At the end of 7 years, the sheeting shall retain at least 80 percent of its original retro-reflectance

1.3.5.2 Prismatic Grade Sheeting (Type IX)

The reflective sheeting shall be retro reflective sheeting made of micro prismatic retro reflective material. The retro reflective surface, after cleaning with soap and water and in dry condition shall have the minimum co-efficient of retro reflection (determined in accordance with ASTM D 4956-09) as indicated in Table 800-5

Table 800-5 Acceptable Minimum Coefficient of Retro-reflection for Type IX Prismatic Grade Sheeting^A
(Candelas Per Lux Per Square Metre)

Observation Angle	Entrance Angle	White	Yellow	Orange	Green	Red	Blue	Fluorescent Yellow-Green	Fluorescent Yellow	Fluorescent Orange
0.1° ^B	-4°	660	500	250	66	130	30	530	400	200
0.1° ^B	+30°	370	280	140	37	74	17	300	220	110
0.2°	-4°	380	285	145	38	76	17	300	230	115
0.2°	+30°	215	162	82	22	43	10	170	130	65
0.5°	-4°	240	180	90	24	48	11	190	145	72
0.5°	+30°	135	100	50	14	27	6	110	81	41
1.0°	-4°	80	60	30	8	16	3.6	64	48	24
1.0°	+30°	45	34	17	4.5	9.0	2	36	27	14

^AMinimum Coefficient of Retro reflection (R_A) ($\text{cd.lx}^{-1}.\text{m}^{-2}$).

^BValues for 0.1° observation angles are supplementary requirements that shall apply only when specified

by the purchaser in the contract or order. When totally wet, the sheeting shall show not less than 90 percent of the values, of retro reflection indicated in above Table. At the end of 10 years, the sheeting shall retain at least 80 percent of its original retro-reflectance.

1.3.5.3 Prismatic Grade Sheeting (Type XI)

Retro reflective sheeting typically manufactured as a cube corner. The reflective sheeting shall be retro reflective sheeting made of micro prismatic retro reflective material. The retro reflective surface, after cleaning with soap and water and in dry condition shall have the minimum co-efficient of retro reflection (determined in accordance with ASTM D 4956-09) as indicated in Table 800-6

Table 800-6 Acceptable Minimum Coefficient of Retro-reflection for Type XI Prismatic Grade Sheeting^A
(Candelas per Lux per Square Metre)

Observation Angle	Entrance Angle	White	Yellow	Orange	Green	Red	Blue	Brown	Fluorescent Yellow-Green	Fluorescent Yellow	Fluorescent Orange
0.1° ^B	-4°	830	620	290	83	125	37	25	660	500	250
0.1° ^B	+30°	325	245	115	33	50	15	10	260	200	100

0.2°	-4°	580	435	200	58	87	26	17	460	350	175
0.2°	+30°	220	165	77	22	33	10	7	180	130	66
0.5°	-4°	420	315	150	42	63	19	13	340	250	125
0.5°	+30°	150	110	53	15	23	7	5	120	90	45
1.0°	-4°	120	90	42	12	18	5	4	96	72	36
1.0°	+30°	45	34	16	5	7	2	1	36	27	14

^AMinimum Coefficient of Retro reflection (R) ($\text{cd.lx}^{-1}.\text{m}^{-2}$).

^BValues for 0.1° observation angles are supplementary requirements that shall apply only when specified by the purchaser in the contract or order. When totally wet, the sheeting shall show not less than 90 percent of the values, of retro reflection indicated in above Table. At the end of 10 years, the sheeting shall retain at least 80 percent of its original retro-reflectance.

1.3.9 Adhesive

The sheeting shall have a pressure-sensitive adhesive of the aggressive-tack type requiring no heat, solvent or other preparation for adhesion to a smooth clean surface, in a manner recommended by the sheeting manufacturer. The adhesive shall be protected by an easily removable liner (removable by peeling without soaking in water or other solvent) and shall be suitable for the type of material of the base plate used for the sign. The adhesive shall form a durable bond to smooth, corrosion and weather resistant surface of the base plate such that it shall not be possible to remove the sheeting from the sign base in one piece by use of sharp instrument. The sheeting shall be applied in accordance with the manufacturer's specifications.

1.3.10 Fabrication

Surface to be reflectorised shall be effectively prepared to receive the retro-reflective sheeting. The aluminium sheeting shall be de-greased either by acid or hot alkaline etching and all scale/dust removed to obtain a smooth plain surface before the application of retro-reflective sheeting. If the surface is rough, approved surface primer may be used. After cleaning, metal shall not be handled, except by suitable device or clean canvas gloves, between all cleaning and preparation operation and application of reflective sheeting/primer. There shall be no opportunity for metal to come in contact with grease, oil or other contaminants prior to the application of retro-reflective sheeting. Complete sheets of the material shall be used on the signs except where it is unavoidable. At splices, sheeting with pressure-sensitive adhesives shall be overlapped not less than 5 mm. Where screen printing with transparent colours is proposed, only butt joint shall be used. The material shall cover the sign surface evenly and shall be free from twists, cracks and folds. Cut-outs to produce legends and borders shall be bonded with the sheeting in the manner specified by the manufacturer.

1.3.11 Message /

Border

The messages (legends, letters, numerals, etc.) and borders shall either be screen-printed or of cut out from durable transparent overlay or cut out from the same type of reflective sheeting for the cautionary/mandatory sign boards. Screen printing shall be processed and finished with materials and in a manner specified by the sheeting manufacturer. For the informatory and other sign boards, the messages (legends, letters, numerals etc.) and borders shall be cut out from durable transparent overlay film or cut-out from the same reflective sheeting only. Cut-outs shall be from durable transparent overlay materials as specified by the sheeting manufacturer and shall be bonded with the sheeting in the manner specified by the manufacturer. For screen-printed transparent coloured areas on white sheeting, the co-efficient of retro-reflection shall not be less than 50 per cent of the corresponding values in Tables 800-2 to 800-6 as applicable. Cut-out messages and borders, wherever used, shall be either made out of retro-reflective sheeting or made out of durable transparent overlay except those in black which shall be of non-reflective sheeting or opaque in case of durable transparent overlay.

1.3.12 Color for Signs

1.3.12.1 Signs shall be provided with retro-reflective sheeting and/or overlay film/screening ink as shown on the detailed drawings. The reverse side of all signs shall be painted grey

1.3.12.2 Except in the case of railway level crossing signs (for which the colour scheme is given later) the sign posts shall be painted in 250 mm wide bands, alternately black and white. The lowest band next to the ground shall be in black

1.3.12.3 The colour of the material shall be located within the area defined by the chromaticity coordinates in Table 8.1 and comply with the luminance factor given in Table 800-7 when measured as per ASTM D:

4956-09

<i>Table 8.1 Specilication Limits (Daytime)^A</i>								
Colour	1		2		3		4	
	x	y	x	y	X	y	x	y
<i>White</i>	0.303	0.300	0.368	0.366	0.340	0.393	0.274	0.329
<i>Yellow</i>	0.498	0.412	0.557	0.442	0.479	0.520	0.438	0.472
<i>Green⁸</i>	0.026	0.399	0.166	0.364	0.286	0.446	0.207	0.771
<i>Red</i>	0.648	0.351	0.735	0.265	0.629	0.281	0.565	0.346
<i>Blue⁸</i>	0.140	0.035	0.244	0.210	0.190	0.255	0.065	0.216
<i>Orange</i>	0.558	0.352	0.636	0.364	0.570	0.429	0.506	0.404
<i>Brown</i>	0.430	0.340	0.610	0.390	0.550	0.450	0.430	0.390
<i>Fluorescent Yellow-Green</i>	0.387	0.610	0.369	0.546	0.428	0.496	0.460	0.540
<i>Fluorescent Yellow</i>	0.479	0.520	0.446	0.483	0.512	0.421	0.557	0.442
<i>Fluorescent Orange</i>	0.583	0.416	0.535	0.400	0.595	0.351	0.645	0.355

The colours shall be durable and uniform in acceptable hue when viewed in day light or under normal headlights at night.

1.3.8.6 The mandatory and warning signs shall be provided with white background and red border. The legend/symbol for these signs shall be in black

1.3.8.7 The colours chosen for informatory or guide signs shall be distinct for different categories of roads. For National Highways and State Highways, these signs shall be of green background with white borders, legends and word messages. For Expressways these signs shall be of blue background with white border, legends and word messages.

1.3.11 Refurbishments

Where existing signs are specified for refurbishments, the sheeting shall have semi-rigid aluminum backing or materials as per clause 1.2.5, pre-coated with aggressive tack type pressure sensitive adhesive. The adhesive shall be suitable for the type of material used for the signs and should thoroughly bond with that material.

1.3.12 Sizes of Letters

1.3.10.1 Letter size should be chosen with due regard to the speed, classification and location of the road, so that the sign is of adequate size for legibility but without being too large or obtrusive. The size of the letter, in terms of x-height, to be chosen as per the design speed is given in Table 800-8.

Table 800-8 Acceptable Limits for Size of Letters and Visibility Distance

Design Speed (kmph)	Minimum 'x' Height of the Letters (mm)	Minimum Sight Distance / Clear visibility distance (m)	Maximum Distance from Centre Line (m)
40	100	45	12
50	125	50	14
65	150	60	16

80	250	80	21
100	300	90	24
120	400	115	32

The thickness of the letters and their relation to the x-height, the width and the heights are indicated in Table IV (a) of the Annexure-IV to facilitate the design of the informatory signs and definition plates.

1.3.10.4 For advance direction signs on non-urban roads, the letter size ('x' height) should be minimum of 150 mm for National and State Highways and 100 mm for other roads. In case of overhead signs, the size ('X' height) of letters may be minimum 300 mm. Thickness of the letter could be varied from 1/6 to 1/5 of the letter 'x' size. The size of the initial uppercase letter shall be 1-1/3 times x-height. In urban areas, letter size shall be 100 mm on all directional signs. For easy and better comprehension, the word messages shall be written in initial upper case letter followed by lower case letters.

1.3.10.5 Letter size on definition plates attached with normal sized signs should be 100 mm or 150 mm. In the case of small signs, it should be 100 mm. Where the message is long, as for instance in "NO PARKING" and "NO STOPPING" signs, the message may be broken with two lines and the size of letters may be varied in the lines so that the definition plate is not too large. The lettering on definition plates will be all in upper case letters.

1.3.11 Warranty and Durability

The Contractor shall obtain from the original manufacturer of the Retro Reflective sheeting for period of Seven (7) years warranty for satisfactory field performance including stipulated retro reflectance of Micro-Prismatic sheeting and a Seven years warranty for High Intensity Grade and submit the same to the Engineer. The warranty shall be inclusive of the screen printed or cut out letters/legends and their bonding to the retro reflective sheeting. The contractor shall also furnish LOT numbers and certificate that the signs and material supplied against the assigned work meet all the stipulated requirements and carry the stipulated warranty and the contractor/supplier is the authorized converter of the particular sheeting.

All the signs shall be dated during the fabrication with indelible marking to indicate the start of the warranty. The warranty shall also cover the replacement obligation by the sheeting manufacturer as well as contractor for replacement/repair/restoration of the retro reflective efficiency.

A certificate in original shall be given by the manufacturer of the sheeting that its offered retro-reflective sheeting has been tested for various parameters such as co-efficient of retro reflection, day/night time color and luminance, shrinkage, flexibility, liner removal, adhesion, impact resistance, specular gloss and fungus resistance.; the tests shall be carried out by a Government laboratory in accordance with the various ASTM procedures and the results must show that the sheeting has passed the requirements for all the above mentioned parameters. A copy of the test reports shall be attached with the certificate.

1.5 Installation

1.4.1

The traffic signs shall be mounted on support posts, which may be of GI pipes conforming to IS 1239, Rectangular Hollow Section conforming to IS 4923 or square hollow Section conforming to IS 3589. Sign posts, their foundations and sign mountings shall be so constructed as to hold these in a proper and permanent position against the normal storm wind loads or displacement by vandalism. Normally, signs with an area up to 0.9 square metre shall be mounted on a single post, and for greater area, two or more supports shall be provided. Post End(s) shall be firmly fixed to the ground by means of properly designed foundation. The work of foundation shall conform to relevant Specifications as specified.

1.5.2 All components of signs and supports, other than the reflective portion of GI posts shall be thoroughly desealed, cleaned, primed and painted with two coats of epoxy paint. Any part of post below ground shall be painted with protective paint.

1.5.3 The signs shall be fixed to the posts by welding in the case of steel posts and by bolts and washers of suitable size in the case of reinforced concrete or GI posts. After the nuts have been tightened, the tails of the bolts shall be furred over with a hammer to prevent removal.

1.7 Measurement for Payment

The measurements of standard cautionary, mandatory and information signs shall be in number of different types of signs supplied and fixed, while for direction and place identification signs, these shall be measured by per Number

1.8 Rate

The Contract unit rate shall be payment in full for the cost of making the road sign, including all materials, installing it at the site and incidentals to complete the work in accordance with the Specifications

ITEM NO.34

Road Marking with Hot Applied paints with reflectorising glass beads on bitumin surface providing and laying a hot applied thermoplasting compund 2.5mm thick including reflectorising glass beads @250 gm per sq.mtr area, thickness of 2.5mm is excluding of surface applied glass beads as per IRC:35-2015 the finished surface to be level, uniform and free from streaks and holes, zebra patta/bump/centerline/edge line/ cut patta. the while color marking should provide liminance coefficient on cement road shall be min. 130 mcd/m²/lux and asphalt road shall be min 100 mcd/m²/lux during the survice life during the date the marking should meet the performanace criteria for night time reflectivity, wet reflectivity and skid resistance as mentioned in the section-15 of IRC 35-2015 warranty for retroreflectivity shall be two years

IRC:35-1977

- 8.2.7 A Line marking the center of a one way street or highway is line and shall be a broken line.
- 8.2.8 If the centre line is to be painted on the pavement of the approaches to a bridge, it shall be continued over the bridge provided that the width between the kerbs os 6m or more otherwise the centre line marking on approaches should be discontinued at 30to 35 m distance from each abutment of the bridge.
- 8.2.9 Centre line on rural roads shall be provided as per Table.1
- 8.2.10 Double lines shall not be normally painted on a two lane bridge except where restricted visibility makes it hazardous to overtake.
- 8.2.11 Typical centre lines markings for rural roads are shown in figs. 3 and 4
- 8.3 Traffic Lane Lines.
- 8.3.1 Further sub division of wide carriageways into separate lanes on either side of the centre line helps to regulate traffic into proper lanes and curbs the meandering tendency of the drivers, thereby promoting safety and ensuring maximum capacity. At intersection and on approaches thereto, marking of traffic lanes eliminates confusion and facilities through and turning movements. Traffic lanes should also be marked near pedestrian crossings, at other dangerous location in rural and urban areas, in congested areas where the carriageway can accommodate more lanes, and on important one way streets. Since respect for road marking grows with proper usage, traffic lane should not be marked indiscriminately.
- 8.3.2 Traffic lane shall normally be single broken lines. Their width shall be 100 mm.
- 8.3.3 In urban areas, the length of line segments shall be 1.5m. The gaps on straight reaches shall be 3 m long and gaps on curved reaches and approaches to intersection shall be 1.5m long. In rural areas the line segment and gaps shall be twice the lengths mentioned above.
- 8.3.4 Solid lane lines can be used on approaches to intersections and in other areas, when lane changes are to be restricted.
- 8.3.5 Typical lane lines are shown in Figs. 2,3, and 4.
- 8.4.0 Marking for No Overtaking Zones.
- 8.4.1 No overtaking zones shall be established on summit curves, horizontal curves and elsewhere on two and three lane highway where overtaking maneuvers must be prohibited because of restricted sight distances or other hazardous conditions.

- 8.4.2 On undivided highways with more than 3 lanes, there is hardly any need for vehicles to cross the centre lines for overtaking. The double solid centre line prescribed for such highway is to be regarded as continuous no overtaking marking which is not to be crossed on either side.
- 8.4.3 A no-overtaking zone shall be marked by a solid yellow line along the centre. In case of double yellow lines the left hand element shall be a solid marrier line, the right hand element will be either a normal broken centre line or a solid barrier line governing the traffic from the opposite direction. Where a solid barrier line is to the right of broken line the passing restriction shall apply only to the opposing traffic.
- 8.4.4 The width each line shall be 100 mm. These shall be separated by 100 mm (Fig.1)
- 8.4.5 No overtaking zone markings shall be marked when the sight distance available is less than the intermediate sight distance given in Table.2 Table 2 also indicates the minimum barrier line distance. The method of locating and setting out of the barrier lines is shown in Fig.5. the steps involved are as follows.
- (i) Using the sighting poles 1.2m in height and a cord in length equal to the corresponding intermediate sight distance indicated in Table 2 establish points A_E and B_E where the sight distance for travel left to right first falls below the intermediate sight distance.
 - (ii) From B_E measure back the corresponding barrier Line distanace indicate in Table 2 point C_E The barrier line starts at this point.
 - (iii) Establish point B_w and A_w where the sight distance is first regained and terminate the barrier line at point B_w
 - (iv) Establish the barrier line for the opposite direction of travel noting that points A_w and B_w have already been established leaving only C_w to be determined.
- 8.4.6 If the length of road with road with sigh distance below the minimum sight distance is less than the minimum length of barrier line shown in Table 2,, the additional length of marking shall be added to the beginning of the zone.
- 8.4.7 Where the distance between the end of one barrier line and the beginning of the next barrier line restricting traveling in the same direction is less than the minimum length of barrier line shown in the Table.2, the barrier lines shall be jointed to form one continuous barrier line.
- 8.4.8 "No-overtaking: signs as per IRC-67-1977 shall be used to emphasis the existence and extent of a no-overtaking zone.
- 8.4.9 The no-overtaking zone markings should preferably be laid with thermoplastic material.
- 8.4.10 The marking of the no-overtaking zone at horizontal and vertical curves shall be as shown in Fig.5

Payment shall made on Sqm basis

ITEM NO.35

Cat Eye / Road Stud / RPM: Supplying Raised Pavement Markers made of polycarbonate and ABS moulded body and reflective panels with Micro prismatic lens (No Glass bead lens) capable of providing total internal reflection of the light entering the lens face and shall support a load of 13635 kgs. tested in accordance to ASTM D 4280 Type H and complying to Specifications of Category A of MORTH Circular No RW/NH/33023/10-97 D DO III Dt 11.06. 1997. The height, width and length shall not exceed 20 mm, 130 mm and 130 mm and with minimum reflective area of 13 Sqcm on each side and the slope to the base shall be 35 +/- 5 degree. The body of the marker should having finger grip for easy and accurate placement and

application with epoxy / bituminous Adhesive as recommended by the manufacturer of the marker. The color of the marker should be as per the IRC 35-2015 and as directed by Engineer-in . (A) Engineer Grade

1.1 General

Reflective Pavement marker (RPM) or road stud is device which is bonded to or anchored within the road surface for lane marking and delineation for night time visibility. It reflects incident light in directions close to the direction from which it came.

1.2 Definitions

1.2.1 Description of Terms Specific to this standard

1.2.1.1 Coefficient of luminous intensity (CIL) or specific intensity = the ratio of luminous intensity of the retro-reflector in the direction of observation to luminance at the retro-reflector on a plane perpendicular to the direction of the incident light expressed in terms of Milaca deal as per incident lux (med/ lx).

1.2.1.2 Horizontal entrance angle – the angle in the horizontal plant between the direction of incident light and the normal to the leading edge of the marker.

1.2.1.3 Observation angle – the angle in the reflector between the illumination axis and the observation axis.

1.2.1.4 Retro – reflection – reflection in which the radiation is returned in direction close to the direction from which it came, this property being maintained over were variations of the direction of incident radiation.

1.2.1.5 Head – that part of a road stud which is above the road surface where the road stud is fixed in position in the road.

1.2.1.6 Upper surface – that part of the external surface of road stud which is visible when the road stud is fixed in position in the road.

1.2.1.7 Anchorage – that part of a road stud which is below the road surface above the road stud is fixed position in the road.

1.3 Material

1.3.1 Plastic body of RPM road stud shall be molded from ASA (Acrylic Sterner Acrylonitrile) or HIPS (Impacts polystyrene) or ABS or any other suitable material approved by the Engineer-in-charge. The marker shall support a load of 13635 kg tested in accordance with ASTM D4280.

1.3.2 Reflective panels shall consist if number of lenses containing single or dual prismatic cubes capable of providing total internal reflection of the light entering the lens face. Lenses shall be molded of methyl methecrylate conforming to ASTMD 788 or equivalent.

1.4 Design

1.4.1 The slope or retro-reflecting surface shall preferably be 35 ± 5 degree to base.

1.4.2 The area of each retro-reflecting surface shall not be less than 13.0 Sq.cm.

1.5 Optical Performance

1.5.1 Unidirectional and bi-directional studs

1.5.1.1 Each reflector or combination of reflectors on each face of the stud shall have a CIL not less than given in Table 1 or 2 as appropriate.

Table 1 Minimum C.I.L. Values for Category "A" studs.

Entrance angle	Observation angle	C.I.L. in med 1 x		
		White	Amber	Red
0" U 5" L & R	0.3"	220	110	44
0" U 10" L & R	0.5"	120	60	24

Table 1 Minimum C.I.L. Values for Category "B" studs.

Entrance angle	Observation angle	C.I.L. in med 1 x		
		White	Amber	Red
0" U 6" L & R	0.3"	20	10	4

0" U 10" L & R	0.5"	15	7.5	3
----------------	------	----	-----	---

Note: The entrance angle of 0"U corresponds to the normal aspect of the reflectors when the reflecting road stud is installed in horizontal road surface.

1.5.1.2 A stud that incorporates one or more corner cube reflectors shall be considered to be included in category "A". A stud that incorporates one or more biconvex reflectors shall be considered to be included in category "B".

1.5.2 Omni – directional studs

Each omni-directional stud shall have a minimum C.I.L. of not less than med/ lx.

1.5.3 Tests

1.5.3.1 Coefficient of luminance intensity can be measured by produced described in ASTM D 809 "Practice for Measuring Photometric Characteristics" or as recommended in BS 873 Part 4:1973.

1.5.3.2 Under test conditions a stud shall not be considered to fail the photometric requirements of the measured C.I.L. at any one position of measurement is less than the values specified in Table 1 or 2 provided that.

(A) The value is not less than 80% of the specified minimum, and

(B) The average of the left and right measurements for the specific angle is greater than the specified minimum.

1.6 Fixing of Reflective Markers

1.6.1 Requirements

1.6.1.1 The enveloping profile of the head of the stud shall be smooth and the studs shall not present any sharp edges to traffic.

1.6.1.2 The reflecting portions of the studs shall be free from crevice or ledges where dirt might accumulate.

1.6.1.3 All road studs shall be legibly marked with the name, trade mark or other means of identification of the manufacture.

1.6.1.4 Marker height shall not exceed 20 mm.

1.6.1.5 Marker width shall not exceed 130 mm.

1.6.1.6 The base of the marker shall be flat within 1.3 mm. If the bottom of the marker is configured. The outermost faces of the configurations shall not deviate more than 1.3 mm from a flat surface.

1.6.2 Placement

1.6.2.1 The reflective marker shall be fixed to the road surface using the adhesives and the produced recommended by the manufacturer. No nails shall be used to affix the marker as nails are hazardous for the roads.

1.6.2.2 Regardless of the type of adhesive used. The markers shall not be fixed if the pavement is not surface dry and on new asphalt concrete surfacing unit the surfacing has been opened to traffic for a period of not less than 14 hours.

1.6.2.3 The portions of the highway surface, to which the marker is to be bonded by the adhesive, shall be free of dirt, curing compound, grease, oil, moisture, loose or unsound layers, paint and any other material which would adversely affect the bond of the adhesive.

1.6.2.4 Use a wire brush, if necessary to loosen and remove dirt. Then brush or blow clean.

1.6.2.5 The adhesive shall be placed uniformly on the cleaned pavement surface or on the bottom to the marker in a quantity sufficient to result in complete coverage of the area of contact of the marker with no voids present and with a slight excess after the marker has been lightly pressed in place.

1.6.2.6 For epoxy installations, excess adhesive around the edge of the marker, excess adhesive on the pavement and adhesive on the exposed surfaces of the markers shall be immediately removed. Soft rags moistened with mineral spirits or kerosene may be used as necessary to remove adhesive from exposed faces of pavement marker.

1.7 Warranty and durability

The contractor shall obtain from the manufacturer a two year warranty for satisfactory light performance including stipulated retro-reflectance of the reflecting panel and submit the same to the Engineer. In addition, a two year warranty for satisfactory in-field performance of the finished road marker shall also be given by the contractor who carried out the work of fixing of reflective road markers. In case the markers are displaced, damaged or get worn out or lose their reflectivity compared to stipulated standards, the contractor would be required to replace all such markers within 15 days of the intimation from the Engineer at his own cost and with no extra remuneration to be paid for such works.

1.8 Measurement for Payment

The measurement of Cats eye shall be in numbers of markers supplied and fixed.

1.9 Rate

The contact unit rate for Cats eye shall be payment in full compensation for furnishing all labour, material, tools, equipment including incidental costs necessary for carrying out the work at site conforming to the specifications complete as per approved drawings or as directed.

ITEM NO.36

STOP SIGN:-Providing and fixing sign boards made out of 2mm aluminium sheet; size 90 * 90cms rectangle as per the design of IRC-67-1977 pre treated with phosphating process & acid etching; coated with one coat of epoxy primer and two coats of best quality epoxy paint; reflectorised with retro reflective sheeting as per latest M.O.S.T. Specifications; 3.1m long stand post and frame fabricated from suitable size iron angle of 35 * 35 * 3mm * 75 * 75 * 6mm as required; painted with best quality epoxy coatings in black and white bends. the details of symbol for each board shall be as per the instruction of engineer in charge. The fixing at site shall be in 1:2:4 CC block of size 45 * 45 * 60cms for each leg. including excavation curing etc. complete under the supervision of engineer in charge. (A) Engineer Grade

AND

ITEM NO.37

Direction sign (Junction board):-Providing and fixing sign boards made out of 2mm aluminium sheet; size 244 * 122cms rectangle as as per the design of IRC-67-1977 pre treated with phosphating process & acid etching; coated with one coat of epoxy primer and two coats of best quality epoxy paint; reflectorised with retro reflective sheeting as per latest M.O.S.T. Specifications; Letters and numerals should be as per IRC-30-1968, 3.1m long (2 nos) stand post and frame fabricated from suitable size iron angle of 50 * 50 * 5mm 75 * 75 * 6mm as required; painted with best quality epoxy coatings in black and white bends. the details of symbol or inscription / numerals for each board shall be as per the instruction of engineer incharge. The fixing at site shall be in 1:2:4 CC block of size 45 * 45 * 60cms for each leg. including plot under the supervision of engineer in charge. (A) Engineer Grade (VR)...

AND

ITEM NO.38

Distance Informatory/ Destubatuib sign: Providing and fixing sign boards made out of 2mm aluminium sheet; size 180 x 120cms. rectangle as as per the design of IRC-67-1977 pre treated with phosphating process & acid etching; coated with one coat of epoxy primer and two coats of best quality epoxy paint; reflectorised with retro reflective sheeting as per latest M.O.S.T. Specifications; Letters and numerals should be as per IRC-30-1968, 3.1m long (2 nos) stand post and frame fabricated from suitable size iron angle of 50 x 50 x 5mm 75 x 75 x 6mm as required; painted with best quality epoxy coatings in black and white bends. the details of symbol or inscription / numerals for each board shall be as per the instruction of engineer in charge. The fixing at site shall be in 1:2:4 CC block of size 45 x 45 x 60cms. for each leg. including excavation curing etc. complete under the supervision of engineer in charge. (A) Engineer Grade

AND

ITEM NO.39

Diversion sign board :-Providing & Fixing sign boards made out of 2mm aluminium sheet, size 180 x 60 cms. rectangle as per the attached drawing pre treated with phosphating process & acid etching. coated with one coat of epoxy primer and two coats of best quality epoxy paint reflectorised with retro reflective sheeting as per latest M.O.S.T. Specifications; Letters and numerals should be as per IRC-30-1968, 3.1m long (2nos) stand post and frame fabricated from iron angle of 35x35x3mm, 50x50x5mm painted with best quality epoxy coatings in black and white bends. The fixing at site shall be in 1:2:4 CC block of size 45 x 45x 60cms for each leg, including excavation curing etc. complete under the supervision of engineer in charge. (A) Engineer Grade (VR)...

801.1. General

801.1.1. The colour, configuration, size and location of all traffic signs for highways other than Expressways shall be in accordance with the Code of Practice for Road Signs, IRC: 67 or as shown on the drawings. For Expressways, the size of the signs, letters and their placement shall be as specified in the contract drawings and relevant Specifications. In the absence of any details or for any missing details, the signs shall be provided as directed by the Engineer.

801.1.2. The signs shall be either reflectorised or non-reflectorised as shown on the drawings or as directed by the Engineer. When they are of reflectorised type, they shall be of retro-reflectorised type and made of encapsulated lens type reflective sheeting vide clause 801.3, fixed over aluminium sheeting as per these Specifications.

801.1.3. In general, cautionary and mandatory signs shall be fabricated through process of screen printing. In regard to informatory signs with inscriptions, either the message could be printed over the reflective sheeting, or cut letters of non-reflective black sheeting used for the purpose which must be bonded well on the base sheeting as directed by the Engineer.

801.2 Materials

The various materials and fabrication of the traffic signs shall conform to the following requirements :

801.2.1. Concrete: Concrete shall be of the grade shown on the Contract drawings or otherwise as directed by the Engineer.

801.2.2. Reinforcing steel: Reinforcing steel shall conform to the requirement of IS: 1786 unless otherwise shown on the drawing.

801.2.3. Bolts, nuts, washers: High strength bolts shall conform to IS: 1367 whereas precision bolts, nuts, etc., shall conform to IS: 1364.

801.2.4. Plates and supports: Plates and support sections for the sign posts shall conform to IS: 226 and IS: 2062 or any other relevant IS Specifications.

801.2.5. Aluminium: Aluminium sheets used for sign boards shall be of smooth, hard and corrosion resistant aluminium alloy conforming to IS: 736 – Material designation 24345 or 1900.

801.2.6. Signs with a maximum side dimension not exceeding 600 mm shall not be less than 1.5 mm thick. All others shall be at least 2 mm thick. The thickness of the sheet be related to the size

of the sign and its support and shall be such that it does not bend or deform under the prevailing wind and other loads.

801.2.7. In respect of sign sizes not covered by IRC: 67, the structural details (thickness, etc.) shall be as per the approved drawings.

801.3. Traffic Signs Having Retro-Reflective Sheeting

801.3.1. General requirements: The retro-reflective sheeting used on the sign shall consist of the white or coloured sheeting having a smooth outer surface which has the property of retro-reflection over its entire surface. It shall be weather-resistant and show colour fastness. It shall be new and unused and shall show no evidence of cracking, scaling, pitting, blistering, edge lifting or curling and shall have the negligible shrinkage and expansion. A certificate of having tested the sheeting for these properties in an unprotected outdoor exposure facing the sun for two years and its having passed these tests shall be obtained from a reputed laboratory, by the manufacturer of the sheeting. The reflective sheeting shall be either of engineering grade material with enclosed lens or of high intensity grade with encapsulated lens. The type of the sheeting to be used would depend upon the type, functional hierarchy and importance of the road.

800.1.3.2. High intensity grade sheeting: This sheeting shall be of encapsulated lens type consisting of spherical glass lens, elements adhered to a synthetic resin and encapsulated by a flexible, transparent waterproof plastic having a smooth surface. The retro-reflective surface after cleaning with soap and water and in dry condition shall have the minimum co-efficient of retro-reflection (determined in accordance with ASTM Standard E: 810) as indicated in Table 800-1.

**TABLE 800- 1. ACCEPTABLE MINIMUM COEFFICIENT OF RETRO-REFLECTION
FOR HIGH INTENSITY GRADE SHEETING
(CANDELAS PER FLUX PER SQUARE METRE)**

Observation angle (in degrees)	Entrance angle (in degrees)	White	Yellow	Orange	Green/ Red	Blue
0.2	-4	250	170	100	45	20
0.2	+30	150	100	60	25	20
0.5	-4	95	62	30	15	7.5
0.5	+30	65	45	25	10	5.0

When totally wet, the sheeting shall now show less than 90 percent of the values of retro-reflectance indicated in Table – 800 – 1. At the end of 7 years, the sheeting shall retain at least 75 percent of its original retro-reflectance.

801.3.3. Engineering grade sheeting: This sheeting shall be of enclosed lens type consisting of microscopic lens elements embedded beneath the surface of a smooth, flexible, transparent, waterproof plastic, resulting in a non-exposed lens optical reflecting system. The retro-reflective surface after cleaning with soap and water and in dry condition shall have the minimum coefficient of retro-reflection (determined in accordance with ASTM Standard: E-810) as indicated in Table 800-2.

**TABLE 800 -2. ACCEPTABLE MINIMUM COEFFICIENT OF RETRO-REFLECTION
FOR ENGINEERING GRADE SHEETING**

(CANDELAS PER LUX PER SQUARE METRE)

Observation angle in degree	Entrance angle in degree	White	Yellow	Orange	Green	Red	Blue
0.2	-4	70	50	25	9.0	14.5	4.0
0.2	+30	30	22	7.0	3.5	6.0	1.7
0.5	-4	30	25	13.5	4.5	7.5	2.0
0.5	+30	15	13	4.0	2.2	3.0	0.8

When totally wet, the sheeting shall not show less than 90 percent of the values, of retro-reflection indicated in Table 800 -2. At the end of 5 years, the sheeting shall retain at least 50 percent of its original retro-reflectance.

801.3.4. Messages / borders: The messages (legends, letters, numerals etc.) and borders shall either be screen printed or of cut-outs. Screen printing shall be processed and finished with materials and in a manner specified by the sheeting manufacturer. Cut-outs shall be of materials as specified by the sheeting manufacturer and shall be bonded with the sheeting in a manner specified by the manufacturer.

801.3.5. For screen-printed transparent coloured areas on white sheeting, the co-efficient of retro-reflection shall not be less than 50 percent of the values of corresponding colour in Table 800-1 and 2, as applicable.

801.3.6. Cut-out messages and borders, wherever used, shall be made out of retro-reflective sheeting (as per Clause 801.3.2. or 801.3.3. as applicable), except those in black which shall be of non-reflective sheeting.

801.3.7. Colour: Unless otherwise specified, the general colour scheme shall be as stipulated in IS: 5 “Colour for Ready Mixed Paints “. viz.

Blue	IS	Colour	No.166	French Blue
Red	IS	Colour	No.537	Signal Red
Green	IS	Colour	No.284	India Green
Orange	IS	Colour	No.591	Deep Orange

The colours shall be durable and uniform in acceptable hue when viewed in day light or under normal headlights at night.

801.3.8. Adhesives: The sheeting shall either have a pressure-sensitive adhesive of the aggressive –tack type requiring no heat, solvent or other preparation for adhesion to a smooth clean surface, or a tack free adhesive activated by heat, applied in a heat – vacuum applicator, in a manner recommended by the sheeting manufacturer. The adhesive shall be protected by an easily removable liner (removable by peeling without soaking in water or other solvent) and shall be

suitable for the type of material of the base plate used for the sign. The adhesive shall form a durable bond to smooth, corrosion and weather resistant surface of the base plate such that it shall not be possible to remove the sheeting from the sign base in one piece by use of sharp instrument. In case of pressure-sensitive adhesive sheeting, the sheeting shall be applied in accordance with the manufacturer's specifications. Sheeting with adhesives requiring use of solvents or other preparation for adhesive shall be applied strictly in accordance with the manufacturer's instructions.

801.3.9. Refurbishment: Where existing signs are specified for refurbishment, the sheeting shall have a semi-rigid aluminium backing pre-coated with aggressive – tack type pressure sensitive adhesive. The adhesive shall be suitable for the type of material used for the sign and should thoroughly bond with that material.

801.3.10 Fabrication:

801.3.10.1. Surface to be reflectorised shall be effectively prepared to receive the retro-reflective sheeting. The aluminium sheeting shall be de-greased either by acid or hot alkaline etching and all scale/dust removed to obtain a smooth plain surface before the application of retro-reflective sheeting. If the surface is rough, approved surface primer may be used. After cleaning, metal shall not be handled, except by suitable device or clean canvas gloves, between all cleaning and preparation operation and application of reflective sheeting/primer. There shall be no opportunity for metal to come in contact with grease, oil or other contaminants prior to the application of retro-reflective sheeting.

801.3.10.2. Complete sheets of the material shall be used on the signs except where it is unavoidable; at splices, sheeting with pressure sensitive adhesives shall be overlapped not less than 5 mm. Sheeting with heat-activated adhesives may be spliced with an overlap not less than 5 mm or butted with a gap not exceeding 0.75 mm. Where screen printing with transparent colours is proposed, only butt jointing shall be used. The material shall cover the sign surface evenly and shall be free from twists, cracks and folds. Cut – outs to produce legends and borders shall be bonded with the sheeting in the manner specified by the manufacturer.

801.3.11. Warranty and durability: The contractor shall obtain from the manufacturer a seven-year warranty for satisfactory field performance including stipulated retro-reflectance of the retro-reflective sheeting of high intensity grade and a five year warranty for the adhesive sheeting of engineering grade and submit the same to the engineer. In addition, a seven year and a five year warranty for satisfactory in-field performance of the finished sign with retro-reflective sheeting of high intensity grade and engineering grade respectively, inclusive of the screen printed or cut out letters/legends and their bonding to the retro-reflective sheeting shall be obtained from the Contractor/supplier and passed on to the Engineer. The Contractor/supplier shall also furnish a certification that the signs and materials supplied against the assigned work meets all the stipulated requirements and carry the stipulated warranty.

Processed and applied in accordance with recommended procedures, the reflective material shall be weather resistant and, following cleaning, shall show no appreciable discolouration, cracking, blistering or dimensional change and shall not have less than 50 percent of the specified minimum reflective intensity values (Table 800-1 and 800-2) when subjected to accelerated weathering for 1000 hours, using type E or EH Weatherometre (AASHTO Designation M 268).

801.4. Installation

801.4.1. Sign posts, their foundations and sign mountings shall be so constructed as to hold these in a proper and permanent position against the normal storm wind loads or displacement of vandalism. Normally, signs with an area up to 0.9 sq. m. shall be mounted on a single post, and for greater area two or more supports shall be provided. Sign supports may be of mild steel, reinforced concrete or galvanized iron (G. I). Post-end(s) shall be firmly fixed to the ground by

means of properly designed foundation. The work of foundation shall conform to relevant Specifications as specified.

801.4.2. All components of signs and supports, other than the reflective portion and G. I. posts shall be thoroughly descaled, cleaned, primed and painted with two coats of epoxy paint. Any part of mild steel (M. S.) post below ground shall be painted with three coats of red lead paint.

801.4.3. The signs shall be fixed to the posts by welding in the case of steel posts and by bolts and washers of suitable size in the case of reinforced concrete or G. I. posts. After the nuts have been tightened, the tails of the bolts shall be furred over with a hammer to prevent removal.

801.5. Measurements for Payment

The measurement of standard cautionary, mandatory and information signs shall be in numbers of different types of signs supplied and fixed, while for direction and place identification signs, these shall be measured by area in square metres.

801.6. Rate

The contract unit rate shall be payment in full for the cost of making the road sign, including all materials, installing it at the site and incidentals to complete the work in accordance with the Specifications

Payment shall made on number basis

Signature of Contractor

Executive Engineer

Panchayat (R&B) Division

Junagadh.

Deputy Executive Engineer

Panchayat R&B Sub Dn

Junagadh-2

Name of work :- Resurfacing of Chhodavadi Kariya Road Ch.00/000 to 6/915 Km. Ta.Bhesan Dist.Junagadh

Schedule for Testing of Material

For ensuring quality control and workmanship, various test prescribed below corresponding to the material concerned shall be taken as periodic intervals as stipulated below.. The Material shall be got tested at GERI or Govt. recognized Laboratory or field Laboratory of GERI for which 1 % of the estimated amount put to tender shall be recovered from the contractor from the R.A. Bill and Final Bills as the testing charges shall be paid by the Govt. to the Laboratory. However if the charges increase over 1 % no excess recovery shall be made from the contractor as per resolution of B&C department dated 10th May 1985, vide TNC/1085 (4) S.

TEST SCHEDULE

Sr. No.	Material /Item	Approx. Qty.		Description of tests.	Frequency of test	No. of reqd. tests
1	Cement	226.29	MT	Fineness, Compressive Strength, Consistency setting time, Chemical Analysis	1 test /50MT	4
2	Asphalt VG-30	175.30	MT	Penetration, Ductility, Softening point, Viscosity,	1 test / 10 tankers	2
3	Earthwork	2756	Cum	PI/ LL/ OMC / MDD / CBR Sieve Analysis	1 test / 3000 cum	1
4	Quarry spall	17	Cum	Gradation, OMC, MDD, PI, CBR	5 test/500 to 1500cum	1
5	Hard murrum	1805	Cum	PI/ LL/ OMC / MDD / CBR Sieve Analysis	1 test / 3000 cum	1
6	Rubble	43	Cum	Weight Soundness water absorption	-	1
7	NP3 600dia Pipe	7.5	Rmt	-	Manu. certificate	Manu. certificate
8	NP3 900dia Pipe	97.5	Rmt	-	Manu. certificate	Manu. certificate
9	G.S.B.					
	53mm to 26.5mm	179	Cum	CBR, Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc	Up to 100 Cum - 1 Test 101 to 500 Cum - 3 Test 501 to 1500 Cum - 5	3

	26.5 to 4.75mm	230	Cum	CBR, Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc	Test 1500 to 5000 Cum - 7 Test	3
	stone dust	102	Cum	CBR, Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc		3
10	W.B.M.-2					
	63 to 45mm	886.1798	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc	Up to 100 Cum - 1 Test 101 to 500 Cum - 3 Test 501 to 1500 Cum - 5 Test 1500 to 5000 Cum - 7 Test	5
	13.20 mm	117.1808	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc		3
	stone dust	58.5904	Cum	PI Value		1
11	Paver BSG					
	25 to 40mm	1030.095	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc	Up to 100 Cum - 1 Test 101 to 500 Cum - 3 Test 501 to 1500 Cum - 5 Test 1500 to 5000 Cum - 7 Test	5
	10 to 20mm	206.019	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc		3
	6 to 10mm	137.346	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc		3
12	B.M.					
	26.5 to 19 mm	70.224	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc	Up to 100 Cum - 1 Test 101 to 500 Cum - 3 Test 501 to 1500 Cum - 5 Test 1500 to 5000 Cum - 7 Test	1
	19 to 13.2 mm	323.456	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc		3
	13.2 to 4.75 mm	646.912	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc		5
	4.75 to 2.36mm	210.672	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc		3
	Stone dust	153.216	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc		3
13	M.S.S.					
	13.2 to 9.5mm	239.184	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc	Up to 100 Cum - 1 Test 101 to 500 Cum - 3 Test 501 to 1500 Cum - 5	3

	2.36 to 4.75 mm	350.32	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc	Test 1500 to 5000 Cum - 7 Test	3
	Stone dust below 75 micron	207.776	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc		3
14	Core Test	-	-	Thickness , Density Bituminous Content	As per GOVT R&B Deptt. Circular Dt. 31/5/2017	As per requirement
For C.C. & C.D. Works						
15	Sand	318.0671	Cum	Silt content Gradation	1test /Work	1
16	40mm	206.245	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc	Up to 100 Cum - 1 Test 101 to 500 Cum - 3 Test 501 to 1500 Cum - 5 Test 1500 to 5000 Cum - 7 Test	3
17	20mm	232.1382	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc	Up to 100 Cum - 1 Test 101 to 500 Cum - 3 Test 501 to 1500 Cum - 5 Test 1500 to 5000 Cum - 7 Test	3
18	10mm	76.6248	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc	Up to 100 Cum - 1 Test 101 to 500 Cum - 3 Test 501 to 1500 Cum - 5 Test 1500 to 5000 Cum - 7 Test	1
19	40 to 63 mm	99.6622	Cum	Elongation, Gradation, Flakiness ,Water absorption, Impact, Abrasion etc	Up to 100 Cum - 1 Test 101 to 500 Cum - 3 Test 501 to 1500 Cum - 5 Test 1500 to 5000 Cum - 7 Test	1
Cocnrete Works						
20	C.C. cube M-10	112	Cum	Comp. strength	1 to 5 Cum -1 Sample 6 to 10 Cum -2 Sample 11 to 15 Cum -3 Sample 16 to 30 Cum - 4 Sample 31 to 50 Cum -5 Sample 51cum above - one additional sample for 50 Cum	6
21	C.C. cube M-15	317	Cum	Comp. strength	1 to 5 Cum -1 Sample 6 to 10 Cum -2 Sample 11 to 15 Cum -3 Sample 16 to 30 Cum - 4 Sample 31 to 50 Cum -5 Sample 51cum above - one additional sample for 50 Cum	10

22	CC Cube M-25	274	Cum	Comp. strength	1 to 5 Cum -1 Sample 6 to 10 Cum -2 Sample 11 to 15 Cum -3 Sample 16 to 30 Cum - 4 Sample 31 to 50 Cum -5 Sample 51cum above - one additional sample for 50 Cum	9
23	TMT Bar reinforcement	6.52	MT	Tensile strength Yield stress Elongation	1 test / for Each dia.	2
24	Water	-	-	Chemical Test	1 test / source	-
ROAD FURNITURE						
25	Retro reflective sheeting for the signage	102	No.	Co-efficient of Retro Reflection.	3 reading for 10 boards for each colour	As per Norms
26	Cat Eye	990	No.	Co-efficient of Luminous Intensity- ASTM D4280	1 sample for each colour	As per Norms
27	Hot applied Thermoplast Road marking	2106	Sq. Mt.	(RL) Retro Reflectivity (mcd/m ² /lux) Proportions of constituents of Marking Material Skid Resistance	5 reading for every 5 km	As Per Norms
Testing Charges shall be born by Govt. No refund be made or extra charge over 1 % shall be recoverable form the contractor.						

Sign of Contractor

Deputy Executive Engineer
Panchayat R&B Sub
Division
junagadh-2

Executive Engineer
Panchayat R&B Division

Junagadh