

SPECIFICATIONS OF MATERIALS INDEX

Particulars

Page No.

General Technical Specifications-General
Standard Technical Specifications

3

M.	1.		Water	5
M.	2.		Lime	5
M.	3.		Cement	5
M.	4.		White Cement	5
M.	5.		Coloured Cement	5
M.	6.		Sand	6
M.	7.		Stone Dust	6
M.	8.		Stone Grit	6
M.	9.		Cinder	7
M.	10.		Lime Mortar	7
M.	11.		Cement Mortar	8
M.	12.		Stone coarse aggregates For Nominal Mix Concrete	8
M.	13.		Black trap or equivalent Hard Stone Coarse aggregate For design Mix concrete	9
M.	14.		Brick bats aggregates	9
M.	15.		Brick	9
M.	16.		Stone	9
M.	17.		Laterite stone	10
M.	18.		Mild Steel Bars	10
M.	19.		High yield strength steel deformed bars	10
M.	20.		High tensile steel wires	10
M.	21.		Mild Steel binding Wires	11
M.	22.		Structural Steels	11
M.	23.		Galvanised iron sheets	11
M.	23.	A	G.I. Valleys gutters ridges	11
M.	24.		Asbestos cement sheets	11
M.	25.		Mangalore pattern roof tiles	11
M.	26.		Shuttering	11
M.	27.		Expansion Joints, premodulded Filler	12
M.	28.		Expansion Joints, copper strips & hold Fasts	12
M.	29.		Teak wood	13
M.	29.	A	Non Teak wood	13
M.	30.		Wooden Flush door shutters (Solid Core)	13
M.	31.		Aluminium Doors, Windows, Ventilators	14
M.	32.		Rolling steel gate	14
M.	33.		Collapsible steel gate	15
M.	34.		Welded steel Wire Fabric	15
M.	35.		Expanded metal sheets	15
M.	36.		Mild Steel Wires (Wire gauze Jali)	15

M.	37.		Plywood	16
M.	38.		Glass	16
M.	39.		Acrylic sheets	17
M.	40.		Particle board	17
M.	41.		Expanded polystyrene or Framed sty roper slabs	17
M.	42.		Resign boded Fiber glass	17
M.	43.		Fixtures and Fastening	18
M.	44.		Paints	19
M.	45.		French Polish	19
M.	46.		Marble pipes For marble mosaic terrazzo	19
M.	47.		Flooring tiles	20
M.	48.		Rough Kota stone	21
M.	49.		Polished Kota stone	22
M.	50.		Dholpur Stone slab	22
M.	51.		Marble slab	22
M.	52.		Granite stone slab	22
M.	53.		P.V.C. Flooring	23
M.	54.		Facing tiles	23
M.	55.		White glazed tiles	24
M.	56.		Galvanized iron pipes and fitting	24
M.	57.		Bib cooks and stop cock	24
M.	58.		Gun metal Wheel valve	24
M.	59.		while glazed porcelain wash basin	24
M.	60.		European type water closed	24
M.	61.		Orrissa type water closet	25
M.	62.		Indian type water closet	25
M.	62.	A	Foot Rests	25
M.	63.		Glazed earthenware sink	25
M.	64.		Glazed earthenware lipped type flat back urinal/Corner type urinal	25
M.	65.		Low level enamel Hushing tank	25
M.	66.		Cast Iron flushing cistern	25
M.	67.		Flush cock	26
M.	68.		Cash iron pipes and fitting	26
M.	69.		Nahni Trap	26
M.	70.		Gulley Trap	26
M.	71.		Glazed stoneware pipes and filling	27
M.	72.		Wall peg rail	27
M.	73.		G. 1. Water spout	27
M.	74.		Asbestos cement pipe (A.C. pipe)	27
M.	75.		Crydon ball valve	27
M.	76.		Bitumen fell for water proofing and damp proofing	27
M.	77.		Selected Earth	27
M.	78.		barbed-Wire	28

GENERAL TECHNICAL SPECIFICATIONS FOR BUILDING WORKS

GENERAL:

1. In the specifications "as directed" / "approved" shall be taken to mean "as directed" / "approved by the Engineer-in-Charge".
2. Wherever a reference to any Indian Standard appears in the specifications, it shall be taken to mean as a reference to the latest edition of the same in force on the date of agreement.
3. In "Mode of Measurement" in the specifications wherever a dispute arises in the absence of specific mention of a particular point of aspect the provisions on these particular points, or aspects in the relevant Indian Standards shall be referred to
4. All measurements and computations, unless otherwise specified, shall be carried out nearest to the following limits:
 - (i) Length, width and depth (height) 0.01 meter
 - (ii) Areas 0.01 Sq.Mt.
 - (iii) Cubic Contents 0.01 Cu.Mt.

In recording dimensions of work the sequence of length, width and height (depth) or thickness shall be followed.
5. The distance which constitutes lead shall be determined along the shortest practical route and note necessarily the route actually taken The decision of the Engineer-in-charge in this regard shall be taken as final.
6. Where no lead is specific, it shall mean "all leads"
7. Lift shall be measured from plinth level.
8. Up to "floor two level" means actual height of floor (Maxi 4 M) up to 3 Mt. above plinth level.
9. Definite particulars covered in the items of work, though not mentioned or elucidated in it specifications shall be deemed to be included therein.
10. Reference to specifications of materials as made in the detailed specification of the items of works is in the form of a designation containing them number of the specification of the material and prefix 'M' e.g. 'M-5',
11. Approval to the samples of various materials given by the Engineer-in-charge shall not absolve the contractor from the responsibility of replacing defective material brought on site or materials used in the work found defective at a later date. The contractor shall have no claim to any payment or compensation whatsoever on account of any such materials being rejected by the Engineer-in-charge.
12. The contract rate of the item of work shall be for the work completed in all aspects.
13. No collection of materials shall be made before it is got approved from the Engineer-in-charge.
14. Collection of approved materials shall be done at site of work in a systematic manner. Materials shall be stored as per IS 4082-1996 and in such a manner as to prevent

- damage, deterioration or intrusion of foreign matter and to ensure the preservation of their quality and fitness for the work.
15. Materials, if and when rejected by the Engineer-in-charge, shall be immediately removed from the site of work.
 16. No materials shall be stored prior to, during and after execution of a structure in such a way as to cause or lead to damage or overloading of the various components of the structure.
 17. All works shall be carried out in a workmanlike manner as per the best techniques for the particular item.
 18. All tools, templates, machinery and equipment for correct execution of the work as well as for checking lines, levels, alignment of the works during execution shall be kept in sufficient numbers and in good working condition on the site of the work.
 19. The mode, procedure and manner of execution shall be such that it does not cause damage or over-loading of the various components of the structure during execution or after completion of the structure.
 20. Special modes of construction not adopted in general Engineering practice if proposed to be adopted by the Contractor, shall be considered only if the contractor provides satisfactory evidence that such special mode of construction is safe, sound and helps in speedy construction and Completion of work to the required strength and quality. Acceptance of the same by the Engineer-in-Charge shall not, however absolve the contractor of the responsibility of any adverse effects and consequences of adopting the same in the course of execution of completion of the work.
 21. All installations pertaining to water supply and fixtures there of as well as drainage lines and sanitary fittings shall be deemed to be completed only after giving satisfactory tests by the contractor.
 22. The contractor shall be responsible for observing the rules and regulations imposed under the "Minor Minerals Act", and such of the laws and rules prescribed by Government from time to time.
 23. All necessary safety measures and precautions {including those laid down in the various relevant Indian Standards} shall be taken to ensure the safety of men. Materials and machinery on the works as also of the work itself.
 24. The testing charges of all materials shall be borne by the Contractor.
 25. Approval to any of the executed items for the work does not in any way relieve the contractor of his responsibility for the correctness, soundness and strength of the structure as per the drawings and specifications.

SPECIFICATIONS OF MATERIALS

M-1 Water

- 1.1. Water shall not be salty brackish and shall be clean, reasonably clear and free objectionable quantities of silt and traces of oil and injurious alkalis, salts, organic matter and other deleterious material which will either weaken the mortar of concrete or cause efflorescence or attack the steel in R.C.C. Container for transport, storage and handling of water shall be clean. Water shall conform to the standard specified in I.S. 456-1978.
- 1.2. If required by the Engineer-in-Charge it shall be tested by comparison with distilled water. Comparison shall be made by means of standard cement tests for soundness time of setting and mortar strength as specified in I.S. 269-1976. Any indication of unsoundness change in time of setting by 30 minutes or more or decrease of more than 10 per cent in strength, of mortar prepared with water sample when compared with the results obtained with mortar prepared with distilled water shall be sufficient cause for rejection of water under test.
- 1.3. Water for curing mortar, concrete or masonry should not be too acidic or too alkaline.
It shall be free of elements which significantly affect the hydration reaction or otherwise interfere with the hardening of mortar or concrete during curing or those which produce objectionable stains or other unsightly deposits on concrete or mortar surfaces
- 1.4. Hard and bitter water shall not be used for curing.
- 1.5. Potable water will generally found suitable for curing mortar or concrete.

M-2. Lime

- 2.1. Lime shall be hydraulic lime as per I.S. 712-1973. Necessary tests shall be carried out as per I.S. 6932 (Parts I to X) 1973
- 2.2. The following field tests for limes are to be carried out:
 - (1) A very rough idea can be formed about the type of lime by its visual examination i.e. fat lime bears pure white colour, lime in form of porous lumps of dirty white colour indicates quick lime, and solid lumps are the unburnt lime stone.
 - (2) Acid tests for determining the carbonate content in lime. Excessive amount of impurities and rough determination of class of lime.
- 2.3. Storage shall comply with I.S. 712-1973. The slaked lime, if stored, shall be kept in a weather proof and damp-proof shed with impervious floor and sides to protect it against rain, moisture, weather and extraneous materials mixing with it. All lime that has been damaged in any way shall be rejected and all rejected materials shall be removed from site of work.
- 2.4. Field testing shall be done according to I.S. 1624-1974 to show the acceptability of materials.

M-3. Cement

- 3.1. Cement shall be ordinary Portland slag cement as per I.S. 269-1976 or Portland slag cement as per I.S. 455-1976

M-4. White Cement

- 4.1. The white cement shall conform to I. S. 8042-E-1978.,

M-5. Coloured Cement

- 5.1. Coloured cement shall be with white or grey Portland cement as specified in the item of the work.

- 5.2.** The pigments used for coloured cement shall be of approved quality and shall not exceed 10% of cement used in the mix. The mixture of pigment add cement shall be properly ground to have a uniform colour and shade. The pigments shall have such properties to provide for durability under exposure to sunlight and weather.
- 5.3.** The pigment shall have the property such that it is neither affected by the cement nor detrimental to it

M-6 Sand

- 6.1.** Sand shall be natural sand, clean, well graded hard strong, durable and gritty particles free from injurious amounts of dust, clay kankar nodules, soft or flaky particles shale, alkali salts organic matter, loam, mica or other deleterious substances and shall be got approved from the Engineer-in-Charge. The sand shall not contain more than 8 percent of silt as determined by field test, if necessary the sand shall be washed to make it clean.
- 6.2. Coarse Sand :** The fineness modulus of coarse sand shall not be less than 2.5 and shall not exceed 3.0. The sieve analysis of coarse shall be as under :

I.S. Sieve Designation	Percentage by Weight Passing sieve	I.S. Sieve Designation	Percentage by Weight Passing Sieve
4.75 mm	100	600 Micron	30 - 100
2.36 mm	90 to 100	300 Micron	5 - 70
1.18 mm	70 - 100	150 Micron	0 - 50

- 6.3. Fine Sand :** The fineness modulus shall not exceed 1.0. The sieve analysis of fine sand shall be as under :

I.S. Sieve Designation	Percentage by Weight Passing through	I.S. Sieve Designation	Percentage by Weight Passing through
4.75 mm	100	600 Micron	40 - 85
2.36 mm	100	300 Micron	5 - 50
1.18 mm	70 - 100	150 Micron	0 - 10

M-7 Stone Dust :

- 7.1.** This shall be obtained from crushing hard black trap or equivalent. It shall not contain more than 8% of silt as determined by field test will measuring cylinder. The method of determining silt contents by fields test is given as under :
- 7.2.** A sample of stone dust to be tested shall be placed without drying in 200 mm. measuring cylinder. The quantity of the sample shall be such that it fills the cylinder up to 100 mm. mark. The clean water shall be added up to 150 mm. mark. The mixture shall be stirred vigorously and the content allowed to settle for 3 hours.
- 7.3.** The height of silt, visible as settled layer above the stone dust shall be expressed as percentage of the height of the stone dust below. The stone dust containing more than 8% silt shall be washed so as to bring the content within the allowable limit.
- 7.4.** The fineness modules of stone dust shall not be less than 1.80.

M-8. Stone Grit

- 8.1.** Grit shall consist of crushed or broken stone and be hard, strong, dense, durable, clean of proper gradation and free from skin or coating likely to prevent proper adhesion of mortar Grit shall generally be cubical in shape and as far as possible flakey elongated pieces shall be avoided. It shall generally

comply with the provisions of I.S. 383-1970. Unless special stone of particular quarries is mentioned grit shall be obtained from the best black trap or equivalent hard stone as approved by the Engineer-in-charge. The grit shall have no deleterious with cement.

8.2. The Grit shall conform to the following gradation as per sieve analysis :

I.S. Sieve Designation	Percentage Passing through sieve	I.S. Sieve Designation	Percentage by Weight Passing through Sieve
4.75 mm	100	600 Micron	40 - 85
2.36 mm	100	300 Micron	5 - 50
1.18 mm	70 - 100	150 Micron	0 - 10

8.3 The crushing strength of grit will be such as to allow the concrete in which it is used to built up the specified strength of concrete.

8.4. The necessary tests for grit shall be carried out as per the requirements of I.S.2386 (Parts I to VIII) 1963 as per instructions of the Engineer-in-charge. The necessity of test will be decided by the Engineer-in-charge.

M-9. Cinder

9.1. Cinder is will burnt furnace residue which has been fused or sintered into lumps of varying sizes.

9.2. Cinder aggregates shall be well burnt furnace residue obtained from furnace using coal fuel only it shall be sound clean and tree from clay dirt, ash or other deleterious matter.

9.3 The average grading for under aggregates shall be as mentioned below :

I.S. Sieve Designation	Percentage Passing	I.S. Sieve Designation	Percentage Passing
20 mm	100	4.75 mm	70
10 mm	86	2.36 mm	32

M-10 Lime Mortar

10.1 Lime shall conform to specification M-2. Water shall conform to specification M-1.

Sand shall conform to specification M-6.

10.2. Proportion of Mix:

10.2.1. mortar shall consist of such proportions of slaked lime and sand as may be specified in item The slaked lime and sand shall be measured by volume

10.3. Preparation of mortar:

10.3.1. Lime mortar shall be prepared by wet process as per I S 1625-1971 .Power driven mill shall be used for preparation of lime mortar. The slaked lime shall be placed in the mill in an even layer and ground for 180 revolutions with a sufficient water. Water shall be added as required during grinding (care being taken not to add more water) that will bring the mixed material to a consistency of stiff paste. Thoroughly wetted sand shall then be added evenly and the mixture ground for another 180 revolutions.

10.4. Storage:

10.4.1. Mortar shall always be kept damp, protected from sun and ram till used up, covering it by tarpaulin or open sheds.

10.5. Use:

10.5.1. All mortar shall be used as soon as possible after grinding. It should be used on the day on which it prepared, But in no case mortar made earlier than 36 hours shall be permitted for use.

M-11. Cement Mortar

11.1. Water shall conform to specification M-1. Cement shall conform to specifications M-3 and Sand shall conform to M-6

11.2. Proportion of Mix

11.2.1. Cement and sand shall be mixed to specified proportion, sand being measured by measuring boxes, the proportion of cement will be by volume on the basis of 50 Kg/Bag of cement being equal to 0.0342 cu.m. The mortar may be hand mixed or machine mixed as directed.

11.3. Preparation of Mortar :

11.3.1. In hand mixed mortar, cement and sand in the specified proportions shall be thoroughly mixed dry on a clean impervious platform by turning over at least 3 times or more till a homogeneous mixture of uniform colour is obtained. Mixing platform shall be so arranged that no deleterious extraneous material shall get mixed with mortar or mortar shall flow out. While mixing, the water shall be gradually added and thoroughly mixed to form a stiff plastic mass of uniform colour so that each particle of sand shall be completely covered with a film of wet cement. The water cement ratio shall be adopted as directed

11.3.2. The mortar so prepared shall be used within 30 minutes of adding water. Only such quantity of mortar shall be prepared as can be used within 30 minutes.

M-12. Stone Coarse Aggregate for Nominal Mix Concrete

12.1. Coarse aggregate shall be of machine crushed stone of black trap or equivalent and be hard strong, dense, durable, clean and free from skin and coating likely to prevent proper adhesion of mortar.

12.2. The aggregate shall generally be cubical in shape unless special stones of particular quarries are mentioned aggregates shall be machine crushed from the best black trap or equivalent hard stone as approved aggregate shall have no deleterious reaction with cement. The size of the coarse aggregate for plain cement and ordinary reinforced cement concrete shall generally be as per the table given below.

However in case of reinforced cement concrete the maximum limit may be restricted to 6 mm. less than the minimum lateral clear distance between bars or 6- mm. less than the cover whichever is smaller.

TABLE

I.S. Sieve Designation	Percentage passing for single sized aggregates of Nominal size			I.S. Sieve Designation	Percentage passing for single sized aggregates of Nominal size		
	40 mm	20 mm	16 mm		40 mm	20 mm	16 mm
80 mm	-	-	-	12.5 mm	-	-	-
63 mm	100	-	-	10 mm	0.5	0.02	0.30
40 mm	85-100	100	-	4.75 mm	-	0.5	0.5
20 mm	0-20	85-100	100	2.35 mm	-	-	-
16 mm	-	-	85-100				

Note : This percentage may be varied some what by the Engineer-in-charge when considered necessary for obtaining better density and strength of concrete.

12.3. The grading test shall be taken in the beginning and at the change of source of materials. The necessary tests, indicated in I.S. 383-1970 and 456-197f shall have to be carried out to ensure the acceptability. The aggregates shall be stored separately and handled in such a manner as to prevent the intermixing of different aggregates. If the aggregates are covered with dust, they shall be washed with water to make them clean. .

M-13. Black Trap or Equivalent Hard Stone Coarse

- 13.1. Aggregate For Design Mix Concrete :** Coarse aggregate shall be of machine crushed stone of black trap or equivalent hard stone and be hard, strong, dense, durable, clean and free from skin and coating likely to prevent proper adhesion of mortar.
- 13.2.** The aggregates shall generally be cubical in shape. Unless special stones of particular quarries are mentioned, aggregates shall be machine crushed, from the best, black trap or equivalent hard stones as approved, Aggregate shall have no deleterious with cement
- 13.3.** The necessary tests indicated in I S. 383-1970 and I.S.456-1978 shall have to be carried out to ensure the acceptability of the material.
- 13.4.** If aggregate is covered with dust it shall be washed with water to make it clean.

M-14. Brick Bats Aggregate

- 14.1.** Brick bat aggregate shall be broken from well burnt or slightly over burnt and dense bricks. It shall be homogeneous in texture, roughly cubical in shape, clean and free from dirt of any other foreign material. The brick bats shall be of 40 mm - 50 mm. size unless otherwise specified in the item. The under burnt or over burnt brick bats shall not be allowed.
- 14.2** The brick bats shall be measured by suitable boxes or as directed.

M-15. Bricks

- 15.1.** The bricks shall be hand or machine molded and made from suitable soils and kiln burnt. They shall be free from cracks and flaws and nodules of free lime they shall have smooth rectangular faces with sharp corners and shall be of uniform colour.
- The bricks shall be moulded with a frog of 100 mm. x 40 mm. and 10 mm. to 20 mm. deep on one of its flat sides. The bricks shall not break when thrown on the ground from a height of 600 mm.
- 15.2.** The size of modular bricks shall be 190 mm.x 90 mm.x 90 mm.
- 15.3.** The size of the conventional bricks shall be as under :
(9" x 4.3/8" x 2,3/4") 225 x 110 x 75 mm.
- 15.4.** Only bricks of one standard size shall be used on one work. The following tolerances shall be permitted in the conventional size adopted in a particular work.
Length + 1/8" (3.0 mm.) Width \pm 1/16" (1.50 mm.) Height + 1/16" (1.50 mm.)
- 15.5.** The crushing strength of the bricks shall not be less than 35 Kg/Sq. Cm. The average water absorption shall not be more the 20 percent by weight necessary tests for crushing strength and water absorption etc. shall be carried out as per I.S. 3495 (Part-I to IV) - 1976

M-16. Stone

- 16.1.** The stone shall be of the specified variety such as Granite/Trap Stone/ Quartzite or any other type of good hard stones. The stones shall be only from the approved quarry and shall be hard sound, durable and free from defects like cavities, cracks, sand holes, flaws injurious veins, patches of loose or soft materials etc. and weathered portions and other structural defects Or imperfections tending to affect their soundness and strength. The stone with round surface shall not be used. The percentage of water absorption shall not be more than 5% of dry weight. When tested in accordance with I.S. 1124-1974. The minimum crushing strength of stone shall be 200 Kg/.Sq. Cm. unless otherwise specified.
- 16.2.** The samples of the stone to be used shall be got approved before the work is started
- 16.3.** The Khanki facing stone shall be dressed by chisel as specified in the item for khanki facing in required shape and size. The face of the stone shall be-so dressed that the bushing on the

exposed face shall not project by more than 40 mm. from the general wall surface and on face to be plastered it shall not project by more than 19 mm. nor shall it have depressions more than 10 mm. from the average wall surface.

M-17. Laterite Stone

- 17.1. Laterite stone shall be obtained from the approved quarry it shall be compacted in texture sound, durable and free from soft patch. It shall have minimum crushing strength of 100 Kg/Sq. Cm. in its dry condition. It shall not absorb water more than 20% of its own weight, when immersed for 24 hours in water. After quarrying, the stone shall be allowed to weather for some time before using in work.
- 17.2. The stone shall be dressed into regular rectangular blocks so that all faces are free from waviness and unevenness, and the edges true and square
- 17.3. Those types of stone in which white clay occurs should not be used
- 17.4. Special corner stones shall be provided where so directed.

M-18. Mild Steel Bars

- 18.1. Mild steel bars reinforcement for R.C C. work shall conform to I.S. 432 (Part -II) 1966 and shall be of tested quality. It shall also comply with relevant part of I.S. 456-1978.
- 18.2. All the reinforcement shall be clean and free from dirt, paint, grease, mill scale or loose or thick rust at the time of placing
- 18.3. For the purpose of payment, the bar shall be measured correct up to 10 mm. length and weight payable worked out at the rate specified below :

1.	6 mm	0.22 Kg./Rmt.	8.	20 mm.	2.47 Kg/Rmt.
2.	8 mm	0.39 Kg./Rmt.	9.	22 mm.	2.98 Kg/Rmt.
3.	10 mm	0.62 Kg./Rmt.	10.	25 mm.	3.85 Kg/Rmt.
4.	12 mm	0.89 Kg./Rmt.	11.	28 mm.	4.83 Kg/Rmt.
5.	14 mm	1.21 Kg./Rmt.	12.	32 mm.	6.31 Kg/Rmt.
6.	16 mm	1.58 Kg./Rmt.	13.	36 mm.	7.99 Kg/Rmt.
7.	18 mm	2.00 Kg./Rmt.	14.	40 mm.	9.86 Kg/Rmt.

M-19. High Yield Strength Steel Deformed Bars

- 19.1. High yield strength steel deformed bars shall be either cold twisted other rolled and shall conform to I.S. 1786-1966 and I.S. 1139-1966 respectively.
- 19.2. Other provisions and requirements shall conform to specification No. M-18 for Mild Steel Bars.

M-20. High Tensile Steel Wires

- 20.1. The high tensile wires for use in pre stressed concrete work shall conform to I.S,2090-1962.
- 20.2. The tensile strength of the high tensile steel bars shall be as specified in the item. In absence of the given strength the minimum strength shall be taken as per Para 6-1 of the I.S. 1785-1962. Testing shall be done as per I.S. requirements.
- 20.3. The high tensile steel shall be free from loose mill scale, rust, oil, grease, or any other harmful matter. Cleaning of steel bars may be carried out by immersion in solvent solution, wire brushing or passing through a pressure box containing Carborudum.
- 20.4. The high tensile wire shall be obtained from manufacturers. in coils having diameter not less then 350 times the diameter of wire itself so that wire springs back straight on being uncoiled .

M-21. Mild Steel Binding Wire

- 21.1.** The mild steel wire shall be of 1.63 mm. or 1.22 mm. (16 to 18 gauge) diameter and shall conform to I.S. 280-1972.
- 21.2.** The use of black wire will be permitted for binding reinforcement bars. It shall be free from rust oil paint, grease loose mill scale or any other undesirable coating which may prevent adhesion of cement mortar.

M-22. Structural Steel

- 22.1.** All structural Steel shall conform to I S. 226-1985: The steel shall be free from the defects mentioned in I.S 226-1975 and shall have a smooth finish. The material shall be free from loose mill scale, rust pits or other defects affecting the strength and durability. River bars shall conform to I.S. 1148-1973.
- 22.2.** When the steel is supplied by the Contractor test certificate of the manufacturers shall be obtained according to I.S. 226-1975 and other relevant Indian Standards.

M-23. Galvanised Iron Sheets

- 23.1.** The galvanised iron sheets shall be plain or corrugated sheets of gauges as specified in item The G.I. Sheets shall conform to I.S.277-1977. The sheets shall be undamaged in carnage and handling either by rubbing off of zinc coating or otherwise. They shall have clean and bright surface and shall be free from dents, bends, holes, rust or white powdery deposit.
- 23.2.** The length and width of G.I. sheets shall be as directed as per site condition.

M-23.A : G.I. Valleys gutter, ridges

- 23.A.1.** The G.I. ridges and hips shall be of plain galvanised sheets Class - 3 of the thickness as specified in item. These shall be 600 mm. in width and properly bent up to shape without damage to the sheets in process of bending.
- 23.A.2.** Valleys gutters and flashings shall also be of galvanised sheet of thickness as specified in item Valleys Shall be 900 mm. wide overall and flashing shall be 380 mm. wide overall They shall be bent to the required shape without damage to the sheet in the process of bending.

M-24. Asbestos Cement Sheets

- 24.1.** Asbestos cement sheets plain, corrugated of semi-corrugated shall conform to I.S.459-1970 The thickness of the sheets shall be as specified in the item. The sheets shall be free from all defects such as cracks, holes, deformities chipped edges or otherwise damaged.
- 24.2. Ridges & Hips :**
- 24.2.1.** Ridges and hips shall be of same thickness as that of A.C. sheets. The types, of ridges shall be suitable for the type of sheets and location.
- 24.2.2.** Other accessories to be used in roof such as flashing pieces eaves filler pieces, valley gutters, north light, and ventilator curves, barge boards etc, shall be of standard manufacture and shall be suitable for the type of sheets and location.

M-25. Manglore Pattern Roof Tiles

- 25.1.** The mangalore pattern tiles shall conform to I S 654-1972 for Class AA or Class A type as specified in item. Samples of the tiles to be provided shall be got approved from the Engineer-in-charge. Necessary tests shall be carried out as directed.

M-26. Shuttering

- 26.1.** The shuttering shall be either of wooden planking of 30 mm. minimum thickness with or without steel lining or of steel plates stiffened by steel angles The shuttering shall be supported on battens and beams and props of vertical bullies properly cross braced together so as to make the

centering rigid. In places of bullies props, brick pillar of adequate section built in mud mortar may be used.

- 26.2. The form work shall be sufficiently strong and shall have camber so that it assumes correct shape after deposition of the concrete and shall be able to resist forces caused by vibration of live load of men working over it and other incidental loads associated with it. The shuttering shall have smooth and even surface and its joints shall permit leakage of cement grout.
- 26.3. If at any stage of work during or after placing concrete in the structure, the form work sags or bulges out beyond the required shape of the structure, the concrete shall be removed and work redone with fresh concrete and adequately rigid form work. The complete form work shall be got inspected by and got approved from the Engineer-in charge, before the reinforcement bars are placed in position.
- 26.4. The props shall consist of bullies having 100 mm minimum diameter measured at mid length and 80 mm. at thin end shall be placed as per design requirement. These shall rest squarely on wooden sole plates 40 mm. thick and minimum bearing area of 0-10 sq.m laid on sufficiently hard base.
- 26.5. Double wedges shall further be provided between the sole plate and the wooden props so as to facilitate tightening and easing of shuttering without jerking the concrete
- 26.6. The timber used in shuttering shall not be so dry as to absorb water from concrete and swell or bulge nor so green or wet as to shrink after erection. The timber shall be properly sawn and planed on the sides and the surface coming in contact with concrete wooden form work with metal sheet lining or steel plates stiffened by steel angles shall be permitted
- 26.7. As far as practicable, clamps shall be used to hold the forms together and use of nails and spikes avoided.
- 26.8. The surface of timber shuttering that would come in contact with concrete shall be well wetted and coated with soap solution before the concreting is done. Alternatively coat of raw linseed oil or oil of approved manufacture may be applied in place of soap solution. In case of steel shuttering either soap solution or raw linseed oil shall be applied after thoroughly cleaning the surface. Under no circumstances black or burnt oil shall be permitted.
- 26.9. The shuttering for beams and slabs shall have camber of 4 mm per meter (1 in 250) or as directed by the Engineer-in-charge so as to offset the subsequent deflection. For cantilevers, the camber at free end shall be 1/50 of the projected length or as directed by the Engineer-in-charge.

M- 27. Expansion Joints - Premoulded filler

- 27.1. The item provides for expansion joints in R.C C. frame structures for internal joints, as well as exposed joints, with the use of premoulded bituminous joint filler.
- 27.2. Premoulded bituminous joints filler i.e. performed strip of expansion joints filler shall not get deformed, or broken by twisting bending or other handling when exposed to atmospheric condition. Pieces of joints filler that have been damaged shall be rejected
- 27.3. Thickness of the per-moulded joints filler shall be 25 mm. unless otherwise specified.
- 27.4. Premoulded bituminous joints filler shall conform to I S 1838-1961

M-28. Expansion joints-Copper strips & hold .fasts

- 28.1. The item provide for expansion joints in R.C.C. frame structure for internal joints, as well as exposed joints, with the use of premoulded bituminous joints filler.
- 28.2. Copper sheet shall be of 1.25 mm. width and or 1 25 mm. width and the " U " shape in the middle. Copper strip shall have holdfast of 3 mm diameter copper rod fixed to the plate soldered on strip at

intervals of about 30 cm or as shown in the drawing or as directed. The width of each flange (horizontal side) of the copper plate Jo be embedded in the concrete work shall be 25 mm depth of "U" to be provided in the expansion joint, in the copper plate shall be of 25 mm.

M-29. Teak wood

29.1. The teak wood shall be of good quality as required for the item to be executed. When the kind of wood is not specifically mentioned, good Indian teak wood as approved shall be used.

29.2. Teak wood shall generally be free from large, loose dead or cluster knots, flaws, shakes, warps, twists, bends or any other defects. It shall generally be uniform in substance and of straight fibers as far as possible. It shall be free from rot decay, harmful fungi and other defects of harmful nature which will affect the strength, durability or its usefulness for the purpose for which it is required. The colour shall be uniform as far as possible. Any effort like painting using any adhesive materials made to hide the defects shall render the pieces liable to rejection by the Engineer-in-charge.

29.3. All scantlings, planks etc. shall be sawn in straight lines and planes in the direction of grains and of uniform thickness.

29.4. The tolerances in the dimensions shall be allowed at the rate of 1.5 mm per face to be planed.

29.5. First class teak wood

29.5.1. First class teak wood shall have no individual hard and-sound knots, more than 6 sq. cm. in size and the aggregate area of such knots shall not be more than 1% of area of piece, The timber shall be closed grained.

29.6. Second Class Teak Wood:

29.6.1. No individual hard and sound knots shall be more than 15 sq. cms. in size and aggregates area of such knots shall be not exceed 2% of the area of piece.

M-29. A Non-teak wood:

The non-teak wood shall be chemically treated, seasoned as per I.S. Specifications and of good quality. The type of wood shall be got approved before collecting the same on site Fabrication of wooden members shall be started only after approval. For this purpose wood of Bio, Kalai, Sires. Saded, Behda, Jamun, Sisoo will be used for door where as only Kalai. Sires, Halda. Kalam etc. will be permitted for shutters after proper seasoning and chemical treatment.

The non-teak wood shall be free from large loose dead of cluster knots, flows, shakes, warps, bends or any other defects, It shall be uniform in substance and of straight fibers as far as possible It shall be free fro rots, decay, harmful fungi and other defects of nature which will effect the strength, durability or its usefulness for the purpose for which it is required. The colour of wood shall be uniform as far as possible. The scantlings planks etc. shall be saw in straight lines and planes in the direction of grain and of uniform thickness. The department will use the Agency to produce certificate from Forest Department in event of dispute and the decision of the Department shall be final and binding to the contractor. The tolerance in the dimension shall be allowed at 1.5 mm. per face to be planed.

M-30. Wooden flush door shutters (solid core)

30.1. The solid core type flush door shutters shall be of decorative or non-decorative type as specified in the drawing. The size and thickness of the shutter shall be as specified in drawings or as directed. The timber species for core shall be used as per I.S.2202 (part -I) 1980. The timber shall be free from decay and insect attack Knots and knot holes less than half the width of cross-section of the members in which they occur may be permitted. Pitch pockets, pitch streaks and harmless pin

holes shall be permissible except in the exposed edges of the core members. The commercial plywood, cross-bands shall conform to I.S. 303-1275.

- 30.2.** The face panel of the shutters shall be formed by gluing by the hot press process on both faces of the core with either plywood or cross-bands and face veneers. The hopping, rebating, opening of glazing, venation etc., shall be provided if specified in the drawing.
- 30.3.** All edges of the door shutters shall be square. The shutters shall be free from twist or warp in its plane. Both faces of the shutters shall be sand papered to smooth even texture.
- 30.4.** The shutters shall be tested for-
- (1) End immersion test:** The test shall be carried out as per I.S.2202 (part-1) 1980 There shall be no delamination at the end of the test.
- (2) Knife Test :** The face panel when tested in accordance with I.S 1659-1979 shall pass the test.
- (3) Glue adhesion test :** The flush door shall be tested for glue adhesive test in accordance with I S 2202 (part -I) 1980. The shutters shall be considered to have passed the test, if no delamination occurs in the glue lines in the plywood and if no single determination more than 80 mm in length and more than 3 mm in depth has occurred in the assembly glue lines between the plywood face and the style and rail. Delamination at the corner shall be measured continuously around the corner Delamination at the knots, knot hole and other permissible wood defects shall not be considered in assessing the sample.
- 30.5.** The tolerance in size of scud core type flush door shall be as under :
- In Nominal thickness ± 1.2 mm. In Nominal height ± 3 mm
- 30.6.** The thickness of the shutter shall be uniform throughout with a permissible variation of not more than 0.8 mm. when measured at any points.

M-31. Aluminum doors, windows, ventilators

- 31.1.** Aluminum alloy used in the manufacture of extruded window sections shall conform to I.S. designation HEAWP of I.S. 733-1975 and also to I S. Designation WVG-WP of I.S 1285-1975 The section shall be as specified in the drawing and design. The fabrication shall be done as directed
- 31.2.** The hinges shall be cast or extruded aluminum hinges of same type as in window but of larger size.
- 31.3.** The hinges shall normally be of 50 mm. projecting type. Non-projecting type of hinges may also be used if directed. The handles of door shall be of specified design A suitable lock for the door Operable either from outside or inside shall be provided. In double shutter door, the first closing shutter shall have concealed aluminum alloy bolt at top and bottom.

M-32. Rolling Shutters

- 32.1.** The rolling shutters shall conform to I.S.6248-1979 Rolling shutters shall be supplied of specified type with accessories. The size of the rolling shutters shall be specified in the drawings. The shutters shall be specified in the drawings. The shutters shall be constructed with interlocking lath sections formed from cold rolled steel strips not less than 0.9 mm. thick and 80 mm. wide for shutters up to 3.5 m .width not less than 1.25 mm. thick and 80 mm wide for shutters 3.5 m. in width and above unless otherwise specified.
- 32.2.** Guide channels shall be of mild steel deep channel section and of rolled pressed or built up (fabricated) joint less construction The thickness of sheet used shall not be less than 3.15 mm.
- 32.3.** Hood covers shall be made of M S. Sheets not less than 0.90 mm. thick. For shutters having width 3.5 Meter and above, the thickness of M.S. sheet for the hood cover shall be not less than 1 25 mm.

- 32.4. The spring shall be of best quality and shall be manufactured from tested high tensile spring steel wire of strip of adequate strength to balance the shutters in all position. The spring pipe shaft etc. shall be supported on strong M S of malleable C I. brackets. The brackets shall be fixed on or under the lintel as specified with raw plugs and screws bolts etc.
- 32.5. The rolling shutters shall be of self rolling up to 8 Sq. m. clear area without ball bearing and up to 12 Sq.m. clear area with ball bearing. If the rolling shutters are of larger, then gear operated type shutters shall be used.
- 32.6. The locking arrangement shall be provided at the bottom of shutter at both ends The shutters shall be opened from outside.
- 32.7. The Shutters shall be completed with door suspension shafts, looking arrangements, pulling hooks, handles and other accessories.

M-33. Collapsible Steel Gate

- 33.1. The collapsible steel gate shall be in one or two leaves and size as per approved drawings or as specified. The gate shall be fabricated from best quality mild steel channels, flats etc. Either steel pulleys or ball-bearings shall be provided in every double channel Unless otherwise specified the particulars of collapsible gate shall be as under.
 - (a) Pickets : These shall be of 20 mm. M.S. channels of heavy sections unless otherwise shown on drawings. The distance centre to centre of pickets shall be 12 cms .with an opening or 10 Cms
 - (b) Pivoted M.S. flats shall be 20 mm x6 mm
 - (c) Top and bottom guides shall be from tee of flat iron of approved size.
 - (d) The fittings like stoppers fixing, locking cleats, brass handles and cast iron rollers shall be of approved design and size

M-34. Welded Steel Wire Fabric

- 34.1 Welded steel wire fabric for general purpose shall be manufactured form cold drawn steel wire "as drawn" or galvenised steel conforming to I.S. 226-1975 with longitudinal and transverse wire securely connected at every intersection by a process of electrical resistance welding and conforming to I.S.4948-1974. it shall be fabricated and finished in workmanlike manner and shall be free from injurious defects and shall be rust proof The type of mesh shall be oblong or square as directed The mesh sizes and sizes if wire for square 3b well as oblong welded steel wire fabric shall be as directed The steel wire fabric in panels shall be in one whole piece in each panel as far as stock sizes permit.

M-35 Expanded Metal Sheets

- 35.1. The expanded metal sheets shall he free from flaws joints broken strands laminations and other harmful surface defects. Expanded metal steel sheet shall confirm to IS-412-1975. except that blank sheets need not be with guaranteed mechanical properties The size of the diamond mesh of expanded metal and dimensions of strands (width and thickness) shall be as specified. The tolerance on nominal weight of expanded metal sheets shall be of + 10 percent.
- 35.2. Expanded metal in panels shall be in one whole piece in each panel as far as stock sizes permit. The expanded metal sheets shall be coated with suitable protective coating to prevent corrosion.

M-36. Mild Steel Wire (Wire Gauze Jali)

- 36.1. Mild steel wire may be galvanized as indicated. All finished steel wire shall be well cleanly drawn to the dimensions and size of wire as specified in item. The wire shall be sound free from splits surface flaws, rough jagged and imperfect edges and other harmful surface defects and shall conform to I.S. 280-1978.

M-37. Plywood

37.1. The plywood for general purpose shall conform I.S. 303-17-1975.

Plywood is made by cementing together than boards or starts of wood into panels. There are always an odd number of layers, 3,5,7,9, ply etc. The piles are placed so that grain of each layer is at right angles to the grain in the adjacent level.

37.2. The chief advantages of plywood a single board of the same thickness is the more uniform strength of the plywood, along the length and width of the plywood and greater resistance to cracking and splitting with charge in moisture content.

37.3. Usually synthetic resins are used to gluing, phenolic resins are usually cured in a hot press which compresses and simultaneously heats the plies between hot plates which maintain a temperature of 90 degree C to 140 degree C and a pressure of 11 to 14 Kg/ Sq. Cm on the wood. The time of heating may be anything from 2 to 60 minutes depending upon thickness

37.4. When water glue are used the wood absorbs so much water that the finished plywood must be dried carefully. When synthetic resins are used as adhesive the finished plywood must be exposed to an atmosphere of controlled humidity until the proper amount of moisture has been absorbed.

37.5. According to I.S. 303-1975 the plywood for general purpose shall be of the grades namely BWR, WWR and CWR depending up to the adhesives used for bonding the veneers and it will be further classified into six types namely AA, AB, AC, BB, BC and CC based on the quality of the two faces each face being of three kinds namely A, Band C After pressing, the finished plywood should be reconditioned to a moisture content not less than 8 percent and not more than 16 percent.

37.6. Thickness of plywood Boards

Board	Thickness	Board	Thickness	Board	Thickness	Board	Thickness
3 Ply	3 mm	5 Ply	5 mm	7 Ply	9 mm	9 Ply	16 mm
	4 mm		6 mm		13 mm		19 mm
	5 mm		8 mm		16 mm	11 Ply	19 mm
	6 mm		9 mm	9 Ply	13 mm		25 mm

M-38. Glass

38.1. All glass shall be of the brief quality, free from specks, bubbles, smokes veins, air holes blisters and other defects. The kind of glass to be used shall be as mentioned in the item or specification or in the special provision or as shown in detailed drawings. Thickness of glass panes shall be uniform. The specifications for different kinds of glass shall be as under.

38.2. Sheet Glass

38.2.1. In absence of any specified thickness or weight in the item or detailed specifications of the item of work, sheet glass shall be weighing 7.5 Kg/Sq. m for panes up to 600 mm x 600 mm.

38.2.2. For panes larger than 600 mm x 600 mm and up to 800 mm x 800 mm the glass weighing not less than 8.75 Kg/Sq m shall be used for bigger panes up to 900 mm x 900 mm. glass weighing not less than 8.75 Kg/Sq. m shall be used. For bigger panes up to 900 mm x 900 mm. glass weighting not less than 11.25 Kg/Sq. m. shall be used

38.2.3. Sheet glass shall be patent flattened glass of best quality and for glazing and framing purposes shall conform to I.S. 1761-1960. Sheet glass of the specified colours shall be used, if so shown, on detailed drawings or so specified For important buildings and for panes with any dimension over 900 mm plate glass of specified thickness shall be used

38.3. Plate Glass:

38.3.1. When plate glass is specified it shall be "polished patent plate glass" of best quality It shall have both the surface ground flat and parallel and polished to obtain clear undisturbed vision and reflection The plate glass shall be of the thickness mentioned in the item or as shown in the detailed drawing or as specified. In absence of any specified thickness, the thickness of plate glass to be supplied shall be 6 mm. and a tolerance of 0.20 mm shall be admissible

38.4. Obscured Glass:

38.4.1. This type of glass transmits light so that vision is partially or almost completely obscured. Glass shall be plain rolled, figured, ribbed or fluted, or frosted glass as may be specified as required. The thickness and type of glass shall be as per details on drawings or as specified or as directed

38.5. Wired Glass:

38.5.1. Glass shall be with wire netting embedded in a sheet of plate glass. Electrically welded 13 mm Georgian square mesh shall be used Thickness of glass shall not be less than 6 mm Wired glass shall be of type and thickness as specified

M-39. Acrylic Sheets

39.1. Acrylic sheets shall be of thickness as specified in the item and of an specified shape and size as the case may be panels may be flat or curved It should be light in weight it shall be colourless or coloured or opaque as specified in the item. Colourless sheet shall be as transparent as the finest optical glass. Its light transmission rate shall be about 95% Transparency shall not be affected for the sheets of larger thickness, it shall be extremely resistant to sunlight weather and low temperatures. It shall not show any significant yellowing or change in physical properties or loss of light transmission over a longer period of use. The sheet shall be impact resistant also Sheets should be of such quality that they can be cut, bent jointed as desired Solution for the joints shall be used as per the requirement of manufacturer.

M-40. Particle board

40.1. The particle boards used for face panels shall be of best quality free from any defects. The particle boards shall be made with phenolaldehyde adhesive The particle boards shall conform to IS 3087-1905 "Specification for wood particle board for general purpose" The size and the thickness shall be as indicated.

M-41. Expanded polystyrene or framed styrofoam slabs

41.1. The expanded polystyrene ceiling boards and tiles shall be of approved make and shall be of sizes, thickness, finish and colour as indicated. It shall be of high density and suitable for use as insulating material. The insulating material shall be like slabs of Thermocole etc.

M-42. Resin bonded fiber glass.

42.1. The resin bonded fiber glass tiles or rolls shall be of approved make and shall be of sizes, thickness and finish as indicated.

42.2. For test of Mineral wool thermal insulation [Blanket IS 3144-1965 shall be followed

42.3. Insulation wool blankets shall be with the following coverings on one or both sides as indicated

- (1) Bituminous Hessian Kraft paper suitable for use in position where moisture has to be excluded.
- (2) Hessian cloth or Kraft paper for keeping out dust
- (3) G.I wire netting, suitable for surfaces to be plaster over

M-43. Fixtures and fastenings

43.1. General:

- 43.1.1. The fixtures and fastenings, that is butt hinges tee and strap hinges sliding door bolts, tower bolts, door latch, bath-room latch, handles door stoppers, casement window fasteners, casement stays and ventilators catch shall be made of the metal as specified in the item or its specification.
- 43.1.2. They shall be of iron, brass, aluminum chromium plated iron, chromium plated brass, copper oxidised iron, copper oxidised brass or anodised aluminum as specified
- 43.1.3. The fixtures shall be heavy medium or light type. The fixtures and fastenings shall be smooth finished and shall be such as will ensue ease of operations.
- 43.1.4. The samples of fixtures and fastenings shall be got approved as regards, quality and shape before providing them in position.
- 43.1.5. Brass and anodised aluminium fixtures and fastenings shall be bright finished

43.2. Holdfasts:

- 43.2.1. Holdfasts shall be made from mild steel flat 30 cm length and one of the holdfasts shall be bent at right angle and two nos. of 6 mm. diameter holes shall be made in it for fixing it to the frame with screws. At the other end, the holdfast shall be forked and bent at right angles in opposite directions.

43.3. Butt hinges:

- 43.3.1. Railway standard heavy type butt hinges shall be used when so specified
- 43.3.2. Tee and strap hinges shall be manufactured from M S Sheet

43.4. Siding door bolts (Aldrops):

- 43.4.1. The aldrops as specified in the item shall be used and shall be got approved.

43.5. Tower bolts (Barrel Type):

- 43.5.1. Tower bolts as specified in the item shall be used and shall be got approved

43.6. Door Latch:

- 43.6.1. The size of door latch shall be taken as the length of latch.

43.7. Bathroom Latch:

- 43.7.1. Bathroom latch shall be similar to tower bolt.

43.8. Handle:

The size of the handles shall be determined by the inside grip length of the handles. Handles shall have a base plate of length 50 mm. more than the size" of the handle.

43.9. Door Catch:

- 43.9.1. Door stoppers shall be either floor door stopper type or door catch type Floor stopper shall be of overall size as specified and-shall have a rubber cushion.

43.10. Door Stoppers:

- 43.10.1. Door catch shall be fixed at a height to about 900 mm from the floor level such that one part of the catch is fitted on the inside of the shutter and the other part is fixed in the wall with necessary wooden plug arrangements for appropriate fixity The catch shall be fixed 20 mm inside the face of the door for easy operation of catch.

43.11. Wooden Door Stop with hinges:

- 43.11.1. Wooden door stop of size 100 mm x 40 mm x 40 mm shall be fixed on the door frame with a hinges of 75 mm. size and at a height of 900 mm. from the floor level The wooden door stop shall be provided with 3 coats of approved oil paint

43.12. Casement Window Fastener:

43.12.1. Casement window fastener for single leaf window shutter shall be left or right handed as directed.

43.13. Casement stays (Straight Red Stay):

43.13.1. The stays shall be made from a channel section having three holes at appropriate position so that the window can be opened either fully or partially as directed. Size of the stay shall be 250 mm to 300 mm. as directed.

43.14. Ventilator Catch:

43.14.1. The pattern and shape of the catch shall be as approved

43.15. Pivot:

43.15.1. The base and socket plate shall be made from minimum 3 mm. thick plate: and projected pivot shall not be less than 12 mm 'diameter and 12 mm. length and shall be firmly riveted to the base plate in case of iron pivot and in single piece plate in the case of brass pivot.

M-44. Paints:

44.1. (A) Oil paints :

44.1.1. Oil paints shall be of the specified colour and as approved. The ready mixed paints shall only be used. However, if ready mixed paint of specified shade or tint is not available white ready mixed paint with approved stainer will be allowed In such a case the contractor shall ensure that the shade of the paint so allowed shall be uniform.

44.1.2. All the paints shall meet with the following general requirements.

(i) Paint shall not show excessive setting in a freshly opened full can and shall easily be ready spread with a paddle to a smooth homogeneous state. The paint shall show no curdling, levering caking or colour separation and shall be free from lumps and skins.

(ii) The paint as received shall brush easily, possess good leveling properties and show no running or sagging tendencies.

(iii) The paint shall not skin within 48 hours in a three quarters filled closed container.

(iv) The paint shall dry to a smooth uniform finish free from roughness, grit unevenness and other imperfections.

44.1.3. Ready mixed paint shall be used exactly as received from the manufacturers and generally according to their instructions and without any admixtures whatsoever

44.2. (B) Enamel paints:

44.2.1. The enamel paint shall satisfy in general requirements in specification of oil paints, Enamel paint shall conform to I.S. 2933-1975.

M-45. French Polish

45.1. The French polish of required tint and shade shall be prepared with the below mentioned ingredients and other necessary materials:

(i) Denatured spirit of approved quality (ii) Chandras (iii) Pigment.

45.2. The French polish so prepared shall conform to I S : 348-1 9C8.

M-46. Marble chips for marble mosaic terrazzo

46.1. The marble chips shall be of approved quality and shades. It shall be hard, sound, dense and homogeneous in texture with crystalline and coarse grains It shall be uniform in colour and free from stains cracks, .decay and weathering.

46.2. The size of various colours of marble chips ranging from the smallest up to 20 mm shall be used where the thickness of top wearing layer is 6 mm size The marble chips of approved quality and

colours only as per grading as decided by the Engineer-in-charge shall be used for marble mosaic tiles or works.

- 46.3.** The marble chips shall be machine crushed. They shall be free from foreign matter, dust etc. Except as above, the chips shall conform to I S 2114-1962

M-47. Flooring Tiles

47.1. (A) Plain Cement tiles;

- 47.1.1.** The plain cement tiles shall be of general purpose type. These are the tiles in the manufacture of which no pigments are used. Cement used in the manufacture of tiles shall be as per Indian Standards.

- 47.1.2.** The tiles shall be manufactured from a mixture of cement and natural aggregates by pressure process. During manufacture the tiles shall be subjected to pressure of not less than 140 Kg/Sq. Cm. The proportion of cement to aggregate in the backing of the tiles shall be not less than 1 .3 by weight The wearing face, through the tiles are of plain cement, shall be provided with stone chips of 1 to 2 mm. size. The proportions of cement to aggregate in the wearing layer of the tiles shall be three parts of cement to one parts chips by weight. The minimum thickness of wearing layer shall be 3 mm. The colour and texture of wearing layer shall be uniform throughout its face and thickness. On removal from mould, the tiles shall be kept in moist condition continuously at least for seven days and subsequently, if necessary, for such long period as would ensure their conformity to requirements of I.S.1237-1980 regarding strength resistance to wear and water absorption.

- 47.1.3** The wearing face of the tiles shall be plane, free from projections, depressions and cracks and shall be reasonably parallel to the back face of the tile. All angles shall be right angle and all edges shall be sharp and true.

- 47.1.4.** The size of tiles generally be square shapes 24.85 Cm x24.85 Cm. or 25 Cm x 25 Cm The thickness of tiles shall be 20 mm.

- 47.1.5.** Tolerance of length and breadth shall be plus or minus one millimeter Tolerance on thickness shall be plus 5mm.

- 47.1.6.** The tiles shall satisfy the tests as regards transverse strength, resistance to wear and water absorption as per I.S 1237-1980.

47.2. (B) Plain Coloured Tiles:

- 47.2.1.** The tiles shall have the same specification as for plain cement tiles as per (A) above expect that they shall have a plain wearing surface wherein pigments are used. They shall conform it I.S. 1237-1980.

- 47.2.2.** The pigments used for colouring cement shall not exceed 10 percent by weight of cement used in the mix. The pigments, synthetic or otherwise, used for colouring tiles shall have permanent colour and shall not contain materials detrimental to concrete

- 47.2.3** The colour of the tiles shall be specified in the item or as directed

47.3. (C) Marble mosaic tiles:

- 47.3.1.** These tiles have same specification as per plain cement tiles except the requirements as stated below.

- 47.3.2.** The marble mosaic tiles shall conform to I.S 1237-1980. The wearing face of the tiles shall be mechanically ground and filled. The wearing face of tiles shall be free from projections depressions and cracks and shall be reasonably parallel to the back face of the tiles. All angles shall be right angles and all edges shall be sharp and true.

- 47.3.3.** Chips used in the tiles be from smallest up to 20 mm. size. The minimum thickness of wearing layer of tiles shall be 6 mm. For pattern of chips to be had on the wearing face; a few samples with or without their full size photographs as directed shall be approved by the Engineer-in-charge, for approval.
- 47.3.4.** Any particular samples if found suitable shall be approved by the Engineer-in-charge, or he may ask for a few more samples to be presented. The samples shall have to be made by the contractor till a suitable sample is finally approved for use in the work. The Contractor shall ensure that the tiles supplied for the work shall be in conformity with the approved sample only, in terms of its dimensions, thickness of backing layer and wearing surface, materials, ingredients, colour, shade, chips, distribution etc. required.
- 47.3.5.** The tiles shall be prepared from cement conforming to Indian Standards or coloured port land cement generally depending upon the colour of tiles to be used or as directed.
- 47.4. (D) Chequered Tiles :**
- 47.4.1.** Chequered tiles shall be plain cement tiles or marble mosaic tiles. The former shall have the same specification as per (A) above and the latter as per marble mosaic tiles as per (C) except as mentioned below
- 47.4.2.** The tiles shall be of nominal size of 250 mm. x 250 mm. or as specified. The centre to centre distance of chequer shall not be less than 25 mm. and not more than 50 mm. The overall thickness of the tile shall be 22 mm
- 47.4.3.** The grooves in the chequers shall be uniform and straight. The depth of the grooves shall not be less than 3 mm. The chequered tiles shall be plain coloured or mosaic as specified. The thickness of the upper layer measured from the top of the chequers shall not be less than 6 mm. The tiles shall be given the first grinding with machine before delivery to site.
- 47.4.4.** Tiles shall conform to relevant I.S 1237-1980.

47.5. (E) Chequered Tiles For Stair Cases :

- 47.5.1.** The requirements of these tiles shall be the same as chequered tiles as per (D) above except in following respects :
- (1) The length of a tile including nosing shall be 300 mm (2) The minimum thickness shall be 28 mm (3) The nosing shall have also the same wearing layer as at the top. (4) The nosing edge shall be rounded (5) The front portion of the tile for a minimum length of 75 mm. from and including the nosing shall have grooves running parallel to nosing and at centers not exceeding 25 mm. Beyond that the tiles shall have normal chequer pattern.

M-48. Rough Kotah Stone

- 48.1.** The Kotah stones shall be hard even, sound, and regular in shape and generally uniform in colour. The colour of the stone shall generally be green Brown coloured shall not be allowed for use. They shall be without any soft veins, cracks or flaws.
- 48.2.** The size of the stones to be used for flooring shall be of size 600 mm x 600 mm and/or size 600 mm. x 450 mm as directed. However smaller sizes will be allowed to be used to the extent of maintaining required pattern. Thickness shall be as specified
- 48.3.** The edges of stones shall be dressed to a minimum of 30 mm on accounts of chisel dressing of edges shall be permitted for length as well as breadth. Tolerance in thickness shall be ± 3 mm
- 48.4.** The edges of stones shall be truly chiseled and table rubbed with coarse sand before paving. All angles and edges of the stones shall be true, square and free from chipping and surface shall be true and plain.

- 48.5.** When machine cut edges are specified, the exposed and the edges at joints shall be machine cut
The thickness of the exposed machine cut edges shall be uniform

M-49. Polished Kotah Stoics

- 49.1.** Polished kotah stone shall have the same specification as per rough kotah stone except as mentioned below :
- 49.2.** The stones shall have machine polished surface. When brought on site, the stones-shall be single polished or double polished depending upon its use. The stones for paving shall generally be single polished The stones to be used for dedo, skirting, sink, veneering, sills steps etc. where machine polishing after the stones are fixed in situ is not possible shall be double polished

M-50. Dholpur Stone Slab

- 50.1.** Dholpur stone slab shall be of best quality as approve by the Engineer-m-charge. The stone slab shall be without my veins, cracks, and flaws The stone slab shall be even sound and durable regular in snaps and of uniform colour
- 50.2.** The size of the stone shall be as specified in the item or detailed drawing or as approved by the Engineer-in-charge. The thickness of the stone shall be as specified in the item of work with the permissible tolerance of plus or minus 2 mm. The provision in respect of polishing as for polished kotah stone shall apply to polished Dholpur stone also. All angles and edges of the face of the stone slab shall be fine chiseled or polished as specified in the item of work and all the four edges shall be machine cut All angles and edges of the stone slab shall be true and plane.
- 50.3.** The sample of stone shall be got approved by the Engineer-in-charge for a particular work It shall be ensured that the stones to be used in a particular work shall not differ much in shade or tint from the approved sample.

M-51. Marble Slab

- 51.1.** Marble slab shall be white or of other and of best quality as approved by the Engineer-in-charge
- 51.2.** Slabs shall be hard, close, uniform and homogeneous in texture. They shall have even crystalline gram and free from defects and cracks. The surface shall be machine polished to an even and perfect plane surface and edges machine cut true and square. The rear f ice shall be rough to provide key for the mortar.
- 51.3.** Marble slabs with natural veins, if selected shall have to be laid as per the pattern given by the Engineer-in-charge.
Size of the slab shall be minimum 460 mm x 450 mm and preferably 600 mm x 600 mm. However, smaller sizes will be allowed to be used of the extent of maintaining required pattern.
- 51.4.** The slab shall not be thinner than the specified thickness at its thinnest part. A few specimen of finished slab to be used shall be deposited by the Contractor in the office for reference
- 51.5.** Except as above the marble slabs shall conform to I.S. 1130-1969

M-52. Granite Stone slab

- 52.1.** Granite shad be of approved colour and quality. The stone shall be hard, even sound and regular in shape and generally uniform in colour. It shall be without any soft veins, cracks of flaws.
- 52.2.** The thickness of the stone shall be specified in items
- 52.3.** All exposed faces shall be double polished to tender truly smooth and even reflecting surface. The exposed edges and corners shall be rounded off as directed. The exposed edges shall be machine cut and shall have uniform thickness.

M-53. P.V.C. Flooring

53.1. P.V.C. sheets for P.V.C., floor covering shall be of homogenous flexible type conforming to I S 3462-1966. The P.V.C. covering shall neither develop any toxic effect while put to use nor shall give off any disagreeable odour.

53.2. Thickness of flexible type covering tiles shall be as specified in the description of the item

53.3. The flexible type shall be backed with Hessian or other woven fabric The following tolerances shall be applicable on the nominal dimensions of the rolls or tiles :

(a) Thickness + 015 mm.

(b) Length or Width

(1) 300 mm. Square tiles ± 0.20 mm. (3) 900 mm Square tiles ± 0.60 mm.

(2) 600 mm. Square tiles ± 0.40 mm. (4) Sheets and roll ±0.10 percent.

53.4. Adhesive:

53.4.1. The adhesive for PVC flooring shall be of the type and make recommended by the manufactures of PVC sheets/tiles.

M-54. Facing Tiles

54.1. The facing tiles (burnt clay facing bricks) shall be free from cracks, and nodules of free lime. They shall be thoroughly burnt and shall have plane rectangular faces with parallel sides and sharp straight right angled faces. The texture of the finished surface that will be exposed when in place shall conform to an approved sample consisting not less than for stretcher bricks each representing the texture desired. The facing tiles shall have a pleasing appearance, sufficient resistance to penetration by ram and greater durability than common bricks. The tiles shall conform to I.S. 2691-1972.

54.2. The standard size of facing brick tiles shall be 19 x 9 x 4 cms. The facing brick tiles shall be provided with frog which shall conform to I.S. 11077-1976.

54.3. The permissible tolerance in dimensions specified above shall be as follows:

Size	Tolerance for	
	1st Class Brick	2nd Class Brick
19 cm.	± 6 mm	± 10 mm
9 cm.	± 3 mm	± 7 mm
4 cm.	± 1.5 mm	± 3 mm

54.4. The tolerance for distortion or warpage of face or edges of individual brick from a plane surface and from a straight line respectively shall be as follows:

Facing dimensions	Permissible tolerance
Max. below 19 cms.	Max. 2.5 mm
- do - above 19 cm.	Max. 3.0 mm

54.5. The average compressive strength obtained as a sample of five tiles when tested in accordance with the procedure laid as per I S 1077-1976 shall be not less than 175 Kg/Sq Cm. The average compressive strength of any individual bricks shall be not less than 160 Kg / Sq.Cm.

54.6. The average water absorption for five bricks tiles shall not exceed 12 percent of average weight of brick before testing. The absorption for each individual bricks shall not exceed 25 percent.

54.7. The brick tiles when tested in accordance with I.S. 1077-1976, the rate of efflorescence shall not be more than "Slightly effloresced"

M-55. White glazed tiles

- 55.1.** The tiles shall be of best quality as approved by the Engineer-in-charge. They shall be flat and true to shape. They shall be free from cracks, crazing spots chipper) edges and corners. The glazing shall be of uniform shade.
- 55.2.** The tiles shall be nominal size of 150 mm x 150 mm unless otherwise, specified. The maximum variation the stated sizes other than the thickness of tile shall be plus or minus 1.5 mm. The thickness of tile shall be 6 mm. Except as above the tiles shall conform to I.S. 1977-19/0.

M-56. Galvanised iron pipes and fittings

- 56.1.** Galvanised iron pipes shall be of the medium type and of required diameter and shall comply with I.S. 1239-1979. The specified diameter of the pipes shall refer to the inside diameter of the bore, clamps, screw and all galvanised iron fittings shall be of the standard 'R' or equivalent make.

M-57. Bib cock and stop cock

- 57.1.** A bib cock is a draw off tap with a horizontal inlet and free outlet A stop cock is a valve with suitable means of connection for insertion in a pipe line for controlling or stopping the flow.
- 57.2.** They shall be of screw down type and of brass chromium plated and of diameter as specified in the description of the item. They shall conform to I.S. 781-1977 and they shall be of best Indian make. They shall be polished bright.
- 57.3.** The minimum finished weight of bib cock and stop cock shall be as given below :

Diameter	Bib Cock	Stop Cock	Diameter	Bib Cock	Stop Cock
8 mm	0.25 Kg.	0.25 Kg.	15 mm	0.40 Kg.	0.40 Kg.
10 mm	0.30 Kg.	0.35 Kg.	20 mm	0.75 Kg.	0.75 Kg.

M-58. Gun metal wheel valve

- 58.1.** The gun metal wheel valve shall be of approved quality. These shall be of gun metal fitted with wheel and shall be of gate valve opening full way and of the size specified. These shall conform to I.S. 778-1971.

M-59. White glazed porcelain wash basin

- 59.1.** Wash basin shall be of white porcelain first quality best Indian make and it shall conform to I.S. 2556 (Part -IV) -1972 and I.S. 771-1979. The size of the wash basin shall be as specified in item. Wash basin shall be of one piece construction with continued over flow arrangements All internal angles shall be designed so as to facilitate cleaning. Wash basin shall have single tap hole as specified. Each basin shall have a circular waste hole which is either riveted or beveled internally with 65 mm. diameter at top and 10 mm. depth to suit the waste fitting. The necessary stud slot to receive the bracket on the under side of the basin shall be provided Basin shall have an internal soap holder which shall fully drain into the bowl.
- 59.2.** White glazed pedestal of the quality and colour as that the basin shall be provided where specified in the item. It shall be completely recessed at the back for reception of supply and wash pipe. It shall be capable of supporting the basin rigidly and adequately and shall be so designed as to make the height from the floor the floor to top of the rim of basin 750 mm. to 800 mm. as directed.

M-60. European type water closet/with low flushing

- 60.1.** The European type water closet shall be white glazed porcelain first quality and shall be of wash down type conforming to I.S. 2556-1973 and I.S. 771-1979.
- 60.2.** 'S' trap shall be provided as required with water seal not than 50 mm. The solid plastic seat and cover shall be of best Indian make conforming to I.S 2548-1980. They shall be made of moulded synthetic materials which shall be tough and hard with high resistance to solvents and shall be free

from blisters and surface defects and shall have chromium plated brass hinges and rubber buffer of suitable size.

M-61. Orrissa type water closet

- 61.1.** The Specification of Orrissa type white glazed water closet of first quality shall conform to I.S. 2256 (Part-III) -1981 and relevant specification of Indian type water closet except that pan will be with the integral squatting pan of size 580 mm x 400 mm with raised footrest.

M-62. Indian type water closet

- 62.1.** The Indian type white glazed water closet of first quality shall be of size as specified in the item and conforming to I.S. 771-1979 and I.S. 2556 – (Part-II) 1981. Each pan shall have integral flushing. It shall also have an inlet at back and front for connecting flush pipes as directed. The inside of the bottom of the pan shall have sufficient slope from the front towards the outlet and surface shall be uniform and smooth. Pan shall be provided with 100 mm. diameter 'P' or 'S' trap with approximately 50 mm. Water seal and 50 mm. diameter vent horn.

M-62. A. Foot Rests

- 62.A.1.** A pair of white glazed earthen ware rectangular foot to minimum size 250 mm. x 130 mm. x 20 mm shall be provided with the water closet.

M-63. Glazed Earthen Ware Sink

- 63.1.** The glazed earthen-ware sink shall be of specified size, colour and quality. The sink shall conform, to I.S. 771 Part – II – 1979. The brackets for sinks shall conform to I.S 775-1970.
- 63.2.** The pipes shall conform to I.S. 1239-part-I 1973 and I.S. 404-1962 for steel and lead pipes respectively. 32 mm. brass waste coupling of standard pattern with brass chain and rubber plug shall be provided with sink.

M-64. Glazed earthen-ware Lipped type flat back urinal/corner type urinal

- 64.1.** The lipped type urinal shall be flat back or corner type as specified in the item and shall conform to I.S 771-1979. It shall be of best Indian make and size as specified and approved by the Engineer-in-charge. The flat back of corner type urinal must be of 1st quality free from any defects, cracks etc.

M-65. Low level Enamel flushing tank

- 65.1.** The low level enamel flushing tank shall be of 15 liters capacity. It shall conform to I S 774-1971. The flushing cistern shall be of best quality and free from any defects. The flushing tank shall have outlet 32 mm. diameter. The outlet shall be connected with W.C. pan by lead pipe or P.V.C. pipe as specified. The flushing tank shall be provided with inlet and outlet for fixing G.I. inlet pipes and over-flow pipes. The flushing cistern shall be provided with chromium plated handle for flushing. The flushing tank shall be provided with bracket of cast iron so that it can be fixed on wall at specified height. The brackets shall conform to I.S. 775-1970.

M-66. Cast iron flushing cistern.

- 66.1.** The cast iron flushing cistern shall be of 15 liters capacity. It shall conform to I.S. 774-1971. The flushing cistern shall be of best quality free from any defects. The flushing cistern shall have outlet of 32 mm diameter. The lead pipe shall conform to I.S 404 (Part-I) - 1962; For fixing G.I. inlet pipes and overflow pipe 20 mm. dia. inlet and outlet shall be provided. The flushing cistern shall be provided with galvanised iron chain and pull of sufficient length and shall be got approved from the Engineer-in-charge. The cast iron flushing cistern shall be painted with one coat of anticorrosive paint and two coats of paint. The flushing cistern shall be fixed on two C I brackets. The C I brackets shall conform to I S 775-1970.

M-67. Flush cock

67.1. Half turn flush cock (Heavy weight) shall be of gun metal chromium plated of diameter as specified in the description of the item. The flush cock shall conform to relevant Indian Standard.

M-68. Cast iron pipes and fittings.

68.1. All soil water, vent and anti syphonage pipes and fitting shall conform to I S.1729-1964. The pipes shall have spigot and socket ends with head on spigot end. The pipes and fitting shall be true to shape smooth, cylindrical, their inner and outer surfaces being as nearly as practicable concentric. They shall be sound and nicely cast and shall be free from cracks, laps, pinholes or there imperfection and shall be neatly dressed and carefully fettled.

68.2. The end of pipes and fittings shall be reasonable square to their axis.

68.3. The sand of cast iron pipes shall be of the diameter as specified in the description and shall be in lengths of 1.5 M., 1.8 M. including socket ends of the pipe unless shorter lengths are either specified or required at junctions etc. The pipes and fittings shall be supplied without ears unless specified or directed otherwise.

68.4. Tolerances :

68.4.1. The Standard weights and thickness of pipes shall be as shown in the following table A tolerance up to minus 10 per cent may however be -allowed against these standard weights

Sr. No.	Nominal dia. of Bore	Thickness	Overall		
			1.5 m long	1.8 m long	2 m. long
1.	75 mm	5.0 mm	12.83 Kg.	16.52 Kg.	18.37 Kg.
2.	100 mm	5.0 mm	18.14 Kg.	21.67 Kg.	24.15 Kg.

68.4.2. A tolerance up to minus 15 percent in thickness and 20 mm. length will be allowed For fittings tolerance in lengths shall be plus 25 mm. and minus 10 mm.

68.4.3. The thickness of fittings and their socket and spigot dimensions shall conform to the thickness and dimensions specified for the corresponding sizes of straight pipes. The tolerance in weights and thickness shall be the same as for straight pipes.

M-69. Nahni Trap

69.1. Nahni trap shall be of cast iron and shall be sound and free from porosity or other defects which affect serviceability The thickness of the base metal shall not be less than 6.5 mm The surface shall be smooth and free .form craze, chips and other flaws or any other kind of defects which affect serviceability The size of nahni trap shall be specified and shall be of self cleaning design.

69.2. The Nahni trap shall be of-quality approved by the Engineer-in-charge and shall generally conform to the relevant Indian Standards.

69.3. The Nahni trap provide shall be with deep seal, minimum 50 mm. except at places where trap with deep seal cannot be accommodated. The cover shall be cast iron perforated cover shall be provided on the trap of appropriate size.

M-70. Gully Trap

70.1. Gully trap shall conform to I.S. 651-1980. If shall be some, free from defects such as fire-cracks or hair cracks. The glaze of the traps shall be free from crazing. They shall give a sharp clear note when struck with light hammer. There shall be no broken blisters.

70.2. The size of the gully trap shall be as specified in the item.

70.3. Each gully trap shall have one C.I. grating of square size corresponding to the dimensions, of inlet of gully trap. It will also have a water tight C.I. cover with frame inside dimensions 300 mm. x 300

mm. the cover with frame inside dimensions 300 mm. x 300 mm. the cover and weighing not less than 4.53 Kg. and the frame not less than 2.72 Kg. The grating cover and frame shall be of sound and good casting and shall have truly square machined seating faces.

M 71. Glazed Stone Ware pipe And Fittings

71.1. The pipes and fittings shall be of best quality as approved, by the Engineer-in-charge. The pipe shall be of best quality manufactured from stone- ware of fire clay, salt glazed thoroughly burnt through the whole thickness, of a close, even texture, free from air blows, fire blisters, cracks and other imperfections, which affect the serviceability. The inner and outer surfaces shall be smooth and perfectly glazed. The pipe shall be capable to withstand pressures or 1.5 M lead without showing sign of leakage. The thickness of the wall shall not be less than 1/12th of the internal dia. The depth of socket shall not be less than 38 mm. The socket shall be sufficiently large to allow a joint of 6 mm. around the pipe.

71.2. The pipes shall generally conform to relevant I S 651-1980.

M-72. Wall Peg Rail

72.1. The aluminum wall peg rail shall have three aluminum pegs approved quality and size. It shall be fixed on teakwood plank of size 450 mm x 75 mm x 20 mm. The teakwood shall be French polished or oil painted as specified.

M-73. G.I. Water Spot

73.1. The G.I. pipes of 40 mm dia shall be of medium quality and specials shall be of 'R' brand or equivalent brand of best approved quality

73.2. The pipe shall have length as required for the thickness of wall in which it is fixed and at outside end tee bend cut at half the length shall be provided and at other end coupling shall be provided to have better fixing. The water spout shall be provided as per detailed drawing or as directed.

M-74. Asbestos Cement pipe (A.C. pipe)

74.1. The asbestos cement pipe of diameter as specified in the description of the item shall conform to I.S. 1626-1980. Special like bends, shoes, cowls, etc. shall conform to relevant Indian Standards. The interior of pipe shall have smooth finish, regular surface and regular internal diameter. The tolerance in all dimensions shall be as I.S. 1626-part-I-1980.

M-75. Crydon Ball valve

75.1. Ball valve of screwed type including polythene float and necessary level etc shall be of the size as mentioned in the description of item and shall conform to I.S 1703-1977

M-76. Bitumen Felt For Water proofing And Damp Proofing

76.1. Bitumen felt shall be on the fiber bases and shall be of type 2, self finished felt grade-2 and shall conform to I.S. 1322-1970

M-77. Selected Earth

77.1. The selected earth shall be that obtained from excavated material or shall have to be brought from outside as indicated in the items If item does not indicate anything the selected earth shall have to be brought from outside.

77.2. The selected earth shall be good yellow soil and shall be got approved from the Engineer-in-charge. In no case black cotton soil or similar expansive and shrinkable soil shall be used. It shall be clean and free from all rubbish and perishable materials, stones or brick bats. The clods shall be broken to a size of 50 mm or less. Contractor shall make his own arrangement at his own cost for land for borrowing selected earth. The stacking of material shall be done as directed by the

Engineer-in-charge in such a way not to interfere with any construction all activities and in proper stacks.

- 77.3.** When excavated material is to be used only selected stuff got approved from the Engineer-in-charge shall be used. It shall be stacked separately and shall, comply with all the requirements of selected earth mentioned above.

M-78. Barbed Wire

- 78.1.** The barbed wire shall be of galvanized steel and it shall generally conform to I.S. 278-1978. The barbed wire shall be of types-I whose nominal diameter for line wire shall be 2.5 mm. and point wire 2.24 mm. The nominal distance between two barbs shall be 75 mm unless otherwise specified in the item. The barbed wire shall be formed by twisting together two line wires. One containing the barbs. The size of the line and point wires and barb spacing shall be as specified above. The permissible deviation from the nominal diameter of the line wire and point wire shall not exceed ± 0.08 mm
- 78.2.** The barbs shall carry four points and shall be formed by twisting two point wires, each two turns tightly round one line wire making altogether four complete turns. The barbs shall have a length of not less than 13 mm and not more than 18 mm. The point shall be sharp and cut at an angle not greater than 35 degree of the axis of the wire forming the barbs.
- 78.3.** The line and point wires shall be circular in section, free from scale and other defects and shall be uniformly galvanized. The line wire shall be in continuous length and shall not contain any welds other than those in the rod before it is drawn. The distance between two successive splices shall not be less than 15 meters.
- 78.4.** The lengths per 100 Kg. of barbed wire I.S. type I shall be as under:
- | | | |
|--------------------|-------------------|---------------------|
| Nominal 1000 meter | Minimum 934 meter | Maximum 1066 Meter. |
|--------------------|-------------------|---------------------|

Item No. 1

Boring of holes 3.0 mt. deep in ordinary soil (for cast in situ piles) and getting out the soil and disposal of the surplus excavated soil as directed with in lead of 50 mt. for following dia. of piles and for under reamed piles of following diameter and deduct from the rate for bore holes of 3.5 mt. depth, if bore holes are made deeper or shallower than 3.5 m. for piles of following diameter (A) 300mm dia.

1.0 Workman ship

1.1. The ground shall be roughly leveled and after making the position of piles the holes shall be bored with a spiral angle to 3.0 meter deep and specified diameter using boring guide

1.2. The bore holes shall be truly vertical and uniform bore through out of specified diameter. After boring to the required depth the bore shall be cleaned off the loose soil and disposal of surplus excavated stuff as directed within a lead of 50 meter.

1.3. After clearing the site the centre lines will be given by the Engineer-in-charge. The contractor shall assume full responsibility for alignment, elevation and dimension of each and all parts of the work Contractor shall supply labours materials etc. required for setting out the reference marks and bench marks and shall maintain them as long as required and directed

1.4. All excavation shall be carried out in conformity with the directions laid here-in-under and in a manner approved by the Engineer in charge. While planning or executing of boring holes the contractor shall take all adequate precautions against soil erosion, water pollution etc. as per clause 306 and take appropriate drainage measures to keep the site free of water in accordance with clause 311.

1.5. The contractor shall not bore holes outside the limits of excavation. Subject to the permitted tolerances, any excess depth which excavated beyond the specified levels dimensions on the drawings shall be made good at the cost of contractor with suitable material of characteristics similar to that removed and compacted to the requirements of clause 305.

1.6. All debris and loose material in and around borehole shall be removed bore holes shall be bored to approved depth on instruction of the Engineer in charge and

1.7. After boring holes, the area shall be trimmed and the area contoured to minimize erosion and pounding, allowing for natural drainage to take place. If trees were removed, new trees shall be planted as directed by Engineer in charge. The cost of planting new trees shall be deemed to be incidental to the work.

1.8. All the excavated materials shall be the property of the Government. Where the excavated material is to be used in the filling of plinth, it shall be directly deposited at the required location, within 50 meters lead.

2.0 MODE OF MEASUREMENT & PAYMENT :

2.1. Boring of holes for structures shall be measured in its number for each class of materials encountered, limited to the dimensions shown on the drawing or as directed by the Engineer-in-charge. Boring holes over increased diameter cutting of slopes, shoring, shuttering and planking shall be deemed as convenience for the contractor in executing the work and shall not be measured and paid for separately.

2.2. The contract under rate for the items of excavation for structures shall be paid in full for carrying out the required operations including:

1. Setting out and fixing bench marks and centre lines stones.
2. Removal of all logs, stumps, grubs and other deleterious matter and obstructions for placing the foundations including trimming of bottoms of excavations;
3. Foundation sealing, dewatering including pumping;
4. All labour, materials, tools equipment, safeguards and incidentals necessary to complete the work to the specification.

2.3. Boring holes shall be for soil such as vegetation or organic soil, turf, sand, silt, loam, clay, mud, black cotton soil, soft shale or soft murrum, required drilling equipment.

2.4. The boring holes work shall be measured for its **Number**, limiting dimensions to those specified on plan or as directed. The rate shall be for a unit of each.

Item No. 2

Boring of holes 2.50 mt. deep in ordinary soil (for cast in situ piles) and getting out the soil and disposal of the surplus excavated soil as directed with in lead of 50 mt. for following dia. of piles and for under reamed piles of following diameter and deduct from the rate for bore holes of 3.5 mt. depth, if bore holes are made deeper or shallower than 3.5 m. for piles of following diameter (B) 250mm dia.

1.0 Workman ship

1.1. The ground shall be roughly leveled and after making the position of piles the holes shall be bored with a spiral angle to 2.5 meter deep and specified diameter using boring guide

1.2. The bore holes shall be truly vertical and uniform bore through out of specified diameter. After boring to the required depth the bore shall be cleaned off the loose soil and disposal of surplus excavated stuff as directed within a lead of 50 meter.

1.3. After clearing the site the centre lines will be given by the Engineer-in-charge. The contractor shall assume full responsibility for alignment, elevation and dimension of each and all parts of the work Contractor shall supply labours materials etc. required for setting out the reference marks and bench marks and shall maintain them as long as required and directed

1.4. All excavation shall be carried out in conformity with the directions laid here-in-under and in a manner approved by the Engineer in charge. While planning or executing of boring holes the contractor shall take all adequate precautions against soil erosion, water pollution etc. as per clause 306 and take appropriate drainage measures to keep the site free of water in accordance with clause 311.

1.5. The contractor shall not bore holes outside the limits of excavation
Subject to the permitted tolerances, any excess depth which excavated beyond the specified levels dimensions on the drawings shall be made good at the cost of contractor with suitable material of characteristics similar to that removed and compacted to the requirements of clause 305.

1.6. All debris and loose material in and around borehole shall be removed bore holes shall be bored to approved depth on instruction of the Engineer in charge.

1.7. After boring holes, the area shall be trimmed and the area contoured to minimize erosion and pounding, allowing for natural drainage to take place. If trees were removed, new trees shall be planted as directed by Engineer in charge. The cost of planting new trees shall be deemed to be incidental to the work.

1.8. All the excavated materials shall be the property of the Government. Where the excavated material is to be used in the filling of plinth, it shall be directly deposited at the required location, within 50 meters lead.

2.0 MODE OF MEASUREMENT & PAYMENT :

2.1. Boring of holes for structures shall be measured in its number for each class of materials encountered, limited to the dimensions shown on the drawing or as directed by the Engineer-in-charge. Boring holes over increased diameter cutting of slopes, shoring, shuttering and planking shall be deemed as convenience for the contractor in executing the work and shall not be measured and paid for separately.

2.2. The contract under rate for the items of excavation for structures shall be paid in full for carrying out the required operations including:

1. Setting out and fixing bench marks and centre lines stones.
2. Removal of all logs, stumps, grubs and other deleterious matter and obstructions for placing the foundations including trimming of bottoms of excavations;
3. Foundation sealing, dewatering including pumping;
4. All labour, materials, tools equipment, safeguards and incidentals necessary to complete the work to the specification.

2.3. Boring holes shall be for soil such as vegetation or organic soil, turf, sand, silt, loam, clay, mud, black cotton soil, soft shale or soft murrum, required drilling equipment.

2.4. The boring holes work shall be measured for its **Number**, limiting dimensions to those specified on plan or as directed. The rate shall be for a unit of each.

Item No. 3 :- Providing and laying cement concrete 1:4:8 (1- cement : 4 coarse sand : 8 hand broken stone aggregates 40 mm nominal size) and curing complete excluding cost of formwork in Foundation and Plinth.

1.0. Materials

- 1.1.** Water shall conform to M-1. Cement shall conform to M-3. Sand shall conform to M-6. Hand broken stone aggregate 40 mm. nominal size shall conform to M-12.

2.0. Workmanship

2.1. General

- 2.1.1.** Before stating concrete the bed of foundation trenches shall be cleared of all loose materials, leveled, watered and rammed as directed

2.2. Proportion of Mix:

- 2.2.1.** The proportion of cement, coarse sand and stone aggregate shall be one part of cement. 4 parts of coarse sand and 8 parts of hand broken stone aggregates and shall be measured by volume.

2.3. Mixing:

- 2.3.1.** The concrete shall be mixed in a mechanical mixer at the site of work. Hand mixing may however be allowed for smaller quantity of work if approved by the Engineer-in-charge. When hand mixing is permitted by the Engineer-in-charge in case of break-down of machineries and in the interest of the work, it shall be carried out on a water tight platform and care shall be taken to ensure that mixing is continued until the mass is uniform in colour and consistency, However in such case 10% more cement than otherwise period 1 1/2 to 2 minutes. The quantity of water shall be just sufficient to produce a dense concrete of required workability for the purpose.

2.4. Transporting & Placing the concrete:

- 2.4.1.** The concrete shall be handed from the place, of mixing to the final position in not more than 15 minutes by the method as directed and shall be placed into its final-position, compacted and finished within 30 minutes of mixing with water i.e. before the setting commences.
- 2.4.2.** The concrete shall be laid in layers of 15 cms. to 20 cms.
- 2.5.1.** The concrete shall be rammed with heavy iron rammers and rapidly to get the required compaction and to allow ail the interstices to be filled with mortar.

2.6. Curing:

- 2.6.1.** After the final set, the concrete shall be kept continuously wet if required by pounding for a period of not less then 7 days form the date of placement.

3.0. Mode of measurement and payment

- 3.1.** The concrete shall be measured for its length, breadth and depth, limiting dimensions to those specified on plans or as directed.
- 3.2.** The rate shall be for a unit of **one cubic meter**.

Item No. 4 :- Providing and laying ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size) and curing etc. complete excluding the cost of formwork in foundation and plinth.

1.0. Materials

- 1.1.** Water shall conform to M-1. Cement shall conform to M-3. Sand shall conform to M-6. Grit shall conform to M-8. Graded stone aggregate 20 mm nominal size shall conform to M-12.
- (a) The bars shall be kept in position by the following methods :
- (i) In case of beam and slab construction, sufficient number of precast cover blocks in cement mortar 1:2 (1 cement : 2 coarse sand) about 4 cms. x 4 cms. section and of thickness equal to the specified cover shall be placed between the bars and shattering as to secure and maintain the requisite cover of concrete over the reinforcement. In case of cantilevered or doubly reinforce beams or slabs, the main reinforcing bars shall be held in position by introducing chain spacers or supports bars at 1.0 to 1.2 meter centers.
- 1.2.** All bars projecting from pillars, columns, beams, slabs etc, to which other bars and concrete are to be attached or bounded to later on, shall be protected with a coat of thin neat cement grout, if the bars are not likely to be incorporated with succeeding mass of concrete within the following 10 days. This coat of thin neat cement shall be removed before concreting.
- 1.3.** The shuttering to be provided shall be of ordinary timber plank and shall conform to M-26.
- 1.4.** The dimensions of scantlings and battens shall conform to the design. The strength of the wood shall not be less than that assumed in the design.

2.0. General

- 2.1.** The concrete mix is not required to be designed by preliminary tests. The proportion of the concrete mix shall be 1:2:4 (1 cement : 2 coarse sand : 4 graded stone aggregate 20 mm. nominal size) by volume concrete work shall have exposed concrete surface or as specified in the item.
- 2.2.** The designation ordinary M-100, M-150, M-200, M-250 specified as per I.S. corresponds approximately to 1:3:6, 1:2:4, 1:1.1/2:3 and 1:1:2 nominal mix of ordinary concrete by volume respectively.
- 2.3.** The ingredients required for ordinary concrete containing one bag of cement of 50 kg. by weight (0.0342 Cu.M.) for different proportions of mix shall be as under:

TABLE

Grade of concrete	Mix by volume	Total quantity of dry aggregates by volume per 50 kg. cement to be taken as sum aggregate of the individual volumes of fine & coarse aggregates, maximum	Proportion of fine aggregate to coarse aggregate	Quantity of water per 50 kg. of cement max.
(1 cubic metre : 1000 Liters)				
1	2	3	4	5
Ordinary	Liters			Liters
M-100	1:3:6	300	Generally 1:2 for fine aggregate to Coarse aggregate by volume but subject to a upper limit of 1:1.1/1 & a lower limit of 1:3.	34
M-150	1:2:4	220		32
M-200	1:1.1/2:3	160		30
M-250	1:1:2	100		27

- 2.4.** The water cement ratios shall not be more than specified in the above table. The cement content of the mix specified in the table shall be increased if the quantity of water in mix has to be met eased to overcome the difficulties of placements and compaction so that the water-cement ratio specified in the table is not exceeded.
- 2.5.** Workability of the concrete shall be controlled by maintaining a water cement-ratio that is found to give a concrete mix which is just sufficient wet to be placed and compacted without difficulty with the means available.
- 2.6.** The maximum size of coarse aggregate shall be as large as possible within the limits specified but in no case greater than one forth of the minimum thickness of the member provided that the concrete can be placed without difficulty so as to surround all reinforcement thoroughly and to fill the corners of the form.

- 2.7. For reinforced concrete work; coarse aggregates having a nominal size of 20 mm. are generally considered satisfactory.
- 2.8. For heavily reinforced concrete members as in the case of ribs of main beams, the nominal maximum size of coarse aggregate should usually be restricted to 5 mm. less than the minimum clear distance between the main bar or 5 mm. less than the minimum cover to the reinforcement whichever is smaller.
- 2.9. Where the reinforcement is widely spaced as in solid slabs, limitations of size of the aggregate may not be so important, and the nominal maximum size may some times be as great as or greater than the minimum cover.
- 2.10. Admixture maybe used in concrete only with approval of Engineer-in-charge based upon the evidence that with the passage of time neither the compressive strength of concrete is reduced not are other requisite qualities of concrete and steel impaired by the use of such admixtures.

3.0. Workmanship

- 3.1. **Proportioning** : Proportioning shall be done by volume, except which shall be measured in terms of bags of 50 kg. weight, the volume of one such bag being taken as 0.0342 cu. meter Boxes of suitable size shall be used for measuring sand aggregate. The size of boxes (internal) shall be 35 x 25 cms. and 40 cms deep while measuring the aggregate and sand the boxes shall be filled without shaking ramming or hammering. The proportioning of sand shall be on the basis of its dry volume and in case of damp saner, allowances for bulk age shall be made.

3.2. Mixing :

- 3.2.1. For all work, concrete shall be mixed in a mechanical mixed which along with other accessories shall be kept in first class working condition and so maintained throughout the construction Measured quantity of aggregate, sand and cement required for each batch shall be poured into the claim of the mechanical mixer while it is continuously running. After half a minute of dry mixing measured quantity of water required for each batch of concrete mix shall be added gradually and mixing continued for another one and a half minute Mixing shall be continued till materials are uniformly distributed and uniform colour of the entire mass is obtained and each individual particle of the coarse aggregate shows complete coating of mortar containing its proportionate amount of cement. In no case shall the mixing he done for less than 2 minutes after-oil ingredients have been put into the mixer.
- 3.2.2. When hand mixing is permitted by the Engineer-in-charge for small jobs or for certain other reasons, it shall be done on the smooth watertight platform large enough to allow efficient tuning over the ingredients of concrete before and after adding water Mixing platform shall be so arranged that no foreign malarial gets mixed with concrete nor does the mixing water flow out. Cement in required number of bags shall be spread in n layer of uniform thickness on the mixing platform. Dry coarse and fine aggregate and cement shall then be mixed thoroughly be turning over to get a mixture to uniform colour. Specified quantity water shall then be added gradually through a rose can and the mass turned over till a mix of required consistency is obtained. In hand mixing quantity of cement shall be increased by 10 percent above that specified.
- 3.2.3. Mixers which haw been out of use for more than 30 minutes shall be thoroughly cleaned before putting in a new batch. Unless otherwise agreed to by the Engineer in-charge the first batch of concrete from the mixture shall contain only two thirds of normal quantity of coarse aggregate Mixing plant shall be thoroughly cleaned before changing from one type of cement to another.
- 3.2.4. The form work shall conform to the shape lines and dimensions as shown on the plans and be constructed as to remain sufficiently rigid during the placing and compacting of the concrete. Adequate arrangements shall be made by the contractor toe safe-guard against any settlement of the form-work during the course of concreting and after concreting. The form work of shuttering, centering, scaffolding, bracing etc. shall be as per design.

3.3. Clearing and Treatment of forms:

- 3.3.1 All rubbish, particularly chipping shaving and saw dust shall be removed from the interior of the form before the concrete work is placed and the-form in contact with concrete shall be cleaned and thoroughly wetted or treated. The surface shall be then coated with soap solution applied before concreting is done. Soap solution for the purpose shaft prepared by dissolving yellow soap in water to get consistency of paint. Alternatively a coat of raw linseed oil shall be applied after thoroughly cleaning the surface. Care shall be taken that the coating does not get on construction joint surface and reinforced bars.

4.0 Stripping time:

- 4.1. In normal circumstances and where ordinary cement is used forms may be struck after expire of following periods.
 - (a) Sides of walls columns and vertical faces of beams.....24 to 48 hours.
 - (b) Beam soffits, (props, left under).....7 days.
 - (c) Removal of props slabs:
 - (i) Slabs spanning up to 4.5. m.....7 days.
 - (ii) Spanning over 4.5 mm.....14 days.
 - (d) Removal of props t beams and Arches:

- (i) Spanning up to 6 mm.....14 days.
- (ii) Spanning over 6 m.....21 days.
- 5.0 Procedure when removing the form work :**
- 5.1.** All form work shall be removed without such shock or vibrations as would damage the reinforced concrete surface. Before the soffits form work and struts are removed, the soffits and the concrete surface shall be exposed where necessary in order to ascertain that the concrete has sufficiently hardened.
- 6.0 Centering:**
- 6.1.** The centering to be provided shall be got approved. It shall be sufficiently strong to ensure absolute safety of the form work and concrete work before, during and after pouring concrete. Watch should be kept to see that behavior or centering and form work is satisfactory during concreting. Erection should also be such that it would allow removal of forms in proper sequence without damaging either the concrete or the forms to be removed.
- 6.2.** The props of centering shall be provided on firm foundation or base of sufficient strength to carry the loads without any settlement.
- 6.3.** The centering and form work shall, be inspected and approved by the Engineer-in-charge before concreting. But this will not relieve the contractor of his responsibility for strength, adequacy and safety of form work and centering. If there is a failure of form work or centering, contractor shall be responsible for the damages to property.
- 7.0 Scaffolding:**
- 7.1.** All scaffolding, hoisting arrangements and ladders etc. required for the facilitating of concreting shall be provided and removed on completion of work by contractor at his own expense. The scaffolding, hoisting arrangements and ladders etc. shall be strong enough to with stand all live, dead and impact loads expected to act and shall be subject to the approval of the Engineer-in-charge. However contractor shall be solely responsible for the safety of the scaffolding, hoisting arrangement, ladders, work and workman etc.
- 7.2.** The scaffolding, hoisting arrangements and ladder shall allow easy approach to the work spot and afford easy inspection.
- 7.3.** The rate is applicable to all condition of working and height up to 4 mts. The rate shall include the cost of materials and labour for various operations involved such as :
 - (a) Splayed edges, notching, allowance for overlaps and passing at angles, battens centering, shuttering propping, bolting, wedging easing, striking and removal.
 - (b) Filleting to form stop chamfered edges or splayed external angles not exceeding 20 mm: width to beams, columns and the like.
 - (c) Temporary openings in the forms for pouring concrete, if required removing rubbish etc.
 - (d) Dressing with oil to prevent adhesion of concrete with shuttering and.
 - (e) Raking or circular cutting.
- 8.0 Re-Use:**
- 8.1.** Before re-use, all form shall be inspected by Engineer-in-charge and their suitability ascertained. The forms shall be scarred, cleaned and joints are gone over, repaired where required. Inside surface shall be retreated to prevent adhesion of concrete.
- 9.0 Consistency:**
- 9.1.** The degree of consistency which shall depend upon the nature of the work and methods of vibration of concrete shall be determined by regular slump tests in accordance with I.S. 1199-193. The slump of 10 mm. to 25 mm shall be adopted when vibrators are used and 80 mm. when vibrators are not used.
- 9.2. Inspection:**
- 9.2.1.** Contractor shall give the Engineer-in-charge due notice before placing any concrete in the forms to permit him to inspect and accept the form work and forms as to their strength, alignment and general fitness but such inspection shall not relieve the contractor of his responsibility for the safety of men machinery materials and for results obtained immediately before concreting all forms shall be thoroughly cleaned.
- 9.2.2.** Centering design and its erection shall be got approved from the engineer-in-charge. One carpenter with helper shall invariably be kept present throughout the period of concreting. Movement of labour and other persons shall be totally prohibited for reinforcement laid in position. For access to different parts suitable mobile platforms shall be provided so that steel reinforcement in position is not disturbed. For ensuring proper cover, mortar blocks of suitable size shall be cast and tied to the reinforcement. Timber kapachi or metal pieces shall not be used for this purpose.
- 9.3. Transporting and laying:**
- 9.3.1.** The method of transporting and placing concrete shall be as approved. Concrete shall be so transported and placed that no contamination, segregation or loss of its constituent material takes place. All form work shall be cleaned and made free from standing water dust, snow or ice

immediately before placing of concrete. No concrete shall be placed in any part of the structure until the approval of the engineer-in-charge has been obtained.

9.3.2. Concreting shall proceed continuously over the area between construction joints. Fresh concrete proper contraction joint is formed. Concrete shall be compacted in its final position within 30 minutes of its discharge from the mixer. Except where otherwise agreed to by the engineer-in-charge, concrete shall be deposited in horizontal layers to a compacted depth of not more than 0.45 meter when internal vibrators are used and not exceeding 0.30 meter in all other cases.

9.3.3. Unless otherwise agreed to by the Engineer-in-charge concrete shall be dropped in to place from a height exceeding 2 meters. When trucking or chutes are used they shall be kept close and used in such a way as to avoid segregation. When concreting has to be resumed on a surface which has hardened, it shall be roughened, swept clean, thoroughly wetted and covered with a 13 mm. thick layer of mortar composed of cement and sand in the same ratio as in the concrete mix itself. This 13 mm. layer of mortar shall be freshly mixed and placed immediately before placing of new concrete. Where concrete has not fully hardened, all lateness shall be removed by scrubbing the wet surface with wire or bristle brushes, care being taken to avoid dislodgement of any particles of coarse aggregate. The surface shall then be thoroughly wetted, all free water removed and then coated with neat cement grout. The first layer of concrete to be placed on this surface shall not exceed 150 mm. in thickness and shall be well rammed against old work, particular attention being given to corners and close spots.

9.3.4. All concrete shall be compacted to produce a dense homogeneous mass with the assistance of vibrators, unless otherwise permitted by the Engineer-in-charge for exceptional cases, such as concreting under water, where vibrators cannot be used. Sufficient vibrators in serviceable condition shall be kept at site so that spare equipment is always available in the even of breakdowns. Concrete shall be judged to be compacted when the mortar fills the spaces between the coarse aggregate and begins to cream up to form an even surface. Compaction shall be completed before the initial setting starts i.e. within 30 minutes of addition of water to dry mixture. During compaction, it shall be observed that needle vibrators are not applied on reinforcement which is likely to destroy the bond between concrete and reinforcement.

9.4. Curing:

Immediately after compaction, concrete weather including rain, running water, shocks, vibration, traffic, rapid temperature charges, frost and drying out process. It shall be covered with wet sacking has Sian or other similar absorbent material approved, soon after the initial set, and shall be kept continuously wet for a period of not less than 14 days from the date of placement. Masonry work over foundation concrete may be started after 48 hours of its laying but curing of concrete shall be continued for a minimum period of 14 days.

9.5. Sampling and testing of concrete:

9.5.1. Samples from fresh concrete shall be taken as per I.S. 1199-1959 and cubes shall be made, cured and tested at 7 days of 28 days as per requirements in accordance with I.S. 526-1959. A random sampling procedure shall be adopted to ensure that each concrete batch shall have a reasonable chance of being tested i.e. the sampling should be spread over the entire period of concreting and cover all mixing units. The minimum frequency of sampling of concrete of each grade shall be in accordance with following :

Quantity of concrete in the work	No of samples	Quantity of concrete in the works	No of samples
1 - 5 Cmt.	1	16-30 Cmt.	3
6 - 15 Cmt.	2	31-50 Cmt.	4
51 and above	4± one additional for each	additional 50 mm. or part thereof.	

Note : At least one sample shall be taken from each shift, Ten test specimens shall be made from each sample, five for testing at 7 days and the remaining five at 28 days. The samples of concrete shall be taken on each day of concreting as per above frequency. The number of specimens may be suitably increased as deemed necessary by the Engineer-in-charge when procedure of tests given above reveals a poor quality of concrete and in other special cases.

9.5.2. The average of the group of cubes cast for each day shall not be less than the specified cube strength of 150 K/g Cm² at 28 days. 20% of the cubes cast for each day may have value less than the specified strength provided the lowest value is not less than 85% of the specified strength. If the concrete made in accordance with the proportions given for a particular grade does not yield the specified strength, such concrete shall be classified as belonging to the appropriate lower grade. Concrete made in accordance with the Proportions given for a particular grade shall not, however be placed in a higher grade on the ground that the test strength are higher than the minimum specified.

9.6. Stripping :

- 9.6.1.** The Engineer-in-charge shall be informed in advance by the contractor of his intention to strike the form work. While fixing the time of removal of form work, due consideration shall be given to local conditions, character of the structure, the weather and other conditions that influence the setting of concrete and of the materials used in the mix. In normal circumstances (generally where temperatures are above 20°C) and where ordinary concrete is used, forms may be struck after expiry or periods specified in item No.9.1 (A) for respective item of form work.
- 9.6.2.** All form work shall be removed without causing any shock or vibration as would damage the concrete. Before the soft and struts are removed, the concrete surface shall be gradually exposed, where necessary in order to ascertain that concrete has sufficiently hardened. Centering shall be gradually and uniformly lowered in such a manner as to permit the concrete to take stresses due to its own weight uniformly and gradually. Where internal metal tiles are permitted, they or their removable parts shall be extracted without causing any damage to the concrete and remaining holes filled with mortar. No permanently embedded metal part shall have less than 25 mm. cover to the finished concrete surface. Where it is intended to re-use the form work, it shall be cleaned and made good to the satisfaction of the Engineer-in-charge. After removal of form work and shutting, the Executive Engineer shall inspect the work and satisfy by random checks that concrete produced is of good quality.
- 9.6.3.** Immediately after the removal of forms, all exposed bolts etc. passing through the cement concrete member and used for shuttering or any other purpose shall be cut inside the cement concrete member to a depth of at least 25 mm. below the surface of the concrete and the resulting holes be filled by cement mortar, all fins, caused by form joints, all cavities produced by the removal of form tiles and all other holes and depressions, honeycomb spots, broken edges or corners and other defects, shall be thoroughly cleaned, saturated with water and carefully pointed and rendered true with mortar of cement and fine aggregate mixed in proportions used in the grade of concrete that is being furnished and of as dry consistency as is possible to use. Considerable pressure shall be applied in filling and pointing to ensure thorough filling in all voids. Surface which are pointed shall be kept moist for a period of 24 hours. If rock pockets/honeycombs in the opinion of the Engineer-in-charge are of such an extent or character as to effect the strength of the structure materially or to endanger the life of the steel reinforcement, he may declare the concrete defective and require the removal and replacement of the portions of structure affected.

10.0. Mode of Measurement & Payment

- 10.1.** The consolidated cubical contents of concrete work as specified in item shall be measured. No deduction shall be made for
- (a) Ends of dissimilar materials such as joints, beams, posts, girders, girders, purling trusses, corbels and steps etc. up to 500 Sq. Cm. in section.
- 10.2.** Form work shall be measured as the area in square meters to shuttering in contract with concrete except in the case of inclined member and portion of curved profile and upper side in which case on area of underside shall be measured for payment.
- 10.3.** Form work to secondary beams shall be measured up to the sides of main beams but no deduction shall be made from the form work of the main beam at the inter section point. No deduction shall be made from the form work of a column at inter section of beams.
- 10.4.** The rate includes cost of all materials labour, tools and plant required for mixing, placing in position, vibrating and compacting, finishing as directed, curing and all other incidental expenses for producing concrete of specified strength. The rate **includes** the cost of form work.
- 10.5.** The volume occupied by reinforcement shall not be deducted from R.C.C. work.
- 10.6.** The rate shall be for a unit of **one cubic meter**.

Item No. 5 :- Providing and laying ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size) and finishing smooth with curing etc. complete including the cost of formwork but excluding the cost of reinforcement for R.C.C. work in Columns having any cross sectional area.

The work shall be executed as per specification of **Item No. 4** except that the **ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size)** and finishing smooth with curing etc. for R.C.C. work in Columns having any cross sectional area instead of **ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size)** and curing etc. in foundation and plinth.

Item No. 6 :- Providing and laying ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size) and finishing smooth with curing etc. complete including the cost of formwork but excluding the cost of reinforcement for R.C.C. work in Beams having any cross sectional area.

The work shall be executed as per specification of **Item No. 4** except that the **ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size)** and finishing smooth with curing etc. for R.C.C. work in beams having any cross sectional area instead of **ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size)** and finishing smooth with curing etc. in foundation and plinth.

Item No. 7 :- Providing and laying ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size) for RCC Lintel including finishing smooth with curing etc. complete including the cost of formwork but excluding the cost of reinforcement.

The work shall be executed as per specification of **Item No. 4** except that the **ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size)** for R.C.C. Lintel including finishing smooth with curing etc. instead of **ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size)** and finishing smooth with curing etc. in foundation and plinth.

Item No. 8 :- Providing and laying ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size) and exposed work with curing etc. complete including the cost of formwork but excluding the cost of reinforcement for R.C.C. work in Slabs having any thickness.

The work shall be executed as per specification of **Item No. 4** except that the **ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size)** and finishing smooth with curing etc. for R.C.C. work in Slabs having any thickness instead of **ordinary cement concrete 1:2:4 (1- cement : 2 coarse sand : 4 graded stone aggregates 20 mm nominal size)** and finishing smooth with curing etc. in foundation and plinth.

Item No. 9 :- Providing and laying brick work using common burnt clay building conventional type bricks having crushing strength not less than 35 kg./Sq.Cm. in foundation and plinth in Cement Mortar 1:6 (1- Cement : 6 fine sand) including the cost of all materials and labour charges etc. complete.

1.0. Materials

Water shall conform to M-1. Cement shall conform to M-3. Sand shall conform to M-6. Bricks shall conform to M-15. Cement mortar shall conform to M-11.

2.0. Workmanship

2.1. Proportion:

2.1.1. The proportion of the cement mortar shall be 1:6 (1 cement : 6 fine sand) by volume.

2.2. Wetting of bricks:

2.2.1. The bricks required for masonry shall be thoroughly wetted with clean water for about two hours before use or as directed. The cessation of bubbles, when the bricks are wetted with water is as indication of through wetting of bricks.

2.3. Laying:

2.3.1. Bricks shall be laid in English bond unless directed otherwise. Half or cut bricks shall not be used except when necessary to complete to bond; closures in such case shall be cut to required size and used near the ends of walls.

2.3.2. A layer of mortar shall be spread on full width for suitable length of the lower course. Each brick shall first be properly bedded and set home by gently tapping with handle of trowel or wooden mallet. Its inside face shall be flushed with mortar before the next brick is laid and pressed against it. On completion of course, the vertical joints shall be fully filled from the top with mortar.

2.3.3. The walls shall be taken up truly in plumb. All courses shall be laid truly horizontal and all vertical joint shall be truly vertical. Vertical joints in alternate course shall generally be directly one over the other. The thickness of brick course shall be kept uniform.

2.3.4. The brick shall be laid with frog up wards. A set of tools comprising of wooden straight edges, man son's spirit level, square half meter rub, and pins, string and plumb shall be kept on the site of work for frequent checking during the progress of work.

2.3.5. Both the faces of walls of thickness greater than 23 cms. shall be kept in proper place. All the connected brick work shall be kept not more than one meter over the rest of the work. Where this is not possible, the work shall be raked back according to bond (and not left toothed) at an angle not steeper than 45 degrees.

2.3.6. All futures, pipes, outlets of water, hold fasts of doors and windows etc. which are required to be built in wall shall be embedded in cement mortar.

2.4. Joints:

2.4.1. Bricks shall be so laid that all joints are quite flush with mortar. Thickness of joints shall not exposed 12 mm. The face joints shall be raked out as directed by raking tools daily during the progress of work, when the mortar is still green so as to provide key for plaster or pointing to done.

2.4.2. The face of brick shall be cleaned the very day on which the work is laid and all mortar dropping removed.

2.5. Curing:

2.5.1. Green work shall be protected from rain suitably. Masonry work shall be kept moist on all the faces for a period of seven days. The top of masonry work shall be kept well wetted at the close of the day.

2.6. Preparation of foundation bed:

2.6.1. If the foundation is to be laid directly on the excavated bed, the shall be leveled, cleared of all loose materials, cleaned and wetted before stating masonry, If masonry is to be laid on concrete footing, the top of concrete shall be cleaned and moistened. The contractor shall obtain the engineer's approval for the foundation bed before foundation masonry is started. When pucca flooring is to be provided flush with the top to plinth, the inside plinth offset shall be kept lower than the outside plinth top by the thickness of the flooring.

3.0. Mode of measurements & payment

3.1. The measurements of this item shall be taken for the brick masonry fully completed in foundation up to plinth. The limiting dimensions not exceeding those shown on the plinths or as directed shall be final. Battered tapered and curved portions shall be measured net.

3.2. No deduction shall be made from quantity of brick work nor any extra payment made for embedding in masonry of marking holes in respect of following item.

(1) Ends of joints, beams, posts, girders, rafters, purlins trusses corbel, steps, etc. where cross sectional area does not exceed 500 sq.cm.

(2) Opening not exceed in 1000 sq.cm.

(3) Wall plate sand bed plates bearing of slab, chhajjas and like whose thickness does not exceed 10 cms. and the bearing does not extend the full thickness of wall.

(4) Drainage holes and recesses for cement concrete blocks to embed hold fasts for doors, window etc.

(5) Iron fixtures, pipes up to 300 mm. dia. hold fasts of doors and window built into masonry and pipes etc. for concealed wiring.

(6) Forming charges of section not exceeding 350 sq.cm. in masonry.

3.3 Apparatuses for fire places shall not be deducted nor shall extra labour required to make splaying of jumps, throating and making trenches over the aperture be paid for separately.

3.4. The rate shall be for a unit of **one cubic meter**.

Item No. 10 :- **Filling in foundation and plinth with murrum or selected soil in layers of 20 cm. thickness including watering, ramming and consolidating etc. comp.**

1.0 MATERIALS

- 1.1. Murrum or selected soil shall be clean, of good binding quality and of approved quality obtained from approved pots / quarries of disintegrated rocks which contain silicon's material and natural mixture of clay of clariions origin. The P.I. value of selected soil used shall not be more than 6.0.

2.0 WORKMANSHIP

- 2.1 The Murrum or selected soil to be used for filling shall be free from salts, organic or other foreign matter all colds of Murrum or selected soil shall be broken.
- 2.2 As soon as the work in foundation has been completed and measured the site of foundation shall be cleared of all debris brick bats mortar dropping etc. and filled with Murrum or selected soil in layers not exceeding 20 cms. Each layer shall be adequately watered, rammed and consolidated before the succeeding layer is laid. The Murrum or selected soil shall be rammed with iron rammers where feasible and with the but ends of crow bars. Where rammer cannot be used.
- 2.3 The plinth shall be similarly tilled with Murrum or selected soil in layers not exceeding 20 cms adequately watered and consolidated by ramming with iron or wooden rammers. When filling reaches finished level the surface shall be flooded with water for at least 24 hours and allowed to dry and then rammed and consolidated.
- 2.4 The finished level of filling shall be kept to shape intended to be given to floor.
- 2.5 In case of large heavy duty flooring like factory flooring, the consolidation may be done by power rollers, where so specified. The extent of consolidation required shall also be as specified.

3.0. MODE OF MEASUREMENTS & PAYMENT

- 3.1 The payment shall be made for filling in plinth and trenches no deduction shall be made for shrinkage or voids, if consolidated as instructed above.
- 3.2 The rate includes cost of collecting and carting murrum / or selected earth of approved quality with all lead and labour required for filling in trenches and plinth.
- 3.3 The rate shall be for a unit of one **Cum.**

Item No. 11 :- Providing and laying brick work using common burnt clay building conventional type bricks having crushing strength not less than 35 kg./Sq.cm. in Super structure in Cement Mortar 1:6 (1- Cement : 6 - fine sand) including the cost of all materials and labour charges etc. complete.

1.0. Materials

Bricks shall conform to M-15. Cement mortar shall conform to M-11.

2.0. Workmanship

2.1. Proportion:

2.1.1. The proportion of the cement mortar shall be 1:6 (1 cement: 6 fine sand) by volume.

2.2. Wetting of bricks:

2.2.1. The bricks required for masonry shall be thoroughly wetted with clean water for about two hours before use or as directed. The cessation of bubbles, when the bricks are wetted with water is as indication of through wetting of bricks.

2.3. Laying:

2.3.1. Bricks shall be laid in English bond unless directed otherwise. Half or cut bricks shall not be used except when necessary to complete to bond; closures in such case shall be cut to required size and used near the ends of walls.

2.3.2. A layer of mortar shall be spread on full width for suitable length of the lower course. Each brick shall first be properly bedded and set home by gently tapping with handle of trowel or wooden mallet. Its inside face shall be flushed with mortar before the next brick is laid and pressed against it. On completion of course, the vertical joints shall be fully filled from the top with mortar.

2.3.3. The walls shall be taken up truly in plumb. All courses shall be laid truly horizontal and all vertical joint shall be truly vertical. Vertical joints in alternate course shall generally be directly one over the other. The thickness of brick course shall be kept uniform.

2.3.4. The brick shall be laid with frog up wards. A set of tools comprising of wooden straight edges, mason's spirit level, square half meter rub, and pins, string and plumb shall be kept on the site of work for frequent checking during the progress of work.

2.3.5. Both the faces of walls of thickness greater than 23 cms. shall be kept in proper place. All the connected brick work shall be kept not more than one meter over the rest of the work. Where this is not possible, the work shall be raked back according to bond (and not left toothed) at an angle not steeper than 45 degrees.

2.3.6. All futures, pipes, outlets of water, hold fasts of doors and windows etc. which are required to be built in wall shall be embedded in cement mortar.

2.4. Joints:

2.4.1. Bricks shall be so laid that all joints are quite flush with mortar. Thickness of joints shall not exposed 12 mm. The face joints shall be raked out as directed by raking tools daily during the progress of work, when the mortar is still green so as to provide key for plaster or pointing to done.

2.4.2. The face of brick shall be cleaned the very day on which the work is laid and all mortar dropping removed.

2.5. Curing:

2.5.1. Green work shall be protected from rain suitably. Masonry work shall be kept moist on all the faces for a period of seven days. The top of masonry work shall be kept well wetted at the close of the day.

2.6. Preparation of foundation bed:

2.6.1. If the foundation is to be laid directly on the excavated bed, it shall be leveled, cleared of all loose materials, cleaned and wetted before starting masonry, If masonry is to be laid on concrete footing, the top of concrete shall be cleaned and moistened. The contractor shall obtain the engineer's approval for the foundation bed before foundation masonry is started. When pucca flooring is to be provided flush with the top to plinth, the inside plinth offset shall be kept lower than the outside plinth top by the thickness of the flooring.

2.7. The frames of doors, windows, cupboards etc. shall be housed into the brick work at the correct location and level as directed. The heavy steel doors, window frames etc. shall be built in with work, but for ordinary steel doors and windows required opening for frames, hold-fasts, etc., shall be in the wall and frame embedded later on in order to avoid damage to the frames.

2.8. Necessary scaffolding shall be provided. The supports of the scaffolding shall be sound and strong tied, together with horizontal pieces over which the scaffolding plunks shall be fixed. Simple scaffolding shall be allowed normally. In this case scaffolding hole shall rest in hole header horizontal coarse only. Minimum number of holes be left in brick work for supporting horizontal scaffolding poles. The contractor is responsible for providing and maintaining sufficiently strong scaffolding so as to withstand all loads likely to come upon it.

2.9. For the face of brick work, where plastering is to be done, joints shall be racked out to a depth not less than thickness of joints. The face of brick work shall be cleaned and mortar dropping removed on very same day that brick work is laid.

3.0. Mode of measurements & payment

3.1. The masonry work of **all floors** shall be measured and paid under this item rate includes cost of all materials & labour.

3.2. Brick work in parapet shall be included in the corresponding masonry item of floor immediately below the floor above which the parapet is built.

3.3. No deduction shall be made from quantity of brick work nor any extra payment made for embedding in masonry of marking holes in respect of following item.

(1) Ends of joints, beams, posts, girders, rafters, purlins trusses corbel, steps, etc. where cross sectional area does not exceed 500 sq.cm.

(2) Opening not exceed in 1000 sq.cm.

(3) Wall plate sand bed plates bearing of slab, chhajjas, and like whose thickness does not exceed 10 cms. and the bearing does not extend the full thickness of wall.

- (4) Drainage holes and recesses for cement concrete blocks to embed hold fasts for doors, window etc.
- (5) Iron fixtures, pipes up to 300 mm. dia. hold fasts of doors, and window built into masonry and pipes etc. for concealed wiring.
- (6) Forming charges of section not exceeding 350 sq.cm. in masonry.
- (7) Apparatuses for fire places shall not be deducted nor shall extra labour required to make splaying of jumps, throating and making trenches over the aperture be paid for separately.

3.4. The rate shall be for a unit of **one cubic meter**.

Item No. 12 :- Providing I.S.I. mark T.M.T. Bar Fe-415 reinforcement for R.C.C. work including bending, binding and placing in position complete upto floor two level.

1.0. GENERAL

This work shall consist of furnishing and placing coated, or uncoated or high strength deformed reinforcement, bars (intentioned) of the shape and dimensions shown on the drawings and conforming to these Specifications or as approved by the Engineer in charge.

2.0. MATERIAL

2.1. T.M.T. Bars

Reinforcements may be either T.M.T. tensile steel, conforms to IS 1786-2008 bars. They may be uncoated or coated with epoxy or with approved protective coatings.

2.2. T.M.T. bars reinforcement for R.C.C. work shall conform IS 432 (Part II) 1982 (Reaffirmed 1995) and shall be of tested quality. It shall also comply with relevant part of IS 456-2000.

2.3. All reinforcement shall be clean and free from dirt, paint, grease or oil, all scale or loose or thick rust at the time of placing

2.4. All steel shall be procured from original producers no re-rolled steel shall be incorporated in the work

2.5. Only new steel shall be delivered to the site every bar shall be inspected before placing to its position and defective brittle or burnt bar shall be discarded cracked ends of bars shall be discarded

3.0. Pitch

3.1. Distance between bars shall be as specified in drawings and as directed by the Engineer in Charge all bars shall be placed at an accurate distance from each other and shall be bind tightly to maintain the desired pitch Suitable means shall be provided for holding bars securely in position

4.0. Binding wire

4.1. Mild steel binding wire shall be of 1.63 mm or 1.22 mm (16 to 18 gauge diameter and shall conform IS 280-2006.

4.2. The use of black wire will be permitted for binding reinforcement bars. It shall be free from dirt, paint, grease or oil, oil scale or loose or thick rust and any other undesirable coating which may prevent adhesion of cement mortar at the time of binding

4.3. Only new binding wire shall be delivered to the site all binding wire shall be inspected before binding to its position and defective brittle, rusted, used wire, shall be discarded

5.0. PROTECTION OF REINFORCEMENT

5.1. Uncoated reinforcing steel shall be protected from rusting or chloride contamination. Reinforcements shall be free from rust, mortar, loose mill scale, grease, oil or paints. This may be ensured either by using reinforcement fresh from the factory or thoroughly cleaning all reinforcement to remove rust using any suitable method such as sand blasting, mechanical wire brushing, etc. as directed by the Engineer. Reinforcements shall be stored on bricks, racks or platforms and above the ground in a clean and dry condition and shall be suitably marked to facilitate inspection and identification.

5.2. Portions of uncoated reinforcing steel and dowels projecting from concrete shall be protected within one week after initial placing of concrete with a brush coat of neat cement mixed with water to a consistency, of thick paint. This coating shall be removed by lightly tapping with a hammer or other tool not more than one week before placing of the adjacent pour of concrete. Coated

reinforcing steel shall be protected against damage to the coating. If the coating on the bars is damaged during transportation or handling and cannot be repaired, the same shall be rejected.

6.0. Workmanship

- 6.1.** The work shall consist of furnishing and placing reinforcement to the shape and dimensions shown as on the drawings or as directed by The Engineer in charge.
- 6.2.** Reinforcing steel shall conform accurate to the dimensions given in the bar bending schedules shown on relevant drawing

7.0. BENDING OF REINFORCEMENT

- 7.1.** Bar bend g schedule shall be furnished by the Contractor and got approved by the Engineer before start of work.
- 7.2.** Reinforcing steel shall conform to the dimensions and shapes given in the approved bar bending Schedules.
- 7.3.** Bars shall be bent cold to the specified shape and dimensions or directed by the Engineer using a proper bar bender operated by hand power to obtain the correct radius of bends and shape.

Bars shall not be bent or straightened in a manner that will damage parent material or the coating bars bent during transport or handling shall, be straightened before being used on work and shall not be heated to facilitate straightening.

8.0. PLACING OF REINFORCEMENT

8.1. The reinforcement cage should generally be fabricated in the yard at ground level, and then shifted and placed in position. The reinforcement shall be placed strictly, in accordance with the drawings and shall be assembled in position, only when structure is otherwise ready for placing of concrete. Prolonged time gap, between assembling of reinforcements and casting of concrete, which may result in rust formation on the surface, shall not be permitted.

8.2. Reinforcement bars shall be placed accurately in position as shown on the drawings. The bars, crossing one another shall be tied together at every intersection with binding wire (annealed), conforming to IS:280 to make the skeleton of the reinforcement rigid such that the reinforcement does not get displaced during placing of concrete, or any other operation. The diameter of binding wire shall not be less than 1 mm.

8.3. Bars shall be kept in position usually by the following methods:

In case of beam and slab construction, industrially produced polymer cover blocks of thickness equal to the specified cover shall be placed between the bars and formwork subject to Satisfactory evidence that the polymer composition is not harmful to concrete and reinforcement. Cover blocks made of concrete may be permitted by the Engineer, provided they have the same strength and specification as those of the member.

8.4. In case of dowels for Columns and walls the vertical reinforcement shall be kept in position by means of timber templates with slots in them accurately, or with cover blocks tied to the Reinforcement Timber templates shall be removed after the concreting has progressed up to a level just below their location.

8.5. Layers of reinforcements shall be separated by spacer bars at approximately One meter intervals. The minimum diameter of spacer bars shall be 12 mm or: equal to maximum size of main reinforcement or maximum size of coarse aggregate, whichever is greater. Horizontal reinforcement shall not be, allowed to sag between supports.

8.6. Necessary stays, blocks, metal chairs, spacers, metal hangers supporting wires etc, or other subsidiary, reinforcement shall be provided to fix the reinforcements firmly in its correct position.

8.7. Use of pebbles, broken stone, metal pipe, brick, mortar or wooden blocks etc as devices for positioning reinforcement shall not be permitted.

8.8. Bars coated with epoxy or any other approved protective coating shall be placed on supports that do not damage the coating. Supports shall be installed in a manner such that planes of weakness are not created in hardened concrete. The coated reinforcing steel shall be held in place by use of plastic or plastic coated binding wires especially manufactured for the purpose.

8.9. Placing and fixing of reinforcement shall be inspected and approved by the Engineer before concrete is deposited.

9.0. Lapping

9.1. All reinforcement shall be furnished in full lengths as indicated on the drawing. No splicing of bars, except where shown on the drawing; will be permitted without approval of the Engineer. The lengths of the splice shall be as indicated on drawing or as approved by the Engineer. Where practicable, overlapping bars shall not touch each other and shall be kept apart by 25 mm or 11 1/4 times the maximum size of coarse aggregate, whichever is greater. If this is not feasible, overlapping bars shall be bound with annealed steel binding wire, not less than 1 mm diameter and twisted tight in such a manner as to maintain minimum clear cover to the reinforcement from the concrete surface. Lapped splices shall be staggered or located at points, along the span where stresses are low.

10.0 Welding

10.1 Splicing by welding of reinforcement will be permitted only if detailed on the drawing or approved by the Engineer. Weld shall develop an ultimate strength equal to or greater than that of the bars connected.

10.2. While welding may be permitted for T.M.T. reinforcing bars conforming to IS:432, welding of deformed bars conforming to IS: 1786 shall in general be prohibited. Welding may be permitted in case of bars of other than S 240 grade including special. Welding grade of S 415 grade bars conforming to IS:1786, for which necessary chemical analysis has been secured and the carbon equivalent (CE) calculated from the chemical composition using the formula:

$$CE = C + \frac{Mn}{6} + \frac{Cr + Mg + V}{5} + \frac{Ni + Cu}{15}$$

is 0.4 or less.

10.3. The method of welding shall conform to IS:2751 and IS:9417 and to any supplemental specifications to the satisfaction of the Engineer

10.4. Bars shall be bent cold to the specified shape and dimensions or as directed by Engineer in charge using the proper bender tool, operated by hand or power to attain proper radius of bends. Bars shall not be bend or straightened in a manner that will injure the material. Bars bent during transport or handling shall be straightened before being used in the work. Bars shall not be heated to facilitate bending

10.5. Unless otherwise specified a 'U' type hook at the end of each bar shall invariably be provided to main reinforcement. The radius of the bane shall not be less then twice the diameter of the round bar and the length of the straight part of the bar beyond the end of the curve shall be at least four times of the diameter of the round bar. In case of bars which are not round and in case of deformed bars, the diameter shall be taken as the diameter of circle having an equivalent effective area. The hooks shall be suitably encased to prevent any spiting of the concrete

10.6. All reinforcement bars shall be accurately placed in exact position shown on the drawings and shall be securely held in position during placing of concrete by annealed binding wire not less than 1 mm in size and by using say blocks or metal chairs spacers, metal hangers, supporting wires or other approved devices at sufficiently close intervals, Bars shall not be allowed to sag between supports not displaced during concreting or any other operations of the work All devices used for positioning shall be of not corrodible material wooden and metal supports shall not extended to the surface of the concrete, except where shown in drawings. Placing bars on layers of freshly laid concrete as the work progresses for adjusting bar spacing shall not be allowed. Pieces of broken stone or brick and wooden blocs shall not be used Layers of bars shall be separated by spacer bars pre-cast mortar blocks or other approved devices. Reinforcement after bending placed in position shall be maintained in a clean condition until completely embedded in concrete, Special care shall be exercised to prevent any displacement of reinforcement in concrete already placed. To prevent reinforcement form corrosion, concrete cover shall be provided as indicated on drawings. All bars protruding from concrete and to which other bars are to be sliced and which are likely to be exposed for a period exceeding 10 days shall be protected by a thick coat of neat cement grout

10.7. Bars crossing each other where required shall be secured by binding wire (annealed) of size not less than 1 mm in such a manner that they do not slip over at the time of fixing and concreting

As far possible bars of full length shall be used in case this is not possible, overlapping of bars shall be done as directed by the Engineer in charge When practicable overlapping bars shall not touch each other, but be kept apart by 25 mm Where no feasible overlapping bars shall be bound with annealed wires not less than 1 mm thick twisted tight The overlaps shall be staggered for different bars and located at points along the span where neither sheer not bending moments is maximum.

10.8. Whenever indicated on drawing or desired the Engineer in charge bars shall be jointed by coupling which shall have a cross section sufficient to transmit the full stresses of bars The end of the bars that are jointed by coupling shall be upset for sufficient length so that the effective cross section at the base of threads is not less than the normal cross section of the bar. Threads shall be standards threads Steel for coupling shall conform to IS 226

10.9. When permitted or specified on the drawings joints of reinforcement bars shall butt-welded so as to transmit their full stresses Welded joints shall preferably be located at points when steel will not be subject to more than 75 percent of the maximum permissible stresses and welds so staggered that at any one section not more than 20 percent of the rods are welded Only electric are welding using a process which excludes air form the molten metal and conforms to any or other special provisions for the work shall be accepted Suitable means shall be provided for holding bars securely in position during welding It shall be ensured that no voids are left in welding and when welding is done in two or three stages previous surface shall be cleaned properly Ends of bars shall be cleaned of all loose scale rust stages paint and other foreign matter before welding Only competent welders shall be employed on the work. The M S electrodes used for welding shall conform IS 814 Welded pieces of reinforcement shall be tested. Specimen shall be taken form the actual site and their number shall frequency to test shall be as directed by the Engineer in charge

11.0 MODE OF MEASUREMENTS & PAYMENT

11.1. For the purpose of payment the bar shall be measured correct up to 10 mm length and weight payable works out at the rate specified below.

Sr. No	Diameter of steel	weight of steel per running meter	Sr. No	Diameter of steel	weight of steel per running meter
1	6 mm	0.22 Kg / Rmt	8	20 mm	2.47 Kg / Rmt
2	8 mm	0.39 Kg / Rmt	9	22 mm	2.98 Kg / Rmt
3	10 mm	0.62 Kg / Rmt	10	25 mm	3.85 Kg / Rmt
4	12 mm	0.89 Kg / Rmt	11	28 mm	4.83 Kg / Rmt
5	14 mm	1.21 Kg / Rmt	12	32 mm	6.31 Kg / Rmt
6	16 mm	1.58 Kg / Rmt	13	36 mm	7.99 Kg / Rmt
7	18 mm	2.00 Kg / Rmt	14	40mm	9.86 Kg / Rmt

11.1. Excess consumption over 5% will be charged at penal rate.

11.2. Reinforcement shall be measured in length including hooks, if any, separately for different diameters as actually used in work, excluding overlaps. From the length so measured, the weight of reinforcement shall be calculated in tonnes on the basis of IS: 1732. Wastage, overlaps, couplings, welded joints, spacer bars, chairs, stays, hangers and annealed steel wire or other methods for binding and placing shall not be measured and cost of these items shall be deemed to be included in the rates for reinforcement.

11.3. The contract unit rate for coated/uncoated reinforcement shall cover the cost of material, fabricating, transporting, storing, bending, placing, binding and fixing in position as shown on the drawings as per these specifications and as directed by the Engineer, including all labour, equipment, supplies, incidentals, sampling, testing and supervision.

The unit rate for coated reinforcement shall be deemed to also include cost of all material, labour, tools and plant, royalty, transportation and expertise required to carry out the work. The rate shall also cover sampling, testing and supervision required for the work.

11.4. The rate shall be for a unit of **One Kg.**

Item No. 13 :- Providing and fixing steel door with shutter frame iron angle, 18mm steel plate with iron oxidized hinges handle, stopper, locking arrangements including welding, cutting, hoisting fixing in position oil painting two coats primer coat etc. complete for Door.

1.0 Scope of work :

The Steel door comprises of M.S. angle & M.S. bars.

2.0 Materials:

2.01 Door Size 1.00 x 3.00 mt.

2.02 Iron angle section 65 mm x 65mm x 6mm size frame.

2.03 Iron angle 20mm dia meter M.S. Bars.

2.04 Oil Painting shall be Confirm to M-44.

2.05 Primer Shall Confirm to IS 3546-1966.

2.06 Iron oxidized fixtures & fastening.

3.0 Workmanship : The Steel door section with shutter frame shall be done with extreme finishing. The M.S. angel welded together to make a box frame and 18mm dia. M.S. bars to be fixed with it by drilling hole in the angle section and welded at 10 cm c/c approximate as directed by engineer in charge using oxidized iron fixture & fastening including primer coat approved quality and two coats of oil paint as directed by Engineer in charge. Door shall be fitted properly so as to align the doors properly and shall be given trial of opening and closing properly.

4.0 Painting : Oil painting including priming coat. The specification of item 19.59 (B) & item. No. 19.77 P.124 & 125 for wood work and item 19.12 / P.121 and Item no. 19.70 for Steel work of building specification book shall be adopted.

5.0 Mode of measurements and Payments :

The rates includes of cost of all type of materials for frame and shutter, labour, fixtures and fastening painting etc. use for all operation in the items of work for 1 sqm.

The Payment shall be mode on **Sq mt.** basis of completed work done.

Item No. 14 :- Providing and fixing steel window with shutter frame 50 x 50 x 6 mm iron angle, 18mm steel plate with 10mm dia. round bars hinges, handle, stopper, locking arrangements etc. steel work welded built up section cutting, hoisting fixing in position oil painting two coats one primer coat etc. complete for Windows.

The mild steel shall confirm to M-22, red lead paint, oil paint shall confirm to their relevant specification.

The steel section as specified or required shall be cut to correct length as per drawing and design. The cut ends exposed to view shall be finished smooth. No Two pieces shall be welded or otherwise jointed to make up the required length of the member. The windows shall be fabricated of M.S. component as given in the description of item and detailed drawing. M.S. sheet shall be of 19 gauge shall be fixed to the frame with weld, with binding patti of M.S. flat shall be in T or L shape so that ensure proper bond. The hold fast shall be embedded in cement concrete. The window shall be coated with oil painting two coats & one priming coat before fixing it is position. It shall be fixed true line, level and plumb. The shutter shall be double leaf shutter.

Necessary arrangement shall be made so that the shutter shall not closed back down in to opening.

The window shutter frame shall be of 50 x 50 x 6 mm iron angle alround with 11 no. of 10mm dia safety bars. The bars shall be supported with 25 x 6 mm M.S. flat at middle.

The window shutter frame shall be of 50 x 50 x 6 mm. Shutter frame shall consist of two vertical members and four horizontal members. The 5 x 6 mm flat shall be welded at the edge of one leaf for proper closing of shutter. The tadi shall be of 20 x 6 mm flat and 12mm dia bars. The M.S. sheet shall be of 19 gauge. The binding patti to M.S. sheet shall be fixed to all edges of cut sheet. It shall be of 25 x 6.

All section should be of good quality of brand and manufacture like Zindal. It should be of size described in item description / as directed by Engineer in charge. All sections should be colour anodized. The section of frame shall be filled by Non teakwood fill.

All sections, fixtures & fastenings shall to be got approved before fitting and it shall be of I.S. grade. It shall be fitted in true line level and working condition.

All necessary fittings like space setting block, brackets joint cleat, E.P.D.M., gasket, bearing etc. comp. should be of good quality and in working condition. The sliding operation should be smooth and noiseless.

Rate is as per finished work with all labour, materials, fixtures, fastening etc. comp.

Payment shall be made on Sq.m. basis for completed item as directed by Engineer in charge.

Item No.15 :- 20mm thick sand faced cement plaster on wall upto height 10 mt. above ground level consisting of 12mm thick backing coat of C.M. 1:3 (1 cement : 3 sand) and 8 mm thick finishing coat of C.M. 1:1 (1 cement : 1 sand) etc. complete.

1.0. Materials

1.1. Water shall conform to M-1. The cement mortar of proportion 1:3 shall conform to M-13.

2.0. Workmanship

2.1. The work shall be carried out in the coats. The backing coat (base coat) shall be 12 mm. thick in C.M. 1:3.

2.2. Scaffolding:

Wooden bullies, bamboos, planks, trestles and other scaffolding shall be sound. These shall be properly examined before erection and use. Stage scaffolding shall be provided for ceiling plaster which shall be independent of the walls.

2.3. Preparation of back ground :

2.3.1. The surface shall be cleaned of all dust, loose mortar droppings, traces of algae, efflorescence and other foreign matter by water or by brushing. Smooth surface shall be toughened by wire brushing if it is not hard and by hacking if it is hard. In case of concrete surface, if a chemical retarded has been applied to the form work, the surface shall be roughened by wire brushing and all the resulting dust and loose particles cleaned off and care shall be taken that none of the readers is left on the surface. Trimming of projections on brick/concrete surfaces where necessary shall be carried out to get an even surface.

2.3.2. Raking of joints in case of masonry where necessary shall be allowed to dry out for sufficient period before carrying out the plaster work.

2.3.3. The work shall not be soaked but only damped evenly before applying the plaster. If the surface becomes dry, such area shall be moistened again.

2.3.4. For external plaster, the plastering operation shall be started from top floor and carried downwards. For internal plaster, the plastering operations may be-started wherever the building frame and cladding work are ready and the temporary supports of the ceiling resting on the wall of the floor have been removed. Ceiling plaster shall be completed before starting plaster to walls.

2.4. Application of plaster :

2.4.1. The plaster about 15x15 cms. shall be first applied horizontally and vertically at not more than 2 meters intervals over the entire surface to serve as gauge. The surfaces of these gauges shall be truly in plane of the finished plastered surface. The mortar shall then be applied in uniform surface slightly more than the specified thickness, then brought to a true surface by working a wooden straight edge reaching across the gauges with small upward and sideways movements at a time. Finally, the surface shall be finished off true with a trowel or wooden float according as a smooth or a smooth or a sandy granular texture is required Excessive troweling or overworking the float shall be avoided. All corners, arises, angles and junctions shall be truly vertical or horizontal as the case may be and shall be carefully finished.

Hounding or chamfering, corners, arises junctions etc. shall be carried out with proper templates to be size required.

2.4.2. Cement plaster shall be used within half an hour after addition of water and mortar or plaster which is partially set shall be rejected and removed forthwith from the site.

2.4.3. In suspending the work at the end of the day, the plaster shall be left out clean to the line both horizontally and vertically, when recommencing the plaster, the edges of the old work shall be scraped clean and wetted with cement putty before plaster is applied to the adjacent areas to enable the two to properly join together. Plastering work shall be closed at the end of the day on the body of the wall and nearer than 15 cm. to any corners or arises. It shall not be closed on the body of features such as plaster bands and cornices not at the corners or arises. Horizontal joints in plaster work shall not also occur on parapet tops and copings as these invariably lead to leakage. No portion of the surface shall be left out initially to be packed up later on.

2.4.4. Each coat shall be kept damp continuously till the next coat is applied or for a minimum period of 7 days. Moistening shall commence as soon as plaster is hardened sufficiently. Soaking of walls shall be avoided and only as much water as can be readily absorbed shall be used, excessive evaporation on the sunny or windward side of building in hot air or dry weather shall be prevented by hanging matting or gunny bags oh the outside of the plaster and keeping them wet.

2.4.5. Before the first coat hardens its surface shall be beaten up by edges of wooden tapers and close dents shall be made on the surface. The subsequent coat shall be applied after this coat has been allowed to set for 3 to 5 days, depending upon the weather conditions. The surface shall not be allowed to dry during this period.

2.4.6. The second coat shall be completed to 8 mm. thickness in C.M. 1:1 as described above, including raising sand facing by bushing. The sample of sand face shall be got approved before the work is started. The whole work shall be carried out uniformly as per sample approved.

2.4.5. The plastering work shall be in single coat on rough side of half brick wall for interior plastering up to floor two level, finished even and smooth in C.M. 1:3.

2.4.6 Curing :

The curing shall be started overnight after finishing of plaster. The plaster shall be kept wet for a period of 7 days. During this period, it shall be protected from all damages.

2.4.7. The finishing shall be gutkha finishing with 1 cm x 1 cm grooves shall be done as directed.

3.0. Mode of measurements & payment

3.1. The rate shall include the cost of all materials, labour and scaffolding etc. involved in the operations described under workmanship.

3.2. All plastering shall be measured in square meters unless otherwise specified. Length breadth or height shall be measured correct to a centimeter.

3.3. Thickness of the plaster shall be exclusive of the thickness of the key i.e. grooves or open joints in brick work, stone work etc. or space between laths. Thickness of plaster shall be average thickness with minimum 20 mm at any point on this surface.

- 3.4. This item includes plastering up to floor two level including making necessary cornices as directed.
- 3.5. The measurement of wall plastering shall be taken between the walls or partition (dimensions before plastering being taken) for length and from the top of floor or skirting to ceiling for height. Depth of cover of cornices if any shall be deducted.
- 3.6. Soffits of stairs shall be measured as plastering on ceilings, following soffits shall be measured separately.
- 3.7. For jambs, soffits, sills etc. for openings not exceeding 0.5 sq. met each in area for ends of joints beams, posts, girders, steps etc. not exceeding 0.5 sq.mt each in area and for openings exceeding 0.5. sq.mt and not exceeding 3.00 sq.mt. in each area deductions and additions shall be made in the following manners.
- (a) No deductions shall be made for ends of joints, beams, posts etc. and openings not exceeding 0.5 sq. mt each and no addition shall be made for reveals, jambs, soffits, sills etc. of these openings, for finish to plaster around ends of joints, beams posts etc.
- (b) Deduction for openings exceeding 0.5 sq. mt but not exceeding 3 sq.mt. each shall be made as follows and no addition shall be made for ravel, jambs, soffits, sills etc. of these openings, (i) When both faces of all wall are plastered with same plaster, deduction shall be made for one face only, (ii) When two faces of wall are plastered with different types of plasters or if one face is plastered and the other pointed, deductions shall be made from the plaster or pointing on the side of frame for door, window etc. on which width of reveals is less than that on the other side but no deductions shall be made on the other side. Where width of reveals on both faces of all are equal, deductions of 50% of area of opening on each face shall be made from areas of plaster and / or pointing as the case may be.
- 3.8. For openings having door frames equal to or projecting beyond the thickness of wall, full deduction for opening shall be made from each plastered face of the wall.
- 3.9. In case of openings of area above 3 sq. mt. each, deduction shall be made for openings but jambs, soffits sand sills shall be measured.
- 3.10. The rate shall be for a unit of **One Sq. meter. No extra payment for making necessary cornices shall be made.**

Item No. 16 :- Providing 15mm thick cement plaster in single coat on brick / concrete wall for interior plastering upto floor two level finished even and smooth in cement mortar 1:3 (1-Cement : 3-sand) for finishing with a floating coat of neat cement slurry.

1.0. Materials

1.1. Water shall conform to M-1. The cement mortar of proportion **1:3** shall conform to M-13.

2.0. Workmanship

2.1. Scaffolding:

Wooden bullies, bamboos, planks, trestles and other scaffolding shall be sound. These shall be properly examined before erection and use. Stage scaffolding shall be provided for ceiling plaster which shall be independent of the walls.

2.2. Preparation of back ground :

2.2.1. The surface shall be cleaned of all dust, loose mortar droppings, traces of algae, efflorescence and other foreign matter by water or by brushing. Smooth surface shall be toughened by wire brushing if it is not hard and by hacking if it is hard. In case of concrete surface, if a chemical retarded has been applied to the form work, the surface shall be roughened by wire brushing and all the resulting dust and loose particles cleaned off and care shall be taken that none of the readers if left on the surface. Trimming of projections on brick/concrete surfaces where necessary shall be carried out to get an even surface.

2.2.2. Raking of joints in case of masonry where necessary shall be allowed to dry out for sufficient period before carrying out the plaster work.

2.2.3. The work shall not be soaked but only damped evenly before applying the plaster. If the surface becomes dry, such area shall be moistened again.

2.2.4. For external plaster, the peasting operation shall be started from top floor and carried downwards. For internal plaster, the plastering operations may be-started wherever the building frame and cladding work are ready and the temporary supports of the ceiling resting on the wall of the floor have been removed. Ceiling plaster shall be completed before starting plaster to walls.

2:3. Application of plaster :

2.3.1. The plaster about 15x15 cms. shall be first applied horizontally and vertically at not more than 2 meters intervals over the entire surface to serve as gauge. The surfaces of these gauges shall be truly in plane of the finished plastered surface. The mortar shall then be applied in uniform surface slightly more than the specified thickness, then brought to a true surface by working a wooden straight edge reaching across the gauges with small upward and sideways movements at a time. Finally, the surface shall be finished off true with a trowel or wooden float according as a smooth or a smooth or a sandy granular texture is required Excessive troweling or overworking the float shall be avoided. All corners, arises, angles and junctions shall be truly vertical or horizontal as the case may be and shall be carefully finished. Hounding or chamfering, corners, arises junctions etc. shall be carried out with proper templates to be size required.

2.3.2. Cement plaster shall be used within half an hour after addition of water and mortar or plaster which is partially set shall be rejected and removed forthwith from the site.

- 2.3.3.** In suspending the work at the end of the day, the plaster shall be left out clean to the line both horizontally and vertically, when recommencing the plaster, the edges of the old work shall be scraped clean and wetted with cement putty before plaster is applied to the adjacent areas to enable the two to properly join together. Plastering work shall be closed at the end of the day on the body of the wall and nearer than **15 cm.** to any corners or arises. It shall not be closed on the body of features such as plaster bands and cornices not at the corners or arises. Horizontal joints in plaster work shall not also occur on parapet tops and copings as these invariably lead to leakage. No portion of the surface shall be left out initially to be packed up later on.
- 2.3.4.** Each coat shall be kept damp continuously till the next coat is applied or for a minimum period of 7 days. Moistening shall commence as soon as plaster is hardened sufficiently. Soaking of walls shall be avoided and only as much water as can be readily absorbed shall be used, excessive evaporation on the sunny or windward side of building in hot air or dry weather shall be prevented by hanging matting or gunny bags on the outside of the plaster and keeping them wet.
- 2.3.5.** The plastering work shall be in single coat on brick / concrete wall for interior plastering up to floor two level, finished even and smooth **in C.M. 1:3.**
- 2.3.6** The coat of cement and fine sand mortar of proportion 1:1 (15 mm thick about) shall be applied to the plastered surface with a trowel to provide uniform texture while the base coat is still plastic.
- 2.3.7.** In any continuous face of wall the finishing treatment should be carried out continuously and day to day breaks made to coincide with architectural breaks in order to avoid unsightly Junctions
- 2.3.8. Curing :** All the plaster work shall be kept damp continuously for a period 7 days.
- 2.3.9.** Providing necessary grooves between structural members as directed by Engineer in charge.
- 3.0. Mode of measurements & payment**
- 3.1.** The rate shall include the cost of all materials, labour and scaffolding etc. involved in the operations described under workmanship.
- 3.2.** All plastering shall be measured in square meters unless otherwise specified. Length breadth or height shall be measured correct to a centimeter.
- 3.3.** Thickness of the plaster shall be exclusive of the thickness of the key i.e. grooves or open joints in brick work, stone work etc. or space between laths. Thickness of plaster shall be average thickness with minimum **15 mm** at any point on this surface.
- 3.4.** This item includes plastering for all floors.
- 3.5.** The measurement of wall plastering shall be taken between the walls or partition (dimensions before plastering being taken) for length and from the top of floor or skirting to ceiling for height. Depth of cover of cornices if any shall be deducted.
- 3.6.** Soffits of stairs shall be measured as plastering on ceilings, following soffits shall be measured separately.

- 3.7.** For jambs, soffits, sills etc. for openings not exceeding 0.5 sq. met each in area for ends of joints beams, posts, girders, steps etc. not exceeding 0.5 sq.mt each in area and for openings exceeding 0.5. sq.mt and not exceeding 3.00 sq.mt. in each area deductions and additions shall be made in the following manners.
- (a) No deductions shall be made for ends of joints, beams, posts etc. and openings not exceeding 0.5 sq. mt each and no addition shall be made for reveals, jambs, soffits, sills etc. of these openings, for finish to plaster around ends of joints, beams posts etc.
- (b) Deduction for openings exceeding 0.5 sq. mt but not exceeding 3 sq.mt. each shall be made as follows and no addition shall be made for reveals, jambs, soffits, sills etc. of these openings, (i) When both faces of all wall are plastered with same plaster, deduction shall be made for one face only, (ii) When two faces of wall are plastered with different types of plasters or if one face is plastered and the other pointed, deductions shall be made from the plaster or pointing on the side of frame for door, window etc. on which width of reveals is less than that on the other side but no deductions shall be made on the other side. Where width of reveals on both faces of all are equal, deductions of 50% of area of opening on each face shall be made from areas of plaster and / or pointing as the case may be.
- 3.8.** For openings having door frames equal to or projecting beyond the thickness of wall, full deduction for opening shall be made from each plastered face of the wall.
- 3.9.** In case of openings of area above 3 sq.mt. each, deduction shall be made for openings but jambs, soffits sand sills shall be measured.
- 3.10** The payment shall be made for a unit of 1.0 sq.mt of work done over an above the finishing of work of base coat.
- 4.0.** The rate shall be for a unit of **One sq. meter.**

Item No. 17 :- Providing 10 mm thick cement plaster in single coat on brick / concrete walls for interior plastering upto floor two level and finished even and smooth in cement mortar 1:3 (1 cement : 3 sand) etc. complete.

1.0. Materials

1.1. Water shall conform to M-1. The cement mortar of proportion 1:3 shall conform to M-13.

2.0. Workmanship

2.1. Scaffolding:

Wooden bullies, bamboos, planks, trestles and other scaffolding shall be sound. These shall be properly examined before erection and use. Stage scaffolding shall be provided for ceiling plaster which shall be independent of the walls.

2.2. Preparation of back ground :

2.2.1. The surface shall be cleaned of all dust, loose mortar droppings, traces of algae, efflorescence and other foreign matter by water or by brushing. Smooth surface shall be toughened by wire brushing if it is not hard and by hacking if it is hard. In case of concrete surface, if a chemical retarded has been applied to the form work, the surface shall be roughened by wire brushing and all the resulting dust and loose particles cleaned off and care shall be taken that none of the readers if left on the surface. Trimming of projections on brick/concrete surfaces where necessary shall be carried out to get an even surface.

2.2.2. Raking of joints in case of masonry where necessary shall be allowed to dry out for sufficient period before carrying out the plaster work.

2.2.3. The work shall not be soaked but only damped evenly before applying the plaster. If the surface becomes dry, such area shall be moistened again.

2.2.4. For external plaster, the peasting operation shall be started from top floor and carried downwards. For internal plaster, the plastering operations may be started wherever the building frame and cladding work are ready and the temporary supports of the ceiling resting on the wall of the floor have been removed. Ceiling plaster shall be completed before starting plaster to walls.

2:3. Application of plaster :

2.3.1. The plaster about 15x15 cms. shall be first applied horizontally and vertically at not more than 2 meters intervals over the entire surface to serve as gauge. The surfaces of these gauges shall be truly in plane of the finished plastered surface. The mortar shall then be applied in uniform surface slightly more than the specified thickness, then brought to a true surface by working a wooden straight edge reaching across the gauges with small upward and sideways movements at a time. Finally, the surface shall be finished off true with a trowel or wooden float according as a smooth or a smooth or a sandy granular texture is required Excessive troweling or overworking the float shall be avoided. All corners, arises, angles and junctions shall be truly vertical or horizontal as the case may be and shall be carefully finished. Hounding or chamfering, corners, arises junctions etc. shall be carried out with proper templates to be size required.

2.3.2. Cement plaster shall be used within half an hour after addition of water and mortar or plaster which is partially set shall be rejected and removed forthwith from the site.

- 2.3.3.** In suspending the work at the end of the day, the plaster shall be left out clean to the line both horizontally and vertically, when recommencing the plaster, the edges of the old work shall be scraped clean and wetted with cement putty before plaster is applied to the adjacent areas to enable the two to properly join together. Plastering work shall be closed at the end of the day on the body of the wall and nearer than 15 cm. to any corners or arises. It shall not be closed on the body of features such as plaster bands and cornices not at the corners or arises. Horizontal joints in plaster work shall not also occur on parapet tops and copings as these invariably lead to leakage. No portion of the surface shall be left out initially to be packed up later on.
- 2.3.4.** Each coat shall be kept damp continuously till the next coat is applied or for a minimum period of 7 days. Moistening shall commence as soon as plaster is hardened sufficiently. Soaking of walls shall be avoided and only as much water as can be readily absorbed shall be used, excessive evaporation on the sunny or windward side of building in hot air or dry weather shall be prevented by hanging matting or gunny bags on the outside of the plaster and keeping them wet.
- 2.3.5.** The plastering work shall be in single coat on brick / concrete wall for interior plastering up to floor two level, finished even and smooth in **C.M. 1:3**.
- 2.3.6** The coat of cement and fine sand mortar of proportion 1:1 (1.5 mm thick about) shall be applied to the plastered surface with a trowel to provide uniform texture while the base coat is still plastic.
- 2.3.7.** In any continuous face of wall the finishing treatment should be carried out continuously and day to day breaks made to coincide with architectural breaks in order to avoid unsightly Junctions
- The smooth concrete shall be suitably say read to provide necessary bond before plastering.
- 2.3.8. Curing :** All the plaster work shall be kept damp continuously for a period 7 days.

3.0. Mode of measurements & payment

- 3.1.** The rate shall include the cost of all materials, labour and scaffolding etc. involved in the operations described under workmanship.
- 3.2.** All plastering shall be measured in square meters unless otherwise specified. Length breadth or height shall be measured correct to a centimeter.
- 3.3.** Thickness of the plaster shall be exclusive of the thickness of the key i.e. grooves or open joints in brick work, stone work etc. or space between laths. Thickness of plaster shall be average thickness with minimum **10 mm** at any point on this surface.
- 3.4.** This item includes plastering up to floor two level.
- 3.5.** The measurement of wall plastering shall be taken between the walls or partition (dimensions before plastering being taken) for length and from the top of floor or skirting to ceiling for height. Depth of cover of cornices if any shall be deducted.
- 3.6.** Soffits of stairs shall be measured as plastering on ceilings, following soffits shall be measured separately.

- 3.7.** For jambs, soffits, sills etc. for openings not exceeding 0.5 sq. met each in area for ends of joints beams, posts, girders, steps etc. not exceeding 0.5 sq.mt each in area and for openings exceeding 0.5. sq.mt and not exceeding 3.00 sq.mt. in each area deductions and additions shall be made in the following manners.
- (a) No deductions shall be made for ends of joints, beams, posts etc. and openings not exceeding 0.5 sq.mt each and no addition shall be made for reveals, jambs, soffits, sills etc. of these openings, for finish to plaster around ends of joints, beams posts etc.
- (b) Deduction for openings exceeding 0.5 sq.mt but not exceeding 3 sq.mt. each shall be made as follows and no addition shall be made for ravel, jambs, soffits, sills etc. of these openings, (i) When both faces of all wall are plastered with same plaster, deduction shall be made for one face only, (ii) When two faces of wall are plastered with different types of plasters or if one face is plastered and the other pointed, deductions shall be made from the plaster or pointing on the side of frame for door, window etc. on which width of reveals is less than that on the other side but no deductions shall be made on the other side. Where width of reveals on both faces of all are equal, deductions of 50% of area of opening on each face shall be made from areas of plaster and / or pointing as the case may be.
- 3.8.** For openings having door frames equal to or projecting beyond the thickness of wall, full deduction for opening shall be made from each plastered face of the wall.
- 3.9.** In case of openings of area above 3 sq.mt. each, deduction shall be made for openings but jambs, soffits and sills shall be measured.
- 3.10.** The payment shall be made extra for this work over and above the plaster work
- 3.11.** The rate shall be for a unit or 1 Kg of water proofing materials used in 1 bag of weighing 50 Kg. cement used extra over the rate of plastering work.
- 3.12.** The rate shall be for a unit of **One sq. meter.**

Item No. 18 :- Providing and laying vitrified tiles 8mm to 10 mm thick, 24" x 24" in flooring, treads of steps and landing laid on a bed of 12 mm thick cement mortar 1:3 (1 cement : 3 coarse sand) finishing with flush pointing in white cement.

1.0. Materials

Water shall conform to M-1. Cement mortar shall conform to M-11. **24" x 24" size 8mm to 10mm thick Vitrified flooring tiles** shall conform to relevant Indian standard. The size & colour of vitrified tiles shall be approved by Engineer in charge.

2.0. Workmanship

2.1. Bedding :

2.1.1. The sub grade shall be cleaned, wetted and mopped. The bedding shall then be laid evenly over the surface tamped and corrected to desired level and allowed to harden enough to offer a rigid cushion to tiles and to enable the mason to place wooden planks across and squat on it.

2.1.2. The **vitrified flooring tiles** shall be laid on cement mortar bedding of 12 mm. thick in C.M. 1:3 (1 cement: 3 coarse sand). The mortar shall have sufficient plasticity for laying and there shall be no hard lumps that would interfere with the evenness of bedding. The base shall be cleared and well wetted. The mortar shall then be spread in thickness not less than 12 mm. at any place and average 20 mm thickness. The proportion of the cement mortar shall be as specified in the item.

2.2. Fixing tiles :

2.2.1. The tiles before laying shall be soaked in water for at least two hours. Neat gray cement grout at 33 kg/Cement/Sq.mt. of honey like consistency shall be spread over the mortar bedding as directed. The edges of the tiles shall be smeared with neat cement slurry. The tiles shall be well pressed and gently tapped with a wooden mallet till they are properly bedded and in level with the adjoining tiles. There shall be no hollows in bed or joints. The joints between the tiles shall be as thin as possible in straight line or as per pattern.

2.2.2. The tiles shall not have staggered joints. The joints shall be true to centre line both ways. The Nahni trap coming in the flooring shall be so positioned that its grating shall replace only one tile as far as possible. Where full size tiles cannot be fixed they shall be cut (Swan) to the required size and the edges rubbed smooth to ensure straight and true joints. The joints shall be filled with grey cement grout with wire brush or trowel to a depth of 5 mm. and loose material removed. White cement shall be used for pointing the joints. After fixing the tiles finally in an even plane the flooring shall be kept wet and allowed to nature undisturbed for 7 days. The pattern shall be approved by Engineer in charge.

2.3. Cleaning :

2.3.1. The surplus cement grout that may have come out of the joints shall be cleaned off before it sets. Once the floor has set, it shall be carefully washed, cleared by dilute acid and dried. Proper precautions and measures shall be taken to ensure that the tiles are not damaged in any way till the completion of the .construction.

3.0. Mode of measurements & payment

3.1. The work done shall be measured in sq.mt. for visible area of work done. The length and width of the flooring shall be measured not between the faces of skirting or dedos or plastered face of wall as the case may be. The paving under dedo or skirting shall not be measured. No deduction shall be made not extra paid for any opening in the floor of area upto 0.1 sq.mt. Nothing extra shall be paid for laying the floors at different levels in the same rooms.

3.2. The rate shall be for a unit of **one sq. meter.**

Item No. 19 :- Distempering (two coats) with oil bound distemper of approved brand and manufacture and of required shade on wall surfaces to give an even shade, over and including a priming coat with alkali resistance primer of approved brand and manufacture after thoroughly brushing the surface and other foreign matter and also including preparing the surface even and sand papered smooth including applying two coats of Birla or Asian lappy putty & two coats of primer of approved brand and manufacture on new wall surface to give an even shade including thoroughly brushing the surface free from mortar dropping and other foreign matter and sand papered smooth.

1.0. Materials

1.1. Oil bound washable distemper and primer shall be of approved brand and manufacture. The distemper shall be of required colour and shade and the same shall conform to I.S. : 428-1969. The shade shall be approved by Engineer in charge. Birla or Asian acrylic lappy (putty) and primer shall be of approved brand and manufacture.

2.0. Workmanship

The distempering shall be carried out on wall surfaces to give an even shade.

2.1. Scaffolding

Where scaffolding is required, it shall be erected in such a way that as far as possible no pail of scaffolding shall rest against the surface to be distempered. A properly secured and well tied suspended platform (Joola) may be used for distempering. Where ladders are used, pieces of old gunny bags shall be tied at top and bottom to prevent scratches to the walls and floors. For distempering to ceiling, proper stage scaffolding shall be erected where necessary.

2.2. Preparation of surface :

2.2.1. The undecorated surface to be distempered shall be thoroughly brushed from dust, dirt, grease, mortar dropping and other foreign matter and sand papered smooth. New plaster surface shall be allowed to dry for at least 2 months before applications of distemper.

2.2.2. All unnecessary nails shall be removed. Pitting in plaster shall be made good with plaster again with a fine grade sand paper and made smooth. A coat of distemper shall be applied over the patches. The surface shall be allowed to dry thoroughly before the regular coat of distemper is allowed. The surface affected by moulds, moss, fungi, algae lichens, efflorescence etc. shall be treated in accordance with I.S; 2395 (Part 01) 1966. Before applying distempering, any unevenness shall be made good by applying putty made of plaster of paris mixed with water on entire surface including filling up the undulation and then sand papering the same after it is dry.

2.2.3 The lappy (putty) shall be carried out on wall surfaces to give an even shade.

2.3. Priming coat :

2.3.1. A priming coat of alkali resistance primer of approved manufacture and shade shall be applied over the papered surface in case of new work on undecorated surface. If the alkali resistance priming is done after the wall surface dries completely, the distemper primer shall be applied.

2.3.2. Application of primer shall be done as under: The primer shall be applied with a brush on the clean dry and smooth surface. Horizontal strokes shall be given first and vertical strokes shall be applied immediately afterwards. This entire operation will constitute one coat. The

surface shall be finished as uniformly as possible leaving no brush marks. It shall be allowed to dry for at least 48 hours before oil bound distemper or paint is applied.

- 2.3.3.** Oil bound distemper is not recommended to be applied within six months of the completion of wall plaster.

2.4. Preparation of oil bound distemper :

- 2.4.1.** The distemper shall be diluted with water or any other prescribed thinner in a manner recommended by the manufacturer only. Sufficient quantity of distemper required for a days work shall be prepared.

2.5. Application of Distemper coat:

- 2.5.1.** For undecorated surfaces, after the primer coat is dried for at least 48 hours, the surface shall be lightly sand papered to make it smooth for receiving the distemper, taking care not to rub out priming coat. All loose particles shall be dusted off after rubbing. Minimum two coats of distemper shall be applied with brushes in horizontal strokes followed immediately by vertical strokes which together shall constitute one coat. The subsequent coats shall be applied after a time interval of at least 24 hours between consecutive coats to permit proper drying of the proceeding coat. The finished surface shall be even and uniform without patches, brush marks, distemper drops etc.

- 2.5.2.** Sufficient quantity of distemper shall be mixed to finish one room at a time. The application of a coat in each room shall be finished in one operation and no work shall be started in any room which cannot be completed on the same day.

- 2.5.3.** 15 cm. double bristled distemper brush shall be used. After day's work brushes shall be thoroughly washed in hot water with soap solution and hung down to dry. Old brushes which are dirty and caked with distemper shall not be used on the work.

- 2.6. Protective measurements :** The surfaces of doors, windows, floors, articles of furniture etc. and such other parts of the buildings as are not to be distempered shall be protected from being splashed upon. Such surfaces shall be cleaned of distemper splashes if any.

3.0. Mode of measurements and payment

- 3.1.** Priming coat of alkali resistance primer, scraping of surface spoiled by struck roots, removal of oil and grease spots, treatment for infestation of effloresces., mould moss, fungi, algae and lichen and patch repairs to plaster shall be included in this item for which nothing extra shall be paid.

- 3.2.** All the work shall be measured net in the decimal system as in place subject to the following limits unless otherwise stated hereinafter:

(a) Dimensions shall be measured to the nearest 0.01 m.

(b) Area in individual items shall be worked out to the nearest 0.01 sq. m. All work shall be made for ends of joints, beams, posts etc. and openings, not exceeding 0.5 sq.mt. each and no addition shall be made for reveals, jambs, soffits, sills etc. of these openings not for finish around ends of joints, beams, posts etc.

- 3.3.** Deductions of opening exceeding 0.5 sq.m. but not exceeding 3 sq. m. each shall be made as follows and net addition shall be made for reveals, jambs, soffits etc. of these openings :

(a) When both the faces of wall are provided with same finish, deductions shall be made for one face only.

(b) When each face of wall is provided with different finish, deduction shall be made for that side of frame for doors, windows etc. on which width of reveals is less than that of the other side but no deduction shall be made on the other side. Where the width of reveals on the both the faces of wall are equal, deduction of 50% of area of opening on each face shall be made from area of finish.

(c) When only one face of wall is treated and the other face is not treated, full deductions shall be made if the width of the reveal on treated side is less than that on untreated side but if the width of the reveal is equal or more than that on untreated side neither deductions nor additions to be made for reveals, jambs, soffits, sills etc.

- 3.4.** In case of opening of area exceeding 3 sq. m. each deduction shall be made for openings but jambs, sills and soffits shall be measured.
- 3.5.** No deductions shall be made for attachments such as casings, conduits, pipes, electric wiring and the like.
- 3.6.** Item includes removing nails, making good holes, patches with materials similar in composition of distemper.
- 3.7.** The extra rate shall be paid for carrying out distemping work on ceiling/sloping roofs over and above.
- 3.8.** The rate includes cost of all materials, labours, scaffolding, protective measures etc. involved in all the operations described above. This shall also include conveyance, delivery, handing, unloading, storing work etc.
- 3.9.** The rate shall be for a unit of one sq. meter.

Item No. 20 :- Finishing wall with water proofing cement paint on wall surfaces (three coats) to give an approved brand and manufacture and of required shape even shade after thoroughly brushing the surface to remove all dirt, dust and remains of loose powdered materials.

1.0. Materials

- 1.1.** The water shall conform to M-1. Water proofing cement paint shall conform to I.S. 5410-1969.

2.0. Workmanship

- 2.1. Scaffolding :** Wherever scaffolding is necessary it shall be erected in such a way that as far as possible on part of scaffolding shall rest against the surface to be white or colour washed. A properly secured strong and well tied suspended platform (Zoola) may be used for white washing. Where ladders are used pieces of old gunny bags shall be tied at top and bottom to prevent scratches to the floors and walls. For white washing of ceilings, proper stage scaffolding shall be erected where necessary.

2.2. Preparation of surface :

- 2.2.1.** The surface shall be thoroughly cleaned of all dust, dirt, mortar cropping and other foreign matter before water proofing cement paint is to be applied.
- 2.2.2.** The surface spoiled by smoke soot shall be scrapped with steel wire brushes or steel scrapers shall be rubbed with over-burnt surkhi or brick bats. The surface shall be then broomed to remove all dust dirt and shall be washed with clean water.
- 2.2.3.** Oil or grease spots shall be removed by suitable chemical and smooth surface shall be rubbed with wire Brushes.
- 2.2.4.** All unsound portion of the surface plaster shall be removed to full depth of plaster in rectangular patches and plastered again after raking the masonry joints properly. Such portion shall be wetted and allowed to dry. They shall then be given one coat of water proofing cement paint.
- 2.2.5.** All unnecessary nails shall be removed the holes, cracks, patches etc. shall be made good with material similar in composition to the surface to be prepared.
The surface shall be thoroughly wetted with clean water before cement water proofing paint is applied.
- 2.3. Preparation of paint:** Portland cement paint shall be prepared by adding paint powder to water and stirring to obtain a thick paste, which shall then be diluted to a brush able consistency. Generally, equal volumes of paint powder and water make a satisfactory paint. In all cases the manufacture's instructions shall be followed. The paint shall be mixed in such quantities as can be used up within an hour of mixing as otherwise the mixture will set and thicken, affecting flowing and finish. The lids of cement paint drums shall be kept tightly when not in use.
- 2.4. Application of Paint:**
- 2.4.1.** No painting shall be done when the paint is likely to be exposed to a temperature of below 70 c within 48 hours after application.

- 2.4.2.** When weather conditions are such as to cause be carried out in the shadow as far as possible. This helps the proper hardening of the paint film by keeping the surface moist for a longer period.
- 2.4.3.** To maintain the uniform mixture and to prevent segregation, the paint shall be stirred frequently in the bucket.
- 2.4.4.** For undecorated surfaces, the surface shall be treated with minimum two coats of water proof cement paint. Not less than 24 hours shall be allowed between two coats. Next coat shall not be started until the proceeding coat has become sufficiently hard to resist marking by the brush being used. In hot dry weather, the proceeding coat shall be slightly moistened before applying the subsequent coat.
- 2.4.5.** The finished surface shall be even and uniform in shade, without patches, brush masks, paint drops etc.
- 2.4.6.** The cement paint shall be applied with a brush with relatively short stiff hog or fiber bristles. The paint shall be brushed in uniform thickness and shall be free from excessively heavy brush marks. The lamps shall be brushed out.
- 2.4.7.** Water proof cement paint shall not be applied on surface already treated with white wash, colour wash, distemper dry or oil bound varnishes, paint etc. It shall not be applied on gypsum, wood and metal surfaces.
- 2.5. Curing :** Painted surfaces shall be sprinkled with water two or three times a day. This shall be done between coats and for at least two days following the final coat. The curing shall be started as soon as the point has hardened so as not be damaged by the sprinkling of water say about 12 hours after the application.
- 2.6. Protective measure :**
- The surface of doors, windows, floors, articles, of furniture etc. and such other parts of the building not to be Water proof cement paint shall be protected from being splashed upon. Such surfaces shall be cleaned of Water proof cement paint splashed if any.
- 3.0. Mode of measurements and payment**
- 3.1.** All the work shall be measured in the decimal system as under:
- (a) Dimensions shall be measured to the nearest 0.01 m.
- (b) Area in individual item shall be worked out to the nearest 0.01 sq.m.
- All the work shall be measured in sq.mt. Deductions for jambs, soffits, sills etc. for openings not exceeding 0.5 sq.mt. each in area, for ends of joists, posts, beams, girders, steps etc. not exceeding 0.5 sq.mt. each in area and for openings exceeding 0.5 sq.mt. and not exceeding 3.0. sq.mt. each in area, deductions and additions shall be made as under.
- 3.2.** No deductions shall be made for ends of joists, beams, posts, etc. and openings not exceeding 0.5 sq mt. each. No addition shall be made for reveals, jambs, soffits, sills etc. of these openings not for finish around ends of joints, beams, posts etc.
- 3.3.** No deductions for openings exceeding 0.5 sq.mt. but not exceeding 3 sq.mt. each shall be made as follows and no addition will be made for reveals, jambs, soffits etc. of these openings :

- (a) When both the faces of walls are provided with finish, deduction shall be made for one face only.
 - (b) When each face of wall is provided with different finish, deduction shall be made for that side of frame for door, windows, etc. on which width of reveals is less than that of the other side. Where width of reveals on both faces of wall are equal, deduction of .50% of area of opening on each face shall be made from total area of finish.
 - (c) When only one face of wall is treated and the other face is not treated, full deduction shall be made if the width of reveal on the treated side is less than that on the untreated side, but if the width of the reveal is equal or more than on the untreated side neither deductions nor additions to be made for reveals, jambs, soffits, sills etc.
- 3.4.** In case of area of openings exceeding 3 sq. mt. each, deductions shall be made for openings but jambs, soffits, sills shall be measured.
- 3.5.** No deductions shall be made for attachment such as casing, conducts, pipe, electric wiring and the like.
- 3.6.** Corrugated surfaces shall be measured flat as fixed and not girth. The quantities so measured shall be increased by the following percentage and the resultant shall be included with the general areas:
- (a) Corrugated steel sheets..... 14%
 - (b) Corrugated A.C. sheets..... 20%
 - (c) Semi corrugated A.C. Sheets..... 10%
 - (d) Nainital pattern roof (Plain sheeting sheets)..... 10%
 - (e) Naintial pattern roof (with corrugated sheets)..... 25%
- 3.7.** Cornices and other wall features, when they are not picked out in a different finish/colour shall be girthed and included in the general area.
- 3.8** Extra payment shall be done on ceiling and sloping roofs.
- 3.9.** The rate shall include the cost of ail materials, labour, scaffolding, protective measures etc. involved in all the operations described above.
- 4.0** The rate shall be for a unit of **One sq.** meter.

Item No. 21 :- Providing and laying half brick masonry in common burnt clay building conventional type bricks having crushing strength not less than 35 Kg/Sq.cm. in cement mortar 1:5 (1 cement : 5 coarse sand) in foundation and plinth including the cost of all materials and labour charges etc. complete.

1.0. Materials

Bricks shall conform to M-15. Water shall conform to M-1. Cement shall conform to M-3. Sand shall conform to M-6. Cement mortar shall conform to M-11.

2.0. Workmanship

- 2.1.** Relevant specifications of bricks, wetting and laying of bricks, joints, curing etc shall conform to **Item No. 9** except that the brick work of half brick shall be carried out.
- 2.2.** Cement mortar used in masonry work shall be in proportion of 1 part of cement and 5 parts of coarse sand by volume.
- 2.3.** All bricks shall be laid stretcher wise, breaking joints with those in the upper and lower courses. The wall shall be taken truly plumb. All courses shall be said truly horizontal and all vertical joints shall be truly vertical. The bricks shall be laid with frogs upwards. A set of masons tools shall be maintained on work as required for frequent checking. After every three course 2 nos. of 6mm mild steel bars shall be embedded in cement mortar.

3.0. Mode of measurement and payment

- 3.1.** The half brick masonry work in foundation and plinth shall be measured under this item the limiting dimensions shall not exceed those shown in the plan or as directed. Any work done extra over the specified dimensions shall be ignored.
- 3.2.** The relevant specifications of **Item No. 9** shall be followed. The length shall be measured nearest to one cm.
- 3.3.** The rate includes the cost of providing 2 nos. of 6mm steel bars after every three course.
- 3.4.** The rate shall be for a unit of one sq. meter.

Item No. 22 :- Providing and fixing wash basin with single hole for pillar tap with C.I. or M.S. brackets painted white including cutting holes and making good the same but excluding fittings (A) Vitreous china (ii) flat back wash basin 550 mm x 400mm size.

1.0. Materials

- 1.1. The Vitreous China flat back wash basin shall be 550 mm. x 400mm. of 1st quality and make as approved by the Engineer-in-charge. The wash basin shall conform to M-59.

2.0. Workmanship

- 2.1. The washbasin shall be fixed on the wall as and where directed. The wash basin shall be supported on a pair of M.S. or C.I. brackets fixed in C.M. 1:3 (1 cement : 3 sand). The bracket shall conform to I.S. : 775-1962. The wall plaster on the rear shall be cut to rest the top edge of the washbasin. After fixing the basing, plaster shall be made good and surface finished to match the existing one.
- 2.2. The brackets shall be painted white with ready mixed paint.
- 2.3. The C.P. brass trap and union shall be connected to 32 mm. dia. waste pipe which shall be suitably bent towards the wall and which shall discharge into an open drain leading to a gully trap or direct in to gully trap on the ground floor and shall be connected to a waste pipe through a floor trap on the upper floors. C.P. brass trap and union may not be provided where the surface drain or a floor trap is placed directly under the basin and the waste is discharged in to vertically.
- 2.4. The height of the front edge to the wash basin from the floor level shall be 80 cms.
- 2.5. The necessary inlet, outlet connections and fittings such as pillar cocks, CP dress waste trap waste pipe, stop cock, chain wish rubber plug etc. shall be fixed.
- 2.6. The payment of fittings shall be made separately under separate items.
- 3.0. Mode of measurements & payment**
- 3.1. The rate includes cost of 32mm dia. C.P. brass waste, 32mm dia. M.I. fisher union, 15 mm brass screw down stop cock, 15mm pillar cock with all labour, materials, tools and plant etc. required for satisfactory completion of this item as specified in workmanship.
- 3.2. The rate shall be for a unit of One number.

Item No. 23 :- Providing and fixing water closet squatting pan (Indian type W.C. Pan) size 580mm (Earthwork, bed concrete, foot rest and trap to be measured and paid for separately) vitreous china (i) long pattern in white colour.

1.0. Materials

- 1.1.** Wash down water closet squatting pan (Indian type W.C. Pan) shall conform to M-62. The 100 mm. size 'P' or 'S' trap for water closet shall confirm to M-62. Cement mortar shall conform to M-11.

2.0. Workmanship

- 2.1.** The pan shall be sunk into the floor and embedded in a cushion of average 15 cm. cement concrete 1:5:10 (1 cement : 5 coarse sand : 10 graded stone aggregate or brick aggregate 40 mm. nominal size) or and its bed concrete, the floor should be left 115 mm. below the top level of the pan so as to allow for flooring and its bed concrete. The floor should be suitably stopped so that the waste water is drained into the pan. The 'P' or 'S' trap shall be fixed with pan cast iron pipe with C.M. 1.1. The pan shall be provided with 100 mm. 'P' or 'S' trap as specified in the item with an approximately 50 mm seal. The joints between the pan and the trap shall be made leak-proof with cement mortar 1:1 (1 cement : 1 fine sand) & providing and fixing G.I. inlet connection for flush pipe with W.C. pan vitreous china long pattern white colour.

3.0. Mode of measurements and payment

- 3.1.** The rate shall include the cost of all materials and labours involved in the operations described under workmanship including testing.
- 3.2.** The rate shall be for a unit of One number.
- 3.3.** The 'P' or 'S' trap unit of One number.

Item No. 24 :- Providing and fixing 100mm size P or S trap for water closet squatting pan including jointing the trap with the pan and soil pipe in cement Mortar 1:1 (1-Cement : 1-Fine sand) (A) Vitreous china.

1.0. Materials

- 1.1.** Wash down water closet squatting pan (Indian type W.C. Pan) shall conform to M-62. The 100 mm. size 'P' or 'S' trap for water closet shall confirm to M-62. Cement mortar shall conform to M-11.

2.0. Workmanship

- 2.1.** The pan shall be sunk into the floor and embedded in a cushion of average 15 cm. cement concrete 1:5:10 (1 cement : 5 coarse sand : 10 graded stone aggregate or brick aggregate 40 mm. nominal size) or and its bed concrete, the floor should be left 115 mm. below the top level of the pan so as to allow for flooring and its bed concrete. The floor should be suitably stopped so that the waste water is drained into the pan. The 'P' or 'S' trap shall be fixed with pan cast iron pipe with C.M. 1.1. The pan shall be provided with 100 mm. 'P' or 'S' trap as specified in the item with an approximately 50 mm seal. The joints between the pan and the trap shall be made leak-proof with cement mortar 1:1 (1 cement : 1 fine sand) & providing and fixing G.I. inlet connection for flush pipe with W.C. pan vitreous china long pattern white colour.

3.0. Mode of measurements and payment

- 3.1.** The rate shall include the cost of all materials and labours involved in the operations described under workmanship including testing.
- 3.2.** The rate shall be for a unit of One number.
- 3.3.** The 'P' or 'S' trap unit of One number.

Item No. 25 :- Providing and fixing Kitchen sink with C.I. or M.S. brackets, painted white including cutting holes in walls and making good the same but excluding fittings (C) Vitreous china sink (i) 600mm x 450mm x 150mm size.

1.0. Materials

- 1.1.** Stainless steel kitchen sink of 600mm x 4560 mm x 150mm size shall conform to M-63.

2.0. Workmanship

- 2.1.** The Kitchen sink of Nirali or equivalent approved brand and standard as directed by the Engineer in charge. The kitchen sink shall be supported on a pair of M.S. or C.I. brackets fixed in cement mortar 1:3 (1 cement : 3 coarse sand). The M.S. or C.I. brackets shall conform to I.S. 775-1962. The wall plaster on the rear shall be cut to rest over the top edge of the sink. After fixing the sink, plaster shall be made good and the surface finished to match with the existing one.
- 2.2.** The C.P. brass trap and union shall be connected to 40 mm. nominal bore galvanized mild steel waste pipe which shall be suitably bent towards the wall and which shall discharge into an open drain leading to gully-trap or direct into the gully-trap on the ground on floor and shall be connected to a waste pipe through a floor trap on the upper floors. C.P. brass trap and union may not be provided where surface drain or a floor trap is placed directly under the sink and the waste is discharged to it vertically.
- 3.0. Mode of measurements & payment**
- 3.1.** The rate includes cost of all labour, materials, tools and plant and other equipment required for satisfactory completion of this item as described in workmanship.
- 3.2.** The rate shall be for a unit of One number.

Item No. 26 :- Providing sock pit of 5.00 Cu.M. Volume including excavating and filling brickbats with dry masonry work at top for 45cm. height including covering the top with stone including providing vatas in C.M. 1:3 with finishing, curing etc. complete as directed.

1.0. Materials : Water shall conform to M-1. Cement mortar conform to M-11. Burnt Bricks shall conform to M-15. Rough stone slab 40 x 50 mm. thick shall conform to M-48. Brick bats shall conform to M-14.

2.0. Workmanship

2.1. The excavation for soak pit shall be carried out as per relevant specifications of Item No. except that the size of soak pit such that the clear volume shall remain 5 cum. The diameter and depth shall be as directed.

2.2. The periphery of the sock pit shall be provided with dry masonry wall with burnt bricks in 23 cms. thick. The masonry wall shall be done with best workman like manner in true line and plumb.

2.3. The sock pit shall be filled in with brick bats of burn brick 40 mm. nominal size in 45 cms. height. The work of filling brick-bats shall be done in such a way that no dry masonry shall be damaged during filling of brick bats.

2.4. The top of the soak pit shall be covered with rough kotah stone slab 40 to 50 mm. thickness. The length of the stone shall be in single piece in length.

2.5. The cement mortar 1:3 shall be used to fill up the joints and preparing vata as directed.

2.6. The cement work shall be cured for 4 days.

3.0. Mode of measurements and payment

3.1. The rate includes costs of all labour and material required for satisfactory completion of this item as described above.

3.2 The payment shall be made on number basis.

Item No. 27 :- Constructing brick masonry road gully chamber 500mm x 450mm x 600mm including 500mm x 450mm C.I. horizontal grating with frame complete.

- 1.0. Materials :** Water shall conform to M-1. Cement shall conform to M-3. Sand shall conform to M-6. Brick shall conform to M-15. C.I. Grating of 500 x 450 mm. size of standard make shall be of approved quality. Stone aggregate 40 mm. nominal size shall conform to M-12. Coal tar shall conform to relevant M-5.
- 2.0. Workmanship**
- 2.1.** The chamber shall be of size 500 mm. x 450 mm. x 600mm internal clear dimensions between the masonry wall faces. The height of 450 mm. shall be measured from the top of the bed concrete to the top of the C.I. frame. The size of grating indicate the clear internal dimensions of the C.I. frame of the grating.
- 2.2.** The excavation shall be done to true dimensions and levels.
- 2.3.** The foundation concrete shall consist of 150 Cms x 100 Cms x 15 cms thick C.C. 1:5:10 (1 cement : 5 sand : 10 graded stone aggregate 40 mm. nominal size).
- 2.4.** The wall of the chamber shall be constructed in brick work C.M. 1:5 and 23 cms. thick as per relevant specifications of Item No. 24.44.
- 2.5.** The walls and the bed concrete of chamber shall be plastered inside with 12 mm. thick cement plaster 1 : 3 (1 cement : 3 coarse sand) finished smooth.
- 2.6.** The gully grating cover shall be hinged to frame to facilitate its opening for cleaning and repairs. The frames of the gully grating g shall be fixed on the top of masonry wall of the chamber in 15 cms. thick C.C. 1:2:4 (1 cement : 2 coarse sand : 4 graded stone aggregate 20 mm. nominal size) laid over the full thickness of walls.
- 2.7.** The chamber shall have connection pipe, the length of which in meter between the road gully chamber and the manhole of the drain shall not be less than 1/40 times the nominal diameter of the pipe in MM. i.e. for 150 mm connection pipe the length shall not be cement plaster on the bed concrete.
- 2.8. Painting :** After the completion of the work of exposed surface of the grating of the frame shall be painted with a thick coat of coal tar.
- 3.0. Mode of measurements and payment**
- 3.1.** The cost of connection pipes is not included in the item and shall be paid separately. However, fixing the connection pipes in the walls of gully chamber is included in the rate for gully chambers and nothing extra shall be paid for this separately.
- 3.2.** The rate shall be for a unit of One number.

Item No. 28 :- Constructing a cooking platform 60 cm. width and 70 cm height resting on B.B. Masonry walls 23 cm. thick in C.M.(1:6) with fixing or precast RCC 1:2:4, 8 cm thick slab with marble chips set in C.M. 1:6 (6mm thick terrazzo) with plastering on exposed faces of wall in C.M. 1:4 etc. complete

1.0. Materials

Water shall conform to M-1. Cement shall conform to M-3. Sand shall conform to M-6. Burnt brick shall conform to M-15. Marble Mosaic chips shall conform to M-46. Stone aggregate 20 mm. nominal size shall conform to M-12. (a) M.S. Bars shall conform to M-18.

2.0. Workmanship

- 2.1. The cooking platform of size as directed shall be constructed in 60 cms. width and 70 cms. height. The brick masonry wall, in C.M. 1:6 shall be constructed in 23 cms. thickness up to full depth. The relevant specifications of Item No. 9 shall be followed for masonry work.
- 2.2. The R.C.C. slab of 8 cms. thickness and of adequate design and size shall be precast and the same shall be put up on the B.B. masonry work.
- 2.3. The top and exposed sides of the R.C.C. slab shall be finished with marble mosaic terrazzo 8 mm. thick with required colour pigment. The work of terrazzo shall be carried out as per relevant specifications of item 14.4 (E).
- 2.4. The whole masonry work shall be finished with cement mortar in C.M. 1:4. The relevant specification of Item No. 9 shall be followed.

3.0. Mode of measurements and payments

- 3.1. The work of cooking platform shall be measured for finished work.
- 3.2. The rate includes cost of all labour and materials, etc. required for satisfactory completion of this item as described above.
- 3.3. The rate shall be for a unit of One running meter.

Item No. 29 :- Providing and fixing to wall, ceiling and floor 6.0 KgF/Cm² working pressure polythene pipes of the following outside dia. low density complete with special flange compression type fittings, wall clips etc. including making good the wall ceiling and floor. (A) 20mm dia.

1.0. Materials

1.1. The low density polythene pipe of specified diameter with **6.0 Kg./Sq.cm.** working pressure shall conform to I.S. 3076-1968. The specials and fittings required shall be of best quality.

2.0. Workmanship

2.1. The P.V.C. pipes of specified diameter shall be fixed as directed. Due to thermal expansion of rigid P.V.C. pipes, due allowance shall be made particularly in over ground pipe lines for any change in length of pipe line which may occur during installation or when pipe line which may occur during installation or when pipe line is in service.

2.2. Above ground installation of rigid P.V.C. pipe should be under taken after preparations are observed for their protection against direct sun rays and mechanical damage.

2.3. The rigid P.V.C. pipe lines should not be kept exposed above ground when it passes through public places, railway lines, road side and foot paths.

2.4. P.V.C. pipes shall be supported at the following intervals :

-20 mm. dia 500 mm. -25 mm. dia 750.mm. -32 mm. dia.900 mm.

2.5. Closer support spacing shall be provided if recommended by the manufacture.

2.6. The guide lines indicated by the manufacturer regarding handling, transportation, storing, laying and jointing pf pipes shall be kept in view during execution.

2.7. P.V.C. pipes shall be fixed on wall with wooden plugs and suitable plastic clamps.

2.8. Jointing the pipes :

2.8.1. The pipes and sockets shall be accurately cut. The ends of the pipes and fittings should be absolutely free from dirt and dust. The outside surface of the pipes and the inside of the fittings shall then be roughened with emery paper, and then solvent cement joint. Since solvent cement is aggressive to P.V.C. care must be taken to avoid applying excessive cement to the inside of pipe sockets as any surplus cement cannot be wiped of after jointing. Empty solvent cement tins, brushes, rags, or paper impregnated with cement should not be buried in the trenches. They should be gathered not left scattered about, as they can prove to be a hazard to animals, which may chew them.

2.8.2. If any manufacturer recommends its own methods of jointing the same shall be adopted after necessary approval from the Engineer-in-charge.

2.9. Laying pipes in Trenches :

2.9.1. The pipes shall be laid over uniform relatively soft fine trained soil found to be free of presence of hard object such as large flints, rocky projections, large tree roots etc. The width of the trenches shall be minimum width required for working.

2.9.2. The pipes laid underground shall not be less than one meter from the ground level. The pipe shall be positioned in the trenches so as to avoid any induced stressed due to deflection. Any deviation required shall be obtained by using proper type of rubber ring joints.

3.0. Mode of measurements & payment

- 3.1.** The description of the item shall, unless otherwise stated be held to include where necessary conveyance and delivery, handling, unloading, storing fabrication, hoisting, all labour for finishing to required shape and size, setting, fitting in position straight, cutting and waste return of packing etc.
- 3.2.** The length shall be measured on running meter basis of finished work. The length shall be taken along the centre line of the pipe and fittings. The pipes fixed to wall, ceiling, floors etc shall be measured and paid under this item.
- 3.3.** All the work shall be measured in decimal system as fixed in its place, subject to tolerance given below unless otherwise stated.
(i) Dimension shall be measured to the nearest 0.01 meter. (ii) Area shall be worked out to the nearest 0.01 sq. meter.
- 3.4.** All measurements of cutting shall unless otherwise stated be held to include the consequent waste
- 3.5.** In case of fitting of unequal bore, the targets bore shall be measured for the test.
- 3.6.** Testing of pipe lines fittings, and joints include for providing all plant appliances necessary for obtaining access to the work to be tested and carrying out the tests
- 3.7.** The rate includes P.V.C. pipes with screwed socket joints. to gather with all fittings (such as bends, sockets springs, elbows, test, crosses, short pieces, clamps and plugs, unions etc.) and fixing complete with clamping wall hooks, wooden plug etc. and also curing, screwing and waste and for making forged (or hand made) bends on piping as required. Connector shall be inserted where required or directed. The rate also includes cutting through walls, floors etc. and their making good and painting exposed threads with anti-corrosive paint as above and testing where tubes are to be fixed to wall, ceiling and flooring, the rates shall not include painting of pipes, providing sleeves and sand filling under floor for which separate payment shall be made.
- 3.8.** The unit rate shall be for a unit of One running meter.

Item No. 30 :- Providing and fixing to wall, ceiling and floor 6.0 KgF/Cm² working pressure polythene pipes of the following outside dia. low density complete with special flange compression type fittings, wall clips etc. including making good the wall ceiling and floor. (B) 25mm dia.

The relevant specifications of **Item No. 29** shall be followed for the work of **providing and fixing to wall, ceiling and floor 6.0 KgF/Cm² working pressure polythene pipes of the following outside dia. low density complete with special flange compression type fittings, wall clips etc. including making good the wall ceiling and floor. (B) 25mm dia.**

Item No. 31 :- Providing and fixing to wall, ceiling and floor 6.0 KgF/Cm² working pressure polythene pipes of the following outside dia. low density complete with special flange compression type fittings, wall clips etc. including making good the wall ceiling and floor. (C) 32mm dia.

The relevant specifications of **Item No. 29** shall be followed for the work of **providing and fixing to wall, ceiling and floor 6.0 KgF/Cm² working pressure polythene pipes of the following outside dia. low density complete with special flange compression type fittings, wall clips etc. including making good the wall ceiling and floor. (C) 32mm dia.**

Item No. 32 :- Providing and fixing cast iron (Spun) Nahni trap of the following nominal diameter of self cleaning design with C.I. screwed down or hinged grating including cost of cutting and making goods the walls and floor 100 mm inlet and 50 mm outlet etc. complete.

1.0. Materials

- 1.1.** The **cast iron** (spun) Nahni trap shall conform to M-69. The C.I. hinged or screwed down cover shall be of best quality and approved by Engineer in charge.

2.0. Workmanship

- 2.1.** The Nahni trap with 100 mm. dia inlet and 50 mm. dia. outlet shall be fixed as per drawing or as directed.
- 2.2.** The Nahni trap shall be jointed with C.I. Pipe, 75 mm. dia. with lead joints. The lead joints shall be done in conformation with I.S. 782-1976.

3.0. Mode of measurements and payment

- 3.1.** The rate includes cost of all labour, materials, tools and plants etc. required for satisfactory completion of this item including lead, jointing and testing.
- 3.2.** The rate shall be for a unit of one number.

Item No. 33 :- Providing and fixing screw down bib taps of following size. (A) Brass screw down bib tap polished bright. (i) 15mm dia.

General

This work shall consist of providing and fixing screw down bib taps of the shape and dimensions shown on the drawings and conforming to these Specifications or as approved by the Engineer in charge.

1.0 MATERIAL

1.0 Bib Cock

1.1. Bib cock of specified 15 mm diameter nominal bore shall conform to I.S. 781-1977. The Bib Cock shall be best Indian make and quality.

1.2 Bib cock shall be brass polished bright of best quality.

1.3 A Bib cock is a draw off tap with a horizontal inlet and free outlet. A stop cock is a valve with a suitable means of connection of insertion in a pipe line for controlling or stopping the flow.

1.4 They shall be screw down type and or brass polished bright and of diameter as specified in the description of the item. They shall conform to I.S 781-1977 and they shall be of best Indian make. They shall be polished bright.

1.5 The minimum finished weight of bib cock and stop cock shall be as given below

Diameter	Bib cock	Stop Cock	Diameter	Bib cock	Stop cock
8 mm	0.25 kg.	0.25 kg.	15 mm	0.40 kg.	0.40 kg.
10 mm	0.30 kg.	0.35 kg.	20 mm	0.75 kg.	0.75 kg.

1.6. The Necessary galvanized fittings like Nipple, Casing etc, of best quality and makes as approved by the Engineer-in-charge required for specified dia. bore Bib cock shall be used for fitting Bib cock as necessary.

2.0. WORKMANSHIP

Curing, Laying & Jointing

2.1. When the Bib cock is to be fitted, the ends shall be carefully filed out so that no obstruction to bore in offered. The Bib cock shall be fitted with pipes carefully in such a manner as will not result in slackness of joints when the two pieces are screwed together.

2.2 In jointing the Bib cock the inside of the socket and the screwed end of the Bib cock shall be oiled and smeared with the white or red lead and wrapping around with a few turns of fine spun yarn round the screwed end of the Bib cock. The end shall then be tightly screwed in the socket, Tees etc with a pipe wrench Care shall be taken that all items are free from dust, dirt and rust during fixing Burr from the joints shall be removed after screwing After laying the open ends of the Bib cock shall be temporarily plugged to prevent excess of water soil or any other foreign matter.

2.3. Any threads exposed after jointing shall be painted or in the case of underground piping thickly coated with approved anti corrosive paint to prevent corrosion

TESTING OF JOINTS

After fitting, the Bib cocks shall be inspected under working conditions of pressure and flow. Any joints found liken shall be redone, and all leaking Bib cocks shall be removed and replaced without extra cost.

The Bib cocks after they are fitted shall be tested to hydraulic pressure of 6 kg / sq. cm. The Bib cock shall be slowly and carefully charged with water allowing all air to escape and avoiding all shock and water hammer. The draw off takes and stop cock shall then be closed and specified hydraulic pressure shall be applied gradually. The Bib cocks shall be tested in sections as the work laying proceeds, veeping the joints exposed for inspection during the testing.

3.0 MODE OF MEASUREMENT & PAYMENT :

3.1. The unit rate of bib cock shall include the cost of all materials, tools and plant required for fitting, the same to specified position as per drawings, and as directed by Engineer in charge finishing structure, etc. and all other incidental expenses for producing Bib cock work to complete the structure or its components as shown on the drawings, and as directed by Engineer in charge and according to these specifications. They shall also include the cost of making, fixing and removing of all scaffolding and forms required for the work.

The rate of bib cocks shall include the cost of all labour, materials, G. I. fittings as required, tools and plant scaffolding and all incidental expenses as described herein above including testing.

3.2. The bib cock shall be measured for its Number, limiting dimensions to those specified on plan or as directed. The rate shall be for a unit of one Number.

3.3. The payment will be made on number basis of the finished work.

Item No. 34 :- Providing and fixing gun metal check or non return fullway wheel valve (i) 15mm dia.

1.0. Materials :

The gun metal check or not return full way wheel valve or specified dia. shall conform to I.S. : 778-1964. The non-return valve shall be of tested quality and approved by Engineer in charge.

2.0. Workmanship

2.1. The gun metal check or non return valve shall be fully cleared of all foreign matter before fixing. The fixing of shall be done by means of bolts nuts and 3 mm. rubber insertions with flags of spigot and socketed tail pieces, drilled to the same specifications as in case of socket and spigot flanges in case of flanged pipes. The joining shall be done leak proof. All necessary testing should be carried out.

3.0. Mode of measurements and payment

3.1. The rate includes all labours, materials, tools and plant etc. required for satisfactory completion of this item.

3.2. The rate shall be for a unit of **One number**.

Item No. 35 :- Providing and fixing PVC Water tank ISI mark Sintex or equivalent as directed.

General

This work shall consist of furnishing and placing providing and fixing I.S.I. mark PVC water tank with necessary G.I. fittings of the shape and dimensions shown on the drawings and conforming to these specifications or as approved by the Engineer in charge.

1.0 MATERIAL

1.1 PVC WATER TANK

PVC Water tank of specified capacity and of I.S.I. mark of approved in liters of approved make and quality equivalent to syntax product.

Net capacity shall be net volume of water stored between the lowest level of overflow and lowest specified level.

1.2 NIPPLE

Galvanize pipe nipple shall be of approved make and of best quality. Relevant specification given in Booklet of Building specification shall be applied for the execution of this item.

1.3 BALL VALVE

Ball valve shall be of approved make and of best quality. Relevant specification given in Booklet of Building specification shall be applied for the execution of this item.

1.4 CONNECTIONS

Connection shall be of approved make and of best quality. Relevant specification given in Booklet of Building specification shall be applied for the execution of this item.

2.0 **WORKMANSHIP**

- 2.1 Tank shall be approved quality and as per IS standard make. Material used in manufacturing tank shall be confirmed to relevant IS code. The material of tank and lead and fittings which may come in contact of water should be such that it does not impart any taste, colour or odour. It does not have any toxic effect and it does not contaminate the water. Thereby making it unpotable.
- 2.2 The tank shall be fixed properly in a level position and making all required necessary correction like inlet outlet flushing overflow and air vent. Tank shall be satisfying the standards of public health.

3.0 **MODE OF MEASUREMENT AND PAYMENT**

- 3.1 The unit rate of **PVC Water tank** shall include the cost of all materials, tools and plant required for lifting to required height with all lead and lift, placing and fixing in position, all required specials and jointing adhesive compound, finishing as per direction of the Engineer-in-charge, and all other incidental expenses for producing **PVC water tank** work of specified diameter to complete the structure or its components as shown on the drawings and according to these specifications, they shall also include the cost of making, fixing and removing of all scaffolding and forms required for the work.

The rate of PVC Water tank shall include the cost of all labour, materials, tools and plant scaffolding and all incidental expenses as described herein above.

- 3.2 The **PVC water tank** work shall be measured for its volume to specified capacity to those specified on plan or as directed. The rate shall be for a unit of one liter basis.
- 3.3 The payment will be made on **liter** basis of the finished work.

Item No. 36 :- Providing and laying (to level or slopes) and jointing with stiff mixture of cement mortar in proportion 1:1, salt glazed stoneware pipes including testing of pipes and joints complete including providing and laying cement concrete 1:5:10 (1 cement : 5 fine sand : 10 graded stone aggregate 40mm nominal size) bedding for stoneware pipes of following internal diameters with necessary formwork and curing complete (B) 150mm dia. (166mm avg. bed thickness).

1.0. Materials

(1) Water shall conform to M-1 (2) Cement mortar of proportion 1:1 shall conform to M-11. (3) 150 mm. dia. glazed stoneware pipe shall conform to M-71. (4) Cement shall conform to M-3. (5) Sand shall conform to M-6 (6) Stone aggregate 40 mm nominal size shall conform to M-12.

2.0. Workmanship

2.1. General

2.1.1. Before laying the pipes in bed of foundation trenches shall be cleared of all loose materials, leveled, watered and rammed as directed

2.2. Laying :

2.2.1. The pipes shall be laid accurately and perfectly true to line, levels and gradients, Great care shall be taken to prevent sand etc. from entering the pipes. The pipes between two manholes shall be laid truly in a straight line without vertical or horizontal undulation. All junctions and changes in direction and diameter shall be made inside manholes by means of curved tapered channels formed in Cement concrete finished smooth and benched on both sides. The body of the pipe shall rest for its entire length, on a even level bed grips being made or left on the bed to receive the sockets of the pipes.

2.3. Jointing:

2.3.1. Tarred gask in or yarn soaked in neat cement slurry shall first be placed around the spigot to each pipe and the spigot shall then be placed well home into the socket of the pipe previously laid. The pipe shall then be adjusted and fixed in the correct position and gaskin caulked home so as to fill not more than 1/4th of the total depth or (13 mm. in depth) of the socket.

2.3.2. The remainder of the sockets shall be filled with stiff mixture of cement mortar in proportion of one part of cement and one part of sharp sand. When the socket is fillet, a filled shall be formed round the joints with a trowel, forming an angle of 45° with the barrel of the pipe.

2.3.3. The mortar shall be mixed as necessary for immediate use.

2.3.4. After the joint is made, any extraneous materials shall be removed from the inside of the joints with a suitable scraper or "badger". The newly made joints shall be protected, until

set, from the sun, dry winds, rain or frost, sacking or other suitable materials which shall be used for the purpose.

2.3.5. The mortar shall be cured for 10 days.

2.4. Testing of Joints:

2.4.1. If any leakage is visible the defective part of the work shall be made good at no extra cost. The pipe line shall be tested as directed.

2.4.2. A slight amount of sweating which is uniform may be overlooked, but excessive sweating from a particular pipe or joints shall be watched for and taken as indicating a defect to be made good.

The width of concrete shall be 300 mm. and average thickness of bedding shall be 166 mm. The concrete shall be brought up at least to the invert level of the pipe to form a cradle and to avoid line contact between the pipe and the bed.

3.0. Mode of measurements and payment

3.1. Pounding or buttering of the fit trenches bed to the lower part of the pipe and "Grips" dug to take socket, collars etc. are included in the rate of laying the pipes.

3.2. The measurements shall be net without any allowance for cutting, and waste. The length of bends, junctions, and other connections shall be included in the total length of the drain pipes. Nothing extra shall be paid for the same. The rate includes necessary excavation refilling trenches etc. complete,

3.3. The rate shall be for a unit of One running meter.

Item No. 37 :- Providing and fixing on wall face PVC rain water pipe 110mm dia. & 4 kg/sqm. is used including fitting the joints with approved brand.

1.0. Materials

- 1.1. The low density PVC Rain water pipe of specified diameter with **4 Kg/Sq.cm.** shall conform to I.S. 3076-1968. The specials and fittings required shall be of best quality.

2.0. Workmanship

- 2.1. The P.V.C. Rain water pipes of specified diameter shall be fixed and laid as directed by Engineer in charge. Due to thermal expansion of rigid P.V.C. Rain water pipes, due allowance shall be made particularly in over ground pipe lines for any change in length of pipe line which may occur during installation or when pipe line which may occur during installation or when pipe line is in service.
- 2.2. Above ground installation of rigid P.V.C. Rain water pipe should be under taken after preparations are observed for their protection against direct sun rays and mechanical damage.
- 2.3. The rigid P.V.C. Rain water pipe lines should not be kept exposed above ground when it passes through public places, railway lines, road side and foot paths.
- 2.4. P.V.C. Rain water pipes shall be supported at the intervals as directed.
- 2.5. Closer support spacing shall be provided if recommended by the manufacture.
- 2.6. The guide lines indicated by the manufacturer regarding handling, transportation, storing, laying and jointing pf pipes shall be kept in view during execution.
- 2.7. P.V.C. Rain water pipes shall be fixed on wall with wooden plugs and suitable plastic clamps.

2.8. Jointing the pipes :

- 2.8.1. The pipes and sockets shall be accurately cut. The ends of the pipes and fittings should be absolutely free from dirt and dust. The outside surface of the pipes and the inside of the fittings shall then be roughened with emery paper, and then solvent cement joint. Since solvent cement is aggressive to P V.C. care must be taken to avoid applying excessive cement to the inside of pipe sockets as any surplus cement cannot be wiped of after jointing. Empty solvent cement tins, brushes, rags, or paper impregnated with cement should not be buried in the trenches. They should be gathered not left scattered about, as-they can prove to be a hazard to animals, which may chew them.
- 2.8.2. If any manufacturer recommends its own methods of jointing the same shall be adopted after necessary approval from the Engineer-in-charge.
- 2.8.3 All necessary testing should be carried out.

3.0. Mode of measurements & payment

- 3.1. The description of tem shall unless otherwise stated be held to include where necessary. conveyance and delivery, handling, unloading, storing fabrication, hoisting, all labour for finishing to required shape and size, setting, fitting in position straight, cutting and waste return of packing etc.

- 3.2.** The length shall be measured on running meter basis of finished work. The length shall be taken along the centre line of the pipe and fittings. The pipes fixed to wall, ceiling, floors etc shall be measured and paid under this item.
- 3.3.** All the work shall be measured in decimal system as fixed in its place, subject to tolerance given below unless otherwise stated.
(i) Dimension shall be measured to the nearest 0.01 meter. (ii) Area shall be worked out to the nearest 0.01 sq. meter.
- 3.4.** All measurements of cutting shall unless otherwise stated be held to include the consequent waste
- 3.5.** In case of fitting of unequal bore, the target bore shall be measured for the test.
- 3.6.** Testing of pipe lines fittings, and joints include for providing all plant appliances necessary for obtaining access to the work to be tested and carrying out the tests
- 3.7.** The rate includes PVC Rain water pipe with screwed socket joints. to gather with all fittings (such as bends, sockets springs, elbows, tees, crosses, short pieces, clamps and plugs, unions etc.) and fixing complete with clamping wall hooks, wooden plug etc. and also curing, screwing and waste and for making forged (or hand made) bends on piping as required. Connector shall be inserted where required or directed. The rate also includes cutting through walls, floors etc. and their making good and painting exposed threads with anti-corrosive paint as above and testing where tubes are to be fixed to wall ceiling and flooring, the rates shall not include painting of pipes, providing sleeves and sand filling under floor for which separate payment shall be made.
- 3.8.** The unit rate shall be for a unit of One running meter.

Item No. 38 :- Providing and laying white glazed tiles 6mm thick in flooring treads of steps and landing laid on a bed of 12mm thick cement mortar 1:3 (1-cement : 3-coarse sand) finishing with flush pointing in white cement.

1.0. Materials

Water shall conform to M-1 Cement mortar shall conform to M-11. **White glazed tiles 6 mm thick** (Kajeria, Asian, Bell ceramic, Somani or equivalent standard quality) shall conform to M-55

2.0. Workmanship

2.1. Bedding :

2.1.1. The sub grade shall be cleaned, wetted and mopped. The bedding shall then be laid evenly over the surface tamped and corrected to desired level and allowed to harden enough to offer a rigid cushion to tiles and to enable the monsoon to place wooden planks across and squat on it.

2.1.2. The **white** glazed tiles shall be laid on cement mortar bedding of 12 mm. thick in C.M. 1:3. The mortar shall have sufficient plasticity for laying and there shall be no hard lumps that would interfere with the evenness of bedding. The base shall be cleared and well wetted. The mortar shall be spread in thickness not less than 12 mm. at any place and average 12 mm. thickness. The proportion of the cement mortar shall be as specified in the item.

2.2. Fixing tiles :

2.2.1. The tiles before laying shall be soaked in water for at least two hours. Neat gray cement grout at 33 kg/Cement/Sq.mt. of honey like consistency shall be spread over the mortar bedding as directed. The edges of the tiles shall be smeared with neat cement slurry. The tiles shall be well pressed and gently tapped with a wooden mallet till they are properly bedded and in level with the adjoining tiles. There shall be no hollows in bed or joints. The joints between the tiles shall be as thin as possible in straight line or as per pattern.

2.2.2. The tiles shall not have staggered joints. The joints shall be true to centre line both ways. The Nahni trap coming in the flooring shall be so positioned that its grating shall replace only one tile as far as possible. Where full size tiles cannot be fixed they shall be cut (Swan) to the required size and the edges rubbed smooth to ensure straight and true joints. The joints shall be filled with grey cement grout with wire brush or trowel to a depth of 5 mm. and loose material removed. White cement shall be used for pointing the joints. After fixing the tiles finally in an even plane the flooring shall be kept wet and allowed to nature undisturbed for 7 days.

2.3. Cleaning :

2.3.1. The surplus cement grout that may have come out of the joints shall be cleaned off before it sets. Once the floor has set, it shall be carefully washed, cleared by dilute acid and dried. Proper precautions and measures shall be taken to ensure that the tiles are not damaged in any way till the completion of the construction.

3.0. Mode of measurements & payment

3.1. The work done shall be measured in sq.mt. for visible area of work done. The length and width of the flooring shall be measured not between the faces of skirting or dados or plastered face of wall as the case may be. The paving under dado or skirting shall not be measured. No deduction shall be made not extra paid for any opening in the floor of area up to 0.1 sq.mt. Nothing extra shall be paid for laying the floors at different levels in the same rooms.

3.2. The payment will be made on square meter basis of the finished work.

Item No. 39 :- Providing and fixing 25mm thick shutters for cupboards etc. including anodized aluminium butt hinges with necessary screws (A) Indian teak wood (i) Fully panelled.

1.0. Materials

1. Wood for shutter shall conform to M-29.
2. Glass shall conform to M-38.
3. Stainless steel fixtures and fastenings shall conform to M-43.

2.0. Workmanship

- 2.1.** The item covers the requirement of frames for doors, windows, clearstory windows, their supply and fixing.

2.2. Frames:

- 2.2.1.** All members of frames shall be exactly at right angles. The right angle shall be checked from inside surfaces of the-frames of the respective members.
- 2.2.2.** All members of frames shall be straight without any warp of bow and shall have smooth surfaces well planed on the three sides exposed at right angles to each other. The surfaces touching the wall may not be planed unless it is required in order to straighten up the member or to obtain the overall sizes within the tolerances as specified.
- 2.2.3.** Frame shall have dovetail joints. When clerestory windows in included, it shall be provided by having full length one piece post for door or windows and clerestory window extending the frame on top at the head to the required extent. Horns shall not be provided in the head of the frame. When no sills are provided, the vertical posts of the frame in the ground floor shall be embedded in the sill masonry for 10 cm. on upper floors, the vertical posts shall be fixed in the floor or masonry by forming notches 10 mm. deep. Slight adjustment of spacing as necessary shall be done to have the hold fasts in the joints of masonry; course. The frame shall be erected in position and held plumb with strong support form north sides and built in masonry as it is being built. The transom shall be through tenoned into the mortises of the jamb post to the full width of the jamb post and the thickness of the tenon shall be not less than 15 mm.
- 2.3. Tolerance:**
- Unless specially mentioned otherwise tolerance of +1.5 mm shall be allowed for each wrought face.
- 2.4.** The tenons shall be closely fitting into the mortises and suitably pinned with wood dowels not less than 10 mm. dia. meter. The depth of rebates for housing the shutter shall be as shown in the detailed drawing or as directed.
- 2.5.** The concrete surface of tenon and mortise shall be treated before putting together with an adhesive of approved make.
- 2.6.** Minimum number of three hold-fasts shall be fixed on each side of door and windows frames, one at the center point and the other two at 30 mm. from the top and bottom of the frames. In case of windows and ventilators frames. The size of each hold-fast shall be 300 x 25 x 6 mm. and of mild steel with split end. The hold fasts shall be fixed with screws to frames.

2.7. Mild steel hold fasts shall be protected with a coating of coal asphalt tar. The surface of frame abutting the masonry or concrete faces shall be properly treated by applying a coat of approved coating.

3.0. Shutters:

3.1. Paneled shutters shall be constructed in the form of timber frame work of styles and rails with panel inserted of type as specified in the detailed drawings. Panel shall be fixed by providing grooves in the style and rails. The styles and rails shall be joined to each other by mortise and tenon joints at right angles.

3.2. All members of the shutters shall be straight without any warp or bow and shall have smooth, well planed faces at right angles to each other.

3.3. The size of styles and rails shall be as per drawings or as directed. Styles and rails of shutters shall be made of one piece only.

4.0. Timber paneling:

4.1. Thickness of the panel shall be as specified in the item as shown in the drawing or as directed. If the panel is made from more than one piece the pieces shall be finished as shown in the detailed drawings and shall be joined with continuous groove with specified size. The end pieces of the panel and the top and bottom of the panel shall be provided with continuous tongue to frame into groove of the frame shutter. An air space of 1.5 mm. shall be left in the groove of frame of shutter while framing the panels in it.

4.2. The faces of the panel as well as various pieces of the panel shall be closely fitted to the sizes of the grooves.

4.3. Finishing of the corners of raised panel edges shall be done as shown in drawings or as directed.

4.4. The thickness specified shall be finished thickness and no tolerance will be permitted.

5.0 Fixtures and Fastenings:

5.1. The rate shall include anodized butt hinges including fixing with iron screws. The size and number of hinges shall be as per table given in annexure-1.

6.1. **Preparation of surfaces :** The surfaces painting shall be cleaned of all rust, scale, dirt and other foreign matter sticking to it with wire brushes, steel wool, scrapers, sand paper etc. This surface shall then be wiped finally with mineral turpentine which shall also remove grease and perspiration of hand marks. The surface shall then be allowed to dry.

6.2. Application of primer :

6.2.1. After the preparation of the surface, the priming coat shall be applied immediately. The brushing operations are to be adjusted to the spreading capacity advised by the manufacturer of the particular primer. The paint shall be applied evenly and smoothly by means of crossing and laying off. The crossing and laying off consists of covering the area over with paint, brushing alternately in opposite directions, two or three times and then finally brushing lightly in a direction at right angles to the same. In this process, no brush marks shall be left after the laying off is finished. The full process of crossing and laying off will constitute one coat.

- 6.2.2.** During painting, every time, after the priming coat has been worked out of the brush bristles or after the brush has been unloaded, the bristles of the brush shall be opened up by striking the brush against portion of the unpainted surface with the end of the bristles, held at right angles to the surface, so that bristles thereafter will collect the correct amount of paint when dipped again into a paint container. The prima/y coat shall be allowed to dry completely before painting is started.
- 6.2.3.** No hair marks from the brush or clogging at pain puddles in the corner of panels angles of molding etc. shall be left on the work
- 6.2.4.** Special care shall be taken while painting over bolts, nuts, rivets, overlaps etc.
- 6.2.5.** The container when not in use shall be kept close and free from air so that paint does not thickness and also shall be kept guarded from dust.

7.0. Mode of measurements & payment

- 7.1.** The new wood and other wood surface shall be measured under this item.
- 7.2.** All the work shall be measured net in the decimal system, as executed subject to the following limits unless otherwise stated hereinafter.
- (a) Dimensions shall be measured to the nearest 0.01 meter.
- (b) Areas shall be worked out to the nearest 0.01 sq. meter.
- 7.3.** No deductions shall be made for openings not exceeding 0.5 sq. mt. each and no addition shall be made for painting to beddings, moldings, edges, jambs, soffits, sills etc. of such opening.
- 7.4.** In case of fabricated structural steel and iron work, priming coat of paint shall be included with frabation. In case of trusses if measured in sq. m. compound girders, stanchions, lattices, grader and similar work, actual area shall be measured in sq. m. and no extra shall be paid for painting on bolts heads, nuts, washers etc. No addition shall be made to be weight calculated for the purpose of measurements of steel and iron works for paint applied on shop or at site.
- 7.5.** The different surfaces shall be grouped into one general item, areas of uneven surfaces being converted into equivalent plain areas in accordance with the table given as per Annexure-II for payment.
- The both side laminated partial board shall be of good quality and approved make. It shall be of specified thickness.
- The teak wood molding strips of good quality and approved make of specified sizes shall be used.
- The rate includes the cost of labour, materials, equipment etc. required for satisfactory completion of the Item with all lead & lift.
- The Rate shall be for a unit of one Sq. meter including cost of all materials, labour charges etc. complete.

Item No. 40 :- Providing and fixing chromium plated brass half turn flush cock of approved quality including fixing in pipe line etc. complete (ii) 25mm dia.

1.0. Materials : Chromium plated brass half turn flush cock shall conform to M-67.

2.0. Workmanship

The half turn flush cock of specified diameter shall be fixed as directed. The flush cock shall be fixed in G.I. pipe line with necessary fittings. The joints shall be made leak proof by using spun yarn and white Zink.

2.1 All pipes and fittings shall be fixed truly vertical and horizontal unless unavoidable. The pipes shall be fixed to walls with standard pattern clamps of required size and shape, one end of which shall be properly plugged or cemented into walls with cement mortar 1:3 (1 cement : 3 coarse sand) and the other tightened round the pipes to hold it securely. These clamps shall be spaced at regular intervals in straight lengths at 2 MC/C interval in horizontal run and 2.5 m. interval in vertical run. For pipe of 15 mm. dia. up to 25 mm. dia. the holes in the walls and floors shall be made by drilling with chisel or jumper and not by dismantling the brick work or concrete. However for bigger diameter pipes the holes shall be carefully made cement : 3 coarse sand), and properly finished to match the adjacent surface.

2.2. Testing of joints :

2.2.1. After laying and jointing, the pipes and fittings shall be inspected under working conditions of pressure and flow. Any joints found leaky shall be redone, and all leaking pipes removed and replaced without extra cost.

2.3.2. The pipes and fittings after they are laid shall be tested to hydraulic pressure of 6 Kg./Sq cm. The pipe shall be slowly and carefully charged with water allowing all air to escape and avoiding all shocks and water hammer. The draw off takes and stop cock shall then be closed and specified hydraulic pressure shall be applied gradually. The pressure gauge must be accurate. The pipes and fittings shall be tested in sections as the work laying proceeds, keeping the joints exposed for inspection during the testing.

3.0. Mode of measurements and payment

3.1. The rate includes cost of all materials and labour required for satisfactory completion of this item including fittings and testing.

3.2. The rate shall be for a unit of One number.

Item No. 41 :- Providing and fixing 100mm dia. PVC spigot and socket soil waste and ventilating pipe including fitting joints in lead or rubber base water proofing solution and fixing with clamps as directed etc. making the walls good etc. as directed.

1.0. Materials

1.1. The specified dia. C.I. Spigot and socket soil or waste pipe shall conform M-68.

2.0. Workmanship

2.1. Asbestos cement rain water pipes and fittings shall be of the diameter, size and type specified in the item. The pipe shall be full lengths of 2 meter as far as possible. All the pipes shall be fixed on wall face at locations indicated on drawings or as ordered by the Engineer-in-charge. Pipe shall be secured to face of wall below all joints by M.S. clamps with wooden gut ties.

2.2. The spigot of the upper pipe shall be properly fitted into the socket of the lower pipe such that there is uniform annular space for fitting with the jointing materials. One third depth of annular space between the item. The pipe shall be full lengths of 2 meter as far as possible. All the pipes shall be fixed on wall face at locations indicated on drawings or as ordered by the Engineer-in-charge. Pipe shall be secured to face of wall below all joints by M.S. clamps with wooden gut ties.

2.2. The spigot of the upper pipe shall be properly fitted into the socket of the lower pipe such that there is uniform annular space for fitting with the jointing materials. One third depth of annular space between the socket and the spigot shall be filled with spun-yarn soaked in bitumatic jointing compound and shall be pressed home by means of caulking tool. The remaining 2/3 depth of the joints shall be filled in with stiff cement mortar 1:2 and shall be pressed with caulking tool and finished smooth at top at an angle of 45 sloping up.

2.3 The joints shall be filled with cement mortar 1:2 (1 cement : 2 sand) span spun yarn. The joints shall be filled with cement mortar 1.2 (1 cement : 2 sand) and spurn yarn. The pipes without care shall be fixed to wall with M.S. clamps The pipes will earns shall be secured with 40 mm before steel or iron barrel distance pieces or boils and stout galvanised iron nails 10 cms long into hand wool plug fixed in walls. Access doors to fittings shall be provided with 3 mm. rubber insertion packing and secured without screws to made air and water tight

2.4. All soil pipes shall be earned up above the roof and shall have a wire ball on guarded or a cowl.

2.5. The ventilating pipe or shaft shall be carried out to a height of at least one meter above the outer covering of the roof of the building or in the case of windows in a gable wall or a dormer windows, it shall carried up to a ridge of the roof or at least tow meters above the top of the windows. In case of flat roof to which access for use is provided, it shall be

carried out up to a height of at least one meter above the parapet or two meters measured vertically from the top of any windows or opening which any exist up to a horizontal distance of five meters from the vent pipe into such building and in no case shall be carried out to a height less than three meters.

- 2.6.** Where ventilating pipes are carried in pipe shafts, the shaft shall be of a minimum size of one meter. If the shafts are also used to give light and air to rooms, the ventilating pipes must be carried out to a horizontal distance at roof level not less than five meters from the site of the shaft.
- 2.7.** The sand cast iron pipes above parapet shall be fixed with M.S. clamps and stays. The clamps shall be made from 1.5 mm. thick MS flat or 3 mm. width band to the required shape and size to fit tightly on the sockets when tightened with screw bolts. It shall be formed of two semi circular pieces with flanged ends on both sides, with holes to fit in the screw bolts and nuts 40 mm. dia. M.S. Bars, One end of the stay shall be bent to form a hook to be fixed with clamps by means of bolts and the other end shall be bent for embedding in wall in cement concrete block of size 200 mm. x 100 mm. x 100 mm. in 1:2:4 mix. The concrete shall be finished to match the surrounding surfaces.
- 2.8.** The connection between the main pipe and branch pipes shall be made by using branches and bends with access doors for cleaning
- 2.9.** The waste from lavatories, kitchens basins, sinks, baths and other floor traps shall be separately connected to respective stacks of upper floor. The waste stack of lavatories shall be connected directly to main hole while the waste stack of other shall be separately discharged over gulley trap.
- 3.0. Mode of measurements and payment**
- 3.1.** The length of pipe shall be measured including all fittings along its length in running meters correct to a centimeter. No allowance shall be made for the portion of pipe length entered in the sockets of the adjacent pipe or fittings.
- 3.2.** The rate includes all labour, and materials, tools and plant etc. required for satisfactory completion of this item.
- 3.3.** The rate shall be for a unit of One running meter.

Item No. 42 :- Providing and fixing in position PVC cowl vent of 100mm dia. pipes.

General

This work shall consist of providing and fixing in position **C.I. cowl vent** of the shape and dimensions shown on the drawings and conforming to these Specifications or as approved by the Engineer in charge.

Material

1.0. Cowl vent

- 1.1. Cowl vent shall be sound and free from porosity or other defects which affect serviceability. The thickness of the base metal shall not be less than 6.5 mm. The surface shall be smooth and free from craze, chips and other flaws or any other kind of defects which affect serviceability. The size of Cowl vent shall be specified.
- 1.2. Cowl vent shall be of quality approved by the Engineer-in-charge and shall generally conform to the relevant Indian Standards.
- 1.3. The cover shall be perforated cover shall be provided on the trap of appropriate size.

2.0 MODE OF MEASUREMENTS & PAYMENT

- 2.1. The rate for cowl vent includes cost of vent, its carting from to work site with all leads and lifts placing and fixing in position.
- 2.2. The rate shall be for a unit of One **Number**.

Item No. 43 :- Providing and fixing 600 mm x 450 mm bevelled edge mirror of superior glass mounted on 6 mm thick A.C. sheet or plywood sheet and fixed to wooden plugs with C.P. brass screws and washers.

1.0. Materials

1.1. The 600 mm. x 450 mm. size mirror shall be of superior glass with edge rounded offer beveled as specified. It shall be free from flaws specks, or bubbles and its thickness shall not be less than 6 mm. The glass for the mirror shall be uniformly silver plated at the back and shall be free from silvering defects Silvering shall have a protective uniform covering of red lead paint. The 6 mm thick ply wood shall conform to M-37. The 6 mm. thick A.C. sheets shall conform to M-24. The 6 mm. thickness of glass shall conform to M-38.

2.0. Workmanship

2.1. The mirror of 600 mm. x 450 mm. size mounted on A.C. Sheet or plywood 6 mm thick with C.P. brass clips shall be fixed as directed, by fixing wooden plugs in wall and C.P. brass screws and washers. The work shall be carried out in best workman like manner.

3.0. Mode of measurements & payment

3.1. The rate includes cost of all labour and materials, tools and plant etc. required for satisfactory completion of this item.

3.2. The rate shall be for a unit of **One number**.

Item No. 44 :- Providing and fixing C.P. brass waste for wash basin or sink (A) 32mm dia.

1.0. Materials

- 1.1. The C.P. brass trap and unions shall be of 32 mm. dia. and of best quality and make as approved by the Engineer-in-charge

2.0. Workmanship

- 2.1. C.P. brass waste trap and union shall be connected to 32 mm dia waste pipe which shall be suitably bent towards the wall which shall discharge into drain through a floor trap The C.P brass waste trap shall be provided for wash basin or sink as the case may be.

3.0. Mode of measurement & payment

- 3.1. The rate includes all labours and providing C.P. brass waste trap and union including waste couplings of 32 mm fin. The rate excludes the cost of waste pipe of 32 mm. dia.
- 3.2. The Rate shall be for a unit of One number.

Item No. 45 :- Providing and fixing fisher union for wash basin (A) 32mm dia.

1.0. Materials

- 1.1. The 32 mm dia M-1. Fisher union shall be of best quality and made as approved by the Engineer-in-charge.

2.0. Workmanship

- 2.1. The 32mm dia. M I. Fisher union shall be fixed to wash basin or sink in best workman like manner.

3.0. Mode of measurements and payment

- 3.1. The rate includes all labours .and materials, tools and plants etc. required for satisfactory completion of the item.
- 3.2. The Rate shall be for a unit of One number.

Item no. 46 :- Providing and laying China mosaic type water proofing treatment on terrace including (a) applying neat cement slurry 2.75 Kg./Sqmt. of cement and mixed with water proofing compound after cleaning the surface (b) laying cement concrete using brick bats 25mm to 100mm size with 50% of C.M. 1:5 (1 cement : 5 coarse sand) admixed with water proofing compound over 20mm thick layer of C.M. 1:5 to required slope including rounding of junction of walls and slab (c) After two days of proper curing applying a second coat of cement slurry (d) Finishing the surface with 20mm thick cement mortar 1:4 (1 cement : 4 coarse sand) and china mosaic tiling and finally finishing the surface with trowel with white cement slurry (e) after finishing the whole terrace shall be flooded with water for a period of two weeks.

1.0 MATERIAL

(a) Water shall confirm to M-1 (b) Cement shall conform to M-3 (c) Sand shall conform to M-6.

1.1 WATER PROOFING COMPOUND

Water proofing compound shall be of approved quality and make as approved by Engineer in charge.

1.2 BRICK BATS

Brick bat aggregates shall be broken from well burnt or slightly over burnt and dense bricks it shall be homogeneous in texture roughly cubical in shape clean and free from dirt or any other foreign material brick bats shall be of 25mm to 100mm size unless otherwise specified in the item the under burnt or over burnt bricks bats shall not be used.

1.3 CHINA MOSAIC TILE PIECES

China mosaic tiles pieces shall be of 50 mm to 90 mm nominal size, tiles pieces shall be made from hard and good quality of tiles.

1.4 WHITE CEMENT

White cement shall be of approved make it shall confirm definition of I.S. 8042-E-1978 the sample of white cement shall be approved by Engineer in charge.

WORKMANSHIP

A First of all surface of the entire terrace shall be cleaned by thoroughly brooming and then by wire brushes. All the loose material, dust and debries shall be removed thoroughly from the entire surface of the terrace.

All joints and cracks shall be racked off and cut in trench which shall be filled by neat cement slurry admixed with water proofing compound. The joints with parapet shall be racked up to 30 cm height and shall be applied by neat cement slurry admixed with water proofing compound.

Neat cement slurry shall be prepared and a water proofing compound of approved make shall be mixed with the slurry in proportion specified by the manufacturer of the compound and shall be laid through out the surface of the terrace by the use of brushes mala etc. cement slurry shall be prepared by adding adequate quantity of water so as to spread it uniformly on the surface.

B Cement concrete 1:5:10 (Using 50% of cement mortar 1:5, 1 part of cement and 5 part of coarse sand by volume admixed with water proofing compound of approved make in specified proportion) of specified thickness shall be laid (Specification of C.C. 1:5:10 shall be followed for the execution of this layer) all over the surface of the terrace in true level and required slope including rounding of junctions of walls and slabs.

- C** After two days of proper curing applying a second coat of cement slurry on entire surface of the terrace.
- D** The entire surface shall be finished with 20 mm thick C.M. 1:4 and China mosaic tilling in true level and slope as directed by Engineer in charge and finally finishing the surface with trowel with white cement slurry (Specification of white glazed tiles flooring shall be followed for the execution of this item).
- E** Finishing the surface with 20 mm thick C.M. 1:4 and China mosaic tilling and finally finishing the surface with trowel with white cement slurry.
- F** After two days proper curing the terrace shall be flooded for 15 days.

2.0 MODE OF MEASUREMENT AND PAYMENT

- 2.1** The unit rate of flooring shall include the cost of all materials, tools and plant required for mixing, laying of base layer in true level and slope as required applying and placing broken pieces of china mosaic tile in position, compacting, finishing, curing, providing treatment of 30 cm high all over the length of parapets and corners and sill of doors etc. and all other incidental expenses for producing flooring work to complete the structure of its components as shown on the drawings and according to these specifications. They shall also include the cost of making, fixing of all scaffolding and forms required for the work.
The rate of plastering shall include the cost of all labour, materials, tools and plants, scaffolding and all incidental expenses as described herein above.
- 2.2** The plaster work shall be measured for its length and width, limiting dimensions to those specified on plan or as directed. The rate shall be for a unit of one Square Meter.
- 2.4** A guarantee bond on appropriately stamped paper shall be given by the contractor to the Department in the manner and form prescribed below.
- 2.3** The payment will be made on **Square Meter** basis of the finished work.

FORM OF GUARANTEE BOND

Contractor I / We _____) here by guarantee that work will remain unaffected and will not be in anyway damaged by water rain and will not leak from surface for a period for 5 years after completion of the work of water proofing treatment as per the terms and conditions of the contract and damage that might be caused on account of water rain and or other similar type of dampness of leakage from walls or above floor.

The guarantee shall remain in force for the period of 5 years from the completion of the work under the contract and it shall remain binding to the contractor for period of 5 years.

The deposit at the rate of 20% of the cost of this item from the running and final bills shall be recovered and remained for the first one year after completion of the work or at least on monsoon season passed which ever is later and 10% shall be retained for the balance of the guarantee period and shall be returned only after completion of the guarantee period.

MODE OF MEASUREMENT AND PAYMENT

The length and breadth shall be measured correct to cm. as per the dimension of the sanctioned plants. No deduction shall be made not extra for paid for any opening for pipes etc. upto 0.1 sq.mt. The rate shall include the cost of all labour and materials required for the operation involved. For satisfactory completion of work & measurement shall be paid on unit of **Sq.m.** of finished work.

Item No. 47 :- Providing and fixing ball cock as directed by Engineer in charge
(A) Copper metal (i) 25 mm dia.

1.0. Materials :

The ball cock of 25 mm diameter of approved quality (copper) shall conform to M-75.

2.0. Workmanship

The ball cock of 25 mm diameter shall be fixed as directed. The ball cock shall be fixed in position by means of Jam nut and socket. The ball cock shall be fixed near the inlet of the water meter or as directed. The joints shall be done with white zinc and spun yarn. The joint shall be tested for leak proofing.

3.0. Mode of measurement & payment

- 3.1.** The rate includes cost of all materials and labour involved for carrying out satisfactory work.
- 3.2.** The rate shall be for a unit of One number.

Item No. 48 :- Providing and laying polished Kota stone slab flooring over 20mm (average) thick base of cement mortar 1:6 (1-cement : 6-coarse sand) or L.M. 1:1.5 laid over and jointed with grey cement slurry including rubbing and polishing etc. complete. (A) 25mm thick.

1.0. Materials

- 1.1. Water shall conform to M-1. Lime mortar shall conform to M-10. Cement mortar shall conform to M-11. 25mm thick polished kota stone slab shall conform to M-49.
- 1.1. Kota stone slab shall be hard even sound, and regular in shape and generally uniform in colour. The colour of the stone shall generally be green. Brown coloured shall not be allowed for use. They shall be without any soft veins cracks or flaws Kota stone slab shall be hard, even, and regular in shape and it should be without fault.
- 1.2. The size of the Kota stone slab to be used for flooring shall be of size 600 mm x 450 mm and or as approved by Engineer in charge or Architect. However smaller sizes will be allowed to be used to the extent of maintaining required pattern. Thickness shall be as specified.
- 1.3. Tolerance of minus 30 mm. on accounts of chisel dressing of edges shall be permitted for length as well as breadth. Tolerance in thickness shall be +3 mm.
- 1.4. The edges of Kota stone slab shall be truly chiseled and table rubbed with coarse sand before paving. All angles and edges of the stones shall be true, square and free chipping and surface shall be true and plain.
- 1.5. When machine cut edges are specified the exposed and the edges at joints shall be machine cut the thickness of the exposed machine cut edges shall be uniform.
- 1.6. The stones shall have machine polished surface. When brought on site, the stones shall be single polished or double polished depending upon its use. The stones for paving shall generally be single polished. The stones to be used for dado, skirting, sink, veneering, sills, steps etc. where machine polishing after the stones are fixed in situ is not possible shall be double polished.

2.0. Workmanship

- 2.1. Each slab shall be cut to the required size and shape and fine chisel dressed at all the edges. The sides thus dressed shall have a full contract if a straight edge is laid along. The sides shall be table rubbed with coarse sand before paving. All angles and edges of the slabs shall be true square and free from chippings and giving a plane surface. The thickness shall be 20 mm. (Average) as specified in the item but not less than 25 mm. at any place of the slab.
- 2.2. Bedding for the polished kota stone slabs shall be of cement mortar 1:6 (1 cement : 6 coarse sand) or L.M. 1:1.5 of average thickness 20 mm given in the description of the item. Sub grade shall be cleaned wetted and mopped mortar of the specified mix and thickness shall then be spread on an area sufficient to receive one blue kota stone slab. The slab shall be washed clean before laying. It shall be laid on top, pressed, tapped gently to bring it in level with the other slabs. It shall then be lifted and laid aside. Top surface of the mortar shall then be corrected by adding fresh mortar at hollows or depressions. The mortar shall then be allowed to harden bit. Over this surface, cement slurry of honey-like consistency shall be applied. The slab shall then be gently placed in position and tapped with wooden mallet till it is properly padded in level with and close to the adjoining slab. The joint shall be as fine as possible. The slabs fixed in the floor adjoining, the walls shall

enter not less than 10 mm. under the plaster, skirting or dedo. The junction between the wan and floor shall be finished neatly. The finished surface shall be true to levels and slopes as directed.

- 2.3. The floor shall be kept wet for a minimum period of 7 days so that bedding and joints set properly
- 2.4. Polishing shall be normally commenced after 14 days of laying the stone slab. First polishing shall be done with carborundum stones of 120 grade grit fitted in the heavy machine and then second polishing shall be done with carborundum stone of 220 to 350 grade grit fitted in heavy machine. Water shall be properly used during polishing. The stone shall then be washed clean with water when directed by the Engineer-in-charge, wax polish of approved quality shall be applied on the surface with the help of soft cloth over a clean and dry surface. Then the polishing machine fitted with bobs shall be run over it.
- 2.5. The holes required for Nahni traps, pipes and any other fittings shall be made, without any extra cost.

3.0. Measurement & payment

- 3.1. The rate shall include the cost of all materials and labour involved in all the operations described above. The kota stone flooring shall be measured in square meters correct to two places decimal, length and breadth shall be measured correct to a centimeter and between the finished face of skirting dedo plaster and no deduction shall be made nor extra paid for any opening in floor of areas upto 0.1 sq.
- 3.2. The rate shall be for a unit of one **sq. meter**.

Item No. 49 :- Filling in plinth with sand under floors including watering, ramming, consolidating and dressing etc. complete.

1.0. Materials

- 1.1.** Sand shall be natural sand, clean, well graded hard strong, durable and gritty particles free from injurious amounts of dust, clay kankar nodules, soft or flaky particles shale, alkali salts organic matter, loam, mica or other deleterious substances and shall be got approved from the Engineer-in-Charge. The sand shall not contain more than 8 percent of silt as determined by field test, if necessary the sand shall be washed to make it clean.
- 1.2. Coarse Sand :** The fineness modulus of coarse sand shall not be less than 2.5 and shall not exceed 3.0. The sieve analysis of coarse shall be as under :

I.S. Sieve Designation	Percentage by Weight Passing sieve	I.S. Sieve Designation	Percentage by Weight Passing Sieve
4.75 mm	100	600 Micron	30 - 100
2.36 mm	90 to 100	300 Micron	5 - 70
1.18 mm	70 - 100	150 Micron	0 - 50

- 1.3. Fine Sand :** The fineness modulus shall not exceed 1.0. The sieve analysis of fine sand shall be as under :

I.S. Sieve Designation	Percentage by Weight Passing through	I.S. Sieve Designation	Percentage by Weight Passing through
4.75 mm	100	600 Micron	40 - 85
2.36 mm	100	300 Micron	5 - 50
1.18 mm	70 - 100	150 Micron	0 - 10

2.0. Workmanship

- 2.1.** The sand to be used for filling shall be free from salts, organic or other foreign matter all clots of earth shall be broken.
- 2.2.** As soon as the work in foundation has been completed and measured the site of foundation shall be cleared of all debris brick bats mortar dropping etc. and filled with earth in layers not exceeding 20 cms. each layer shall be adequately watered, rammed and consolidated before the succeeding layer is laid. The sand shall be rammed with iron rammers where feasible and with the ends of crow-bars, where rammer cannot be used.
- 2.3.** The plinth shall be similarly filled with sand in layers not exceeding 20 cms adequately watered and consolidated by ramming with iron or wooden rammers. When filling reaches finished level the surface shall be flooded with water for at least 24 hours and allowed to dry and then rammed and consolidated.
- 2.4.** The finished level of filling shall be kept to shape intended to be given to floor.
- 2.5.** In case of large heavy duty flooring like factory flooring, the consolidation may be done by power rollers, where so specified. The extent of consolidation required shall also be as specified.

3.0. Mode of Measurements & Payment

- 3.1.** The payment shall be made for filling in plinth and trenches. No deduction shall be made for shrinkage or voids, if consolidated as instructed above.
- 3.2.** The rate includes cost of collecting, carting sand with all lead and labour for filling the same in plinth under floors.
- 3.3.** The rate shall be for a unit of one **cubic meter**.

Item No. 50 :- Providing & fixing a board showing "Aanganwadi" of size 0.60 x 0.30 m including painting Gujarati Language as directed.

The item covers the providing and fixing of board showing "**Aanganwadi**" of Gujarati language letters of size 0.60 x 0.30 m including painting as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The letters shall be fixed as and where directed by Engineer in charge.

The payment shall be made on **No.** basis of letters supplied and fixed.

Item No. 51 :- Boring holes 3.5 m deep in ordinary soil (for cast in situ piles) and getting out the soil and disposal of the surplus excavated soil as directed within a lead of 50 Meter for following diameter of pipes.(iii) 300 mm

The relevant specifications of **Item No. 1** shall be followed for the work of **Boring holes 3.5 m deep in ordinary soil (for cast in situ piles) and getting out the soil and disposal of the surplus excavated soil as directed within a lead of 50 Meter for following diameter of pipes.(iii) 300 mm**

Item No. 52 :- Providing and laying cement concrete 1:3:6 (1- Cement : 3- Coarse sand : 6- crushed stone aggregates 20 mm nominal size) and curing complete including cost of formwork in (A) Wall Caps / Coping.

1.0. Materials

1.1. Water shall conform to M-1. Cement shall conform to M-3. Sand shall conform to M-6. Crushed Stones aggregate 20 mm. nominal size shall conform to M-12.

2.0. Workmanship

2.1. General

2.1.1. Before stating concrete the bed of foundation trenches shall be cleared of all loose materials, leveled, watered and rammed as directed.

2.2. Proportion of Mix:

2.2.1. The proportion of cement, sand and stone aggregate shall be one part of cement. 3 parts of coarse sand and **6** parts of **crushed** stone aggregates and shall be measured by volume.

2.3. Mixing:

2.3.1. The concrete shall be mixed in a mechanical mixer at the site of work. Hand mixing may however be allowed for smaller quantity of work if approved by the Engineer-in-charge. When hand mixing is permitted by the Engineer-in-charge in case of break-down of machineries and in the interest of the work, it shall be carried out on a water tight platform and care shall be taken to ensure that mixing is continued until the mass is uniform in colour and consistency, However in such case 10% more cement than otherwise period 1½ to 2 minutes. The quantity of water shall be just sufficient to produce a dense concrete of required workability for the purpose.

2.4. Transporting & Placing the Concrete:

2.4.1. The concrete shall be handed from the place, of mixing to the final position in not more than 15 minutes by the method as directed and shall be placed into its final-position, compacted and finished within 30 minutes of mixing with water i.e. before the setting commences.

2.4.2. The concrete shall be laid in layers of 15 cms. to 20 cms.

2.5.1. The concrete shall be rammed with heavy iron rammers and rapidly to get the required compaction and to allow all the interstices to be filled with mortar.

2.6. Curing:

2.6.1. After the final set, the concrete-shall be kept continuously wet if required by pounding for a period of not less then 7 days form the date of placement.

2.7 The concrete work of wall caps/coping.

3.0. Mode of Measurement & Payment:

3.1. The concrete shall be measured for its length, breadth and depth, limiting dimensions to those specified on plan or as directed. Rate includes cost of necessary form work.

3.2. The rate shall be for a unit of **one cubic meter**.

Item No. 53 :- Providing and fixing precast Rubber Dye / steel Dye inter locking concrete block 60mm thick with grade of concrete M-300 pneumatic compressed / vibrated mechanically and as per approved design confirming to IS 15658 : 2006 including 35 mm sand layer for levelling and filling the joint with sand in proper line and level as per guidelines of IRC : SP 63-2018 etc. complete.

General

This work shall consist of providing and laying precast Rubber dye / steel dye inter locking concrete block **60 mm thick** with grade of concrete M-300 as per approved design over a base layer of 35 mm thick layer of sand of the shape and dimensions shown on the drawings and conforming to these specifications or as approved by the Engineer in charge.

1.0 MATERIAL

Water shall conform to M-1. Cement shall conform to M-3.

1.0 Precast Rubber dye / steel dye inter locking concrete block

Precast Rubber dye / steel dye inter locking concrete block shall be of approved size brand and make as approved by Engineer in charge.

- 1.1** The size shape and design of precast Rubber dye / steel dye inter locking concrete block shall generally be as per manufacturers product or as directed by the Engineer in charge and Architect.
- 1.2** The precast Rubber dye / steel dye inter locking concrete block shall satisfy the tests as regards compress strength transverse strength resistance to wear and water absorption.
- 1.3** The colour size shape and design of the precast Rubber dye / steel dye inter locking concrete block shall be directed by Engineer or Architect.
- 1.4** The precast rubber dye / steel dye inter locking concrete block shall be of best quality as approved by the Engineer In charge. They shall be flat and true to shape. They shall be free from cracks, crazing spots, chipped edges and corners. The glazing shall be of uniform shade.

2.0 SAND

- 2.1** Sand shall be natural sand, clean well graded, hard strong durable and gritty particular free from immures amounts of dust, clay, kankar modules.
- 2.2.** For masonry works sand shall confirm to the requirements of IS: 2116.
- 2.3.** For plain and reinforced cement concrete (PCC and RCC) or pre stressed concrete (PSC) works fine aggregates shall consist of clean, hard strong and durable prices of crushed stone, crushed gravel or suitable combination of natural sand crushed stone or gravel, They shall not contain dust lumps soft or flaky materials mica or other deleterious materials in such quantities as to reduce the strength and durability of concrete, or to attack the embedded steel. Motorized sand washing machines should be used to remove impurities from sand. Fine aggregate having positive alkali-silica reaction shall not be used. All fine aggregates shall conform to IS L 383 and tests for conformity shall be carried out as per IS : 2386 (Part I to VIII) The contractor shall submit to the Engineer in charge the entire information indicated in Appendix A of IS : 383. The fineness modulus of fine aggregate shall neither be less than 2.00 nor greater than 3.5.
- 2.4.** Sand fine aggregates for structural concrete shall conform to the following grading requirements as shown in the table below.
- 2.5 Fine Sand:** The fineness module shall not exceed 1.0 the sieve analysis of fine sand be as under:

IS. Sieve Designation	% by wt. passing		
	Zone I	Zone II	Zone III
10 mm	100	100	100

4.75 mm	90-100	90-100	90-100
2.3 6mm	60-95	75-100	85-100
1.18 mm	30-70	55-90	75-100
600 MC	15-34	35-59	60-79
300 MC	5-20	8-30	12-40
150 MC	0-10	0-10	0-10

- **Coarse Sand:** The fineness modules of coarse sand shall not be less than 2.5 and shall not exceed 3.0. The sieve analysis of coarse sand be as under:

I. S. Sieve Designation	% by wt. passing
4.75 mm	100
2.36mm	90 to 100
1.18 mm	70 to 100
600 MC	30 to 100
300 MC	85 to 70
150 MC	00 to 50

3.0 WORKMANSHIP

- 3.1** The precast Rubber dye / steel dye inter locking concrete block shall be laid on a layer 35 mm thick layer of coarse sand. The slope in the floors shall be provided in the sub grade. The base layer shall be properly watered, rammed and consolidated. Before laying the pavers blocks, it shall be moisture. Plinth masonry offset shall be depressed so as to allow the sub grade concrete to rest on it.
- 3.2** Precast Rubber dye / steel dye inter locking concrete block of approved quality shape and design and shall be laid evenly to level and slope as directed by Engineer in charge over a bed of a base layer consisting of 35mm thick sand layer.
- 3.3 Laying:** The precast Rubber dye / steel dye inter locking concrete block shall be laid in plain, diagonal or other pattern as directed. The cement concrete blocks shall be laid properly and set home by gentle tapping.
- 3.4** End portion of pavement shall be finished with C.M. 1:3 as per detailed drawing etc. complete.

4.0 MODE OF MEASUREMENT AND PAYMENT

- 4.1** The unit rate precast Rubber dye / steel dye inter locking concrete block flooring shall include the cost of all materials, tools and plant required for supplying and laying material like brick bats sand pavers blocks, laying of base layer in true level and slope as required applying & placing pavers blocks in position, compacting, finishing, curing.
- 4.2** The length and breadth shall be measured correct to a Square meter correct to 2 places of decimal. Length and breadth shall be measured to correct to a centimeter and between the finished the finished face of the skirting, dedo or wall plaster and no deduction shall be made nor extra paid for any opening in floors or areas up to 0.1 square meter.
- 4.3** The rate shall be for a unit of **one Square meter**.

Item No. 54 :- Colour washing with lime on wall surface (three coat) over and including a primer coat of white washing to give an even shade after thoroughly brooming the surface to remove all dirt, dust, mortar drops and other foreign matter.

1.0. Materials

- 1.1. Clear-Cole :** This shall be made from glue and boiling water by mixing 1 kg. of glue to every 15 liters of water. The mixing shall be suitably tinted to match with colour of white washing as directed. Glue shall conform to I.S. 852-1969.
- 1.2. Lime :** Lime used shall be freshly burnt class 'C' lime (Fat lime) and white in colour conforming to I.S. 712- 1973.
- 1.3. Water :** Water shall conform to M-1.
- 1.4. Gum :** Best quality of gum shall be used in the preparation of white or colour wash. The colour pigment of required tint and shade shall be mixed in lime cream. The mineral colour not affected by lime shall be used in preparing the white wash.

2.0. Workmanship

- 2.1.** Sufficient quantity of white wash enough for the complete job shall be prepared in one operation to avoid any difference in shade. The basic colour wash solution shall be prepared in accordance with item 18.11. Mineral colours not affected by lime shall be added to the colour wash solution. No colour wash shall be done until a sample of the colour has been approved. It shall be noted that small samples of colour appears lighter in shade than when the same shades are applied precisely to large surface. The colour shall be of even, tint, over the colour shall be of even tint, over the whole surface. If it is patchy or otherwise badly applied, it shall be rejected. Preparation of the colour wash with pigment shall be as under:

(a) With Yellow and Red Ocher : Solid lumps if any in the powder shall be crushed to powder and solution in water prepared and then added to colour wash sieving it through a coarse cloth, mixed evenly and thoroughly to colour wash in-small quantities till required shade is obtained.

(b) With Blue Vitriol : Fresh crystals of hydrous copper sulfate (i.e. vitriol) shall be ground to fine power and dissolved in small quantity of water. Sufficient quantity of solution enough to produce the colour wash of required shade shall be strained through a clean cloth, the filtrate being mixed evenly and thoroughly to the colour wash.

(c) Colour wash from other colouring pigment shall be prepared in accordance with the instructions of the manufacturer.

2.2. Preparation of Surface :

The surface shall be prepared by removing mortar dropping and foreign matter and thoroughly cleaned with wire of fiber brush or any other suitable means as directed by the

Engineer-in-charge. All loose pieces and scales shall be scrapped off and holes filled with mortar.

- 2.2.1.** For scaffoldings and application of white wash, relevant specification of item No. 18.11. above shall be followed. The colour wash shall be applied as under:

The Colour wash shall be applied in accordance with the procedure given in item No. 18.11. "Application of colour wash for colour washing on undercoated surface after the surface has been prepared. The first primary coat shall be of colour wash and subsequent coats (minimum two) shall be colour wash and the entire surface shall represent a smooth and uniform finish. To start with, patch of 0.1 sq. mt. on prepared surface shall be colour washed with first coat of colour wash and subsequent coats of colour wash solution entire work of white washing is taken up in hand, it shall be noted that small areas of colour wash will appear lighter than when the same shade is applied to the large surface.

- 2.2.2.** For colour washing on decorated surfaces, after (the surface has been prepared, a coat of colour wash shall be applied for the patches and repairs. Then one coat or more of colour wash shall be applied over the entire surface, such that the colour washed surface shall present a uniform colour shade. No primary coat is needed for a decorated surface bearing colour of same shade on surface required change of colour after the surface has been prepared as described above. Two coats of colour wash shall be applied before application of specified number (minimum TWO) of coats of colour wash of the new shade.

2.3. Protective measures :

The surface of doors, windows, floors, articles, of furniture etc. and such other parts of the building not to be white washed shall be protected from being splashed upon. Such surfaces shall be cleaned of white wash splashed if any.

3.0. Mode of measurements and payment

- 3.1.** All the work shall be measured in the decimal system as under:

(a) Dimensions shall be measured to the nearest 0.01 m.

(b) Area in individual item shall be worked out to the nearest 0.01 sq.m.

All the work shall be measured in sq. mt. Deductions for jambs, soffits, sills etc. for openings not exceeding 0.5 sq. mt. each in area, for ends of joists, posts, beams, girders, steps etc. not exceeding 0.5 sq mt. each in area and for openings exceeding 0.5 sq. mt. and not exceeding 3.0. sq. mt. each in area, deductions and additions shall be made as under.

- 3.2.** No deductions shall be made for ends of joists, beams, posts, etc. and openings not exceeding 0.5 sq mt. each. No addition shall be made for reveals, jambs, soffits, sills etc. of these openings not for finish around ends of joints, beams, posts etc.

- 3.3.** No deductions for openings exceeding 0.5 sq.mt. but not exceeding 3 sq. mt. each shall be made as follows and no addition will be made for reveals, jambs, soffits etc. of these openings :

(a) When both the faces of walls are provided with finish, deduction shall be made for one face only.

(b) When each face of wall is provided with different finish, deduction shall be made for that side of frame for door, windows, etc. on which width of reveals is less than that of the other side. Where width of reveals on both faces of wall are equal, deduction of .50% of area of opening on each face shall be made from total area of finish.

(c) When only one face of wall is treated and the other face is not treated, full deduction shall be made if the width of reveal on the treated side is less than that on the untreated side, but if the width of the reveal is equal or more than on the untreated side neither deductions nor additions to be made for reveals, jambs, soffits, sills etc.

3.4. In case of area of openings exceeding 3 sq.mt. each, deductions shall be made for openings but jambs, soffits, sills shall be measured.

3.5. No deductions shall be made for attachment such as casing, conducts, pipe, electric wiring and the like.

3.6. Corrugated surfaces shall be measured flat as fixed and not girth. The quantities so measured shall be increased by the following percentage and the resultant shall be included with the general areas:

(a) Corrugated steel sheets..... 14%

(b) Corrugated A.C. sheets..... 20%

(c) Semi corrugated A.C. Sheets..... 10%

(d) Nainital pattern roof (Plain sheeting sheets)..... 10%

(e) Naintial pattern roof (with corrugated sheets)..... 25%

3.7. Cornices and other wall features, when they are not picked out in a different finish/colour shall be girthed and included in the general area.

3.8. The rate shall include the cost of ail materials, labour, scaffolding, protective measures etc. involved in all the operations described above.

3.9. The rate shall be for a unit of **One sq.** meter.

Item No. 55 :- Measured Around Us Scales - Horizontally and Vertically : Vertically Scales painted on the wall 15 cm. wide and length 3 mtr. on existing wall surfaces with single coat including priming on existing wall surface and ceiling.

The item covers the Measured Around Us Scales - Horizontally and Vertically : Vertically Scales painted on the wall 15 cm. wide and length 3 mtr. on existing wall surfaces with single coat including priming on existing wall surface and ceiling as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **No.** basis.

Item No. 56 :- Symmetry Around Us : Symmetrical shapes (like round, square etc.) with Revealing part of whole images (Painting on door or window surface) including painting whole door & windows with finishing etc. complete.

The item covers the Symmetry Around Us : Symmetrical shapes (like round, square etc.) with Revealing part of whole images (Painting on door or window surface) including painting whole door & windows with finishing as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 57 :- Colour Teasures :- Painting colour teasers on existing metal surface like fan colour wheel, metallic fan blades (each is a circle with dia. 3 cm approx.) with metal primer and enamel matt paint with all necessary finishing etc. complete.

The item covers the Colour Teasures :- Painting colour teasers on existing metal surface like fan colour wheel, metallic fan blades (each is a circle with dia. 3 cm approx.) with metal primer and enamel matt paint with all necessary finishing etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **No.** basis.

Item No. 58 :- Map Your World :- Mapping the Neighbourhood / Village / Mapping the City / District / State / Mapping the Country / Mapping the World / Me and my world painting (1.5 mtr. dia.) on existing wall surface and print on plastered wall surface with cement primer and enamel (matt paint) etc..

The item covers the Map Your World :- Mapping the Neighbourhood / Village / Mapping the City / District / State / Mapping the Country / Mapping the World / Me and my world painting (1.5 mtr. dia.) on existing wall surface and print on plastered wall surface with cement primer and enamel (matt paint) etc. as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 59 :- Time Devices : Making Clock with MS arms and writing surface, 60 cm in diameter by making new chalk board surface on existing masonry wall with 1:6 cement sand in two coats and finished coat with 1:2 cement marble stone dust and painting on this surface with providing and fixing hands of the wall clock with MS flat (0.4 cm thick and 2 cm wide) and MS flat (0.4 cm thick and 1 cm wide) with galvanised steel bolts and washers with painting clock dial and hands including all necessary surface preparation etc. complete.

The item covers the Time Devices : Making Clock with MS arms and writing surface, 60 cm in diameter by making new chalk board surface on existing masonry wall with 1:6 cement sand in two coats and finished coat with 1:2 cement marble stone dust and painting on this surface with providing and fixing hands of the wall clock with MS flat (0.4 cm thick and 2 cm wide) and MS flat (0.4 cm thick and 1 cm wide) with galvanised steel bolts and washers with painting clock dial and hands including all necessary surface preparation etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **No.** basis.

Item No. 60 :- Number Lines : (A) Number Line Caterpillar / Number Line Train Number / Number Line in a row of Children on existing walls surface as per approved drawing and design etc. complete.

The item covers the Number Lines : (A) Number Line Caterpillar / Number Line Train Number / Number Line in a row of Children on existing walls surface as per approved drawing and design etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 61 :- Abacus as a Built Element : Making Hoop Abacus set for classroom on wall (Different length for different classes) as per approved drawing and design etc. complete.

The item covers the Abacus as a Built Element : Making Hoop Abacus set for classroom on wall (Different length for different classes) as per approved drawing and design etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Set** basis.

Item No. 62 :- Prewriting Patterns on Window Grills as per approved drawing and design etc. complete.

The item covers the Prewriting Patterns on Window Grills as per approved drawing and design etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 63 :- Prewriting Patterns on Wall surfaces by making new chalkboard surface on existing masonry wall with 1:6 cement sand in two coats and finished coat with 1:2 cement marble stone dust with painting and printing on new chalkboard wall surface and ceiling.

The item covers the Prewriting Patterns on Wall surfaces by making new chalkboard surface on existing masonry wall with 1:6 cement sand in two coats and finished coat with 1:2 cement marble stone dust with painting and printing on new chalkboard wall surface and ceiling as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 64 :- Writing and Displaying Surfaces / New Chalkboard : Providing writing and displaying surfaces on existing walls / Chalkboard by painting on existing wall surface etc. complete.

The item covers the Writing and Displaying Surfaces / New Chalkboard : Providing writing and displaying surfaces on existing walls / Chalkboard by painting on existing wall surface etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 65 :- Play with words : Making World wall with Alphabet border by making 60 x 140 cm writing surface on wall with 10 cm wide border including making new chalkboard surface 1:6 (1 cement : 6 sand) in two coats and finished coat with 1:2 with cement marble stone dust with painting grid/t.

The item covers the Play with words : Making World wall with Alphabet border by making 60 x 140 cm writing surface on wall with 10 cm wide border including making new chalkboard surface 1:6 (1 cement : 6 sand) in two coats and finished coat with 1:2 with cement marble stone dust with painting grid/t as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 66 :- Dot Boards on floor and walls :- Making DOT Board & GRID Board on floor and walls with painting and painting dots in straight rows, dots staggered in straight rows on existing wall surface and ceiling as per approved drawing and design etc. complete.

The item covers the Dot Boards on floor and walls :- Making DOT Board & GRID Board on floor and walls with painting and painting dots in straight rows, dots staggered in straight rows on existing wall surface and ceiling as per approved drawing and design etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 67 :- Grid Boards : Provide a Floor Grid Boards of size 60cm x 60cm with 1:2:4 P.C.C. flooring with glass / PVC strips as per approved drawing and design etc. complete.

The item covers the Grid Boards : Provide a Floor Grid Boards of size 60cm x 60cm with 1:2:4 P.C.C. flooring with glass / PVC strips as per approved drawing and design etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 68 :- Board games on floor : Making Indigenous Board Games / Flat Dice like Sapaat Pasa with necessary smooth floor finish as per drawing etc. complete.

The item covers the Board games on floor : Making Indigenous Board Games / Flat Dice like Sapaat Pasa with necessary smooth floor finish as per drawing etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 69 :- Magic squares on floor and walls : Providing magic squares on floors and walls with 3 x 3 Magic Square / 4 x 4 Magic Square by making new chalk board on existing masonry wall 1:6 (1 cement : 6 sand) in two coats and finished coat with 1:2 with cement marble stone dust and than making painting.

The item covers the Magic squares on floor and walls : Providing magic squares on floors and walls with 3 x 3 Magic Square / 4 x 4 Magic Square by making new chalk board on existing masonry wall 1:6 (1 cement : 6 sand) in two coats and finished coat with 1:2 with cement marble stone dust and than making painting as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 70 :- Cubby Holes and Peep Holes on walls : Making cubbyholes with bricks in the existing low heights walls with necessary finishing etc. complete as per design.

The item covers the Cubby Holes and Peep Holes on walls : Making cubbyholes with bricks in the existing low heights walls with necessary finishing etc. complete as per design as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 71 :- Periscope : 2 - For Ground floor building periscope provided with 1.00 mt. clear height with 15 cm dia. PVC pipe including fixing with 2 elbows at top and bottom with transparent glass including all necessary fixing with making necessary holes and finishing it etc. complete.

The item covers the Periscope : 2 - For Ground floor building periscope provided with 1.00 mt. clear height with 15 cm dia. PVC pipe including fixing with 2 elbows at top and bottom with transparent glass including all necessary fixing with making necessary holes and finishing it etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **No.** basis.

Item No. 72 :- Providing and fixing PIN UP BOARD with necessary base fitting as per given drawing etc. complete.

The item covers the providing and fixing PIN UP BOARD with necessary base fitting as per given drawing etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Sq.mt.** basis.

Item No. 73 :- Pipe phone : Making pipe phone by providing B class MS pipe of 50mm dia. and necessary length with existing ramp including all fixing and finishing etc. complete.

The item covers the Pipe phone : Making pipe phone by providing B class MS pipe of 50mm dia. and necessary length with existing ramp including all fixing and finishing etc. complete as directed by Engineer-in-charge with all necessary tools & plants etc. complete.

The payment shall be made on **Rmt.** basis.

Item No. 96 : Demolition including stacking of serviceable materials and disposal of unserviceable materials with all lead and lift (i) R.C.C. work.

1.0. Workmanship

- 1.1. The demolition shall consist of demolition of one or more parts of the building as specified or shown in the drawings. Demolition implies taking up or down or breaking up. This shall consist of demolishing whole or part of work including all relevant items as specified or shown in the drawings.
- 1.2. The demolition shall always be planned before hand shall be done in reverse order to the one in which the structure was constructed. This scheme shall be got approved from the Engineer-in-charge before starting the work. This however will not absolve the contractor from the responsibility of proper and safe demolition.
- 1.3. Necessary propping, shoring and under pinning shall be provided for the safety of the adjoining work or property, which is to be left intact, before dismantling and demolishing is taken up and the work shall be carried out in such a way that no damage is caused to the adjoining property.
- 1.4. Wherever required, temporary enclosures or partitions shall also be provided. Necessary precautions shall be taken to keep the dust nuisance down as and where necessary.
- 1.5. Dismantling shall be commenced in a systematic manner. All materials which are likely to be damaged by dropping from a height or demolishing roof, masonry etc. shall be carefully dismantled first. The dismantled articles shall be properly stacked as directed.
- 1.6. All materials obtained from demolition shall be the property of Government unless otherwise specified and shall be kept in safe custody until handed over to the Engineer-in-charge.
- 1.7. Any serviceable materials, obtained during dismantling or demolition shall be separated out and stacked properly as directed with all lead and lift. All unserviceable materials, rubbish etc., shall be stacked as directed' by the Engineer-in-charge.
- 1.8. On completion of work, the site shall be cleared of all debris rubbish and cleaned as directed.

2.0. Mode of measurements and payment

- 2.1. Measurements of all work except hidden work shall be taken before demolition or dismantling and no allowance for increase in bulk shall be allowed. The demolition of lime concrete shall be measured under this item. Specification for deduction for voids, openings etc. shall be on same basis as that employed for construction of work.
- 2.2. All work shall be measured in decimal system as fixed in its place subject to the following limits; unless otherwise stated hereinafter : (a) Dimensions shall be measured to the nearest 0.01 mt. (b) Area shall be worked out to the nearest 0.01 sq. mt.(c) Cubical contents shall be worked out to the nearest 0.01 Cu.m.
- 2.4. The unserviceable materials shall be stacked as directed by Engineer-in-charge with all leads and lifts.

- 2.5. The rate shall include cost of all labour involved and tools used in demolishing and dismantling including scaffolding. The rate shall also include the charges for separating out and stacking the serviceable materials properly and disposing the unserviceable materials with all lead and lift. The rate also includes for temporary shoring for the safety of the portion not required to be pulled down or of adjoining property and providing temporary enclosures or portions where considered necessary.
- 2.6. The rate shall be for a unit of one cubic meter.

Item No. 97 : Demolition of brick work and stone masonry including stacking of serviceable materials and disposal of unserviceable materials with all lead and lift (ii) in cement mortar.

1.0. Workmanship

- 1.1. The relevant specifications of **Item No. 96** shall be followed except that demolition of cement mortar is to be done.

2.0. Mode of measurements and payment

- 2.1. The relevant specifications of **Item No. 96** shall be followed except that the demolition of cement mortar is to be done. The unserviceable materials shall be disposed of at all leads and lifts. The rate excludes scraping straightening of reinforcement but includes cutting of reinforcement.
- 2.2. The rate shall be for a unit of **one cubic meter**.

Item No. 98 :- Dismantling doors, windows, ventilators etc. (wood or steel) shutters including chowkhats architraves, holdfasts and other attachment etc. complete and stacking them within all lead and lift. (ii) Exceeding 3 Sq.m. in area.

1.0. Workmanship

The relevant specifications of **item No. 99** shall be followed except that the door, windows, ventilators etc. (wood or steel) shutters including chowkhats, architraves, hold fasts and other attachments etc. are to be dismantled.

2.0. Mode of measurements & payment

- 2.1. The relevant specifications of **item No. 99** shall be followed.
- 2.2. The doors, windows, ventilator etc. exceeding 3 sq. mt. in area (each) including shutters and chowkhats. architraves, hold fasts and other attachments to frames etc. will be dismantled and measured under this item.
- 2.3. The rate includes stacking the serviceable materials as and where directed with all leads and lifts.
- 2.4. The rate shall be for a unit of one **number**.

Item No. 99 : Dismantling tiled of stone floors laid in mortar including stacking of serviceable materials and disposal of unserviceable materials with all lead and lift (i) in cement mortar.

1.0. Workmanship

- 1.1. The dismantling tiled of stone floors laid in mortar shall consist of dismantling of one or more parts of the building as specified or shown in the drawings. Dismantling implies taking up or down or breaking up. This shall consist of demolishing whole or part of work including all relevant items as specified or shown in the drawings.
- 1.2. The dismantling tiled of stone floors laid in mortar shall always be planned before hand shall be done in reverse order to the one in which the structure was constructed. This scheme shall be got approved from the Engineer-in-charge before starting the work.
This however will not absolve the contractor from the responsibility of proper and safe demolition.
- 1.3. Necessary propping, shoring and under pinning shall be provided for the safety of the adjoining work or property, which is to be left intact, before dismantling and demolishing is taken up and the work shall be carried out in such a way that no damage is caused to the adjoining property.
- 1.4. Wherever required, temporary enclosures or partitions shall also be provided. Necessary precautions shall be taken to keep the dust nuisance down as and where necessary.
- 1.5. Dismantling shall be commenced in a systematic manner. All materials which are likely to be damaged by dropping from a height or demolishing roof, masonry etc. shall be carefully dismantled first. The dismantled articles shall be properly stacked as directed.
- 1.6. All materials obtained from demolition shall be the property of Government unless otherwise specified and shall be kept in safe custody until handed over to the Engineer-in-charge.
- 1.7. Any serviceable materials, obtained during dismantling or demolition shall be separated out and stacked properly as directed with all lead and lift. All unserviceable materials, rubbish etc. shall be stacked as directed by the Engineer-in-charge.
- 1.8. On completion of work, the site shall be cleared of all debris rubbish and cleaned as directed. Dismantling implies carefully taking up or down or removing without damage. The articles shall be passed by hand where necessary and lowered and where these are fixed by nail, screws, bolts etc., these shall be taken out with proper tools.

2.0. Mode of measurements and payment

- 2.1. Measurements of all work except hidden work shall be taken before dismantling tiled of stone floors laid in mortar and no allowance for increase in bulk shall be allowed. The dismantling tiled of stone floors laid in mortar of lime concrete shall be measured under this item. Specification for deduction for voids, openings etc. shall be on same basis as that employed for construction of work,

2.2. All work shall be measured in decimal system as fixed in its place subject to the following limits; unless otherwise stated hereinafter : (a) Dimensions shall be measured to the nearest 0.01 mt. (b) Area shall be worked out to the nearest 0.01 sq. mt.(c) Cubical contents shall be worked out to the nearest 0.01 Cu.m.

2.3. The rate shall include cost of all labour involved and tools used in demolishing and dismantling including scaffolding. The rate shall also include the charges for separating out and stacking the serviceable materials properly and disposing the unserviceable materials with all lead and lift. The rate also includes for temporary shoring for the safety of the portion not required to be pulled down or of adjoining property arid providing temporary enclosures or portions where considered necessary.

The rate shall include staking the unserviceable materials as directed with all lead and lift.

2.2. The Rate shall be for a unit of one **sq. meter**.