

# **TECHNICAL SPECIFICATION FOR 11 KV COMPOSITE PIN INSULATORS**

## **1.0 SCOPE :**

This specification covers the design, manufacture, testing and supply of 11KV Composite Insulators. The composite insulators shall be pin insulators for straight line locations.

## **2.0 SYSTEM PARTICULARS:**

- Nominal System Voltage 11 kV
- Corresponding highest system Voltage 12 kV
- Frequency 50 Hz with 3% tolerance
- Number of phase 3
- Neutral earthing: effectively grounded.

## **3.0 STANDARDS :**

Unless otherwise specified elsewhere in the specifications insulators shall confirm to the latest revisions of all relevant standards available at the time of placement of the order. The standards are listed in Annexure 'A'.

## **4.0 GENERAL REQUIREMENTS**

- 4.1 The composite insulators shall generally conform to latest Standards as listed in Annexure 'A'
- 4.2 The Composite Insulators will be used on lines on which the conductors will be ACSR of any size up to Coyote. The insulators should withstand the conductor tension, the reversible wind load as well as the high frequency vibrations due to wind.
- 4.3 Insulators shall have sheds with good self-cleaning properties. Insulator shed profile, spacing, projection etc. and selection in respect of polluted conditions shall be generally in accordance with the recommendation of IEC-60815/IS: 13134.
- 4.4 The size of Composite insulator, minimum creepage distance and mechanical strength along with hardware fittings shall be as follows:

Type of Composite insulator	Nominal System Voltage kV(rms)	Highest System Voltage kV(rms)	Visible discharge test voltage kV(rms)	Wet power frequency withstand voltage kV (rms)	Impulse withstand voltage kV(peak)	Minimum creepage distance in mm	Min. failing load kN
Pin Insulator	11	12	9	35	75	320	5

#### **4.6 Dimensional Tolerance of Composite Insulators**

The tolerances on all dimensions e.g. diameter, length and creepage distance shall be allowed as follows in line with-IEC 61109:

$\pm (0.04d+1.5)$  mm when  $d \leq 300$ mm

$\pm (0.025d+6)$  mm when  $d > 300$  mm.

Where, d being the dimensions in millimeters for diameter, length or creepage distance as the case may be. However no negative tolerance shall be applicable to creepage distance.

#### **4.7 Corona and RI Performance**

All surfaces shall be clean, smooth, without cuts, abrasions or projections. No part shall be subjected to excessive localized pressure. The insulator and metal parts shall be so designed and manufactured that it shall avoid local corona formation and not generate any radio interference beyond specified limit under the operating conditions.

### **5.0 TECHNICAL DESCRIPTION OF COMPOSITE INSULATORS**

Polymeric Insulators shall be designed to meet the high quality, safety and reliability and should be capable of withstanding a wide range of environmental conditions: Polymeric Insulators shall consist of THREE parts, at least two of which are insulating Parts:- (a) Core- the internal insulating part (b) Housing- the external insulating part (c) Metal end fittings.

#### **5.1 CORE**

It shall be a glass-fiber reinforced epoxy resin rod of high strength (FRP rod). Glass fibers and resin shall be optimized in the FRP rod. Glass fibers shall be Boron free electrically corrosion resistant (ECR) glass fiber or Boron free E-Glass and shall exhibit both high electrical integrity and high resistance to acid corrosion. The matrix of the FRP rod shall be Hydrolysis resistant. The FRP rod shall be manufactured through Pultrusion process. The FRP rod shall be void free as proven through die penetration test. The FRP rod must pass electric leakage current test of 175V/mm. The leakage current shall not exceed 0.05mA.

#### **5.2 HOUSING:**

The FRP rod shall be covered by a seamless sheath of a silicone elastometric compound or silicone alloy or EVA compound of a thickness of 3mm minimum. It shall be one-piece housing using Injection Molding Principle to extrude directly onto the core and cover the core. The elastomer housing shall be designed to provide the

necessary creepage distance and protection against environmental influences. Housing shall conform to the requirements of IEC 61109/92-93 with latest amendments. The bonding of the elastomeric compound to the fibre glass rod shall be perfect and shall be proved by a peel off test as described elsewhere in this specification.

### **5.3 WEATHERSHEDS**

The composite polymer weather sheds made of a silicone elastomeric compound or silicone alloy or EVA compound shall be firmly bonded to the sheath, vulcanized to the sheath or molded as part of the sheath and shall be free from imperfections. It should protect the FRP rod against environmental influences, external pollution and humidity. The weather sheds should either be of EVA or have silicon content of minimum 30% by weight. The strength of the weather shed to sheath interface shall be greater than the tearing strength of the polymer. The interface, if any, between sheds and sheath (housing) shall be free from voids. Housing and weathershed materials shall have tensile strength of 10MPa with 300% elongation minimum and tear strength of 20N/mm.

### **5.4 METAL END FITTINGS (Pins):**

End fitting transmit the mechanical load to the core. They shall be made of spheroidal graphite cast iron, malleable cast iron or forged steel or aluminum alloy. They shall be connected to the rod by means of a controlled compression technique. Metal end fittings shall be hot dip galvanized after, all fittings have been completed. The material used in fittings shall be corrosion resistant. As the main duty of the end fittings is the transfer of mechanical loads to the core the fittings should be properly attached to the core by a coaxial or hexagonal compression process & should not damage the individual fibers or crack the core. The gap between fitting and sheath shall be sealed by a flexible EVA or silicone elastomeric compound or silicone alloy compound sealant. System of attachment of end fitting to the rod shall provide superior sealing performance between housing, i.e. seamless sheath and metal connection. The sealing must be moisture proof. The dimensions of end fittings of Insulators shall be in accordance with the standard dimensions stated in IEC: 60120/ IS: 2486 - Part-II /1989.

## **6.0 WORKMANSHIP**

6.1 All the materials shall be of latest design and conform to the best engineering Practices adopted in the high voltage field. Bidders shall offer only such

insulators as are guaranteed by them to be satisfactory and suitable for continued good service in power transmission/distribution lines.

- 6.2 The design, manufacturing process and material control at various stages shall be such as to give maximum working load, highest mobility, best resistance to corrosion, good finish and elimination of sharp edges and corners.
- 6.3 The design of the insulators shall be such that stresses due to expansion and contraction in any part of the insulator shall not lead to deterioration.
- 6.4 The core shall be sound and free of cracks and voids that may adversely affect the insulators.
- 6.5 Weather sheds shall be uniform in quality. They shall be clean, sound, smooth and shall be free from defects and excessive flashing at parting lines.
- 6.6 End fittings shall be free from cracks, seams, shrinks, air holes and rough edges. End fittings should be effectively sealed to prevent moisture ingress; effectiveness of sealing system must be supported by test documents. All surfaces of the metal parts shall be perfectly smooth without projecting points or irregularities, which may cause corona. All load bearing surfaces shall be smooth and uniform so as to distribute the loading stresses uniformly.
- 6.7 All ferrous parts shall be hot dip galvanized to give a minimum average coating of zinc equivalent to 610 gm/sq.m. or 87 micron thickness and shall be in accordance with the requirement of IS:4759. the zinc used for galvanizing shall be of purity 99.5% as per IS:4699. The zinc coating shall be uniform, adherent, smooth, reasonably bright continuous and free from imperfections such as flux, ash rust stains, bulky white deposits and blisters. The galvanized metal parts shall be guaranteed to withstand at least four successive dips each lasting for one (1) minute duration under the standard preece test. The galvanizing shall be carried out only after any machining.

## **7.0 TESTS AND STANDARDS**

Insulators offered shall be manufactured with the same configuration & raw materials as used in the insulators for which design & type test reports are submitted. The manufacturer shall submit a certificate for the same. **The design & type test reports submitted should have been carried out within five years prior** to the date of opening of this tender.

### **7.1 DESIGN TESTS:**

For polymeric insulators it is essential to carry out design test as per clause 4.1 of IEC 61109/92-93 with latest amendments. The design tests are intended to verify

the suitability of the design, materials and method of manufacture (technology). When a composite insulator is submitted to the design tests, the result shall be considered valid for the whole class of insulators, which are represented by the one tested and having the following characteristics:

- Same materials for the core, and sheds and same manufacturing method;
- Same material of the fittings, the same design, the same method of attachment;
- Same or greater layer thickness of the shed material over the core (including a sheath where used );
- Same or smaller ratio of the highest system voltage to insulation length;
- Same or smaller ratio of all mechanical loads to the smallest core diameter between fittings
- Same or greater diameter of the core.

The tested composite insulators shall be identified by a drawing giving all the dimensions with the manufacturing tolerances.

**Manufacturer should submit test reports for Design Tests as per IEC – 61109 (clause – 5) along with the bid.** Additionally following tests shall be carried out or reports for the tests shall be submitted after award of contract:

**UV test:** the test shall be carried out in line with clause 7.2 of ANSI C29.13.

## 7.2 TYPE TESTS:

The type tests are intended to verify the main characteristics of a composite insulator. The type tests shall be applied to composite insulators, the class of which has passed the design tests.

**7.2.1** Following Type test shall be conducted on a suitable number of individual insulator units, components, materials :

SL. No	Description of type test	Test procedure/standard
1	Dry lightning impulse withstand voltage test	As per IEC 61109 (clause 6.1)
2	Wet power frequency test	As per IEC 611 09 (clause 6.2)
3	Mechanical load-time test	As per IEC 611 09 (clause 6.4)
4	Radio interference test	As per IEC 61109 (clause 6.5) revised
5	Recovery of Hydrophobicity test	Annexure - B This test may be repeated every 3yrs by the manufacturer
6	Chemical composition test for silicon content	Annexure - B Or any other test method acceptable to the owner.
7	Brittle fracture resistance test	Annexure – B

The bidder shall submit type test reports as per IEC 61109 along with the bid. Additional type tests required if any shall be carried out by the manufacturer, after award of contract for which no additional charges shall be payable. In case, the tests have already been carried out, the manufacturer shall submit reports for the same.

**7.2.2 UV Resistance as per ASTM G 53:** 5000 Hours- UV Light for 8 hours and condensation for 4 hours in a continuous cycle. Elongation to be limited to 20% (% of elongation to break before and after the test)

**7.2.3 Salt Fog Test:** On Insulator for 1000hours as per IEC.

### 7.3. Acceptance (sample) Tests

The test samples after having withstood the routine test shall be subject to the following acceptance tests in order indicated below:

(a)	Verification of dimensions	Clause 7.2 IEC: 61109,
(b)	Verification of the locking system: (if applicable)	Clause 7.3 IEC : 61109,
©	Galvanizing test	IS:2633/15: 6745
(d)	Verification of the specified mechanical load	Clause 7.4 IEC: 61109,
(e)	Verification of tightness of the interface between end fitting & insulator housing	Clause 7.4 IEC: 61109, amendment 1 of 1995

### 7.4 Routine Tests

Sl No	Description	Standard
1	Identification of marking	As per IEC: 61109
2	Visual Inspection	As per IEC: 61109
3	Mechanical Routine test	As per IEC: 61106

Every Polymeric Insulator shall withstand Mechanical Routine test at ambient temperature, Tensile Load at RTL corresponding to atleast 50% of the SML for atleast 10 seconds.

### 7.5 Tests during manufacture:

Following tests shall also be carried out on all components as applicable

a)	Chemical analysis of zinc used for galvanizing
b)	Chemical analysis, mechanical, metallographic test and magnetic particle inspection for malleable castings.
c)	Chemical analysis, hardness tests and magnetic particle inspection for forgings.
d)	Peel off test to confirm adhesion of EVA/ Silicon /Silicon alloy to the core of the insulator.

### 7.6 Tests on the material used in manufacture of the insulator:

The bidder shall furnish following test reports conducted on the raw materials (i.e., silicon rubber or EVA) for confirming following properties along with their bid.

Sl. No	Property	Standard
1	Tensile Strength (MPa)	ISO37/ASTM D 638
2	Elongation (%)	ISO37/ASTM D 638
3	Tear Strength (N/mm)	ASTM D624B

4	TERT (4.5KV 360min)	ASTM D2303/IEC507
5	Volume Resistivity (Ohm -cm)	ASTM D257/IEC93
6	Dielectric constant	IEC 250/ ASTM D150
7	Dielectric Strength (kV/mm)	ASTM D149/IEC93
8	Density	ISO 1183A
9	Hardness (shore A)	ISO868
10	Accelerated aging	ISO188/ ASTM G53
11	Flammability test	UL-94 V0/IEC60707
12	Arc Resistance	IEC61621

7.7 The following characteristics shall be met by FRP rods used in manufacture of the insulator:

1. Tensile strength: 760 N/mm<sup>2</sup> Min
2. Glass content (%) : 75% min
3. Tg by DSC – 110 Deg C min
4. Dye penetration – No dye rise on 10 sample of 10 mm thick > 15 mins
5. Water diffusion & Voltage tests – 100 hours – 12kv for 1 min, no puncture or flashover on the FRP & current shall not exceed 1 mA
6. Hardness > 51 Barcol No
7. ECR glass – Boron/alkali content not more than 0.8%.

## 7.8 Additional Tests

7.8.1 The Owner reserves the right at his own expenses, for carrying out any other test(s) of reasonable nature carried out at Supplier's premises, at site, or in any other place in addition to the aforesaid type, acceptance and routine tests to satisfy himself that the material comply with the Specifications.

7.8.2 The Owner also reserves the right to conduct all the tests mentioned in this specification at his own expense on the samples drawn from the site at Supplier's premises or at any other test center. In case of evidence of non compliance, it shall be binding on the part of the Supplier to prove the compliance of the items to the technical specifications by repeat tests or correction of deficiencies or replacement of defective items, all without any extra cost to the Owner.

## 7.9 Co-ordination for Testing

7.9.1 The bidder shall intimate the Owner about carrying out of the type tests along with detailed testing programme at least 3 weeks in advance of the scheduled date of testing during which the Owner will arrange to depute his representative to be present at the time of carrying out the tests.

## 8.0 QUALITY ASSURANCE PLAN :

8.1 The bidder shall submit following information along with the bid:

8.1.1 Test certificates of the raw materials and bought out accessories.

- 8.1.2 Statement giving list of important raw material, their grades along with names of Sub suppliers for raw materials, list of standards according to which the raw materials are tested. List of tests normally carried out on raw materials in the presence of bidder's representative.
- 8.1.3 List of manufacturing facilities available.
- 8.1.4 Level of automation achieved and lists of areas where manual processing exists.
- 8.1.5 List of areas in manufacturing process, where stage inspections are normally carried out for quality control and details of such tests and inspections.
- 8.1.6 List of testing equipments available with the bidder for final testing of equipment along with valid calibration reports.
- 8.1.7 The manufacturer shall submit Manufacturing Quality Assurance Plan (QAP) followed during manufacture and testing.
- 8.2 The successful bidder shall submit the routine test certificates of bought out raw materials/accessories and central excise passes for raw material at the time of inspection.
- 8.3 The Purchaser representative shall at all times be entitled to have access to the works and all places of manufacture, where insulator, and its component parts shall be manufactured and the representatives shall have full facilities for unrestricted inspection of the Supplier's and sub-Supplier's works, raw materials, manufacture of the material and for conducting necessary test as detailed herein.
- 8.4 The material for final inspection shall be offered by the Supplier only under packed condition. The owner shall select samples at random from the packed lot for carrying out acceptance tests. The lot offered for inspection shall be homogeneous and shall contain insulators manufactured in 3-4 consecutive weeks.
- 8.5 The Supplier shall keep the Owner informed in advance of the time of starting and the progress of manufacture of material in their various stages so that arrangements could be made for inspection.
- 8.6 No material shall be dispatched from its point of manufacture before it has been satisfactorily inspected and tested unless the owner in writing waives off the inspection. In the later case also the material shall be dispatched only after satisfactory testing specified herein has been completed.
- 8.7 The acceptance of any quantity of material shall in no way relieve the Supplier of his responsibility for meeting all the requirements of the specification and shall not prevent subsequent rejection, if such materials are later found to be defective.



## 9.0 TEST CERTIFICATE :

The tenderer shall furnish detailed type test reports of the offered composite Insulators as per clause 8.2 of the Technical Specifications at the NABL approved laboratories to prove that the composite Insulators offered meet the requirements of the specification. These Type Tests should have been carried out within five years prior to the date of opening of this tender.

## 10.0 TESTING FACILITIES :

The tenderer must clearly indicate what testing facilities are available in the works of the manufacturer and whether facilities are adequate to carry out all Routine & acceptance Tests. These facilities should be available to Purchasers Engineers if deputed to carry out or witness the tests in the manufacturer works. If any test cannot be carried out at the manufacturer's work, the reasons should be clearly stated in the tender. The insulators shall be tested in accordance with the procedure detailed in IEC 61109 / 92-93 with latest amendments.

## 11.0. DRAWINGS :

The insulator shall be as per the Drawing enclosed.

## 12.0 RETEST AND REJECTION:

12.1 Sample Procedure for testing of insulators shall be as per clause 7.1 to 7.6 of IEC 61109 for Acceptance & Routine Tests. For the sampling tests, two samples are used, E1 and E2. The sizes of these samples are indicated in the table below.

Lot Size(N)	Sample size	
	E1	E2
N<300	Subject to agreement	
300<N<2000	4	3
2000<N<5000	8	4
5000<N<10000	12	6

If more than 10000 insulators are concerned, they shall be divided into an optimum number of lots comprising between 2000 and 10000 insulators. The results of the tests shall be evaluated separately for each lot. The insulators shall be selected by the purchaser's representative from the lot at random. The samples shall be subjected to the applicable sampling tests.

The sampling tests are:

Verification of dimensions	- (E1 + E2)
Verification of the locking system	- (E2)
Verification of tightness of the interface between end fittings & Insulator housing	- (E2)

Verification of the specified mechanical load SML - (E1)  
Galvanizing test - (E2)

In the event of a failure of the sample to satisfy a test, the retesting procedure shall be as follows :

- If only one insulator or metal part fails to comply with the sampling tests, a new sample equal to twice the quantity originally submitted to the tests shall be subjected to retesting. The retesting shall comprise the test in which failure occurs.
- If two or more insulator or metal parts fail to comply with any of the sampling tests or if any failure occurs during the retesting, the complete lot is considered as not complying with this standard and shall be withdrawn by the manufacturer.
- Provided the cause of the failure can be clearly identified, the manufacturer may sort the lot to eliminate all the insulators with these defects. The sorted lot then be resubmitted for testing. The number then selected shall be three times the first chosen quantity for tests. If any insulators fail during this retesting, the complete lot is considered as not complying with this standard and shall be withdrawn by the manufacturer.

#### 12.2 Verification of dimensions (E1 + E2)

The dimensions given in the drawings shall be verified. The tolerances given in the drawing are valid. If no tolerances are given in the drawings the values mentioned in this specification shall hold good.

#### 12.3 Verification of the locking system (E2)

This test applies only to the insulators equipped with socket coupling as specified by IEC 120 and is performed according to IEC 383.

#### 12.4 Verification of tightness of the interface between end fittings & Insulator housing (E2)

One insulator selected randomly from the sample E2, shall be subjected to crack indication by dye penetration, in accordance with ISO 3452, on the housing in the zone embracing the complete length of the interface between the housing and metal fitting and including an additional area, sufficiently extended beyond the end of the metal part. The indication shall be performed in the following way.

- the surface shall be properly pre-cleaned with the cleaner ;
- the penetrant, which shall act during 20 minutes, shall be applied on the cleaned surface;
- within 5 minutes after the application of the penetrant, the insulator shall be subjected, at the ambient temperature, to a tensile load of 70 % of the SML, applied between the metal fittings; the tensile load shall be increased rapidly but smoothly from zero up to 70 % of the SML, and then maintained at this value for 1 minute;

- the surface shall be cleaned with the excess penetrant removed, and dried;
- the developer shall be applied if necessary;
- the surface shall be inspected.

Some housing materials may be penetrated by the penetrant. In such cases evidence shall be provided to validate the interpretation of the results. After the 1 min. test at 70 % of the SML, if any cracks occur, the housing and, if necessary, the metal fittings and the core shall be cut, perpendicularly to the crack in the middle of the widest of the indicated cracks, into two halves. The surface of the two halves shall then be investigated for the depth of the cracks.

#### 12.5 Verification of the specified mechanical load SML

The insulators of the sample E1 shall be subjected at ambient temperature to a tensile load, applied between the couplings. The tensile load shall be increased rapidly but smoothly from zero to approximately 75 % of the SML, and then be gradually increased to the SML in a time between 30 sec. to 90 sec. If 100 % of the SML is reached in less than 90 s, the load (100 % of the SML) shall be maintained for the remainder of the 90 s. (This test is considered to be equivalent to a 1 min withstand test at the SML). The insulators have passed the test at 13.4 & 13.5 above if:

- No failure (breakage or complete pull out of the core, or fracture of the metal fitting) occurs either during the 1 min. 70 % withstand test (a) or during the 1 min. 100 % withstand test (b).
- No cracks are indicated after the dye penetration method described in 13.4 above.
- The investigation of the halves described in 13.4 above shows clearly that the cracks do not reach the core.

#### 12.6 Galvanizing test

This test shall be performed according to IS: 2633/IS: 6745 on galvanized parts.

#### 13.0 MARKINGS:

Each insulator shall be legibly and indelibly marked with the following details as per IEC- 61109:

- a) Name or trademark of the manufacturer.
- b) Voltage & Type
- c) Month and year of manufacturing.
- d) Min. failing load/guaranteed mechanical strength in kilo Newton followed by the word 'KN' to facilitate easy identification.
- e) Country of Manufacturer.

#### 14.0 PACKING :

14.1 All insulators shall be packed in strong corrugated box of min. 7 ply duly palletted or wooden crates. The gross weight of the crates along with the material shall not normally exceed 100 Kg to avoid hackling problem. The crates shall be suitable for outdoor storage under wet climate during rainy season.

- 14.2 The packing shall be of sufficient strength to withstand rough handling during transit, storage at site and subsequent handling in the field.
- 14.3 Suitable cushioning, protective padding, or Dunn age or spacers shall be provided to prevent damage or deformation during transit and handling.
- 14.4 All packing cases shall be marked legibly and correctly so as to ensure safe arrival at their destination and to avoid the possibility of goods being lost or wrongly dispatched on account of faulty packing and faulty or illegible markings. Each wooden case /crate /corrugated box shall have all the markings stenciled on it in indelible ink.
- 14.5 The bidder shall provide instructions regarding handling and storage precautions to be taken at site.

## Annexure-A

### STANDARDS TO BE ADOPTED FOR COMPLETE INSULATORS

Sl No	IS Standard	Title	International Standard
1		Definition, test methods and acceptance criteria for composite insulators for a.c. overhead lines above 1000 V	IEC: 61109
2	IS: 731	Porcelain insulators for overhead Power lines with a nominal voltage greater than 1000 V	IEC: 60383
3	IS: 2071	Methods of High Voltage Testing	IEC: 60060-1
4	IS: 2486	Specification for Insulator fittings for Overhead Power Lines with a nominal Voltage greater than 1000V General Requirements and Tests Dimensional Requirements Locking Devices	IEC: 60120 IEC: 60372
5		Thermal Mechanical Performance test and mechanical performance test on string insulator units	IEC: 60575
6	IS: 13134	Guide for the selection of insulators in respect of polluted Conditions	IEC: 60815
7		Characteristics of string insulator units of the long rod type	IEC: 60433
8		Hydrophobicity Classification Guide	STRI Guide 1.92/1
9		Radio interference characteristics of overhead power lines and high-voltage equipment.	CISPR:18-2 Part-2
10	IS: 8263	Methods of RI Test of HV insulators	IEC: 60437
11		Standard for Insulators Composite-Distribution Dead-end Type	ANSI C29. 13-2000
12	IS: 4759	Hot dip zinc coatings on structural steel & other allied products	ISO:1459 ISO:1461
13	IS:2629	Recommended Practice for Hot. Dip . Galvanisation for iron and steel	ISO:1461(E)
14	IS: 6745	Determination of Weight of Zinc Coating on Zinc coated iron and steel articles	ISO:1460
15	IS:3203	Methods of testing of local thickness of electroplated coatings	ISO:2173
16	IS:2633	Testing of Uniformity of Coating of zinc coated articles	
17		Standard specification for glass fiber strands	ASTM D 578-05
18		Standard test method for compositional analysis by Thermogravimetry	ASTM E 1131-03
19	IS: 4699	Specification for refined secondary Zinc	

## **Annexure-B**

### **Tests on Insulator units**

#### **1. RIV Test (Dry)**

The insulator string along with complete hardware fittings shall have a radio interference voltage level below 100 micro volts at one MHz when subjected to 50 Hz AC voltage of 10 kV & 30 kV for 11 kV insulators under dry condition. The test procedure shall be in accordance with 15:8263 IEC: 437/CISPR 18-2.

#### **2. Brittle Fracture Resistance Test**

Brittle fracture test shall be carried out on naked rod along with end fittings by applying "1 n HN03 acid" (63 gm conc. HN03 added to 937 gm water) to the rod. The rod should be held at 80% of SML for the duration of the test. The rod should not fail within the 96-hour test duration. Test arrangement should ensure continuous wetting of the rod with Nitric acid.

#### **3. Recovery of Hydrophobicity & Corona test**

The test shall be carried out on 4mm thick samples of 5cm x 7cm.

- i) The surface of selected samples shall be cleaned with isopropyl alcohol. Allow the surface to dry and spray with water. Record the Hydrophobicity classification in line with STRJ guide for Hydrophobicity classification (Extract enclosed at Annexure - D). Dry the sample surface.
- ii) The sample shall subjected to mechanical stress by bending the sample over a ground electrode. Corona is continuously generated by applying 12 kV to a needle like electrode placed 1 mm above the sample surface. The test shall be done for 100 hrs.
- iii) Immediately after the corona treatment, spray the surface with water and record the HC classification. Dry the surface and repeat the corona treatment as at clause 2 above. Note HC classification. Repeat the cycle for 1000 hrs. or until an HC of 6 or 7 is obtained. Dry the sample surface.
- iv) Allow the sample to recover and repeat hydrophobicity measurement at several time intervals. Silicone rubber should recover to HC 1 - HC 2 within 24 to 48 hours, depending on the material and the intensity of the corona treatment.

#### **4. Chemical composition test for Silicon content**

The content of silicon in the composite polymer shall be evaluated by EDX (Energy Dispersion X-ray) Analysis or Thermo-gravimetric analysis. The test may be carried out at CPRI/ERDA or any other NABL accredited govt laboratory.